

SLOVENSKI STANDARD
oSIST prEN ISO 17138:2022
01-januar-2022

Fina keramika (sodobna keramika, sodobna tehnična keramika) - Mehanske lastnosti keramičnih kompozitov pri sobni temperaturi - Ugotavljanje upogibne trdnosti (ISO 17138:2014)

Fine ceramics (advanced ceramics, advanced technical ceramics) - Mechanical properties of ceramic composites at room temperature - Determination of flexural strength (ISO 17138:2014)

Hochleistungskeramik - Mechanische Eigenschaften von keramischen Verbundwerkstoffen bei Raumtemperatur - Bestimmung der Biegefestigkeit (ISO 17138:2014)

Céramiques techniques - Propriétés mécaniques des composites céramiques à température ambiante - Détermination de la résistance en flexion (ISO 17138:2014)

Ta slovenski standard je istoveten z: prEN ISO 17138

ICS:

81.060.30 Sodobna keramika Advanced ceramics

oSIST prEN ISO 17138:2022 en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN ISO 17138:2022](https://standards.iteh.ai/catalog/standards/sist/0d8d591a-766c-451b-95f4-50666c4a705b/osist-pren-iso-17138-2022)

<https://standards.iteh.ai/catalog/standards/sist/0d8d591a-766c-451b-95f4-50666c4a705b/osist-pren-iso-17138-2022>

INTERNATIONAL
STANDARD

ISO
17138

First edition
2014-12-01

**Fine ceramics (advanced ceramics,
advanced technical ceramics) —
Mechanical properties of ceramic
composites at room temperature —
Determination of flexural strength**

*Céramiques techniques — Propriétés mécaniques des composites
céramiques à température ambiante — Détermination de la
résistance en flexion*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN ISO 17138:2022](https://standards.iteh.ai/catalog/standards/sist/0d8d591a-766c-451b-95f4-50666c4a705b/osist-pren-iso-17138-2022)

<https://standards.iteh.ai/catalog/standards/sist/0d8d591a-766c-451b-95f4-50666c4a705b/osist-pren-iso-17138-2022>



Reference number
ISO 17138:2014(E)

© ISO 2014

iTeh STANDARD PREVIEW (standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/sist/0d8d591a-766c-451b-95f4-50666c4a705b/osist-pren-iso-17138-2022>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms, definitions, and symbols	1
4 Principle	2
5 Apparatus	2
5.1 Test machine.....	2
5.2 Test fixture.....	2
5.3 Data recording system.....	2
5.4 Dimension measuring devices.....	2
6 Test specimens	2
7 Test specimen preparation	3
7.1 Machining and preparation.....	3
7.2 Number of test specimens.....	3
8 Test procedures	4
8.1 Displacement rate.....	4
8.2 Measurement of dimensions.....	4
8.3 Testing technique.....	4
8.4 Test validity.....	4
8.5 Calculation of results.....	5
9 Test report	6
Bibliography	8

<https://standards.iteh.ai/catalog/standards/sist/0d8d591a-766c-451b-95f4-50666c4a705b/osist-pren-iso-17138-2022>

ISO 17138:2014(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 206, *Fine ceramics*.

oSIST prEN ISO 17138:2022
<https://standards.iteh.ai/catalog/standards/sist/0d8d591a-766c-451b-95f4-50666c4a705b/osist-pren-iso-17138-2022>

Fine ceramics (advanced ceramics, advanced technical ceramics) — Mechanical properties of ceramic composites at room temperature — Determination of flexural strength

1 Scope

This International Standard describes a method for the determination of the flexural strength of ceramic matrix composite materials with continuous fibre reinforcement, under three-point or four-point bend at room temperature. This method applies to all ceramic matrix composites with a continuous fibre reinforcement, unidirectional (1D), bidirectional (2D), and tridirectional xD with ($2 < x \leq 3$) as defined in CEN/TR 13233, loaded along one principal axis of reinforcement.

NOTE The method is not intended to be used to obtain absolute values of strength for design purposes.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 7500-1, *Metallic materials — Verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Verification and calibration of the force-measuring system*

ISO 3611, *Geometrical product specifications (GPS) — Dimensional measuring equipment: Micrometers for external measurements — Design and metrological characteristics*

CEN/TR 13233: 2007, *Advanced technical ceramics — Ceramic composites — Notations and symbols*

3 Terms, definitions, and symbols

For the purposes of this document, the terms and definitions given in CEN/TR 13233¹⁾ and the following apply.

3.1

maximum flexural force

F_m

highest recorded force in a flexural test on the test specimen when tested to failure

3.2

flexural stress

σ

nominal stress on the outer surface of the test specimen, calculated at mid-span

Note 1 to entry: This stress is conventionally calculated according to the beam theory, whose basic assumptions cannot be met by ceramic matrix composite materials.

3.3

flexural strength

$\sigma_{f,m}$

maximum flexural stress applied to a test specimen that fractures during a flexural test

1) An International Standard, ISO 19634, *Fine ceramics (advanced ceramics, advanced technical ceramics) — Notations and symbols of ceramic composites* is under preparation.

ISO 17138:2014(E)

4 Principle

A beam is supported on two outer points, and subjected to an external load applied perpendicularly to a longitudinal axis. The test is performed at constant crosshead displacement rate.

5 Apparatus

5.1 Test machine

The machine shall be equipped with a system for measuring the force applied to the test specimen. The system shall conform to grade 1 according to ISO 7500-1.

5.2 Test fixture

The test fixture is composed of two parts, linked to the fixed and mobile parts of the machine. It has two outer support rollers and one (three-point bend) or two (four-point bend) inner rollers for application of load.

The cylindrical rollers shall have a diameter between 4 mm and 10 mm. Their length shall be at least equal to the width of the test specimen. They shall be made of a material with hardness at least equal to that of the test specimen. The axes of the rollers shall be parallel to within 0,01 mm/mm. (See [Figure 1](#).)

Pivoting rollers may be used to adapt the non-parallelism of the upper and lower faces of un-machined test specimens. Either two or three rollers, for three-point or four-point bend, respectively, shall be free to pivot around an axis parallel to the longitudinal direction of the test specimen.

The distance between rollers shall be in accordance with [Clause 6](#).

The inner rollers shall be centred with respect to the outer rollers to within 0,2 mm. In case of four-point bend, the test fixture shall ensure symmetrical loading of the test specimen.

5.3 Data recording system

A calibrated recorder shall be used to record the force-time curve. The use of a digital data recording system is recommended.

5.4 Dimension measuring devices

Devices used for measuring linear dimensions of the test specimen shall be accurate to $\pm 0,1$ mm. Micrometers shall be in accordance with ISO 3611.

6 Test specimens

Recommended test specimen dimensions are given in [Table 1](#). These dimensions have been successfully used and take into account the following factors.

The volume of material under load shall be representative of the nature of the material and of the reinforcement structure. This sets minimum limits to the span and to the width and thickness of the test specimen. In case of flexural, as opposed to tensile, testing, the distribution of the longitudinal reinforcement through the thickness has to be considered. When this distribution is not symmetrical with respect to the neutral plane, care shall be taken to ensure that it is similar for all test specimens.

Two types of test specimens can be distinguished as follows:

- a) as fabricated test specimens, where only the length and the width are machined to give to the test specimens the specified size. In this case, the tensile and compressive surfaces can be unmachined and thus irregular;

- b) machined test specimens, where the length, the width, and the thickness of the test specimen have been machined.

Tolerance on thickness is only for machined test specimens. For as fabricated test specimens, the maximum difference in thickness of three measurements (at the centre and at each end of the outer span length) shall not exceed 5 % of the average of the three measurements.

The thickness of the test specimen and the distance between the inner and outer roller(s) shall be chosen so as to avoid shear failure. This is achieved by setting a minimum limit to the ratio between the moment arm and the test specimen thickness (see [Table 1](#)). A value of 10 is commonly used and translates into a minimum L/h ratio of 20 in three-point bend, and a minimum $(L-L_i)/h$ ratio of 20 in four-point bend with $L_i = L/3$.

Table 1 — Recommended test specimen and span dimensions

Dimensions in millimetres

	1D, 2D, xD	Tolerance
l_t , total length	$L + 20$	± 1
b , width	10	$\pm 0,2$
h , mean thickness of test specimen	≥ 2	$\pm 0,2$
Inner span		
L_i , four-point bend	25	$\pm 0,1$
Outer span		
L , four-point bend	75	$\pm 0,1$
L , three-point bend	50	$\pm 0,1$

If it is necessary to define test specimens of different dimensions, the conditions of [Clause 6](#) should be taken into account.

7 Test specimen preparation

7.1 Machining and preparation

During cutting out, care shall be taken to align the longitudinal test specimen axis with one of the principal axes of reinforcement.

Test specimens can be tested with either machined or non-machined tensile and compressive surfaces. In some cases machining is not recommended because it might cause damage to the material near the tensile and compressive surfaces. When machining these surfaces, care shall be taken to maintain reinforcement geometry across the thickness of the test specimen, which is representative of the material in the as-processed condition. In particular, it shall be ensured that the symmetry of originally symmetric reinforcement geometry is preserved in the test specimen cross section after machining.

Machining parameters which avoid damage to the material shall be established and documented. These parameters shall be adhered to during test specimen preparation.

7.2 Number of test specimens

At least five valid test results (see [8.4](#)) are required.

For test specimens with a non-symmetric reinforcement geometry with respect to the neutral plane, tests in two orientations for which the tensile and compressive face are interchanged might be necessary.

NOTE If statistical evaluation is required, the number of test specimens should be in accordance with EN 843-5.

ISO 17138:2014(E)

8 Test procedures

8.1 Displacement rate

Use a constant crosshead displacement rate which allows quasi-static loading of test specimen and the absence of subcritical crack growth. $(0,5 \pm 0,1)$ mm/min or a rate which allows test specimen failure in about 1 min is recommended. The displacement rate shall be reported.

8.2 Measurement of dimensions

8.2.1 Test specimen dimensions

The width and thickness shall be measured to the nearest 0,01 mm in three points near the centre for three-point bend and between the inner rollers for four-point bend, and at each end of the test specimen.

The arithmetic means of the measurements shall be used for calculations.

8.2.2 Distances between supporting rollers

The distance between axes of the outer rollers and for four-point bend also the inner rollers shall be measured to the nearest 0,1 mm.

NOTE This can be achieved by the use of a travelling microscope or other suitable device accurate to 0,05 mm.

8.3 Testing technique

iTeh STANDARD PREVIEW
(standards.iteh.ai)

8.3.1 Test specimen mounting

The test specimen shall be installed in the test jig centred with respect to the rollers and with its longitudinal axis perpendicular to the axes of the rollers.

NOTE It is recommended to use a setting tool for this purpose.

Zero the load cell output. When required, a small preload can be applied in order to maintain correct positioning of the test specimen. This preload shall not increase beyond 5 % of the expected failure force at any time.

8.3.2 Measurements

Perform the measurements as follows:

- set the displacement rate on the test machine;
- zero the load cell;
- record the force versus time;
- load the test specimen up to failure;
- read the load signal after test specimen failure;
- note the position of fracture location relative to the mid-point of the test specimen to the nearest 1 mm and the failure mode (tensile or compressive).

8.4 Test validity

The following circumstances invalidate a test:

- failure to specify and record test conditions;