

Designation: D946-09 Designation: D946/D946M - 09a

Standard Specification for Penetration-Graded Asphalt Cement for Use in Pavement Construction¹

This standard is issued under the fixed designation D946/D946M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

- 1.1 This specification covers asphalt cement for use in the construction of pavements.
- 1.2 This specification covers the following penetration grades:

40–50, 120–150, and 60–70, 200–300.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

2. Referenced Documents

- 2.1 ASTM Standards:²
- D5 Test Method for Penetration of Bituminous Materials
- D36 Test Method for Softening Point of Bitumen (Ring-and-Ball Apparatus)
- D92 Test Method for Flash and Fire Points by Cleveland Open Cup Tester
- D113 Test Method for Ductility of Bituminous Materials
- D140 Practice for Sampling Bituminous Materials
- D1754 Test Method for Effects of Heat and Air on Asphaltic Materials (Thin-Film Oven Test)
- D2042 Test Method for Solubility of Asphalt Materials in Trichloroethylene

3. Manufacture

3.1 Asphalt cement shall be prepared by the refining of crude petroleum by suitable methods.

4. Properties

- 4.1 The asphalt cement shall be homogeneous and shall not foam when heated to 347°F (174°C). 175°C [350°F].
- 4.2 The asphalt cement shall conform to the requirements given in Table 1 or Table 2, as specified by the purchaser. Table 2 requirements limit the temperature susceptibility of asphalt over Table 1 requirements. Asphalts that meet Table 2 requirements will also meet Table 1 requirements of the same grade.

5. Methods of Sampling and Testing

- 5.1 The material shall be sampled and the properties enumerated in this specification shall be determined in accordance with the following ASTM methods:
 - 5.1.1 Sampling—Practice D140.
 - 5.1.2 Penetration—Test Method D5.
 - 5.1.3 Softening Point—Test Method D36.
 - 5.1.4 Flash Point—Test Method D92.
 - 5.1.5 Ductility—Test Method D113.

1

¹ This specification is under the jurisdiction of ASTM Committee D04 on Road and Paving Materials and is the direct responsibility of Subcommittee D04.40 on Asphalt Specifications.

Current edition approved $\frac{\text{July Dec.}}{\text{D01: }}$ 1, 2009. Published $\frac{\text{July }2009.}{\text{January }2010.}$ Originally approved in 1947. Last previous edition approved in $\frac{20052009}{\text{D03: }}$ as $\frac{\text{D946-82(2005).D946-09.}}{\text{D01: }}$ 10.1520/D0946_D0946M-09A.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.