



Designation: C638-92 (Reapproved 2002) Designation: C638 – 09

Standard Descriptive Nomenclature of Constituents of Aggregates for Radiation-Shielding Concrete¹

This standard is issued under the fixed designation C638; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This descriptive nomenclature is intended to give accurate descriptions of some common or important naturally occurring and synthetic constituents of aggregates for radiation-shielding concrete, that, at the same time, are not common or important constituents of concrete aggregates in general use. While most of the minerals and rocks discussed below may occur in small quantities in aggregates in general use, they are not major constituents of such aggregates. Common constituents of aggregates in general use are described in Descriptive Nomenclature C294. Radiation-shielding concrete often contains such aggregates, but other special aggregates are used in some circumstances.

1.2 The synthetic aggregates included are ferrophosphorus and boron frit.

1.3 The descriptions are not adequate to permit the identification of materials, since accurate identification of natural and synthetic aggregate constituents in many cases can only be made by a qualified geologist, mineralogist, or petrographer, using the apparatus and procedures of those sciences.

1.4 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

2. Referenced Documents

2.1 *ASTM Standards*:²

C294 Descriptive Nomenclature for Constituents of Concrete Aggregates

3. Types of Materials

3.1 Two classes of materials are described below. The first class consists of minerals and rocks formed from them, and synthetic materials, that have high relative density (specific gravity) and in addition contain substantial proportions of atoms of high or moderately high atomic weight. They are referred to as heavy or high-density aggregates. The second class consists of minerals and synthetic glasses of substantial boron content that are particularly effective in absorbing thermal neutrons without producing highly penetrating gamma rays. The boron-frit glasses are included because of their frequent use.

HEAVY AGGREGATES

4. Descriptions of Naturally Occurring Constituents

4.1 Members of this group have higher specific gravities relative density (specific gravity) than aggregates in general use. Six are iron minerals, of which five are important iron ore minerals and the sixth is an ore of titanium. Two are barium minerals worked as the principal sources of barium salts. The other is ferrophosphorus, a mixture of synthetic iron phosphides.

4.2 The constituents are described below first as minerals, and then as major constituents of ores when their aspect as major constituents of ores affects the behavior of ores as concrete aggregates.

5. Iron Minerals and Ores

5.1 *Hematite* (Fe_2O_3)—Hematite has a hardness of 5 to 6 on Mohs' scale (will be scratched by hard steel), and a relative density (specific gravity) of 5.26 when pure. The color varies from bright red to dull red to steel gray; luster varies from metallic to

¹ This descriptive nomenclature is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.41 on Pre-placed Aggregate Concrete for Radiation Shielding.

Current edition approved Dec. 10, 2002. Published February 2003. Originally approved in 1973. Last previous edition approved in 1992 as C638—92. DOI: 10.1520/C0638-92R02.

Current edition approved Dec. 1, 2009. Published January 2010. Originally approved in 1973. Last previous edition approved in 2002 as C638-92(2002). DOI: 10.1520/C0638-09.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard.

submetallic to dull; the streak is cherry red or reddish brown; it is nonmagnetic.

5.1.1 *Hematite Ores*—Rocks of which hematite is the major constituent vary from one deposit to another, and within the deposit, in specific gravity, toughness, compactness, amount of impurities, degree of weathering, and suitability for use as concrete aggregate. Hematite appears to be the iron ore mineral most exploited as a source of iron. The ores of the Lake Superior region are banded sedimentary ores consisting of layers rich in hematite, and sometimes goethite, iron silicates, such as stilpnomelane, minnesotaite, greenalite, grunerite, and iron carbonate, alternating with silica-rich layers of chert or fine-grained quartz or a mixture. The Birmingham, AL ores are oolitic with hematite replacements of oörites and fossils in a matrix that ranges from fine-grained earthy hematite, with or without calcite, to crystalline calcite. Hematite ores dust in handling, with the dust ranging in color from moderate red to dusky red to moderate reddish brown (5R 4/6 to 5R 3/4 to 10R 4/6).³

5.2 *Ilmenite (FeTiO_3 with minor Mg and Mn)*—Ilmenite has a hardness of 5 to 6 and relative density (specific gravity) of 4.72 ± 0.04 when pure. The color is iron black with metallic to submetallic luster; the streak is black; it is feebly magnetic.

5.2.1 *Ilmenite Ores*—These ores consist of crystalline ilmenite with either magnetite or hematite and constituents of the associated gabbroic or anorthositic rocks. Massive ilmenite ores can form coarsely crystalline massive tough rocks but vary, from deposit to deposit, and within a deposit, in relative density (specific gravity), composition, hardness, and suitability for use as concrete aggregate. Many ilmenite ores consist of ilmenite disseminated in rock rather than concentrated as a major rock-forming mineral. Ilmenite concentrated from beach sands is usually altered to a variable degree, and its mechanical properties probably differ from those of unaltered ilmenite. One of the most widely used types of heavy aggregates is ilmenite ore.

5.3 *Lepidocrocite ($\text{FeO}(\text{OH})$)*—Lepidocrocite has a hardness of 5 and relative density (specific gravity) of 4.09 when pure. The color varies from ruby red to reddish brown and the streak is dull orange. Lepidocrocite and goethite occur together, and lepidocrocite may be a constituent of goethite and limonite ores.

5.4 *Goethite (HFeO_2)*—Goethite has the same chemical composition as lepidocrocite but crystallizes differently. The hardness is 5 to $5\frac{1}{2}$ and the relative density (specific gravity) is 4.28 ± 0.01 when pure and 3.3 to 4.3 in massive goethite. The color varies with the form, from crystals that are blackish brown with imperfect adamantine-metallic luster, to dull or silky luster in fibrous varieties; massive goethite is yellowish brown to reddish brown; clayey material is brownish yellow to ochre yellow. The streak is brownish yellow to ochre yellow.

5.4.1 *Goethite Ores*—These ores range from hard tough massive rocks to soft crumbling earths; these alterations frequently occur within fractions of an inch.

5.5 *Limonite*—A general name for hydrous iron oxides of unknown composition frequently cryptocrystalline goethite with adsorbed and capillary water, and probably mixtures of such goethite with similar lepidocrocite or hematite, or both, with adsorbed and capillary water⁴. The relative density (specific gravity) ranges from 2.7 to 4.3 and the color from brownish black through browns to yellows. Limonite deposits range from recognizable crystalline goethite to dull massive material of indefinite composition, and therefore, properly limonite. Limonites of high iron content are also called brown iron ores. Frequently they contain sand, colloidal silica, clays, and other impurities.

5.6 *Magnetite (FeFe_2O_4)*—Magnetite has a hardness of $5\frac{1}{2}$ to $6\frac{1}{2}$ and relative density (specific gravity) of 5.17 when pure. It is strongly magnetic; the color is black with metallic to semimetallic luster; the streak is black.

5.6.1 *Magnetite Ores*—These ores can form dense, tough, usually coarse-grained rocks with few impurities. Magnetite ores are associated with metamorphic or igneous or sedimentary rocks, and therefore, the impurities associated with magnetite ores may include a wide variety of rock-forming and accessory minerals. Magnetite occurs in association with hematite and ilmenite; magnetic ores are widely distributed, but many are not suitable for use as heavy aggregate because the magnetite occurs disseminated through rock rather than as a major rock-forming mineral. One of the most widely used types of heavy aggregates is magnetite ore.

6. Barium Minerals

6.1 *Witherite (BaCO_3)*—Witherite has a hardness of 3 to $3\frac{1}{2}$ and a relative density (specific gravity) of 4.29 when pure. The color ranges from colorless to white to grayish or many pale colors. Like calcite and aragonite, witherite is decomposed with effervescence by dilute hydrochloric acid (HCl). Witherite, the second most common barium mineral, occurs with barite and galena. England is the chief producer of witherite, and barium-containing heavy aggregates in Great Britain might be expected to contain witherite as a major constituent.

6.2 *Barite (BaSO_4)* (also, but improperly, called barytes)—Barite has a hardness of 3 to $3\frac{1}{2}$ and a relative density (specific gravity) of 4.50 when pure. The color ranges from colorless to white to many usually pale colors.

6.2.1 Barite is the most common barium mineral and the major barium ore. It occurs in veins transecting many kinds of rocks, concentrated in sedimentary rocks, and as residual nodules in clays formed by the solution of sedimentary rocks. In many of its occurrences it is accompanied by clay or a calcium sulfate mineral (gypsum or anhydrite) or both. Although barite from residual deposits is often weathered, it is possible to obtain clean, well-graded barite aggregate.

³ National Research Council, Washington, DC, *Rock Color Chart* (1948) reissued 1964 by Geological Soc. Am., New York, NY.

⁴ Palache, Charles, et al., *The System of Mineralogy of J. D. Dana and E. S. Dana, Vol 1, Elements, Sulfides, Sulfosalts, Oxides*, Ed. 7, New York, NY, 1944, p 685.