

# SLOVENSKI STANDARD oSIST prEN 13877-1:2022

01-marec-2022

Betonska vozišča - 1. del: Materiali

Concrete pavements - Part 1: Materials

Fahrbahnbefestigungen aus Beton - Teil 1: Baustoffe

iTeh STANDARD

Chaussées en béton - Partie 1 : Matériaux

Ta slovenski standard je istoveten zi a rprEN 13877-1ai)

<u>oSIST prEN 13877-1:2022</u>

https://standards.iteh.ai/catalog/standards/sist/389655f6-

91.100.30 Beton in betonski izdelki 20 Concrete and concrete

products

93.080.20 Materiali za gradnjo cest Road construction materials

oSIST prEN 13877-1:2022 en,fr,de

oSIST prEN 13877-1:2022

## iTeh STANDARD PREVIEW (standards.iteh.ai)

oSIST prEN 13877-1:2022

https://standards.iteh.ai/catalog/standards/sist/389655f6-5ea6-40e7-a97e-e4e0025e68ba/osist-pren-13877-1-2022

## EUROPEAN STANDARD NORME EUROPÉENNE EUROPÄISCHE NORM

# **DRAFT** prEN 13877-1

January 2022

ICS 93.080.20

Will supersede EN 13877-1:2013

#### **English Version**

### Concrete pavements - Part 1: Materials

Chaussées en béton - Partie 1 : Matériaux

Fahrbahnbefestigungen aus Beton - Teil 1: Baustoffe

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 227.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

**Warning**: This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard. Sean-40e -a 9/e-e 4e 0025e 68ba/osist-pren-13877-1-

2022



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents		Page	
European foreword			
1	Scope	4	
2	Normative references	4	
3	Terms and definitions	5	
4	Requirements for constituent materials of concrete		
4.1	General		
4.2	Type of cement		
4.3	Aggregates		
4.3.1	General		
4.3.2	Maximum size of aggregates		
4.4	Mixing water		
4.5	Other constituent materials		
5	Basic requirements for concrete	6	
5.1	General	6	
<b>5.2</b>	Fresh concrete Teh STANDARD	6	
<b>5.2.1</b>	CONSISTENCE	0	
5.2.2	Air content PREVIEW	7	
5.2.3			
5.2.4	Content of particles smaller than 0,250 mm	7	
5.2.5	Chloride content (Standards.Iten.al)		
5.3	Hardened concrete		
5.3.1	Resistance to the effects of freeze-thaw and de-icing agents		
5.3.2	Mechanical strength	7	
6	Basic requirements for other materials for concrete payements 7.7	9	
6.1	General	9	
6.2	Curing materials	9	
6.3	Surface retarders	9	
6.4	Joint sealants	10	
6.5	Tie bars		
6.6	Dowels		
6.7	Reinforcing bars		
6.8	Reinforcing fibres	10	
Biblio	ngranhy	11	

#### **European foreword**

This document (prEN 13877-1:2022) has been prepared by Technical Committee CEN/TC 227 "Road materials", the secretariat of which is held by BSI.

This document is currently submitted to the CEN Enquiry.

This document will supersede EN 13877-1:2013.

In comparison with the previous edition, the following technical modifications have been made:

- the normative references have been updated;
- the scope has been adapted;
- lean concrete has been removed;
- the requirements on the density of fresh concrete have been removed;
- the steel fibres have been included in the definition of reinforcement;
- the notes in Table 1 have been updated;
- Table 3, Dimensions for tie bars, has been removed;
- EN 197-1, prEN 13863-6 and EN 14889-1 have been added to the normative references;
- the Bibliography has been deleted.

EN 13877, Concrete pavements, is currently composed with the following parts:

- Part 1: Materials 5ea6-40e7-a97e-e4e0025e68ba/osist-pren-13877-1-
- Part 2: Functional requirements for concrete pavements
- Part 3: Specifications for dowels to be used in concrete pavements

This European standard refers to EN 206. In accordance with the scope of EN 206 some additional or different requirements are necessary for pavements, particularly to comply with safety of users, durability, environment and health.

#### 1 Scope

This document specifies requirements for the constituents (concrete and other materials) of concrete pavements, cast *in situ*. Concrete compacted by rollers is not covered by this document.

This document covers concrete pavements for roads, airfields, pedestrian footpaths, cycle tracks, storage areas, and in general for all traffic-bearing structures.

#### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 197-1, Cement — Part 1: Composition, specifications and conformity criteria for common cements

EN 206, Concrete — Specification, performance, production and conformity

EN 1008, Mixing water for concrete — Specification for sampling, testing and assessing the suitability of water, including water recovered from processes in the concrete industry, as mixing water for concrete

EN ISO 9227:2017, Corrosion tests in artificial atmospheres — Salt spray tests (ISO 9227:2017)

EN 10080, Steel for the reinforcement of concrete — Weldable reinforcing steel — General

EN 10025-2, Hot rolled products of structural steels—Part 2: Technical delivery conditions for non-alloy structural steels

(standards.iteh.ai)

EN 10060, Hot rolled round steel bars for general purposes — Dimensions and tolerances on shape and dimensions

oSIST prEN 13877-1:2022

EN 12350-7, Testing fresh concrete and Part 7: Air content Pressure methods

EN 12390-3, Testing hardened concrete — Part 3: Compressive strength of test specimens

EN 12390-5, Testing hardened concrete — Part 5: Flexural strength of test specimens

EN 12390-6, Testing hardened concrete — Part 6: Tensile splitting strength of test specimens

EN 12620, Aggregates for concrete

prEN 13877-2, Concrete pavements — Part 2: Functional requirements for concrete pavements

EN 13877-3, Concrete pavements — Part 3: Specifications for dowels to be used in concrete pavements

prEN 13863-6, Concrete pavements — Part 6: Test method for the determination of the tensile strength of concrete on cylindrical discs

EN 14188-1, Joint fillers and sealants — Part 1: Specifications for hot applied sealants

EN 14188-2, Joint fillers and sealants — Part 2: Specifications for cold applied sealants

EN 14188-3, Joint fillers and sealants — Part 3: Specifications for preformed joint seals

CEN/TS 14754-1, Curing compounds — Test methods — Part 1: Determination of water retention efficiency of common curing compounds

EN 14889-1, Fibres for concrete — Part 1: Steel fibres — Definitions, specifications and conformity

#### Terms and definitions 3

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <a href="https://www.electropedia.org/">https://www.electropedia.org/</a>
- ISO Online browsing platform: available at <a href="https://www.iso.org/obp">https://www.iso.org/obp</a>

#### 3.1

#### concrete pavement

concrete layer capable of withstanding direct passage of traffic and environmental effects

Note 1 to entry: Several types exist: jointed unreinforced, jointed reinforced, continuously reinforced.

#### 3.2

#### exposed aggregate concrete surface

exposed aggregate concrete surface surface surface finish for concrete pavements achieved by removing the surface mortar, in order to expose the coarse aggregate **PREVIEW** 

#### 3.3

#### curing compound

(standards.iteh.ai)

product that can be applied on the surface of newly placed concrete to minimize the loss of moisture and in the case of pigmented compounds to reflect heat minimizing heating up of the concrete

#### 3.4

https://standards.iteh.ai/catalog/standards/sist/389655f6-

5ea6-40e7-a97e-e4e0025e68ba/osist-pren-13877-1dowel

smooth bar which extends into adjoining slabs at a joint in a concrete pavement, to improve load transfer and to avoid faulting

#### 3.5

#### tie bar

bar used to keep joints closed, normally longitudinal joints, or used for cross-stitching of cracks or joints

#### 3.6

#### reinforcement

bars, meshes or fibres embedded in concrete to control cracking and/or to provide tensile capacity

#### Requirements for constituent materials of concrete

#### 4.1 General

Only constituent materials permitted in EN 206 shall be used.

The constituent materials for concrete shall be selected to satisfy the specified requirements of this document for fresh and hardened concrete including consistence, strength, durability, and protection of embedded steel against corrosion.

Where there is no European standard for a particular constituent material which refers specifically to the use of this constituent material in concrete conforming to EN 206, the establishment of suitability may result from:

- a European Technical Approval which refers specifically to the use of the constituent material in concrete conforming to EN 206; or
- the relevant national standards or provisions valid in the place of use of the concrete which refers specifically to the use of the component's material in concrete conforming to EN 206.

Characteristics of constituent materials and properties of concrete shall be measured in accordance with EN 206 except where otherwise given in the following clauses.

#### 4.2 Type of cement

Cement shall comply with EN 197-1 and the type of cement shall be selected in accordance with EN 206 for the specified exposure class. Additional requirements may be specified by relevant national standard or provisions in the place of use.

#### 4.3 Aggregates

#### 4.3.1 General

Aggregates shall comply with EN 12620. The permitted types and classes of aggregates shall be specified by relevant national standard or provisions in the place of use. PREVIEW

#### 4.3.2 Maximum size of aggregates

The maximum nominal size of aggregate shall not exceed one third (1/3) of the layer thickness.

For jointed reinforced concrete and continuously reinforced concrete pavements, the maximum aggregate size shall not exceed one fourth  $(\frac{1}{4})$  of the spacing between the reinforcing bars.

#### 4.4 Mixing water

https://standards.iteh.ai/catalog/standards/sist/389655f6-5ea6-40e7-a97e-e4e0025e68ba/osist-pren-13877-1-

Mixing water for concrete shall comply with EN 10082022

#### 4.5 Other constituent materials

Admixtures, additions and other constituent materials, when used, shall comply with the requirements of EN 206.

#### **Basic requirements for concrete** 5

#### 5.1 General

The specified properties of the concrete shall be measured as prescribed in EN 206 and in this document. In specifying the concrete, account shall be taken of the environmental, traffic and site conditions, and the effect these may have on the concrete.

#### 5.2 Fresh concrete

#### 5.2.1 Consistence

The consistence of concrete shall be in accordance with the requirements of EN 206.

The consistence of concrete may be specified by consistence class or by target value in accordance with EN 206, which should be suitable for the construction equipment.

#### 5.2.2 Air content

When the air content of concrete is to be determined, it shall be measured *in situ* in accordance with EN 12350-7.

Air content may be specified by relevant national standards or provisions in the place of use.

#### 5.2.3 Cement content

The minimum cement content shall be in accordance with the requirements of EN 206. A higher minimum cement content may be specified by relevant national standards or provisions in the place of use.

#### 5.2.4 Content of particles smaller than 0,250 mm

The content of particles smaller than 0,250 mm shall conform to the national standards or the provisions in the place of use.

#### 5.2.5 Chloride content

When concrete contains embedded steel not protected against chloride induced corrosion the total chloride ions content shall not exceed 0,40 % of the mass of cement in accordance with EN 206.

#### 5.3 Hardened concrete

## 5.3.1 Resistance to the effects of freeze-thaw and de-icing agents

Where concrete is exposed to significant attack by freeze—thaw cycles with and without de-icing agents, the freeze—thaw resistance can be specified according to a test method described in CEN/TS 12390-9 or by relevant national standards or provisions in the place of use.

## 5.3.2 Mechanical strength (standards.iteh.ai)

Specimens shall be evaluated for mechanical strength by one (or more) of the following methods:

- compressive strength/in accordance with EN 12390-3;rds/sist/389655f6-5ea6-40e7-a97e-e4e0025e68ba/osist-pren-13877-1-
- tensile splitting strength in accordance with EN 12390-6;
- tensile strength on cylindrical discs in accordance with prEN 13863-6;
- flexural strength in accordance with EN 12390-5.

NOTE 1 The standards EN 12390-6 and EN 13863-6 make use of different types of specimens for the determination of the tensile strength and can yield different results. EN 13863-6 contains precision data, while EN 12390-6 does not. The same table of classes (Table 1) is used for both types of tensile strength.

#### Where required

- a class of compressive strength shall be selected and specified in accordance with EN 206;
- a class of tensile splitting strength or tensile strength on cylindrical discs shall be selected and specified in accordance with Table 1;
- a class of flexural strength shall be selected and specified in accordance with Table 2.

NOTE 2 The required class is related to a specific type of specimen.

- All concrete will be assessed for conformity by the producer using the requirements in EN 206.
   Where flexural strength is specified, conformity assessment shall be made in the same way as for tensile splitting strength.
- When mechanical strength is to be evaluated on cores, the procedure given in prEN 13877-2:2021, 4.2, shall be followed.

Table 1 — Tensile splitting strength,  $f_{SK}$  or tensile strength on cylindrical discs,  $f_{ct,cd}$  classes

Strength class <sup>a</sup>	$f_{ m sk}$ or $f_{ct,cd}$ b [MPa]	
S1,3	1,3	
S1,7	1,7	
S2,0	2,0	
S2,4	2,4	
S2,7	2,7	
sa,o iTeh S'	TANDA 3,0D	
S3,3 <b>PR</b>	F.VIF.W 3,3	
S3,7	3,7	
S4,0 (Standa	irds.iteh <sub>4,31)</sub>	
S4,3	4,3	
https://standards.iteh.ai/catalog/standards/sist/389655f6-		
5 <b>\$4</b> ( <b>8</b> 40e7-a97e-e4e(025e68ba/osist-p <b>4</b> ; <b>8</b> -13877-1-		
S5,0	5,0	
S5,5	5,5	
S6,0	6,0	

 $<sup>^{\</sup>rm a}$  In special cases intermediate strength levels between those given may be used if this is permitted by the relevant design standard.

 $<sup>^</sup>b\ f_{sk}$  is the characteristic tensile splitting strength and  $f_{ct,cd}$  is the tensile strength on cylindrical discs. Unless specified otherwise in national regulations this strength is determined at 28 days. The diameter of the specimen shall be at least three times the nominal size of the aggregate in the concrete.