
**Rubber hoses and hose assemblies,
wire or textile reinforced, for dredging
applications — Specification**

*Tuyaux et flexibles en caoutchouc, à armature textile ou métallique,
pour des applications de dragage — Spécifications*

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO 28017:2018

<https://standards.iteh.ai/catalog/standards/iso/c0a8aebf-0b77-4139-8a66-f73340fc74cf/iso-28017-2018>



iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO 28017:2018

<https://standards.iteh.ai/catalog/standards/iso/c0a8aebf-0b77-4139-8a66-f73340fc74cf/iso-28017-2018>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Classification	2
4.1 Classes	2
4.2 Grades	2
5 Materials and construction	3
5.1 Hoses	3
5.2 Flotation material	3
5.3 End fittings and end connections	4
6 Dimension and tolerances	4
6.1 Diameters	4
6.2 Hose assembly length	5
7 Physical properties	5
7.1 Rubber compounds	5
7.1.1 Abrasion resistance of lining	5
7.1.2 Tear strength of lining	5
7.1.3 Rebound resilience of lining	5
7.1.4 Ozone resistance of cover	5
7.2 Performance requirements	6
7.2.1 Hydrostatic requirements	6
7.2.2 Change in length	6
7.2.3 Bending test	7
7.2.4 Leakage of hose assemblies (proof pressure test)	7
7.2.5 Minimum reserve buoyancy	7
7.2.6 Flotation material recovery	8
7.2.7 Adhesion between components	8
7.2.8 Adhesion between end fitting and lining	8
7.2.9 Minimum tensile strength of empty hose assemblies	9
7.2.10 Vacuum resistance	9
7.2.11 Dimensions of flange and other connections	9
7.2.12 Visual examination	9
7.3 Frequency of testing	9
8 Test certificate or report	10
9 Marking	10
10 Recommendations for packaging and storage	10
Annex A (normative) Type tests and routine tests	11
Annex B (normative) Measurement of adhesion between end fitting and lining	12
Annex C (normative) Hose assembly tensile-strength test	15
Bibliography	18

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 1, *Rubber and plastics hoses and hose assemblies*.

This third edition cancels and replaces the second edition (ISO 28017:2011), of which it constitutes a minor revision. The changes compared to previous edition are as follows: the Amendment ISO 28017:2011/Amd 1:2015 has been incorporated and the normative references have been updated.

Rubber hoses and hose assemblies, wire or textile reinforced, for dredging applications — Specification

1 Scope

This document specifies requirements for two types, seven classes and three grades of wire- or textile-reinforced dredging hoses with nominal sizes ranging from 100 to 1 200. Within each class, all grades and sizes have the same maximum working pressure. Such hoses are suitable for the delivery or suction of seawater or freshwater mixed with silt, sand, coral and small stones with a specific gravity in the range from 1,0 to 2,3 at ambient temperatures ranging from -10 °C to +40 °C.

This document covers two types of hose, as follows:

- type 1: floating type, for delivery only, which includes flotation material to give the hose buoyancy;
- type 2: submarine type for delivery and suction.

This document does not specify requirements concerning the service life of hoses or hose assemblies. Specifying such requirements is the responsibility of the customer, in consultation with the hose manufacturer.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 34-2:2015, *Rubber, vulcanized or thermoplastic — Determination of tear strength — Part 2: Small (Delft) test pieces*

ISO 1402, *Rubber and plastics hoses and hose assemblies — Hydrostatic testing*

ISO 1431-1, *Rubber, vulcanized or thermoplastic — Resistance to ozone cracking — Part 1: Static and dynamic strain testing*

ISO 4649:2010, *Rubber, vulcanized or thermoplastic — Determination of abrasion resistance using a rotating cylindrical drum device*

ISO 4662:2017, *Rubber, vulcanized or thermoplastic — Determination of rebound resilience*

ISO 4671, *Rubber and plastics hoses and hose assemblies — Methods of measurement of the dimensions of hoses and the lengths of hose assemblies*

ISO 7233:2016, *Rubber and plastics hoses and hose assemblies — Determination of resistance to vacuum*

ISO 8033, *Rubber and plastics hoses — Determination of adhesion between components*

ISO 8330, *Rubber and plastics hoses and hose assemblies — Vocabulary*

ISO 10619-1, *Rubber and plastics hoses and tubing — Measurement of flexibility and stiffness — Part 1: Bending tests at ambient temperature*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 8330 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

4 Classification

4.1 Classes

Seven classes of hose are specified, distinguished by their maximum working pressure, of nominal sizes from 100 to 1 200, as shown in Table 1.

Table 1 — Classes and corresponding maximum working pressures and nominal sizes

Nominal size	Class						
	5	10	15	20	25	30	40
	Maximum working pressure, MWP						
	bar						
	5	10	15	20	25	30	40
	MPa						
	0,5	1,0	1,5	2,0	2,5	3,0	4,0
100	X	X	X	X	X	X	X
150	X	X	X	X	X	X	X
200	X	X	X	X	X	X	X
250	X	X	X	X	X	X	N/A
300	X	X	X	X	X	X	N/A
350	X	X	X	X	X	X	N/A
400	X	X	X	X	X	X	N/A
450	X	X	X	X	X	X	N/A
500	X	X	X	X	X	X	N/A
550	X	X	X	X	X	X	N/A
600	X	X	X	X	X	X	N/A
650	X	X	X	X	X	X	N/A
700	X	X	X	X	X	X	N/A
750	X	X	X	X	X	X	N/A
800	X	X	X	X	X	X	N/A
850	X	X	X	X	X	X	N/A
900	X	X	X	X	X	X	N/A
1 000	X	X	X	X	X	X	N/A
1 100	X	X	X	X	X	X	N/A
1 200	X	X	X	X	X	N/A	N/A
X: Applicable							
N/A: Not applicable							

4.2 Grades

Type 2 hoses are classified into three grades, A, B and C, according to their construction (number of reinforcing helical wires), as shown in Table 2.

Type 1 hoses are not divided into grades.

Table 2 — Grades

Type	Grade	Construction and purpose	
		Number of reinforcing wires	Purpose
1	—	0	Delivery only
2	A	2	Delivery or suction
	B	1	Delivery or suction
	C	0	Delivery only

The types and grades available in each class (i.e. for each maximum working pressure) are as shown in [Table 3](#).

Table 3 — Types and grades available in each class

Type	Grade	Class						
		5	10	15	20	25	30	40
		Maximum working pressure, MWP						
		bar						
		5	10	15	20	25	30	40
		MPa						
		0,5	1,0	1,5	2,0	2,5	3,0	4,0
1	—	X	X	X	X	X	X	X
2	A	X	X	X	N/A	N/A	N/A	N/A
	B	X	X	X	N/A	N/A	N/A	N/A
	C	X	X	X	X	X	X	X

X: Applicable
N/A: Not applicable

5 Materials and construction

5.1 Hoses

Type 1 hose assemblies shall consist of an abrasion-resistant rubber lining, one or more layers of steel or textile reinforcement, a textile-reinforced rubber undercover, a flexible closed-cell flotation material integrally fitted round the hose body as described in [5.2](#), an abrasion- and weather-resistant rubber or thermoplastic outer cover (which, in the case of a rubber cover, can include one or two textile breaker layers), and end fittings as described in [5.3](#) on both ends.

Type 2 hose assemblies shall consist of an abrasion-resistant rubber lining, one or more layers of steel or textile reinforcement, a textile-reinforced rubber, full rubber or thermoplastic cover at least 6 mm thick for hoses of nominal size less than 500, at least 10 mm thick for hoses of nominal size in the range from 500 to 850 inclusive and at least 12 mm thick for hoses of nominal size in the range from 900 to 1 200 inclusive, and end fittings as described in [5.3](#) on both ends. The lining thickness shall be at least 8 mm for nominal sizes up to and including 200, at least 10 mm for nominal sizes 250 to 500 inclusive, at least 12 mm for nominal sizes 550 to 800 inclusive and at least 16 mm for nominal sizes 850 to 1 200 inclusive.

5.2 Flotation material

The closed-cell flotation material used in type 1 hose assemblies shall adhere firmly both to the hose body and to the outer cover so that it cannot move or tend to become detached in service. At the ends of the hose, a space shall be provided to facilitate the insertion of connection bolts and to allow the use

of mechanical tools for tightening nuts on the bolts. The flotation material shall be distributed over the whole length of the hose assembly in such a manner that the hose assembly floats evenly when connected to other assemblies in a string. This does not apply to hose assemblies for special applications (e.g. the end of a string, tapered hose, etc.).

5.3 End fittings and end connections

End fittings shall be mechanically and chemically bonded to the hose body. With hoses intended for delivery use only, clamped-on and swaged-on nipples are not acceptable, but such nipples may be utilized with hoses intended for suction use. Alternatively, flanged end connections built up of hose reinforcement, lining and cover material are acceptable provided they are additionally reinforced by steel stiffening rings to avoid distortion when the connection bolts are tightened. All hose assemblies shall be fitted with either end fittings or flanged end connections unless otherwise required by the end user.

6 Dimension and tolerances

6.1 Diameters

When measured in accordance with ISO 4671, the inside diameters of hoses shall conform to the values given in [Table 4](#).

When measured in accordance with ISO 4671, the outside diameters of hoses shall conform to the values specified by the customer.

NOTE For hoses manufactured on mandrels with diameters in inches, the tolerances on the inside diameter are the same as those given for hoses with diameters in metric units in [Table 4](#) (i.e. ± 3 mm for sizes 4 in to 8 in inclusive, ± 4 mm for 10 in to 12 in inclusive, ± 5 mm for 14 in to 30 in inclusive, ± 6 mm for 32 in to 40 in inclusive and ± 7 mm for 44 in and 48 in).

Table 4 — Diameters of hoses

Nominal size	Actual inside diameter	
	min.	max.
100	97	103
150	147	153
200	197	203
250	246	254
300	296	304
350	345	355
400	395	405
450	445	455
500	495	505
550	545	555
600	595	605
650	645	655
700	695	705
750	745	755
800	794	806
850	844	856
900	894	906

Table 4 (continued)

Nominal size	Actual inside diameter	
	mm	
	min.	max.
1 000	994	1 006
1 100	1 093	1 107
1 200	1 193	1 207

6.2 Hose assembly length

The hose assembly length shall be determined according to the conditions of use. Unless otherwise agreed between the customer and the manufacturer, the tolerances on the hose assembly length shall be +2 % and -2 %.

7 Physical properties

7.1 Rubber compounds

7.1.1 Abrasion resistance of lining

7.1.1.1 Test pieces

Test pieces shall be prepared from sheets of lining compound (of cure state equivalent to that of the hose) of thickness at least 6 mm. The method of preparation shall be as specified in ISO 4649.

7.1.1.2 Abrasion resistance

When the test is carried out in accordance with ISO 4649:2010, method A, the relative volume loss, ΔV_{rel} , shall not be greater than 200 mm³. This test is required each time type testing is carried out and when a change in lining compound is made, and shall be regularly repeated in accordance with the manufacturer's quality control procedures.

7.1.2 Tear strength of lining

When tested in accordance with ISO 34-2:2015, measuring the test pieces in accordance with method 2 (ISO 34-2:2015, 6.2.2.3), the tear strength, F_0 , shall be greater than 35 N. This test is required for each batch of lining compound (which might be used to manufacture more than one hose). Alternatively, the tear strength of the lining may be determined in accordance with ISO 34-1:2015, method B, procedure (b), in which case the minimum required value is 35 kN/m.

7.1.3 Rebound resilience of lining

For certain slurries containing a large quantity of sharp gravel, broken rocks or coral, the hose user can require a lining with high rebound resilience properties. In this case, the lining compound shall be tested for rebound resilience in accordance with ISO 4662:2017, Clause 5 (the pendulum method). A recommended minimum rebound resilience value is 35 %.

7.1.4 Ozone resistance of cover

7.1.4.1 Test pieces

Test pieces shall be prepared from sheets of cover compound (of cure state equivalent to that of the hose) of thickness at least 2 mm. The method of preparation shall be as specified in ISO 1431-1. For

type 1 hoses, it is the compound from which the outer cover (that surrounds the flotation material) is made which is tested.

7.1.4.2 Ozone resistance

When the test is carried out in accordance with ISO 1431-1, no cracking or other deterioration of the test pieces shall be visible under $\times 2$ magnification after 72 h at 40 °C and 20 % strain in 50 pphm ozone. This test is required each time type testing is carried out and shall be repeated whenever a change in compound is made and regularly afterwards when required by the manufacturer's quality control procedures.

7.2 Performance requirements

7.2.1 Hydrostatic requirements

When determined in accordance with ISO 1402, the proof pressure and the minimum burst pressure of hoses and hose assemblies shall conform to the values given in [Table 5](#).

The theoretical minimum burst pressure for each hose assembly of each design in a manufacturer's range shall be calculated and included in the manufacturer's sales documentation for the information of potential users.

Burst testing shall be carried out on a mid-range or larger nominal size of each design in the manufacturer's range. The minimum burst pressure of other sizes of the same design, construction (with a reinforcement type identical to that of the hose assembly tested but not necessarily the same number of plies), materials and method of manufacture shall be determined by calculation. However, this is an acceptable method only if calculation, before testing, of the burst pressure of the hose assembly tested gives a result which is not more than 5 % higher than the actual measured burst pressure. If the calculated burst pressure is more than 5 % higher, the minimum burst pressure of all other sizes in the range shall be determined by testing.

For type 1 hoses, the burst test shall be carried out on a hose assembly without its flotation material.

Table 5 — Maximum working pressure, proof pressure and minimum burst pressure

Class	Maximum working pressure	Proof pressure		Minimum burst pressure	
		Type 1	Type 2	Type 1	Type 2
	MPa (bar)	MPa (bar)	MPa (bar)	MPa (bar)	MPa (bar)
5	0,5 (5)	0,5 (5)	0,5 (5)	1,5 (15)	1,5 (15)
10	1,0 (10)	1,0 (10)	1,0 (10)	3,0 (30)	3,0 (30)
15	1,5 (15)	1,5 (15)	1,5 (15)	4,5 (45)	4,5 (45)
20	2,0 (20)	2,0 (20)	2,0 (20)	6,0 (60)	6,0 (60)
25	2,5 (25)	2,5 (25)	2,5 (25)	7,5 (75)	7,5 (75)
30	3,0 (30)	3,0 (30)	3,0 (30)	9,0 (90)	9,0 (90)
40	4,0 (40)	4,0 (40)	4,0 (40)	12,0 (120)	12,0 (120)

7.2.2 Change in length

When determined in accordance with ISO 1402, the change in length of the hose at the maximum working pressure shall not exceed +11 % or -2 %.