INTERNATIONAL STANDARD

Seventh edition 2020-02

Natural rubber latex concentrate — Determination of alkalinity

Latex concentré de caoutchouc naturel — Détermination de l'alcalinité

iTeh Standards (https://standards.iteh.ai) Document Preview

ISO 125:2020

https://standards.iteh.ai/catalog/standards/iso/9b7edcca-6cdd-4fc5-862e-79e5e63d3bcb/iso-125-2020



Reference number ISO 125:2020(E)

iTeh Standards (https://standards.iteh.ai) Document Preview

ISO 125:2020

https://standards.iteh.ai/catalog/standards/iso/9b7edcca-6cdd-4fc5-862e-79e5e63d3bcb/iso-125-2020



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Fax: +41 22 749 09 47 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

Page

Contents

Foreword		iv
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Principle	1
5	Reagents	1
6	Apparatus	2
7	Sampling	2
8	Procedure 8.1 General 8.2 Potentiometric titration 8.3 Titration using a visual indicator	2 2 2 3
9	Expression of results	3
10	Precision	3
11	Test report	3
Annex Biblio	Annex A (informative) Precision data Bibliography	

Document Preview

ISO 125:2020

https://standards.iteh.ai/catalog/standards/iso/9b7edcca-6cdd-4fc5-862e-79e5e63d3bcb/iso-125-2020

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see <u>www.iso.org/</u> iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

This seventh edition cancels and replaces the sixth edition (ISO 125:2011), which has been technically revised. The main changes are as follows: ISO 125:2020

- addition of <u>5.2.1</u> on the standardization of sulfuric acid;
- update of 8.3 to include titration with sulfuric acid;
- update of the precision statement in <u>Annex A</u>.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at <u>www.iso.org/members.html</u>.

Natural rubber latex concentrate — Determination of alkalinity

WARNING — Persons using this document should be familiar with normal laboratory practice. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and determine the applicability of regulatory limitations.

1 Scope

This document specifies a method for the determination of the alkalinity of natural rubber latex concentrate.

The method is not necessarily suitable for latices from natural sources other than *Hevea brasiliensis* or for synthetic rubber latices, compounded latex, vulcanized latex or artificial dispersions of rubber.

NOTE A method for the determination of the alkalinity of polychloroprene latex is specified in ISO 13773.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 123, Rubber latex — Sampling cument Preview

ISO 976, Rubber and plastics — Polymer dispersions and rubber latices — Determination of pH

[SO 125:2020

ntti 3://sTerms and definitions dards/iso/9b7edcca-6cdd-4fc5-862e-79e5e63d3bcb/iso-125-2020

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <u>https://www.iso.org/obp</u>
- IEC Electropedia: available at <u>http://www.electropedia.org/</u>

4 Principle

A test portion of latex concentrate is titrated with acid to pH 6 in the presence of a stabilizer to prevent coagulation, either electrometrically or with methyl red as a visual indicator. The alkalinity is calculated from the quantity of acid required.

5 Reagents

Use distilled water or water of equivalent purity, wherever water is specified, and reagents of recognized analytical quality.

5.1 Stabilizer solution: 5 % (by mass) solution of a non-ionic stabilizer of the alkyl phenol polyethylene oxide condensate type. Before use, the pH of the solution shall be adjusted to a value of $6,0 \pm 0,05$.

5.2 Sulfuric acid, $c(H_2SO_4) = 0.05 \text{ mol/dm}^3$, or hydrochloric acid, $c(HCl) = 0.1 \text{ mol/dm}^3$, standard volumetric solution.

5.2.1 Standardization of sulfuric acid, standardize 0,05 mol/dm³ H_2SO_4 by pipetting 10 cm³ of 0,05 mol/dm³ Na_2CO_3 solution (5.5) into a flask and titrating with 0,05 mol/dm³ H_2SO_4 , using methyl orange (5.4) as indicator.

5.2.2 Standardization of hydrochloric acid, standardize 0,1 mol/dm³ HCl by pipetting 10 cm³ of 0,05 mol/dm³ Na₂CO₃ solution (5.5) into a flask and titrating with 0,1 mol/dm³ HCl, using methyl orange (5.4) as indicator.

5.3 Methyl red, 0,1 % solution in ethanol of minimum purity 95 % (by volume).

5.4 Methyl orange, 0,1 % solution in ethanol of minimum purity 95 % (by volume).

5.5 Sodium carbonate solution, $c(Na_2CO_3) = 0.05 \text{ mol/dm}^3$.

Dry the Na₂CO₃ used to prepare this solution at 120 °C \pm 5 °C for 2 h before preparing the solution.

6 Apparatus

Standard laboratory equipment together with:

6.1 Electrical stirrer, with earthed (grounded) motor and non-metallic propeller-type blade, or **magnetic stirrer**.

6.2 pH-meter, equipped with a combined electrode suitable for use in solutions up to pH 12, as specified in ISO 976, and capable of being read to 0,02 pH-units.

6.3 Balance, capable of being read to 0,01 g. <u>ISO 125:2020</u> https://standards.iteh.ai/catalog/standards/iso/9b7edcca-6cdd-4fc5-862e-79e5e63d3bcb/iso-125-2020

7 Sampling

Carry out sampling in accordance with one of the methods specified in ISO 123.

8 Procedure

8.1 General

Carry out the determination in duplicate.

Add, while stirring, 10 cm³ of stabilizer solution (<u>5.1</u>) to about 200 cm³ of water in a 400 cm³ beaker.

Weighing to the nearest 10 mg, add between 5 g and 10 g of the latex concentrate by difference from a weighing bottle and stir until thoroughly mixed.

Ensure that the latex is added so that none runs down the side of the beaker (which could result in loss of ammonia) or down the side of the weighing bottle.

Titrate the resulting mixture either by the method described in 8.2 or by that described in 8.3.

8.2 Potentiometric titration

Insert the electrode of the pH-meter and, with continual stirring, add sulfuric acid or hydrochloric acid solution (5.2) from a burette, adding the acid drop by drop on approaching the end point of pH 6,0 \pm 0,05.