



Designation: D 6116 – 00 (Reapproved 2005)

## Standard Test Method for Blocking<sup>1</sup>

This standard is issued under the fixed designation D 6116; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This test method covers the determination of the resistance of leather to blocking under specific conditions of temperature, humidity, and pressure. This test method does not apply to wet blue.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Apparatus

2.1 *Forced Circulating Hot Air Oven*, capable of maintaining  $80 \pm 3^\circ\text{C}$ .

2.2 *American Medical Museum Jar (with Lid)*, having inner dimensions of 16 cm high, 10 cm long, and 8 cm wide. There shall be three indentations at the top of each 8 cm side.

2.3 *Petri Dish*, 100 by 15 mm, with cover.

2.4 *Weight*, 2000 g.

### 3. Test Specimen

3.1 Test one rectangular 2.5 by 10 cm specimen per sample.

### 4. Procedure

4.1 The specimen shall be perforated 2 mm from one end and hung on a standard size paper clip that has been opened to its full length. No more than five specimens shall be hung on one clip. The clip holding the specimen shall be set into the indentations of the jar. No more than three clips shall be placed in a jar. The jar shall be filled with tap water at  $23 \pm 2^\circ\text{C}$  to a level no higher than 1.25 cm from the bottom of the hanging

specimen. The lid shall then be placed on the jar and the specimen allowed to condition for 4 h.

4.2 After conditioning, the specimen shall be removed from the jar and immediately folded grain to grain to form a 2.5 by 5 cm rectangle. The folded specimen shall then be placed in an inverted (rim up) petri dish cover. The bottom plate of the dish shall then be placed concentrically within the inverted cover plate so as to cover the specimen evenly.

4.3 A 2000 g weight shall be placed on top of the inverted bottom plate. The whole assembly shall then be placed in an oven at  $80 \pm 3^\circ\text{C}$  for 2 h and then removed. The weight and cover plate shall be removed from the assembly and the specimen allowed to cool for 30 min.

4.4 The cooled and folded specimen shall be examined by slowly pulling the fold apart by hand. The specimen shall be examined for ease of separation, grain damage, and finish peeling.

### 5. Report

5.1 Report resistance of specimen to blocking by the following scale:

- 1—Pass. No blocking.
- 2—Fail. Finish peeling.

### 6. Precision and Bias

6.1 This test method is adopted from the procedures of the federal government where it has been in use and where it was approved for publication before the inclusion of precision and bias statements was mandated. The original interlaboratory test data is no longer available. The user is cautioned to verify by use of reference materials, if available, that the precision and bias of this test method is adequate for contemplated use.

### 7. Keywords

7.1 blocking; leather

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D31 on Leather and is the direct responsibility of Subcommittee D31.05 on Upholstery.

Current edition approved Sept. 1, 2005. Published September 2005. Originally approved in 1997. Last previous edition approved in 2000 as D 6116 – 00.



**D 6116 – 00 (2005)**

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)).*

## iTeh Standards (<https://standards.iteh.ai>) Document Preview

[ASTM D6116-00](#)

[/catalog/standards/astm/23406e01-293d-4715-af36-f143b8f50977/astm-d6116-00](#)