



SLOVENSKI STANDARD
oSIST prEN ISO 4035:2022
01-junij-2022

Vežni elementi - Šestrobe nizke matice (tip 0) (ISO/DIS 4035:2022)

Fasteners - Hexagon thin nuts (style 0) (ISO/DIS 4035:2022)

Mechanische Verbindungselemente – Niedrige Sechskantmuttern (Typ 0) (ISO/DIS 4035:2022)

Fixations - Écrous bas hexagonaux (style 0) (ISO/DIS 4035:2022)

Ta slovenski standard je istoveten z: prEN ISO 4035

[oSIST prEN ISO 4035:2022](https://standards.iteh.ai/catalog/standards/sist/d744672d-88a9-4648-9b42-1aa00db2afd7/osist-pren-iso-4035-2022)

<https://standards.iteh.ai/catalog/standards/sist/d744672d-88a9-4648-9b42-1aa00db2afd7/osist-pren-iso-4035-2022>

ICS:

21.060.20 Matice Nuts

oSIST prEN ISO 4035:2022

en,fr,de

**iTeh STANDARD
PREVIEW
(standards.iteh.ai)**

[oSIST prEN ISO 4035:2022](https://standards.iteh.ai/catalog/standards/sist/d744672d-88a9-4648-9b42-1aa00db2afd7/osist-pren-iso-4035-2022)

<https://standards.iteh.ai/catalog/standards/sist/d744672d-88a9-4648-9b42-1aa00db2afd7/osist-pren-iso-4035-2022>

DRAFT INTERNATIONAL STANDARD

ISO/DIS 4035

ISO/TC 2/SC 12

Secretariat: DIN

Voting begins on:
2022-04-20Voting terminates on:
2022-07-13

Fasteners — Hexagon thin nuts (style 0)

Fixations — Écrous bas hexagonaux (style 0)

ICS: 21.060.20

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 4035:2022](https://standards.iteh.ai/catalog/standards/sist/d744672d-88a9-4648-9b42-1aa00db2afd7/osist-pren-iso-4035-2022)<https://standards.iteh.ai/catalog/standards/sist/d744672d-88a9-4648-9b42-1aa00db2afd7/osist-pren-iso-4035-2022>

This document is circulated as received from the committee secretariat.

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 4035:2022(E)

© ISO 2022

**iTeh STANDARD
PREVIEW
(standards.iteh.ai)**

[oSIST prEN ISO 4035:2022](https://standards.iteh.ai/catalog/standards/sist/d744672d-88a9-4648-9b42-1aa00db2afd7/osist-pren-iso-4035-2022)

<https://standards.iteh.ai/catalog/standards/sist/d744672d-88a9-4648-9b42-1aa00db2afd7/osist-pren-iso-4035-2022>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents		Page
Foreword		iv
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Dimensions	2
5	Requirements and reference International Standards	3
6	Marking and labelling	5
	6.1 Marking on product.....	5
	6.2 Labelling on package.....	5
7	Designation	5
Annex A (normative) Nuts with $D < M5$ and $D > M39$, not included in ISO 898-2		6
Bibliography		10

**iTeh STANDARD
PREVIEW
(standards.iteh.ai)**

[oSIST prEN ISO 4035:2022](https://standards.iteh.ai/catalog/standards/sist/d744672d-88a9-4648-9b42-1aa00db2afd7/osist-pren-iso-4035-2022)

<https://standards.iteh.ai/catalog/standards/sist/d744672d-88a9-4648-9b42-1aa00db2afd7/osist-pren-iso-4035-2022>

ISO/DIS 4035:2022(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword Supplementary information

The committee responsible for this document is ISO/TC 2, Fasteners, Subcommittee SC 12, Fasteners with metric internal thread.

This fifth edition cancels and replaces the fourth edition (ISO 4035:2012).

The main changes compared to the previous edition are as follows:

- the use of thin nuts and a warning in relation to lower thread stripping resistance have been added in scope;
- nuts with $D < M5$ and $D > M39$ (not included in ISO 898-2) have been dealt with in normative [Annex A](#);
- M7 has been added;
- $d_{w,min}$ for sizes $d \leq M5$ has been changed from $s_{min} - IT16$ to $s_{min} - IT15$ in order to have a larger bearing surface area and thus less contact pressure;
- $d_{a,max}$ and $d_{w,min}$ have been specified with two decimal places;
- for steel nuts, quenching and tempering condition has been specified in accordance with ISO 898-2;
- for stainless-steel nuts, grades D4 and D6 and property classes 80 have been added;
- non-ferrous metal nuts have been cancelled (as a consequence of the cancellation of ISO 8839);
- specifications for marking and labelling have been added as [Clause 6](#).

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Fasteners — Hexagon thin nuts (style 0)

1 Scope

This document specifies the characteristics of hexagon thin nuts (style 0), in steel and stainless steel, with metric coarse pitch thread M1,6 to M64, and with product grades A and B.

Thin nuts used as jam nuts are to be assembled together with a regular or high nut.

WARNING — Thin nuts (style 0) have a reduced loadability compared to regular nuts or high nuts, and are not designed to provide resistance to thread stripping (see ISO 898-2).

If in certain cases other specifications are requested, stainless steel grades and property classes can be selected from ISO 3506-2.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 225, *Fasteners — Bolts, screws, studs and nuts — Symbols and descriptions of dimensions*

ISO 898-2, *Fasteners — Mechanical properties of fasteners made of carbon steel and alloy steel — Part 2: Nuts with specified property classes*

ISO 965-1, *ISO general purpose metric screw threads — Tolerances — Part 1: Principles and basic data*

ISO 1891-4, *Fasteners — Vocabulary — Part 4: Control, inspection, delivery, acceptance and quality*

ISO 3269, *Fasteners — Acceptance inspection*

ISO 3506-2, *Fasteners — Mechanical properties of corrosion-resistant stainless steel fasteners — Part 2: Nuts with specified grades and property classes*

ISO 4042, *Fasteners — Electroplated coating systems*

ISO 4759-1, *Tolerances for fasteners — Part 1: Bolts, screws, studs and nuts — Product grades A, B and C*

ISO 6157-2, *Fasteners — Surface discontinuities — Part 2: Nuts*

ISO 8991, *Designation system for fasteners*

ISO 8992, *Fasteners — General requirements for bolts, screws, studs and nuts*

ISO 10683, *Fasteners — Non-electrolytically applied zinc flake coating systems*

ISO 10684, *Fasteners — Hot dip galvanized coatings*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at <https://www.iso.org/obp>

ISO/DIS 4035:2022(E)

— IEC Electropedia: available at <https://www.electropedia.org/>

4 Dimensions

Dimensions for nuts with sizes M5 to M39 shall be in accordance with [Figure 1](#) and with [Tables 1](#) and [2](#). Dimensions for nuts with sizes $D < M5$ and $D > M39$ shall be in accordance with [Annex A](#).

Symbols and descriptions of dimensions are defined in ISO 225.




Figure 1 — Nuts without washer-face

(standards.iteh.ai)

[oSIST prEN ISO 4035:2022](https://standards.iteh.ai/catalog/standards/sist/d744672d-88a9-4648-9b42-1aa00db2afd7/osist-pren-iso-4035-2022)

<https://standards.iteh.ai/catalog/standards/sist/d744672d-88a9-4648-9b42-1aa00db2afd7/osist-pren-iso-4035-2022>

Table 1 — Dimensions for nuts M5 to M18

Dimensions in millimetres

Thread, D		M5	M6	(M7)	M8	M10	M12	(M14)	M16	(M18)
p^a		0,8	1	1	1,25	1,5	1,75	2	2	2,5
d_a	max.	5,75	6,75	7,75	8,75	10,80	12,96	15,12	17,28	19,44
	min.	5,00	6,00	7,00	8,00	10,00	12,00	14,00	16,00	18,00
d_w	min.	7,20	8,88	9,63	11,63	14,63	16,63	19,64	22,49	24,85
e	min.	8,79	11,05	12,12	14,38	17,77	20,03	23,36	26,75	29,56
m	max.	2,70	3,20	3,70	4,00	5,00	6,00	7,00	8,00	9,00
	min.	2,45	2,90	3,40	3,70	4,70	5,70	6,42	7,42	8,42
m_w	min.	1,96	2,32	2,72	2,96	3,76	4,56	5,14	5,94	6,74
s	nom. = max.	8,00	10,00	11,00	13,00	16,00	18,00	21,00	24,00	27,00
	min.	7,78	9,78	10,73	12,73	15,73	17,73	20,67	23,67	26,16

NOTE Sizes shown in brackets are non-preferred dimensions.

^a P is the pitch of the thread.

Table 2 — Dimensions for nuts M20 to M39

Dimensions in millimetres

Thread, D		M20	(M22)	M24	(M27)	M30	(M33)	M36	(M39)
p^a		2,5	2,5	3	3	3,5	3,5	4	4
d_a	max.	21,60	23,76	25,92	29,16	32,40	35,64	38,88	42,12
	min.	20,00	22,00	24,00	27,00	30,00	33,00	36,00	39,00
d_w	min.	27,70	31,35	33,25	38,00	42,75	46,55	51,11	55,86
e	min.	32,95	37,29	39,55	45,20	50,85	55,37	60,79	66,44
m	max.	10,00	11,00	12,00	13,50	15,00	16,50	18,00	19,50
	min.	9,10	9,90	10,90	12,40	13,90	15,40	16,90	18,20
m_w	min.	7,28	7,92	8,72	9,92	11,12	12,32	13,52	14,56
s	nom. = max.	30,00	34,00	36,00	41,00	46,00	50,00	55,00	60,00
	min.	29,16	33,00	35,00	40,00	45,00	49,00	53,80	58,80

NOTE Sizes shown in brackets are non-preferred dimensions.

^a P is the pitch of the thread.

5 Requirements and reference International Standards

The requirements specified in the International Standards referenced in [Table 3](#) shall apply. For nuts with $D < M5$ and $D > M39$, [Annex A](#) shall apply.

Table 3 — Requirements and reference International Standards

Material		Steel	Stainless steel	
General requirements	International Standard	ISO 8992		
Thread	Tolerance class	6H ^a		
	International Standard	ISO 965-1		
Mechanical properties	Style	0		
	Property class and symbol	M5 ≤ D ≤ M39	04 ^b , 05 ^c	
		D < M5 and D > M39	Annex A	—
	Grade ^d and property class and symbol	—		M5 ≤ D ≤ M24
		—		M24 < D ≤ M39
—		D < M5 and D > M39		
International Standard	ISO 898-2	ISO 3506-2		
Tolerances	Product grade	D ≤ M16: A (except for M5 where $d_{w,min} = s_{min} - IT15$) D > M16: B		
	International Standard	ISO 4759-1		
Finish - Coating	As processed (no coating)		Clean and bright and/or Passivated ^e	
	Electroplated coatings as specified in ISO 4042			
Surface integrity	Non-electrolytically applied zinc flake coatings as specified in ISO 10683		As agreed ^f	
	Hot dip galvanized coatings as specified in ISO 10684			
		Other finishes, coatings and/or additional requirements shall be agreed between the purchaser and the supplier		
Surface integrity	Limits for surface discontinuities as specified in ISO 6157-2		As agreed ^f	
Acceptability	Acceptance inspection as specified in ISO 3269			

^a Depending on the type of coating to be applied, another tolerance position of the thread may be specified for the uncoated nuts in accordance with the relevant coating standard.

^b Shall not be quenched and tempered in accordance with ISO 898-2 (NQT nuts).

^c Shall be quenched and tempered in accordance with ISO 898-2 (QT nuts).

^d The most common stainless steel grades are A2 and A4; however, depending on the application, it can be necessary to select other grades in ISO 3506-2 suitable for the service corrosive environment. For use at high temperatures (up to 800 °C), mechanical properties are specified in ISO/FDIS 3506-5. See also ISO 3506-6 for the selection of suitable stainless steel grades.

^e See e.g. ISO 16048.

^f See e.g. ISO 6157-2.