



SLOVENSKI STANDARD
oSIST prEN 18064-3:2024
01-april-2024

Polimerni materiali - Priporočila za kakovost in podlaga za specifikacije za uporabo polimernih reciklatov v izdelkih - 3. del: Polipropilen (PP)

Plastics Quality recommendations and basis for specifications for application of plastic recyclates in products - Part 3 : Polypropylene (PP)

Kunststoffe - Qualitätsempfehlungen und Grundlagen für Spezifikationen für die Verwendung von Kunststoffrecyklaten in Produkten - Teil 3: Polypropylen (PP)

Plastiques - Recommandations qualité et base de spécification pour l'application des recyclats de plastiques dans les produits - Partie 3 : Polypropylène (PP)

Ta slovenski standard je istoveten z: prEN 18064-3

[oSIST prEN 18064-3:2024](https://standards.slovenski-standard.si/standard/sist/3534062-012-1-PP30-0001-3576672001-PrOSIST-prEN-18064-3-2024)

<https://standards.slovenski-standard.si/standard/sist/3534062-012-1-PP30-0001-3576672001-PrOSIST-prEN-18064-3-2024>

ICS:

13.030.50	Recikliranje	Recycling
83.080.01	Polimerni materiali na splošno	Plastics in general

oSIST prEN 18064-3:2024

en,fr,de

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

DRAFT
prEN 18064-3

April 2024

ICS 13.030.50; 83.080.01; 83.140.01

English Version

Plastics Quality recommendations and basis for specifications for application of plastic recyclates in products - Part 3 : Polypropylene (PP)

Kunststoffe - Qualitätsempfehlungen und Grundlagen für Spezifikationen für die Verwendung von Kunststoffrezyklaten in Produkten - Teil 3: Polypropylen (PP)

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 249.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword	3
Introduction	4
1 Scope.....	5
2 Normative references.....	5
3 Terms and definitions.....	6
4 Categorization of polypropylene (PP) applications and requirements.....	7
5 Selection of relevant properties for polypropylene (PP) recyclates.....	7
6 Typical range for characteristics of product families.....	7
7 Designation of polypropylene (PP) recyclates.....	7
Annex A (normative) Designatory properties polypropylene recyclate	8
A.1 Generic and additional designatory properties	8
A.2 Designation of polypropylene recyclate.....	8
A.2.1 General.....	8
A.2.2 Data block 1	8
A.2.3 Data block 2	9
A.2.4 Data block 3	10
A.2.5 Data block 4	11
A.2.5.1 General.....	11
A.2.5.2 Tensile modulus of elasticity.....	11
A.2.5.3 Charpy impact strength	11
A.2.5.4 Melt mass-flow rate.....	12
A.2.6 Data block 5	13
A.2.7 Designation examples	13
A.2.7.1 First designation example from EN ISO 19069-1	13
Annex B (normative) Typical values for product families	15
B.1 Typical values.....	15
Bibliography	21

European foreword

This document (prEN 18064-3:2024) has been prepared by Technical Committee CEN/TC 249 “Plastics”, the secretariat of which is held by SIS.

This document is currently submitted to the CEN Enquiry.

This document is part of the prEN 18064¹-series, currently consisting of all parts as listed below. This series of standards consists of a general part 1, and material specific parts for different types of plastics. This particular part covers typical values (ranges, or min/max values) for polypropylene (PP) general purpose plastics, that can be composed of 100 % recyclates (mechanical and/or chemical), or a combination of recyclates and virgin plastic.

This part is supported by other standards on test methods to which references are made throughout this document.

prEN 18064, *Plastics — Quality recommendations and basis for specifications for application of plastic recyclates in products*, is currently composed with the following parts:

- *Part 1: General aspects*
- *Part 2: Polyethylene (PE)*
- *Part 3: Polypropylene (PP)*
- *Part 4: Poly(ethylene terephthalate) (PET)*
- *Part 5: Poly(vinyl chloride) (PVC)*
- *Part 6: Polystyrene (PS)*
- *Part 7: Acrylonitrile-butadiene-styrene (ABS)*

NOTE Part 6 for PS also includes EPS and XPS.

¹ Under preparation.

prEN 18064-3:2024 (E)

Introduction

See prEN 18064-1.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[oSIST prEN 18064-3:2024](https://standards.iteh.ai/catalog/standards/sist/3f53f602-b124-449d-a0da-3570692dde44/osist-pren-18064-3-2024)

<https://standards.iteh.ai/catalog/standards/sist/3f53f602-b124-449d-a0da-3570692dde44/osist-pren-18064-3-2024>

1 Scope

This document provides relevant characteristics and typical values for polypropylene (PP) recyclates intended for groups of defined applications (the product families).

The relevant characteristics and typical values for the different product families are derived from the performance requirements of the products belonging to that family, including requirements for product manufacturing processes where applicable.

This document applies to plastic recyclates intended to be used for the manufacturing of (intermediate) products.

This document is intended to be used in conjunction with part 1 of this standard series, which describes the designation system for plastic recyclates. The designation system allows comparison between recycled and virgin material at the level of the polymer's defined designatory properties.

NOTE 1 Examples of designations of plastic recyclates are given in Annex A.

NOTE 2 The selection of relevant properties for a product family is based on EN ISO 10350-1, extended with specific properties related to plastic recyclates.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

prEN 18065², *Plastics - Recycled plastics - Classification of recycled plastics based on Data Quality Levels for use and (digital) trading*

CEN/TR 15353, *Plastics - Recycled plastics - Guidelines for the development of standards for recycled plastics*

prEN 18064-1³, *Plastics - Quality recommendations and basis for specifications for application of plastic recyclates in products - Part 1: General aspects*

EN 12099, *Plastics piping systems - Polyethylene piping materials and components - Determination of volatile content*

EN 15343, *Plastics - Recycled Plastics - Plastics recycling traceability and assessment of conformity and recycled content*

EN 15345, *Plastics - Recycled Plastics - Characterisation of Polypropylene (PP) recyclates*

EN 16516, *Construction products: Assessment of release of dangerous substances — Determination of emissions into indoor air*

EN ISO 60, *Plastics - Determination of apparent density of material that can be poured from a specified funnel (ISO 60)*

EN ISO 75-2, *Plastics - Determination of temperature of deflection under load - Part 2: Plastics and ebonite (ISO 75-2)*

² Under preparation.

³ Under preparation.

prEN 18064-3:2024 (E)

EN ISO 178, *Plastics - Determination of flexural properties (ISO 178)*

EN ISO 179-1, *Plastics - Determination of Charpy impact properties - Part 1: Non-instrumented impact test (ISO 179-1)*

EN ISO 179-2, *Plastics - Determination of Charpy impact properties - Part 2: Instrumented impact test (ISO 179-2)*

EN ISO 472:2013, *Plastics - Vocabulary (ISO 472:2013)*

EN ISO 527-1, *Plastics - Determination of tensile properties - Part 1: General principles (ISO 527-1 including Corr 1)*

EN ISO 527-2, *Plastics - Determination of tensile properties - Part 2: Test conditions for moulding and extrusion plastics (ISO 527-2)*

EN ISO 527-3, *Plastics - Determination of tensile properties - Part 3: Test conditions for films and sheets (ISO 527-3)*

EN ISO 1043-1, *Plastics - Symbols and abbreviated terms - Part 1: Basic polymers and their special characteristics (ISO 1043-1)*

EN ISO 3451-1, *Plastics - Determination of ash - Part 1: General methods (ISO 3451-1)*

EN ISO 11357-3, *Plastics - Differential scanning calorimetry (DSC) - Part 3: Determination of temperature and enthalpy of melting and crystallization (ISO 11357-3)*

EN ISO 14021, *Environmental labels and declarations - Self-declared environmental claims (Type II environmental labelling) (ISO 14021)*

EN ISO 15512, *Plastics - Determination of water content (ISO 15512)*

EN ISO 19069-1, *Plastics - Polypropylene (PP) moulding and extrusion materials - Part 1: Designation system and basis for specifications (ISO 19069-1)*

EN ISO 19069-2, *Plastics - Polypropylene (PP) moulding and extrusion materials - Part 2: Preparation of test specimens and determination of properties (ISO 19069-2)*

EN ISO 1133-1, *Plastics - Determination of the melt mass-flow rate (MFR) and melt volume-flow rate (MVR) of thermoplastics - Part 1: Standard method (ISO 1133-1)*

ISO 5677, *Testing and characterization of mechanically recycled polypropylene (PP) and polyethylene (PE) for intended use in different plastics processing techniques*

ASTM D1895, *Standard Test Methods for Apparent Density, Bulk Factor, and Pourability of Plastic Materials*

ASTM D6980-12, *Standard Test Method for Determination of Moisture in Plastics by Loss in Weight*

3 Terms, definitions and abbreviations

3.1 Terms and definitions

For the purposes of this document, the terms and definitions given in EN ISO 472:2013 and CEN/TR 15353 and the following apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1.1

typical value

indicative value intended for first contact, e. g. between converter and recycler

Note 1 to entry: Final values to be agreed e.g. between converter and recycler.

3.2 Abbreviations

For the purposes of this document, the abbreviated terms related to recyclates given in EN ISO 1043-1, prEN 18064-1 apply.

4 Categorization of polypropylene (PP) applications and requirements

The product families in combination with the relevant converting technologies are given in the dedicated annexes. In here description is given of the intended use(s) of these product families (for example impact resistant application), and for which products can these be used (containers, sheet materials, ...).

5 Selection of relevant properties for polypropylene (PP) recyclates

The mandatory characteristics are given in EN 15345.

Relevant characteristics per product family in combination with the relevant production technologies are given in Annex B.

NOTE Next to mandatory characteristics from EN 15345, this can include the optional characteristics given in EN 15345, EN ISO 19069-2 and ISO 10350-1.

6 Typical range for characteristics of product families

The relevant typical characteristics are specified in Annex B, which provides typical values (min/max values or a range as applicable) for the relevant characteristics for that product family in combination with the relevant converting technologies. This information is intended to be used for material selection by buyers of recyclate.

NOTE This part is not intended for use as a specification system, and hence cannot be used as a means to guarantee a certain recyclate quality to a buyer of plastic recyclate.

7 Designation of polypropylene (PP) recyclates

The principle for this designation system is given in prEN 18064-1

This designation provides a code describing how to declare characteristics and related typical values for recyclate materials, intended to be used for a defined category group (product family), enabling effective communication between supplier and purchaser of recyclate materials, based on the intended use (product family in combination with the relevant production technologies).

Below, in Table A.1, please find an example of designation of a polypropylene thermoplastic material is given, based on the first example given in EN ISO 19069-1.

Under A.2.7 examples of designation of a polypropylene thermoplastic material are given.

Annex A (informative)

Designatory properties polypropylene recyclate

A.1 Generic and additional designatory properties

The types of polypropylene plastics are differentiated from each other by a classification system based on appropriate levels of the designatory properties (prEN 18064-1) and the following additional designatory properties related to polypropylene:

- a) viscosity number,
- b) tensile modulus of elasticity
- c) information about chemical structure, method of processing, important properties, additives, colour, fillers and reinforcing materials.

A.2 Designation of polypropylene recyclate

A.2.1 General

The designation and specification system for thermoplastics is based on the following standardized pattern.

Designation					
Identity Block					
Description block (optional)	International Standard Block	Individual Item Block			
		Data Block 1	Data Block 2	Data Block 3	Data Block 4

The designation consists of an optional description block, reading “Thermoplastics”, and an identity block comprising the International Standard number and an individual-item block. For unambiguous coding, the individual-item block is subdivided into 5 data blocks comprising the following information.

For further information on this designation system refer to prEN 18064-1, EN ISO 19069-1 and ISO/IEC Directives, Part 2, 2021, Annex C.

A.2.2 Data block 1

Data block 1 contains information on Polymer and DQL.

In this data block, after the hyphen, polypropylene plastics are identified by the symbol “PP”, in accordance with ISO 1043-1 and EN ISO 19069-1 as below.