



Designation: D4877 – 10

Standard Test Method for Polyurethane Raw Materials: Determination of APHA Color in Isocyanates¹

This standard is issued under the fixed designation D4877; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This test method measures the color of clear liquids. It is applicable only to materials whose color-producing bodies have light-absorption characteristics similar to those of the platinum cobalt color standards used.² (See Test Method D1209 and Note 1.)

1.2 The values stated in SI units are to be regarded as standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—This standard is equivalent to ISO 6271-1:2004.

2. Referenced Documents

2.1 *ASTM Standards:*³

D883 Terminology Relating to Plastics

D1193 Specification for Reagent Water

D1209 Test Method for Color of Clear Liquids (Platinum-Cobalt Scale)

D5386 Test Method for Color of Liquids Using Tristimulus Colorimetry

2.2 *ISO Standards:*

ISO 6271-1:2004 Clear Liquids—Estimation of Color by the Platinum Cobalt Scale⁴

3. Terminology

3.1 For definitions of terms used in this test method see Terminology D883.

¹ This test method is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.22 on Cellular Materials - Plastics and Elastomers.

Current edition approved Jan. 1, 2010. Published February 2010. Originally approved in 1988. Last previous edition approved in 2004 as D4877 - 04. DOI: 10.1520/D4877-10.

² See Standard Methods for the Examination of Water, Sewage, and Industrial Wastes, AM. Public Health Assn., 1015 15th St. NW Washington, DC 20005.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

⁴ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

4. Summary of Test Method

4.1 The color of the material to be tested is compared to a series of platinum cobalt color standards, designated by mg of Pt/mL of standard solution. The results are reported as the color standard, which best matches the sample (Note 2).

NOTE 2—Color of liquids also can be measured by visible spectroscopy and the results converted to any of several color scales. These results can be converted to the APHA scale by appropriate manipulations, as for example in Test Method D5386.

5. Significance and Use

5.1 This test method can be used for research or for quality control to characterize isocyanates used in polyurethane products.

5.2 For toluene diisocyanate, results from this test method can relate to reactivity or performance in polyurethane systems.

6. Apparatus

6.1 *Nessler Tubes*, matched, 100-mL tall-form.

7. Reagents and Materials

7.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society where such specifications are available.⁵ Other grades can be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

7.2 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean reagent water as defined by Type IV or better of Specification D1193.

7.3 *Cobaltous Chloride Hexahydrate* ($\text{CoCl}_2 \cdot 6\text{H}_2\text{O}$).

⁵ *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.

*A Summary of Changes section appears at the end of this standard