
**High-pressure decorative laminates
(HPL, HPDL) — Sheets based on
thermosetting resins (usually called
laminates) —**

Part 2:

Determination of properties

iTeh STANDARD PREVIEW
(standards.iteh.ai)

*Stratifiés décoratifs haute pression (HPL, HPDL) — Plaques à base de
résines thermodurcissables (communément appelées stratifiés) —*

Partie 2: Détermination des caractéristiques

<https://standards.iteh.ai/catalog/standards/sist/c52c5dd1-81bb-4ba2-b5a8-8c843b57fa13/iso-4586-2-2018>



iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 4586-2:2018

<https://standards.iteh.ai/catalog/standards/sist/c52c5dd1-81bb-4ba2-b5a8-8c843b57fa13/iso-4586-2-2018>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	ix
Introduction	x
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Assessment of appearance	3
4.1 Principle.....	3
4.2 Apparatus.....	3
4.3 Test specimen.....	3
4.4 Procedure.....	3
4.5 Test report.....	3
5 Determination of thickness	3
5.1 Principle.....	3
5.2 Apparatus.....	4
5.3 Test specimen.....	4
5.4 Procedure.....	4
5.5 Test report.....	4
6 Determination of length and width	4
6.1 Principle.....	4
6.2 Apparatus.....	4
6.3 Test specimen.....	4
6.4 Procedure.....	4
6.5 Expression of results.....	4
6.6 Test report.....	5
7 Determination of edge straightness	5
7.1 Principle.....	5
7.2 Apparatus.....	5
7.3 Test specimen.....	5
7.4 Procedure.....	5
7.5 Expression of results.....	5
7.6 Test report.....	5
8 Determination of edge squareness (Method A)	6
8.1 Principle.....	6
8.2 Apparatus.....	6
8.3 Test specimen.....	6
8.4 Procedure.....	6
8.5 Expression of results.....	7
8.6 Test report.....	7
9 Determination of edge squareness (Method B)	7
9.1 Principle.....	7
9.2 Apparatus.....	7
9.3 Test specimen.....	7
9.4 Procedure.....	8
9.5 Expression of results.....	8
9.6 Test report.....	8
10 Determination of flatness	8
10.1 Principle.....	8
10.2 Apparatus.....	8
10.3 Test specimens.....	9
10.4 Procedure.....	9

10.5	Expression of results	9
10.6	Test report	10
11	Resistance to surface wear	10
11.1	Principle	10
11.2	Materials	10
11.3	Apparatus	10
11.4	Test specimens	11
11.5	Preparation of specimens and abrasive paper	11
11.6	Procedure	11
	11.6.1 Preparation of abrasive wheels	11
	11.6.2 Calibration of abrasive paper	11
	11.6.3 Abrasion of specimen	11
11.7	Expression of results	12
11.8	Test report	12
12	Resistance to abrasion (Flooring grade laminates)	13
12.1	Principle	13
12.2	Materials	13
12.3	Apparatus	13
12.4	Test specimens	13
12.5	Preparation of specimens and abrasive paper	13
12.6	Procedure	14
	12.6.1 Preparation of abrasive wheels	14
	12.6.2 Calibration of abrasive paper	14
	12.6.3 Abrasion of specimen	14
12.7	Expression of results	15
12.8	Test report	15
13	Resistance to immersion in boiling water	15
13.1	Principle	15
13.2	Apparatus	15
13.3	Test specimens	15
13.4	Procedure	16
13.5	Expression of results	16
13.6	Test report	17
14	Substrate protection against water vapour	17
14.1	Principle	17
14.2	Apparatus	17
14.3	Test specimens	18
14.4	Procedure	18
14.5	Expression of results	18
14.6	Test report	19
15	Resistance to water vapour	19
15.1	Principle	19
15.2	Apparatus	19
15.3	Test specimen	19
15.4	Procedure	19
15.5	Expression of results	20
15.6	Test report	21
16	Resistance to wet conditions (Exterior grade laminates)	21
16.1	Principle	21
16.2	Apparatus	21
16.3	Test specimens	21
16.4	Procedure	21
16.5	Expression of results	22
16.6	Test report	22
17	Resistance to dry heat (Method A)	23


 (standards.iteh.ai)

17.1	Principle.....	23
17.2	Apparatus and materials	23
17.3	Test specimen.....	24
17.4	Test procedure	24
17.5	Examination of the test specimen	25
17.6	Expression of results.....	25
17.7	Test report	25
18	Resistance to dry heat (Method B)	26
18.1	Principle.....	26
18.2	Materials.....	26
18.3	Apparatus	26
18.4	Test specimen.....	26
18.5	Procedure	27
18.6	Expression of results.....	27
18.7	Test report	29
19	Dimensional stability at elevated temperature (Method A).....	29
19.1	Principle.....	29
19.2	Apparatus	29
19.3	Test specimens.....	29
19.4	Procedure	30
19.5	Expression of results.....	30
19.6	Test report	30
20	Dimensional stability at elevated temperature (Method B).....	30
20.1	Principle.....	30
20.2	Apparatus	30
20.3	Test specimens.....	32
20.4	Procedure	32
20.4.1	General	32
20.5	Expression of results.....	32
20.6	Test report	33
21	Dimensional stability at ambient temperature (Method A).....	33
21.1	Principle.....	33
21.2	Apparatus	33
21.3	Test specimens.....	34
21.4	Procedure	34
21.5	Expression of results.....	34
21.6	Test report	34
22	Dimensional stability at ambient temperature (Method B).....	35
22.1	Principle.....	35
22.2	Apparatus	35
22.3	Test specimens.....	35
22.4	Procedure	35
22.5	Expression of results.....	36
22.6	Test report	36
23	Resistance to climatic shock (exterior grade laminates).....	36
23.1	Principle.....	36
23.2	Apparatus	36
23.3	Test specimens.....	37
23.4	Procedure	37
23.5	Expression of results.....	38
23.6	Test report	38
24	Resistance to impact by small diameter ball.....	38
24.1	Principle.....	38
24.2	Materials.....	38
24.3	Apparatus	39

24.4	Test specimens.....	40
24.5	Calibration of the impact tester.....	40
24.6	Procedure.....	42
24.7	Expression of results.....	42
24.8	Test report.....	43
25	Resistance to impact by large diameter ball.....	43
25.1	Principle.....	43
25.2	Materials.....	43
25.3	Apparatus.....	43
25.4	Test specimens.....	46
25.5	Procedure.....	46
25.6	Expression of results.....	46
25.7	Test report.....	46
26	Resistance to impact by large diameter ball (Flooring grade laminates).....	47
26.1	Principle.....	47
26.2	Materials.....	47
26.3	Apparatus.....	47
26.4	Test specimens.....	47
26.5	Procedure.....	47
26.6	Expression of results.....	48
26.7	Test report.....	48
27	Resistance to cracking under stress (Laminates ≤ 2 mm thick).....	48
27.1	Principle.....	48
27.2	Apparatus.....	48
27.3	Test specimens.....	50
27.4	Procedure.....	50
27.5	Expression of results.....	51
27.6	Test report.....	51
28	Resistance to crazing (Compact laminates).....	52
28.1	Principle.....	52
28.2	Apparatus.....	52
28.3	Test specimens.....	52
28.4	Procedure.....	53
28.5	Expression of results.....	53
28.6	Test report.....	53
29	Resistance to scratching.....	53
29.1	Principle.....	53
29.2	Materials.....	53
29.3	Apparatus.....	54
29.4	Calibration of apparatus.....	54
29.5	Test specimen.....	56
29.6	Procedure.....	57
29.7	Expression of results.....	58
29.8	Test report.....	58
30	Resistance to staining (Method A).....	60
30.1	Principle.....	60
30.2	Staining agents.....	60
30.3	Materials.....	61
30.4	Apparatus.....	61
30.5	Test specimens.....	62
30.6	Procedure.....	62
30.7	Expression of results.....	62
30.8	Test report.....	62
31	Resistance to staining (Method B).....	63
31.1	Principle.....	63

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 4586-2:2018
<https://standards.iteh.ai/catalog/standards/sist/c52c5dd1-81bb-4ba2-b5a8-8c645b571a15/iso-4586-2-2018>

31.2	Materials.....	63
31.3	Apparatus.....	64
31.4	Test specimens.....	64
31.5	Procedure.....	64
31.6	Expression of results.....	65
31.7	Test report.....	66
32	Lightfastness (xenon arc) (Method A).....	66
32.1	Principle.....	66
32.2	Apparatus.....	66
32.3	Test specimen.....	67
32.4	Procedure.....	67
32.5	Assessment and expression of results.....	67
32.6	Test report.....	67
33	Lightfastness (xenon arc) (Method B).....	68
33.1	Principle.....	68
33.2	Apparatus.....	68
33.3	Test specimen.....	68
33.4	Procedure.....	69
33.5	Expression of results.....	69
33.6	Test report.....	70
34	Resistance to UV light (Exterior grade laminates).....	70
34.1	Principle.....	70
34.2	Apparatus.....	70
34.3	Test specimens.....	70
34.4	Procedure.....	70
34.5	Evaluation and expression of results.....	71
	34.5.1 Contrast.....	71
	34.5.2 Appearance.....	71
34.6	Test report.....	71
35	Resistance to artificial weathering (Exterior grade laminates).....	72
35.1	Principle.....	72
35.2	Apparatus.....	72
35.3	Test specimens.....	72
35.4	Procedure.....	72
35.5	Examination and expression of results.....	73
	35.5.1 General.....	73
	35.5.2 Contrast.....	73
	35.5.3 Appearance.....	73
35.6	Test report.....	73
36	Resistance to radiant heat.....	74
36.1	Principle.....	74
36.2	Apparatus.....	74
36.3	Test specimen.....	74
36.4	Procedure.....	76
36.5	Test report.....	76
37	Formability (Method A).....	76
37.1	Principle.....	76
37.2	Apparatus.....	77
37.3	Test specimens.....	77
37.4	Procedure.....	77
	37.4.1 General.....	77
	37.4.2 Calibration of test apparatus.....	78
	37.4.3 Test procedure.....	79
37.5	Test report.....	80
38	Formability (Method B).....	80

38.1	Principle.....	80
38.2	Apparatus.....	80
38.3	Test specimens.....	81
38.4	Procedure.....	81
	38.4.1 Calibration of test apparatus.....	81
	38.4.2 Test procedure.....	81
38.5	Test report.....	88
39	Resistance to blistering (Method A).....	88
39.1	Principle.....	88
39.2	Apparatus.....	88
39.3	Test specimens.....	88
39.4	Procedure.....	88
	39.4.1 Calibration of test apparatus.....	88
	39.4.2 Test procedure.....	88
39.5	Test report.....	89
40	Resistance to blistering (Method B).....	89
40.1	Principle.....	89
40.2	Apparatus.....	89
40.3	Test specimens.....	90
40.4	Procedure.....	90
40.5	Test procedure.....	90
40.6	Test report.....	90
41	Resistance to wet heat (100 °C).....	90
41.1	Principle.....	90
41.2	Apparatus.....	90
41.3	Test specimen.....	91
41.4	Procedure.....	91
41.5	Expression of results.....	92
41.6	Test report.....	93
42	Determination of microscratch resistance.....	93
42.1	Principle.....	93
42.2	Apparatus.....	93
42.3	Materials.....	94
42.4	Calibration.....	95
	42.4.1 Assembly and maintenance of the Martindale tester.....	95
	42.4.2 Method for checking the Lissajous figure.....	95
42.5	Test specimens.....	96
	42.5.1 Preparation.....	96
	42.5.2 Test surface.....	96
42.6	Procedure.....	96
	42.6.1 General.....	96
	42.6.2 Method.....	97
42.7	Classification of the image after testing to procedure B.....	98
42.8	Test report.....	98
	Bibliography.....	100

ITeH STANDARD PREVIEW

(standards.iteh.ai)

ISO 4586-2:2018

<https://standards.iteh.ai/catalog/standards/sist/c52c5dd1-81bb-4ba2-b5a8-8c843b57fa13/iso-4586-2-2018>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 11, *Products*.

This seventh edition cancels and replaces the sixth edition (ISO 4586-2:2015) which has been technically revised.

The main changes compared to the previous edition are as follows:

- correction of errors due to typographical, formatting, and omission issues.

A list of all parts in the ISO 4586 series can be found on the ISO website.

Introduction

In an effort to harmonize ISO 4586 with other high-pressure decorative laminate standards, multiple methods may be published that demonstrate similar properties. In these instances, the same test method title is given and is annotated as either “Method A” or “Method B”. This is the case in the following tests: Edge squareness — 8/9, Dry heat — 17/18 Dimensional stability at elevated temperatures — 19/20, Dimensional stability at ambient temperature — 21/22, Staining — 30/31, Lightfastness — 32/33, Formability — 38/39, and Blistering — 40/41. In these instances, either method may be utilized in testing. Compliance to both methods is not required. While these tests are similar they are by no means identical and results of one method do not necessarily correspond to the results of the accompanying test. In these situations, it is intended that the documentation in specific parts of ISO 4586 for performance requirements be consulted. Each specific method has performance requirements particular to that method for individual grades of high-pressure decorative laminate.

This document has been harmonized with EN 438-2 whenever possible.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 4586-2:2018](https://standards.iteh.ai/catalog/standards/sist/c52c5dd1-81bb-4ba2-b5a8-8c843b57fa13/iso-4586-2-2018)

<https://standards.iteh.ai/catalog/standards/sist/c52c5dd1-81bb-4ba2-b5a8-8c843b57fa13/iso-4586-2-2018>

High-pressure decorative laminates (HPL, HPDL) — Sheets based on thermosetting resins (usually called laminates) —

Part 2: Determination of properties

1 Scope

This document specifies the methods of test for determination of the properties of high-pressure decorative laminates (HPL, HPDL) as defined in [Clause 3](#). These methods are primarily intended for testing the sheets specified from ISO 4586-3 to ISO 4586-8.

The precision of the test methods specified in [Clauses 5, 6, 7, 8, 9, 10, 13, 14, 16, 19, 20, 21, 22, 24, 25, 26, 39, and 40](#) is not known because interlaboratory data are not available. When interlaboratory data are obtained, precision statements will be added to the test methods at the following revision. As all the other test methods have an end point determination based on subjective judgement, it is not meaningful to make a statement of precision in these cases.

2 Normative references (standards.iteh.ai)

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 62, *Plastics — Determination of water absorption*

ISO 105-A02, *Textiles — Tests for colour fastness — Part A02: Grey scale for assessing change in colour*

ISO 178, *Plastics — Determination of flexural properties*

ISO 291, *Plastics — Standard atmospheres for conditioning and testing*

ISO 1770, *Solid-stem general purpose thermometers*

ISO 3668, *Paints and varnishes — Visual comparison of colour of paints*

ISO 4892-1, *Plastics — Methods of exposure to laboratory light sources — Part 1: General guidance*

ISO 4892-2:2013, *Plastics — Methods of exposure to laboratory light sources — Part 2: Xenon-arc lamps*

ISO 4892-3, *Plastics — Methods of exposure to laboratory light sources — Part 3: Fluorescent UV lamps*

ISO 6506-1, *Metallic materials — Brinell hardness test — Part 1: Test method*

ISO 9352, *Plastics — Determination of resistance to wear by abrasive wheels*

ISO 9370, *Plastics — Instrumental determination of radiant exposure in weathering tests — General guidance and basic test method*

ISO 12945-2, *Textiles — Determination of fabric propensity to surface fuzzing and to pilling — Part 2: Modified Martindale method*

ISO 12947-1, *Textiles — Determination of the abrasion resistance of fabrics by the Martindale method — Part 1: Martindale abrasion testing apparatus*

EN 312, *Particleboards — Specifications*

EN 316, *Wood fibreboards — Definition, classification and symbols*

ASTM G155, *Standard Practice for Operating Xenon Arc Light Apparatus for Exposure of Non-Metallic Materials*

CIE publication no. 85: 1989, *Solar spectral irradiance*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <https://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

3.1 high-pressure decorative laminate

HPL

HPDL

sheet consisting of layers of cellulosic fibrous material (normally paper) impregnated with thermosetting resins and bonded together by the *high-pressure process* (3.2)

Note 1 to entry: This is a general definition of high-pressure decorative laminate(s). More specific product definitions can be found from ISO 4586-3 to ISO 4586-8.3.2:2018

<https://standards.iteh.ai/catalog/standards/sist/c52c5dd1-81bb-4ba2-b5a8-8c843b57fa13/iso-4586-2-2018>

3.2 high-pressure process

simultaneous application of heat (temperature ≥ 120 °C) and high specific pressure (≥ 5 MPa), to provide flowing and subsequent curing of the thermosetting resins to obtain a homogeneous non-porous material with increased density ($\geq 1,35$ g/cm³), and with the required surface finish

3.3 rub

<microscratch resistance> one revolution of the two outer drives of the Martindale tester

3.4 cycle

<microscratch resistance> completion of all the translational movements tracing a *Lissajous figure* (3.5) comprising 16 *rubs* (3.3)

3.5 Lissajous figure

<microscratch resistance> figure created by movement which ranges changes from a circle gradually narrowing ellipses, until it becomes a straight line, from which progressively widening ellipses develop, in a diagonally opposite direction before the pattern is repeated

Note 1 to entry: This comprises 16 revolutions of the two outer drives and 15 revolutions of the inner drive of the Martindale tester.

4 Assessment of appearance

4.1 Principle

Laminates shall be inspected for surface appearance under standardised conditions of lighting and viewing.

4.2 Apparatus

4.2.1 Horizontal inspection table, of height approximately 700 mm and large enough to accommodate the largest sheets to be inspected.

4.2.2 Overhead white fluorescent lights, of colour temperature approximately 5 000 K and giving an intensity of 800 lx to 1 000 lx over the whole area of the largest sheets to be inspected. A convenient distance of the lights from the inspection table is approximately 1,5 m.

4.3 Test specimen

The specimen shall be the laminate under test, as supplied by the manufacturer.

4.4 Procedure

Place the laminate, decorative face uppermost, on the inspection table. Wipe it free of any loose contamination with a soft cloth, using a suitable cleaning agent if necessary. Inspect it from the distance required by the relevant part of ISO 4586 for defects such as smudges, smears, fingerprints, scratches, foreign particles, damage, or any other form of blemish evident within the decorative surface.

The inspector shall use normal vision, corrected if necessary.

<https://standards.iteh.ai/catalog/standards/sist/c52c5dd1-81bb-4ba2-b5a8-8c843b57fa13/iso-4586-2-2018>

4.5 Test report

The test report shall include the following information:

- a) a reference to this document, i.e. ISO 4586-2;
- b) name, type and nominal thickness of the product;
- c) size of the laminate under test;
- d) viewing distance;
- e) total area of spot-type defects in square millimetres;
- f) total length of hair-like defects in millimetres;
- g) any deviation from the specified test method;
- h) date of the test.

5 Determination of thickness

5.1 Principle

The thickness of a laminate is measured using a micrometer or a dial gauge indicator.

5.2 Apparatus

5.2.1 Thickness gauge, (ratchet-type micrometer or dial gauge indicator), having two flat parallel measuring surfaces of diameter 6 mm and capable of being read to 0,01 mm.

When the thickness of a decorative laminate is being measured, the two surfaces shall exert a pressure of 10 kPa to 100 kPa upon each other.

5.3 Test specimen

The specimen shall be the laminate under test, as supplied by the manufacturer.

5.4 Procedure

Check the gauge for accuracy and then determine the thickness of the laminate to the nearest 0,01 mm. The thickness shall be measured at the centre of each edge, at a distance of at least 20 mm from the edge of the sheet.

5.5 Test report

The test report shall include the following information:

- a) a reference to this document, i.e. ISO 4586-2;
 - b) name, type and nominal thickness of the product;
 - c) all values measured;
 - d) any deviation from the specified test method;
 - e) date of the test.
- STANDARD PREVIEW**
(standards.iteh.ai)
ISO 4586-2:2018
<https://standards.iteh.ai/catalog/standards/sist/c52c5dd1-81bb-4ba2-b5a8-8c843b57fa13/iso-4586-2-2018>

6 Determination of length and width

6.1 Principle

Measuring the length and width of the laminate using a metal tape or rule.

6.2 Apparatus

6.2.1 Steel tape or rule, of sufficient length to measure the greatest dimension of the laminate, and graduated to allow a reading accuracy of 1 mm.

6.3 Test specimen

The specimen shall be the laminate under test, as supplied by the manufacturer.

6.4 Procedure

Apply the steel tape or rule (see 6.2.1) to each edge of the laminate in turn, on a line approximately 25 mm from and parallel to the edge. Measure the length on each edge to the nearest 1 mm.

6.5 Expression of results

The arithmetical means of the pairs of length and width measurements shall be calculated and expressed to the nearest 1 mm as the length and width of the laminate.

6.6 Test report

The test report shall include the following information:

- a) a reference to this document, i.e. ISO 4586-2;
- b) name, type and nominal thickness of the product;
- c) length and width values;
- d) any deviation from the specified test method;
- e) date of the test.

7 Determination of edge straightness

7.1 Principle

Applying a metal straightedge to the edge of the laminate and measuring the deviation of the sheet edge from the metal straightedge using a steel rule.

7.2 Apparatus

7.2.1 **Metal straightedge**, of 1 000 mm length.

7.2.2 **Steel rule**, graduated in 0,5 mm divisions.

7.3 Test specimen

The specimen shall be the laminate under test, as supplied by the manufacturer.

7.4 Procedure

Apply the metal straightedge (see [7.2.1](#)) to each edge of the laminate in turn, and use the steel rule (see [7.2.2](#)) to measure the maximum deviation of the edge of the laminate from the metal straightedge (x in [Figure 1](#)) to the nearest 0,5 mm.

7.5 Expression of results

The maximum deviation from the metal straightedge shall be recorded for each of the four edges. Results shall be designated (+) if the edge is convex, and (–) if the edge is concave.

7.6 Test report

The test report shall include the following information:

- a) a reference to this document, i.e. ISO 4586-2;
- b) name, type and nominal thickness of the product;
- c) test result for each of the four edges;
- d) any deviation from the specified test method;
- e) date of the test.