



Designation: D4640–86(Reapproved2001) Designation: D4640 – 86 (Reapproved 2009)

Standard Test Method for Determining Stroke Cure Time of Thermosetting Phenol- Formaldehyde Resins¹

This standard is issued under the fixed designation D4640; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of the cure rate at any specified temperature for a thermosetting phenol-formaldehyde resin. The time at that temperature required to make a fluid mixture change into a hard immovable mass indicates speed of cure.

1.2

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Terminology

2.1 Definitions of Terms Specific to This Standard:

2.1.1 ~~stroke cure time~~ stroke cure time, n —the time required for a resin being held at a specified temperature on a hot plate and being stroked with a spatula, to adhere to the hot plate and not to the spatula.

3. Summary of Test Method

3.1 This test method employs the use of controlled heat and a thin layer of resin to determine the time in seconds required to change from a fluid stage to a cured immovable stage.

4. Significance and Use

4.1 This method is significant as a process control for polymerization time.

4.2 When the cure times are determined at several temperatures and plotted as time versus temperature, different resins can be compared for curing characteristics.

5. Apparatus

5.1 Electric Hot Cure Plate, with a smooth surface free of rough spots with adjustable control to hold the temperature within 3.5°F (2°C) (Note 1).

5.2 Spatula, 3 by $\frac{7}{16}$ in. (75 by 10 mm), stainless.

5.3 Stopwatch.

5.4 Knife, brass, putty with straight edge.

6. Procedure

6.1 Adjust the hot plate to the desired test temperature.

NOTE 1—Usual temperatures are 300°F (150°C), 320°F (160°C), and 330°F (165°C).

6.2 Place an approximately 0.5-g specimen on the hot plate and spread over an approximately 2-in.² (130-mm²) area with a clean spatula as quickly as possible. Start the stopwatch immediately upon adding the specimen to the hot plate, then stroke steadily across the specimen in alternating smoothing and patting motions.

¹ This test method is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.33 on Polymers and Resins.

Current edition approved Nov. 28, 1986. Published January 1987. DOI: 10.1520/D4640-86R01.

Current edition approved Dec. 1, 2009. Published December 2009. Originally approved in 1986. Last previous edition approved in 2001 as D4640 - 86 (2001). DOI: 10.1520/D4640-86R09.