



Designation: D4832 – 10

Standard Test Method for Preparation and Testing of Controlled Low Strength Material (CLSM) Test Cylinders¹

This standard is issued under the fixed designation D4832; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This test method covers procedures for the preparation, curing, transporting and testing of cylindrical test specimens of controlled low strength material (CLSM) for the determination of compressive strength.

1.2 This test method covers CLSM materials that have a higher strength than the soil but less than 8400 kPa (1200 psi). Typical strengths for most applications fall between 350 to 700 kPa (50 to 100 psi).

1.3 The CLSM used to make the molded specimens shall be sampled after all on-site adjustments have been made to the mixture proportions, including the addition of mix water and any admixtures.

1.4 This test method may be used to prepare and test cylindrical specimens of other mixtures of soil and cementitious materials, such as self-cementing fly ashes.

1.5 CLSM is also known as flowable fill, controlled density fill, soil-cement slurry, soil-cement grout, unshrinkable fill, K-Krete, and other similar names.

1.6 All observed and calculated values shall conform to the guidelines for significant digits and rounding established in Practice D6026.

1.6.1 The procedures used to specify how data are collected/recorded and calculated in this standard are regarded as the industry standard. In addition, they are representative of the significant digits that should generally be retained. The procedures used do not consider material variation, purpose for obtaining the data, special purpose studies, or any considerations for the user's objectives; and it is common practice to increase or reduce significant digits of reported data to be commensurate with these considerations. It is beyond the scope of this standard to consider significant digits used in analysis methods for engineering design.

1.7 The values stated in SI units are to be regarded as the standard. The inch-pound equivalents given in brackets are, in most cases, rationalized units and are shown for information only.

1.8 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. See Section 7.*

2. Referenced Documents

2.1 *ASTM Standards:*²

C31/C31M Practice for Making and Curing Concrete Test Specimens in the Field

C39/C39M Test Method for Compressive Strength of Cylindrical Concrete Specimens

C125 Terminology Relating to Concrete and Concrete Aggregates

C192/C192M Practice for Making and Curing Concrete Test Specimens in the Laboratory

C470/C470M Specification for Molds for Forming Concrete Test Cylinders Vertically

C617 Practice for Capping Cylindrical Concrete Specimens

C1231/C1231M Practice for Use of Unbonded Caps in Determination of Compressive Strength of Hardened Concrete Cylinders

D653 Terminology Relating to Soil, Rock, and Contained Fluids

D3740 Practice for Minimum Requirements for Agencies Engaged in Testing and/or Inspection of Soil and Rock as Used in Engineering Design and Construction

D5971 Practice for Sampling Freshly Mixed Controlled Low-Strength Material

D6023 Test Method for Density (Unit Weight), Yield, Cement Content, and Air Content (Gravimetric) of Controlled Low-Strength Material (CLSM)

D6024 Test Method for Ball Drop on Controlled Low

¹ This test method is under the jurisdiction of ASTM Committee D18 on Soil and Rock and is the direct responsibility of Subcommittee D18.15 on Stabilization With Admixtures.

Current edition approved Jan. 15, 2010. Published March 2010. Originally approved in 1988. Last previous edition approved in 2002 as D4832 – 02. DOI: 10.1520/D4832-10.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

Strength Material (CLSM) to Determine Suitability for Load Application

D6026 Practice for Using Significant Digits in Geotechnical Data

D6103 Test Method for Flow Consistency of Controlled Low Strength Material (CLSM)

3. Terminology

3.1 Definitions:

3.1.1 For common definitions of terms in this standard, refer to Terminology **C125** and **D653**.

3.1.2 *Controlled Low Strength Material (CLSM), n*—A mixture of soil, aggregates (sand, gravel, or both), cementitious materials, potable water, and sometimes admixtures, that hardens into a material with a higher strength than the soil but less than about 8400 kPa (1200 psi). Used as a replacement for compacted backfill, CLSM can be placed as a slurry, a mortar, or a compacted material and typically has strengths of 350 to 700 kPa (50 to 100 psi) for most applications.

4. Summary of Test Method

4.1 Cylinders are tested to determine the compressive strength of the CLSM. The cylinders are prepared by pouring a representative CLSM sample into molds, then depending on the strength development, either curing the cylinders then removing them from the molds or removing the molds prior to curing the cylinders, and preparing the cylinders for compression testing. The cylinders are then tested to obtain compressive strengths. Duplicate cylinders are required for each test age specified.

5. Significance and Use

5.1 This test method provides standardized requirements for the preparation, curing, transporting and testing of test cylinders of CLSM under field conditions by replicating a “field cure” of the material.

5.1.1 If the cylinders are field cured, as stipulated herein, the resulting compressive strength test data may be used for the following purposes:

5.1.1.1 Acceptance testing for specified strength,

5.1.1.2 Checking the adequacy of mixture proportions for strength,

5.1.1.3 Quality control,

5.1.1.4 Determination of whether the CLSM is capable of being put in service,

5.1.1.5 Adequacy of curing.

5.2 CLSM is typically used as a backfill material around structures, particularly in confined or limited spaces. Compressive strength testing is performed to assist in the design of the mix and to serve as a quality control technique during construction. Mix design is typically based on 28-day strengths and construction control tests performed 7 days after placement. The compressive strength(s) and other test age(s) will vary according to the requirements for the end product. Additional information on the use and history of CLSM is contained in **Appendix X1**.

5.3 This test is one of a series of quality control tests that can be performed on CLSM during construction to monitor

compliance with specification requirements. The other tests that can be used during construction control of CLSM are Practice **D5971** and Test Methods **D6023**, **D6024**, and **D6103**.

5.4 There are many other combinations of soil, cement, fly ash (cementitious or not), admixtures, water quality or other materials that could be tested using this method. The mixtures will vary depending on the intended use, availability of materials, and placement requirements.

NOTE 1—The quality of the result produced by this standard is dependent on the competence of the personnel performing it, and the suitability of the equipment and facilities used. Agencies that meet the criteria of Practice **D3740** are generally considered capable of competent and objective testing/sampling/inspection and the like. Users of this standard are cautioned that compliance with Practice **D3740** does not in itself assure reliable results. Reliable results depend on many factors; Practice **D3740** provides a means of evaluating some of those factors.

6. Apparatus

6.1 *Single-Use Cylindrical Molds*—Plastic single-use 150 × 300 mm (6 × 12 in.) or 100 × 200 mm (4 × 8 in.) cylinder molds with tight-fitting lids (see **9.2.2.1** regarding cautionary statement for “air-tight” lids), conforming to Specification **C470/C470M**. Other sizes and types of molds may be used as long as the length to diameter ratio is 2 to 1. The 150 × 300 mm (6 × 12 in.) molds are preferred for use in concrete compression apparatus’ (Section **6.5**) because of the low strength of the material and the larger surface area of the ends of the cylinders.

6.1.1 Mold removal can be accomplished with the use of low air pressure. The pressure shall be low enough so the sample is undamaged.

6.2 *Sampling and Mixing Receptacle*—The receptacle shall be a suitable non-absorbent material (heavy-gauge metal or heavy duty plastic container, wheelbarrow, etc.) of sufficient capacity to allow easy sampling and remixing with a shovel or scoop and to allow preparation of at least two cylinders and for other tests such as described in Test Methods **D5971**, **D6023**, and **D6103**.

6.3 *Storage Container*—A tightly constructed, insulated, firmly braced wooden box with a cover or other suitable container for storage of the CLSM cylinders at the construction site. The container shall be equipped, as necessary, to maintain the temperature immediately adjacent to the cylinders in the range of 16 to 27°C (60 to 80°F). The location of the storage container shall be away from direct sunlight and protected from freezing temperatures for extended lengths of time (for additional guidance see Section on Curing in Practice **C31/C31M**). The container shall be marked for identification and shall be a bright color to avoid disturbance.

6.4 *Transportation Container*—A sturdy wooden box or other suitable container constructed with adequate padding to minimize shock, vibration, or damage to the CLSM cylinders when transported to the laboratory.

6.5 *Testing Machine*—The testing machine shall meet the requirements as described in Test Method **C39/C39M** with the following exceptions.

6.5.1 The readability shall be a minimum of two significant digits with interpolation of the second digit not more than 0.11 kN (25 lbf) for strengths less than about 350 kPa (50 psi). For

strengths greater than about 350 kPa (50 psi), the minimum readability should be two significant digits with interpolation of the second digit not more than 0.55 kN (100 lbf).

6.5.2 Since the compressive strength of CLSM cylinders will typically be 100 to 8400 kPa (about 15 to 1200 lbf/in.²), the testing machine must have a loading range such that valid values of compressive strength can be obtained.

6.6 *Curing Environment*—A curing environment (water bath, damp sand, fog room) that meets the requirements of Practice **C192/C192M**. The cylinders may be cured in the same curing environment used for concrete cylinders at the laboratory performing the testing.

6.7 *Small Tools*—Tools and items that may be required such as shovels, pails, trowels, tamping rod and scoops.

7. Hazards

7.1 *Technical Precaution*—The procedure for the preparation of CLSM test cylinders has many similarities to preparing concrete test cylinders (Practice **C31/C31M** and Practice **C192/C192M**). However, the cylinders are much more fragile than concrete cylinders, and special care should be taken in their preparation, storage, and handling.

7.2 Safety Hazards:

7.2.1 Strictly observe the safety precautions stated in Practice **C617**.

7.2.2 If the cylinders are capped with molten sulfur mortar (which is not advised for CLSM cylinders, see Section 10 on Capping the Cylinders), wear proper personnel protective equipment, including gloves with cuffs at least 15 cm (6-in.) long. **Warning**—Fresh hydraulic cementitious mixtures are caustic and may cause chemical burns to skin and tissue upon prolonged exposure.³

8. CLSM Sampling and Test Specimens

8.1 Take samples of the CLSM for each test cylinder in accordance with **D5971**. Record the identity of the CLSM represented and the date and time of casting.

8.2 The sample from the batch should be a minimum of 0.03 m³ (1 ft³) for each two cylinders to be prepared. Prepare a minimum of two compressive strength cylinders for each test age to represent each sampled batch. Additional material may be required if other testing is to be performed, such as in Test Methods **D5971**, **D6023**, and **D6103**.

NOTE 2—In the initial stage of CLSM usage, preparation of three cylinders is recommended to obtain reliable compressive strength data for each test age. Subsequently, two cylinders may be used to maintain testing records and to ascertain an overall quality of the mix. However, since the cylinders are fragile and may be damaged during transportation, mold removal, and capping, preparation of an extra cylinder may be necessary to provide the minimum number of test cylinders (see **Note 4** and **10.2**). In addition, it may be useful to determine the density of the test cylinders to help evaluate the uniformity of the compressive strength values.

9. CLSM Cylinder Molding and Curing

9.1 *Place of Molding*—Mold cylinders promptly on a level, rigid, horizontal surface free from vibration and other distur-

bances. The cylinders should be prepared at a place as near as practicable to the location where they are to be stored during the first four days.

9.2 Placing the CLSM:

9.2.1 Thoroughly mix the CLSM in the sampling and mixing receptacle to avoid segregation and to maintain homogeneity. Because CLSM mixtures can bleed easily (the appearance of free water at the surface), the sample must be routinely mixed during cylinder production to ensure homogeneity, avoid segregation and ensure that the cylinder produced represents the material placed in the trench.

9.2.2 With a scoop or pail, scoop through the center portion of the receptacle and pour the CLSM into the mold. Repeat until the mold is full. Tap the outsides of the cylinder mold no more than ten times with a tamping rod or open face of the hand to close holes that remain and to release entrapped air voids, assuring complete filling of the mold. If necessary, level off the top layer with the trowel or straight-edge so it remains even and relatively smooth. Place a lid or plastic bag loosely on the mold.

NOTE 3—The placement of CLSM into the cylinder molds generally does not follow Practices **C31/C31M** or **C192/C192M** as the placement is not done in layers and does not require rodding or vibrating. However if the CLSM mixture contains high gravel contents, Practice **C31/C31M** should be followed with the applicable layering, rodding and/or vibration pertaining to the cylinder mold size.

9.2.2.1 Use of an airtight lid has been known to cause low strength materials to crack, possibly due to the creation of a vacuum inside the mold. If an airtight lid is contemplated, its use should be evaluated before doing routine testing. A pin-sized hole in the lid has been used successfully in many cases.

9.2.2.2 Some mixtures will bleed rapidly, that is, free water will appear in the sample while in the mixing receptacle and also while in the mold. Obtaining the material to fill the cylinder must be done quickly after mixing. A few minutes after filling the mold, thoroughly mix the CLSM in the sampling and mixing receptacle and place a scoopful in the top of the mold, displacing the water. This refilling may be required again after about 15 min. Smooth the top and cover after all refilling is finished.

9.3 Curing:

9.3.1 Store the cylinders at the construction site in the storage container until the fourth day after preparation. Refer to **9.2** for curing requirements.

9.3.2 The cylinders shall be stored under conditions that maintain the temperature immediately adjacent to the cylinders in the range of 16 to 27°C (60 to 80°F). The cylinders must always be protected from freezing. After the first day, provide a high humidity environment by surrounding the cylinders with wet burlap or other highly adsorbent material.

9.3.3 On the fourth day, carefully transport the cylinders to the site of the curing environment in the transportation container and place in a curing environment (see **6.6**).

9.3.4 The cylinders are typically left at the construction site for four days and then transported to a curing environment. If extremely low strength CLSM (below 350 kPa) would be damaged by moving on the fourth day, then the cylinders are to

³ Section on Safety Precautions, Manual of Aggregate and Concrete Testing, Annual Book of ASTM Standards, Vol. 04.02.