
Analizna kolorimetrija - 4. del: Metamerični indeks parov vzorcev pri spremembi vrste svetila (ISO 18314-4:2020)

Analytical colorimetry - Part 4: Metamerism index for pairs of samples for change of illuminant (ISO 18314-4:2020)

Analytische Farbmessung - Teil 4: Metamerie-Index von Probenpaaren bei Lichtartwechsel (ISO 18314-4:2020)

Analyse colorimétrique - Partie 4: Indice de métamérisme de paires d'échantillon pour changement d'illuminant (ISO 18314-4:2020)

<https://standards.iteh.ai/catalog/standards/sist/48bb74e6-8910-43e6-80b5-2be2705e8e25/osist-pr-en-iso-18314-4-2021>

Ta slovenski standard je istoveten z: prEN ISO 18314-4

ICS:

17.180.20	Barve in merjenje svetlobe	Colours and measurement of light
87.060.10	Pigmenti in polnila	Pigments and extenders

oSIST prEN ISO 18314-4:2021

en,fr,de

iTeh STANDARD PREVIEW **(standards.iteh.ai)**

[oSIST prEN ISO 18314-4:2021](https://standards.iteh.ai/catalog/standards/sist/48bb74e6-8910-43e6-80b5-2be2705a8c25/osist-pren-iso-18314-4-2021)

<https://standards.iteh.ai/catalog/standards/sist/48bb74e6-8910-43e6-80b5-2be2705a8c25/osist-pren-iso-18314-4-2021>

INTERNATIONAL STANDARD

ISO
18314-4

First edition
2020-08

Analytical colorimetry — Part 4: Metamerism index for pairs of samples for change of illuminant

Analyse colorimétrique —

*Partie 4: Indice de métamérisme de paires d'échantillon pour
changement d'illuminant*
(standards.iteh.ai)

[oSIST prEN ISO 18314-4:2021](https://standards.iteh.ai/catalog/standards/sist/48bb74e6-8910-43e6-80b5-2be2705a8c25/osist-pren-iso-18314-4-2021)

[https://standards.iteh.ai/catalog/standards/sist/48bb74e6-8910-43e6-80b5-
2be2705a8c25/osist-pren-iso-18314-4-2021](https://standards.iteh.ai/catalog/standards/sist/48bb74e6-8910-43e6-80b5-2be2705a8c25/osist-pren-iso-18314-4-2021)



Reference number
ISO 18314-4:2020(E)

© ISO 2020

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 18314-4:2021](https://standards.iteh.ai/catalog/standards/sist/48bb74e6-8910-43e6-80b5-2be2705a8c25/osist-pren-iso-18314-4-2021)

<https://standards.iteh.ai/catalog/standards/sist/48bb74e6-8910-43e6-80b5-2be2705a8c25/osist-pren-iso-18314-4-2021>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Symbols and abbreviated terms	2
5 Reference illuminant	3
6 Test illuminant	3
7 CIELAB coordinates L^*, a^*, b^*	3
8 Metamerism index for change in illuminant	4
8.1 General calculation methods.....	4
8.2 Basic calculation of the metamerism index from colour differences.....	4
8.3 Correction methods.....	5
8.3.1 Additive correction.....	5
8.3.2 Multiplicative correction.....	5
8.3.3 Spectral correction.....	6
8.4 Test report.....	9
Annex A (informative) Calculation examples	10
Bibliography	23

<https://standards.iteh.ai/catalog/standards/sist/48bb74e6-8910-43e6-80b5-2be2705a8c25/osist-pren-iso-18314-4-2021>
 oSIST prEN ISO 18314-4:2021

ISO 18314-4:2020(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 256, *Pigments, dyestuff and extenders*.

A list of all parts in the ISO 18314 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

For the phenomenon of metamerism of pairs of samples, three different kinds are distinguished:

- a) Illuminant metamerism occurs if both of the object colours of a pair of samples are perceived as being the same only under a specific illuminant (e.g. under illuminant D65), while they differ under a different illuminant (e.g. illuminant A).
- b) Observer metamerism occurs if the object colours of a pair of samples are perceived as being the same by one observer, while a different observer perceives a colour difference under the same illuminant and the same reference conditions.

NOTE 1 The observer metamerism is caused by differences between the distributions of spectral colour matching functions of different observers.

- c) Field-size metamerism occurs if both of the object colours of a pair of samples are perceived as being the same on the retina for a size of an observation field (e.g. defined by the 2° standard observer), while they differ for a different observation field on the retina (e.g. 10°).

NOTE 2 The reason for field-size metamerism is based on the existent colour matching functions of an observer during an observation situation. The colour matching functions change with the size of the observation field on the retina. Such change of the observation field can also occur if, for example, the pair of samples is examined from different distances.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN ISO 18314-4:2021](https://standards.iteh.ai/catalog/standards/sist/48bb74e6-8910-43e6-80b5-2be2705a8c25/osist-pren-iso-18314-4-2021)

<https://standards.iteh.ai/catalog/standards/sist/48bb74e6-8910-43e6-80b5-2be2705a8c25/osist-pren-iso-18314-4-2021>

iTeh STANDARD PREVIEW **(standards.iteh.ai)**

[oSIST prEN ISO 18314-4:2021](https://standards.iteh.ai/catalog/standards/sist/48bb74e6-8910-43e6-80b5-2be2705a8c25/osist-pren-iso-18314-4-2021)

<https://standards.iteh.ai/catalog/standards/sist/48bb74e6-8910-43e6-80b5-2be2705a8c25/osist-pren-iso-18314-4-2021>

Analytical colorimetry —

Part 4:

Metamerism index for pairs of samples for change of illuminant

1 Scope

This document specifies a formalism for the calculation of the illuminant metamerism of solid surface colours. It cannot be applied to colours of effect coatings without metrical adaptation.

This document only covers the phenomenon of metamerism for change of illuminant, which has the greatest meaning in practical application. In the case of chromaticity coordinates of a pair of samples under reference conditions that do not exactly match, recommendations are given on which correction measures are to be taken. Regarding the reproduction of colours, the metamerism index is used as a measure of quality in order to specify tolerances for colour differences between a colour sample and a colour match under different illumination conditions.

The quantification of the illuminant metamerism of pairs of samples is formally performed by a colour difference assessment, for which tolerances that are common for the evaluation of residual colour differences can be used.

NOTE In the colorimetric literature and textbooks, the term geometric metamerism is sometimes used for the case that two colours appear to be the same under a specific geometry for visual assessment and selected standard observer and standard illuminant pair, but is perceived as two different colours at changed observation geometry. The term geometric metamerism is different to metamerism described in this document.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO/CIE 11664-1, *Colorimetry — Part 1: CIE standard colorimetric observers*

ISO/CIE 11664-2:—¹⁾, *Colorimetry — Part 2: CIE standard illuminants*

ISO/CIE 11664-4, *Colorimetry — Part 4: CIE 1976 $L^*a^*b^*$ colour space*

CIE 015, *Colorimetry*

CIE S 017, *International Lighting Vocabulary*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in CIE S 017 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

1) Under preparation. Stage at the time of preparation: ISO/CIE DIS 11664-2:2020.

ISO 18314-4:2020(E)

3.1

metamerism

property of spectrally different colour stimuli that have the same tristimulus values in a specified colorimetric system

[SOURCE: CIE 017:2016, 17-23-006]

3.2

paramerism

characteristic of a pair of samples with spectral colour stimulus functions which have different fundamental colour stimulus functions as well as different residuals or metameric black values within the visible spectral range

Note 1 to entry: Parameric objects are characterized by the fact that they reflect colour stimuli of different spectral power distribution functions under a specified standard illuminant, which cause approximately the same colour perception under the selected observation conditions.

3.3

colour difference

ΔE^*

difference between two colour stimuli, defined as a distance between the points representing them in a specified colour space

[SOURCE: CIE 017:2016, 17-22-041, modified — symbol ΔE^* was amended, “Euclidean” and Note 1 to entry have been deleted.]

iTeh STANDARD PREVIEW
(standards.iteh.ai)

3.4

reference illuminant

illuminant with which other illuminants are compared

[SOURCE: CIE S 017:2016, 17-22-109 17] oSIST prEN ISO 18314-4:2021
<https://standards.iteh.ai/catalog/standards/sist/48bb74e6-8910-43e6-80b5-2be2705a8c25/osist-pren-iso-18314-4-2021>

3.5

test illuminant

illuminant, for which the *colour difference* (3.3) between the two samples to be tested is assessed

3.6

metamerism-index for change in illuminant

M_t

colour difference ΔE^* (3.3) between the two samples under *test illuminant* (3.5) if $\Delta E^* = 0$ is observed under the *reference illuminant* (3.4)

3.7

correction method

algorithm for theoretically eliminating a *colour difference* (3.3) of the pair of samples under the *reference illuminant* (3.4)

4 Symbols and abbreviated terms

For the application of this document, the symbols given in Table 1 apply.

Table 1 — Symbols

Symbol	Identification
X, Y, Z	Standard tristimulus values of a measured object colour
X_n, Y_n, Z_n	Standard tristimulus values of the used illuminant
$\bar{x}, \bar{y}, \bar{z}$	Colour-matching functions

Table 1 (continued)

Symbol	Identification
L^*, a^*, b^*	Basic coordinates of the CIELAB system
$\Delta L^*, \Delta a^*, \Delta b^*$	Differences between basic coordinates of the CIELAB system
M_t	Metamerism index for change in illuminant
$\vec{N}, \vec{N}_f, \vec{N}_r$	Vector of the radiometric function of a sample with associated fundamental colour stimulus (f) and metamer black (r)
λ	Wavelength
S	Relative spectral distribution function of an illuminant
\vec{W}	Vector of the standard tristimulus values
w	Integration weights for the calculation of the standard tristimulus values
A	Matrix of the integration weights w for the calculation of the standard tristimulus values
R	Projection matrix
I	Identity matrix
Index spl	Sample
Index std	Standard
Index t	Test illuminant
Index corr	Corrected value
Index f	Fundamental colour stimulus
Index r	Metamer black values (residuals)
Index ref	Reference illuminant
Index T	Transposed matrix

oSIST prEN ISO 18314-4:2021

<https://standards.iteh.ai/catalog/standards/sist/48bb74e6-8910-43e6-80b5-2be2705a8c25/osist-pren-iso-18314-4-2021>

5 Reference illuminant

The standard illuminant D65 is chosen as reference illuminant in accordance with ISO/CIE 11664-2. Other reference illuminants required in special cases shall be particularly specified.

6 Test illuminant

The selection of the test illuminant depends on the application. If the test illuminants are not particularly specified, standard illuminant A in accordance with ISO 11664-2 and/or illuminants of the fluorescent lamp type, such as FL11 in accordance with CIE 015, shall preferably be selected. The test illuminant used shall be indicated as an index to M , e.g. M_A or M_{FL11} .

When calculating the standard tristimulus values X, Y, Z under the selected test illuminants, the basic raster of wavelengths given in ISO 11664-2 or CIE 015 for A and D65, and in CIE 015 for FL11 and FL2 shall be complied with. In cases of missing measuring values of the standard or sample for these wavelengths, these values shall be interpolated and/or extrapolated.

7 CIELAB coordinates L^*, a^*, b^*

The metamerism index M_t is based on the CIELAB coordinates L^*, a^*, b^* of samples 1 and 2 which are to be compared. L^*, a^*, b^* is calculated in accordance with ISO/CIE 11664-4 from the standard tristimulus values X, Y, Z of the sample for the CIE 1964 10° standard observer in accordance with ISO/CIE 11664-1 for the reference illuminant and the selected test illuminant. If calculating L^*, a^*, b^* under the test illuminant, the respective standard tristimulus values X_n, Y_n, Z_n of the entirely matt white surface shall be used (see CIE 015). For the standard illuminants A and D65 or for the illuminant

ISO 18314-4:2020(E)

recommendation FL11, the standard tristimulus values X_n , Y_n , Z_n of the entirely matt white surface apply in accordance with [Table 2](#).

[Table 2](#) specifies standard tristimulus values for the frequently used standard illuminants D65 and A as well as illuminant FL11 and both of the standard observers in accordance with CIE 015.

Table 2 — Standard tristimulus values

Standard tristimulus values	2° standard observer			10° standard observer		
	Illuminant					
	D65	A	FL11	D65	A	FL11
X_n	95,04	109,85	100,96	94,81	111,14	103,86
Y_n	100,00	100,00	100,00	100,00	100,00	100,00
Z_n	108,88	35,58	64,35	107,32	35,20	65,61

For fluorescent samples, the illuminant used for measurement shall be adjusted as close as possible to that illuminant for which the standard tristimulus values are to be determined.

NOTE In contrast to non-fluorescent samples, the calculation of metamerism indices for fluorescent samples is erroneous if the samples are measured only under one illuminant.

8 Metamerism index for change in illuminant

(standards.iteh.ai)

8.1 General calculation methods

Three different correction methods for calculating a metamerism index in the case of parameterism have been proposed in References [6] to [13]. All methods assume that, for practical cases, there might be already a small difference between the colours of the sample and the standard even under the reference illuminant from the very beginning, due to problems of fabrication. In the case of two methods, called the additive and the multiplicative correction, these inherent colour differences often merge with the difference introduced by the change of the illuminant. The third method, the spectral correction, works more fundamentally by the separation of inherent colour differences under the reference illuminant from those introduced by the change of the illuminant.

NOTE [Annex A](#) includes calculation examples.

8.2 Basic calculation of the metamerism index from colour differences

The common formula for a metamerism index at change in illuminant, expressed in CIELAB coordinates for the test illuminant (t), is given by [Formula \(1\)](#):

$$M_t = \sqrt{(\Delta L_t^*)^2 + (\Delta a_t^*)^2 + (\Delta b_t^*)^2} \quad (1)$$

where

t is the test colour;

$$\Delta L_t^* = L_{\text{spl,corr,t}}^* - L_{\text{std,t}}^* ;$$

$$\Delta a_t^* = a_{\text{spl,corr,t}}^* - a_{\text{std,t}}^* ;$$

$$\Delta b_t^* = b_{\text{spl,corr,t}}^* - b_{\text{std,t}}^* .$$