
Fina keramika (sodobna keramika, sodobna tehnična keramika) - Keramični kompoziti - Oznake in simboli (ISO 19634:2017)

Fine ceramics (advanced ceramics, advanced technical ceramics) - Ceramic composites - Notations and symbols (ISO 19634:2017)

Hochleistungskeramik - Keramische Verbundwerkstoffe - Bezeichnungen und Formelzeichen (ISO 19634:2017)

Céramiques techniques - Céramiques composites - Notations et symboles (ISO 19634:2017)

[oSIST prEN ISO 19634:2021](https://standards.iteh.ai/catalog/standards/sist/8f26e072-daa9-4d07-8b64-6243e82eb595/osist-pr-en-iso-19634-2021)

[https://standards.iteh.ai/catalog/standards/sist/8f26e072-daa9-4d07-8b64-](https://standards.iteh.ai/catalog/standards/sist/8f26e072-daa9-4d07-8b64-6243e82eb595/osist-pr-en-iso-19634-2021)

Ta slovenski standard je istoveten z: prEN ISO 19634

ICS:

01.075	Simboli za znake	Character symbols
81.060.30	Sodobna keramika	Advanced ceramics

oSIST prEN ISO 19634:2021

en,fr,de

iTeh STANDARD PREVIEW **(standards.iteh.ai)**

[oSIST prEN ISO 19634:2021](https://standards.iteh.ai/catalog/standards/sist/8f26e072-daa9-4d07-8b64-6243c82eb595/osist-pren-iso-19634-2021)

<https://standards.iteh.ai/catalog/standards/sist/8f26e072-daa9-4d07-8b64-6243c82eb595/osist-pren-iso-19634-2021>

INTERNATIONAL STANDARD

ISO
19634

First edition
2017-10

Fine ceramics (advanced ceramics, advanced technical ceramics) — Ceramic composites — Notations and symbols

*Céramiques techniques — Céramiques composites — Notations et
symboles*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN ISO 19634:2021](https://standards.iteh.ai/catalog/standards/sist/8f26e072-daa9-4d07-8b64-6243c82eb595/osist-pren-iso-19634-2021)

[https://standards.iteh.ai/catalog/standards/sist/8f26e072-daa9-4d07-8b64-
6243c82eb595/osist-pren-iso-19634-2021](https://standards.iteh.ai/catalog/standards/sist/8f26e072-daa9-4d07-8b64-6243c82eb595/osist-pren-iso-19634-2021)



Reference number
ISO 19634:2017(E)

© ISO 2017

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 19634:2021](https://standards.iteh.ai/catalog/standards/sist/8f26e072-daa9-4d07-8b64-6243c82eb595/osist-pren-iso-19634-2021)
<https://standards.iteh.ai/catalog/standards/sist/8f26e072-daa9-4d07-8b64-6243c82eb595/osist-pren-iso-19634-2021>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Symbols	4
5 Significance and use	12
5.1 Significance	12
5.2 Use	12
Bibliography	13

iTeh STANDARD PREVIEW (standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/sist/8f26e072-daa9-4d07-8b64-6243c82eb595/osist-pren-iso-19634-2021>

ISO 19634:2017(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html. (standards.iteh.ai)

This document was prepared by Technical Committee ISO/TC 206, *Fine ceramics*.

<https://standards.iteh.ai/catalog/standards/sist/8f26e072-daa9-4d07-8b64-6243c82eb595/osist-pren-iso-19634-2021>

Fine ceramics (advanced ceramics, advanced technical ceramics) — Ceramic composites — Notations and symbols

1 Scope

This document defines the symbols to be used to represent physical, mechanical and thermal characteristics, as determined by methods described in relevant ISO publications, for ceramic matrix composites. It is aimed at avoiding confusion in reporting measurements and characteristics of products.

Where possible, the definitions are in accordance with the relevant parts of ISO 80000. In addition, the symbols used in undertaking measurements of these characteristics are also defined.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 80000-4, *Quantities and units — Part 4: Mechanics*

ISO 80000-5, *Quantities and units — Part 5: Thermodynamics*

3 Terms and definitions

oSIST prEN ISO 19634:2021

<https://standards.iteh.ai/catalog/standards/sist/8f26e072-daa9-4d07-8b64-0b33e0e00000/iso-19634-2021>

For the purposes of this document, the terms and definitions given in ISO 80000-4 and ISO 80000-5 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

3.1

ceramic matrix composite

ceramic, carbon or glass matrix containing reinforcement distributed in one or more spatial directions

Note 1 to entry: Composites with continuous reinforcements constitute a specific class of these materials. Several subclasses of ceramic matrix composites with continuous reinforcements can be distinguished.

3.2

nomenclature

The symbol F/I/M applies usually to ceramic matrix composites:

- F indicates the chemical nature of fibrous reinforcement: C stands for carbon, SiC for silicon carbide, Al₂O₃ for alumina, etc.
- I indicates the chemical nature of fibre/matrix interphase: C stands for carbon, BN for boron nitride, LaPO₄ for monazite, etc.
- M indicates the chemical nature of matrix: C for carbon, SiC for silicon carbide, Al₂O₃ for alumina.

EXAMPLE 1 A ceramic matrix composite composed of a silicon carbide fibre, a carbon interphase and a silicon carbide matrix is denoted by SiC/C/SiC.

ISO 19634:2017(E)

Note 1 to entry: More complex symbols can be used to describe the constituents with a greater degree of precision.

EXAMPLE 2 For a composite composed of a carbon fibre, a multi-layered interphase of four alternate layers of carbon and silicon carbide, and a silicon carbide matrix, the symbol is: $C_f/[C/SiC]_4/SiC_m$.


3.3

unidirectional ceramic matrix composite

1D material

ceramic matrix composite (3.1), the reinforcement of which is distributed in one single direction

Note 1 to entry: See Figure 1.

**Key**

- 1 direction of reinforcement
- 2 direction of the greater transverse dimension (width), perpendicular to direction 1
- 3 direction of the smaller transverse dimension (thickness), perpendicular to direction 1

NOTE When the width and the thickness are equal, then directions 2 and 3 are equivalent and can be chosen freely.

Figure 1 — Schematic diagram of a 1D material


3.4

in-plane reinforced ceramic matrix composite

2D material

ceramic matrix composite (3.1), where the reinforcements are placed along at least two directions in a single plane

Note 1 to entry: See Figure 2.

**Key**

- 1 direction of the greater fraction of reinforcement
- 2 direction perpendicular to direction 1 in the plane of reinforcement (not necessarily a direction of reinforcement)
- 3 direction perpendicular to the plane of reinforcement

NOTE Strictly more than one direction of fibrous reinforcement, all contained within one plane [in the present case, three directions of reinforcement in plane (1,2)].
 When several directions have an equal fraction of reinforcement, it shall be stated which direction is chosen as direction 1 in relation to the reinforcement structure (for example, orthogonal reinforced fabric: warp in direction 1, weft in direction 2).

Figure 2 — Schematic diagram of a 2D material

3.5**multidirectional ceramic matrix composite**

x D ($2 < x \leq 3$) material

ceramic matrix composite (3.1), where the reinforcement is spatially distributed in at least three directions not in a single plane

Note 1 to entry: See [Figures 3](#) and [4](#).





Figure 3 — Schematic diagram of a x_D ($2 < x \leq 3$) material



Key

- 1 direction of the greater fraction of reinforcement
- 2 direction perpendicular to direction 1
- 3 direction perpendicular to the plane containing directions 1 and 2

When several directions have equal fraction of reinforcement, it shall be stated which direction is chosen as direction 1, in relation to the reinforcement structure. When it is possible to define a plane of reinforcement, direction 2 will be chosen in this plane perpendicular to direction 1 (direction 2 is not necessarily a direction of reinforcement), and direction 3 will be perpendicular to the plane containing directions 1 and 2. When it is not possible to define a plane of reinforcement, direction 2 is chosen arbitrarily, but perpendicular to direction 1 and shall be clearly identified.

Figure 4 — Schematic diagram of a 3D material

4 Symbols

The symbols used for the various mechanical and thermal quantities are given in [Tables 1 to 4](#).