TECHNICAL SPECIFICATION

Second edition 2018-12

Nanotechnologies — Specification for developing representative test materials consisting of nano-objects in dry powder form

Nanotechnologies — Spécifications relatives au développement de matériaux d'essai représentatifs constitués de nano-objets sous forme **iTeh ST**de poudre sèched PREVIEW

(standards.iteh.ai)

<u>ISO/TS 16195:2018</u> https://standards.iteh.ai/catalog/standards/sist/f38c983e-8777-40d0-b43c-4b80c03fb97c/iso-ts-16195-2018



Reference number ISO/TS 16195:2018(E)

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO/TS 16195:2018</u> https://standards.iteh.ai/catalog/standards/sist/f38c983e-8777-40d0-b43c-4b80c03fb97c/iso-ts-16195-2018



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Fax: +41 22 749 09 47 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

Page

Contents

Fore	word		iv
Introduction			v
1	Scop	e	
2	Norr	- nativa rafarancas	1
2	morn		L
3	Tern	is and definitions	1
4	Spec mate 4.1 4.2	ific physico-chemical characterization requirements for representative testcrials consisting of nano-objects in dry powder formGeneralProperties and measurement methods4.2.1Size and shape of nano-objects4.2.2Specific surface area4.2.3Bulk chemical composition4.2.4Crystal structure4.2.5Evaluation of stability4.2.6Evaluation of homogeneity	2 2 2 3 3 3 3 3 3 3 3 3
5	Info	mation related to quality management	4
6	Cont 6.1 6.2 6.3	ents of verification report General Description of the representative test material E.V.I.E.W Measurement result 6.3.1 Size and shape of nano-objectsteh.al 6.3.2 Specific surface area 6.3.3 Bulk chemical composition 95:2018 6.3.4 https://www.allocation.com/position/95:2018 6.3.4 https://www.allocation.com/position/95:2018	4 4 4 4 4 5 5 5 5
Ann	ex A (in	formative) Verification report (example) 95-2018	6
Bibliography			8

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see <u>www.iso</u> .org/iso/foreword.html. (standards.iteh.ai)

This document was prepared by Technical Committee ISO/TC 229, Nanotechnologies.

This second edition cancels and replaces/the first edition (USO/TS716195:2013), which has been technically revised. 4b80c03fb97c/iso-ts-16195-2018

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at <u>www.iso.org/members.html</u>.

Introduction

As new manufactured nano-objects are developed and find a wider range of industrial applications, the roles of physico-chemical, performance, and safety testing of their powders (i.e. dry, unsuspended accumulations of such objects) have become more important than ever. However, many testing methods are still under development and have to be properly evaluated in terms of their reliability. Where possible, validation of new measurement methods is performed using certified reference materials, which have known and quantified properties. In the absence of certified reference materials, one often has to rely on non-certified reference materials, with assigned but not certified property values. However, in developing fields of measurement and testing, such as that of nanotechnology, even non-certified reference materials are scarce. In such cases, "test materials," which are evaluated for homogeneity and stability of one or several of their properties, will be helpful in efforts to improve the reproducibility of testing methods across testing laboratories and the comparability of test results across different test methods. This document specifies that for dry powders of nano-objects the following minimum information be gathered and provided in a verification report to qualify the material as a nanoscale representative test material:

- information describing the manufacturing process,
- information on the quality management of its manufacturing process,
- data from physico-chemical measurements representing the principal features of the representative test material, and
- data on the stability and homogeneity of the above parameters.

Conformity to this document, expressed in the form of a verification report, will provide a level of assurance that the representative test material is homogeneous, statistically representative of the manufacturing process, and has stability. This will increase the likelihood that measurements that are undertaken on the representative test material, whether for safety or function, are comparable across testing laboratories, even for properties for which methods are being developed and for which homogeneity and stability have not been quantitatively assessed.

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO/TS 16195:2018</u> https://standards.iteh.ai/catalog/standards/sist/f38c983e-8777-40d0-b43c-4b80c03fb97c/iso-ts-16195-2018

Nanotechnologies — Specification for developing representative test materials consisting of nano-objects in dry powder form

1 Scope

This document specifies development of representative test materials consisting of nano-objects in dry powder form, to enable test method development and improve comparability of data for nanotechnology applications. It includes the physico-chemical properties (specifically, size and shape, specific surface area, crystal structure, and bulk chemical composition) that are required to be measured and reported with the representative test material.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO Guide 31:2015, Reference materials — Contents of certificates, labels and accompanying documentation

ISO Guide 35, Reference materials — Guidance for characterization and assessment of homogeneity and stability

ISO 9276-1, Representation of results of particle size-analysis — Part 1: Graphical representation

ISO/TS 80004-1, Nanotechnologies 400 Standards. iteh ai/catalog/standards/sist/38c983e-8777-40d0-b43c-

ISO/TS 80004-2:2015, Nanotechnologies — Vocabulary — Part 2: Nano-objects

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO/TS 80004-1 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at <u>https://www.iso.org/obp</u>

— IEC Electropedia: available at http://www.electropedia.org/

3.1

representative test material RTM

material, which is sufficiently homogenous and stable with respect to one or more specified properties, and is implicitly assumed to be fit for its intended use in the development of measurement and test methods that target properties other than those for which homogeneity and stability have been demonstrated

Note 1 to entry: An RTM may be a reference material for other properties (i.e. properties for which homogeneity and stability have been demonstrated), and a candidate reference material for the target property.

Note 2 to entry: An RTM can be a useful tool in inter- or intra-laboratory developments of test methods for which reference materials cannot (yet) be produced.

4 Specific physico-chemical characterization requirements for representative test materials consisting of nano-objects in dry powder form

4.1 General

Following physico-chemical properties shall be evaluated in order to represent the principal features of the representative test material consisting of nano-objects in dry powder form.

4.2 Properties and measurement methods

4.2.1 Size and shape of nano-objects

4.2.1.1 Size distribution of primary particles and of their aggregates

A particle counting-based method shall be performed for measurement of the size distribution of primary particles or of their aggregates. An example of such a measurement method is transmission electron microscopy (TEM). Scanning electron microscopy (SEM) can also be used if the SEM resolution is sufficient to measure the particle size of interest. The method or calibrant used to calibrate the sizing method should be given, as an indication of the metrological traceability [1] of the obtained data.

One critical issue is sample preparation, in particular the dispersion of agglomerated particles and deposition onto the substrate without overlapping of particles. A defined dispersion procedure shall be followed and details thereof reported.

Another critical issue is statistical representativeness of the particles selected for analysis. Depending on the width of the size distribution and on the particle shape, a large number of particles might need to be counted to obtain sufficient statistical reliability.

Typically two different types of particle size distributions may be determined. It shall be reported whether the size distribution is that of primary particles or that of their aggregates. Also, the resulting size distribution shall be reported in a table and/or a graphical representation (histograms, density distributions or cumulative distributions) in accordance with ISO 9276-1.

If traceability to SI units is not available, metrological traceability should be established by a traceability to appropriate measurement standard [1][2] such as:

- the use of certified reference materials provided by a competent supplier to give a reliable physical or chemical characterization of a material;
- the use of specified methods and/or consensus standards that are clearly described and agreed by all parties concerned.

Use of ISO 13322-1 is recommended as a comprehensive guide for image analysis^[3]. It also provides information about the number of particles to be measured.

4.2.1.2 Representative size of primary particles and of their aggregates

Representative size of primary particles and of their aggregates shall be derived from the size distribution (4.2.1.1). It may be reported as, for example, mean and standard deviation, and/or 10, 50, and 90th percentiles of the cumulative size distribution.

ISO 9276-2 and ISO 9276-3 should be used for the expression of the representative size^{[4][5]}.

4.2.1.3 Shape of primary particles and of their aggregates

Shape of primary particles and of their aggregates shall be deduced from imaging techniques, such as TEM, SEM or atomic force microscopy (AFM). A brief, qualitative description shall be done using clearly-defined or widely-acknowledged vocabulary.

Attention should be paid to the fact that TEM and SEM provides 2D-images of the contours (TEM) or surface (SEM) of nano-objects, and that AFM provides a surface topographical image of the particles. Image acquisition with AFM requires special attention, because tip geometry can cause significant ambiguity of particle shape.

NOTE Examples of the description are: spherical, spheroidal, polygonal, ellipsoidal, spherical aggregates, fractal aggregates. Some useful guidance is given in ISO 3252 and ISO/TS 80004-3^[6] ^[Z]. More detailed, quantitative description can be made using shape factors defined, for example, in ISO 9276-6^[8].

4.2.1.4 Images showing representative primary particles and their aggregates

Representative TEM, SEM or AFM images that illustrate both primary particles and their aggregates shall be acquired. To ensure representativeness, take several images of the specimen to show the size and shape of different nano-objects. Sample identification and scale bar shall be presented with each image. Instrumental settings and preparation method should be reported if they are different from those employed in 4.2.1.1.

4.2.2 Specific surface area

Specific surface area of the representative test material shall be determined, for example, by gas adsorption using the BET method as described in ISO 9277^[12].

4.2.3 Bulk chemical composition iTen STANDARD PREVIEW

Bulk chemical composition of the representative test material shall be measured. Depending on the material, any suitable method(s) (e.g., Cttrimetry, gravinetry, X-ray fluorescence spectrometry, inductively coupled plasma-mass spectrometry, inductively coupled plasma-atomic emission spectrometry or atomic absorption spectrometry) can be used. The results shall be provided with a metrological traceability.^[1] statement, where appropriate_{983e-8777-40d0-b43c-}

4b80c03fb97c/iso-ts-16195-2018

4.2.4 Crystal structure

The structure of the nano-objects constituting the representative test material shall be characterized. In case that the nano-objects are crystalline, the crystalline phase (e.g. rutile and anatase in titanium dioxide) shall be identified by X-ray diffraction. In case that the nano-objects are not crystalline (i.e. "amorphous"), this shall be reported.

4.2.5 Evaluation of stability

Stability of the physico-chemical properties specified in <u>4.2.1.2</u>, <u>4.2.2</u>, <u>4.2.3</u> and <u>4.2.4</u> shall be assessed according to, e.g. ISO Guide 35 by measurements in classical or isochronous stability studies^[9]. In the measurements, and depending on the material, the influence of environmental temperature, humidity and/or electromagnetic radiation, and the influence of vibration, are studied and a tolerable environment for storage should be deduced. Representative test materials described in this document should be supplied in an appropriately packaged form (e.g. bottles or vials) in order to minimize the potential for changes in environmental conditions that influence the physico-chemical properties.

NOTE Stability is a characteristic of a representative test material, when stored under specified conditions, to maintain a stated property value within specified limits for a specified period of time [SOURCE: ISO Guide 30:2015].

4.2.6 Evaluation of homogeneity

The homogeneity of the physico-chemical properties specified in <u>4.2.1.2</u>, <u>4.2.2</u>, <u>4.2.3</u> and <u>4.2.4</u> shall be evaluated between packages (e.g. bottles, vials or test pieces) as described in ISO Guide 35. Homogeneity within a single package ("Within-bottle homogeneity" in ISO Guide 35) should be evaluated if appropriate.