

---

**Dielektrične in uporovne lastnosti trdnih izolacijskih materialov - 2-2. del:  
Relativna permitivnost in faktor izgube - Visoke frekvence (1 MHz do 300 MHz) -  
Metode AC (IEC 62631-2-2:2022)**

Dielectric and resistive properties of solid insulating materials - Part 2-2: Relative permittivity and dissipation factor - High frequencies (1 MHz to 300 MHz) - AC methods (IEC 62631-2-2:2022)

Dielektrische und resistive Eigenschaften fester Elektroisolerstoffe - Teil 2-2: Relative Permittivität und Verlustfaktor - Hohe Frequenzen (1 MHz bis 300 MHz) - Wechselspannungsverfahren (IEC 62631-2-2:2022)

<https://standards.iteh.ai/catalog/standards/sist/521d3f91-85e4-42f7-835e-3cf8cc536ead/sist-en-iec-62631-2-2:2022>

Propriétés diélectriques et résistives des matériaux isolants solides - Partie 2-2: Permittivité relative et facteur de dissipation diélectrique - Hautes fréquences (1 MHz à 300 MHz) - Méthodes en courant alternatif (IEC 62631-2-2:2022)

**Ta slovenski standard je istoveten z: EN IEC 62631-2-2:2022**

---

**ICS:**

17.220.99	Drugi standardi v zvezi z električno in magnetizmom	Other standards related to electricity and magnetism
29.035.01	Izolacijski materiali na splošno	Insulating materials in general

**SIST EN IEC 62631-2-2:2022****en**



EUROPEAN STANDARD

**EN IEC 62631-2-2**

NORME EUROPÉENNE

EUROPÄISCHE NORM

May 2022

ICS 17.220.99; 29.035.01

English Version

**Dielectric and resistive properties of solid insulating materials -  
Part 2-2: Relative permittivity and dissipation factor - High  
frequencies (1 MHz to 300 MHz) - AC methods  
(IEC 62631-2-2:2022)**

Propriétés diélectriques et résistives des matériaux isolants  
solides - Partie 2-2: Permittivité relative et facteur de  
dissipation - Hautes fréquences (1 MHz à 300 MHz) -  
Méthodes en courant alternatif  
(IEC 62631-2-2:2022)

Dielektrische und resistive Eigenschaften fester  
Elektroisolerstoffe - Teil 2-2: Relative Permittivität und  
Verlustfaktor - Hohe Frequenzen (1 MHz bis 300 MHz) -  
Wechselspannungsverfahren  
(IEC 62631-2-2:2022)

This European Standard was approved by CENELEC on 2022-05-12. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

[https://standards.iteh.ai/catalog/standards/sist/521d3f91-85e4-42f7-835e-3cf8cc536ead/sist-](https://standards.iteh.ai/catalog/standards/sist/521d3f91-85e4-42f7-835e-3cf8cc536ead/sist-62631-2-2:2022)

CENELEC members are the national electrotechnical committees of Austria, Belgium, Bulgaria, Croatia, Cyprus, the Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.



European Committee for Electrotechnical Standardization  
Comité Européen de Normalisation Electrotechnique  
Europäisches Komitee für Elektrotechnische Normung

**CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels**

**EN IEC 62631-2-2:2022 (E)****European foreword**

The text of document 112/562/FDIS, future edition 1 of IEC 62631-2-2, prepared by IEC/TC 112 "Evaluation and qualification of electrical insulating materials and systems" was submitted to the IEC-CENELEC parallel vote and approved by CENELEC as EN IEC 62631-2-2:2022.

The following dates are fixed:

- latest date by which the document has to be implemented at national level by publication of an identical national standard or by endorsement (dop) 2023-02-12
- latest date by which the national standards conflicting with the document have to be withdrawn (dow) 2025-05-12

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CENELEC shall not be held responsible for identifying any or all such patent rights.

Any feedback and questions on this document should be directed to the users' national committee. A complete listing of these bodies can be found on the CENELEC website.

**Endorsement notice**

The text of the International Standard IEC 62631-2-2:2022 was approved by CENELEC as a European Standard without any modification.

In the official version, for Bibliography, the following notes have to be added for the standards indicated:

IEC 60247 NOTE Harmonized as EN 60247

IEC 62631-2-1:2018 NOTE Harmonized as EN IEC 62631-2-1:2018 (not modified)

## Annex ZA (normative)

### Normative references to international publications with their corresponding European publications

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

NOTE 1 Where an International Publication has been modified by common modifications, indicated by (mod), the relevant EN/HD applies.

NOTE 2 Up-to-date information on the latest versions of the European Standards listed in this annex is available here: [www.cenelec.eu](http://www.cenelec.eu).

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN/HD</u>	<u>Year</u>
IEC 60212	-	Standard conditions for use prior to and during the testing of solid electrical insulating materials	EN 60212	-

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

SIST EN IEC 62631-2-2:2022

<https://standards.iteh.ai/catalog/standards/sist/521d3f91-85e4-42f7-835e-3cf8cc536ead/sist-en-iec-62631-2-2-2022>





IEC 62631-2-2

Edition 1.0 2022-04

# INTERNATIONAL STANDARD

## NORME INTERNATIONALE

**Dielectric and resistive properties of solid insulating materials –  
Part 2-2: Relative permittivity and dissipation factor – High frequencies  
(1 MHz to 300 MHz) – AC methods**

**Propriétés diélectriques et résistives des matériaux isolants solides –  
Partie 2-2: Permittivité relative et facteur de dissipation – Hautes fréquences  
(1 MHz à 300 MHz) – Méthodes en courant alternatif**

INTERNATIONAL  
ELECTROTECHNICAL  
COMMISSION

COMMISSION  
ELECTROTECHNIQUE  
INTERNATIONALE

ICS 17.220.99; 29.035.01

ISBN 978-2-8322-1096-7

**Warning! Make sure that you obtained this publication from an authorized distributor.  
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.**

## CONTENTS

FOREWORD.....	4
INTRODUCTION.....	6
1 Scope.....	7
2 Normative references .....	7
3 Terms and definitions .....	7
4 Methods of test.....	8
4.1 Basic theory.....	8
4.2 Distinctive factors for the measurement in high frequency range.....	12
4.3 Power supply .....	13
4.4 Equipment .....	13
4.4.1 Accuracy .....	13
4.4.2 Distinctive feature of equipment for measurement in high frequency range.....	14
4.4.3 Choice of measurement methods.....	15
4.5 Calibration .....	16
4.6 Test specimen .....	16
4.6.1 General .....	16
4.6.2 Recommended dimensions of test specimen and electrode arrangements .....	16
4.6.3 Number of test specimens .....	16
4.6.4 Conditioning and pre-treatment of test specimen .....	16
4.7 Procedures for specific materials .....	17
5 Test procedure .....	17
5.1 General.....	17
5.2 Calculation of permittivity and relative permittivity.....	17
5.2.1 Relative permittivity .....	17
5.2.2 Dielectric dissipation factor $\tan \delta$ .....	17
6 Report .....	17
7 Repeatability and reproducibility.....	18
Annex A (informative) Compensation method using a series circuit.....	19
Annex B (informative) Parallel electrodes with shield ring .....	20
Annex C (informative) Apparatus .....	21
C.1 Parallel T network bridge .....	21
C.2 Resonance method .....	22
C.3 I-V method designed for high frequencies .....	24
C.4 Auto-balancing bridge method.....	24
Annex D (informative) Non-contacting electrode method with micrometer-controlled parallel electrodes in air.....	26
Bibliography.....	28
Figure 1 – Dielectric dissipation factor .....	10
Figure 2 – Equivalent circuit diagrams with capacitive test specimen .....	11
Figure 3 – Equivalent parallel circuit for test fixture with sample and leads to equipment.....	12
Figure 4 – Existence of residual impedance and stray capacitance in directly connected system .....	15



Figure A.1 – Compensation method using a series circuit .....	19
Figure B.1 – Configuration of parallel electrode with shield ring .....	20
Figure C.1 – Parallel T network, principal circuit diagram .....	21
Figure C.2 – Parallel T network, practical circuit diagram .....	21
Figure C.3 – Principle of resonance method, circuit diagram (originally from Q meter) .....	23
Figure C.4 – Auto-balancing circuit .....	25
Figure D.1 – Non-contacting electrode method .....	27
Table 1 – Applicable frequency range in effective apparatus .....	16

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN IEC 62631-2-2:2022](https://standards.iteh.ai/catalog/standards/sist/521d3f91-85e4-42f7-835e-3cf8cc536ead/sist-en-iec-62631-2-2-2022)

<https://standards.iteh.ai/catalog/standards/sist/521d3f91-85e4-42f7-835e-3cf8cc536ead/sist-en-iec-62631-2-2-2022>

## INTERNATIONAL ELECTROTECHNICAL COMMISSION

---

**DIELECTRIC AND RESISTIVE PROPERTIES OF  
SOLID INSULATING MATERIALS –**
**Part 2-2: Relative permittivity and dissipation factor –  
High frequencies (1 MHz to 300 MHz) – AC methods**
**FOREWORD**

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

IEC 62631-2-2 has been prepared by of IEC technical committee 112: Evaluation and qualification of electrical insulating materials and systems. It is an International Standard.

The text of this International Standard is based on the following documents:

Draft	Report on voting
112/562/FDIS	112/565/RVD

Full information on the voting for its approval can be found in the report on voting indicated in the above table.

The language used for the development of this International Standard is English.

This document was drafted in accordance with ISO/IEC Directives, Part 2, and developed in accordance with ISO/IEC Directives, Part 1 and ISO/IEC Directives, IEC Supplement, available at [www.iec.ch/members\\_experts/refdocs](http://www.iec.ch/members_experts/refdocs). The main document types developed by IEC are described in greater detail at [www.iec.ch/standardsdev/publications](http://www.iec.ch/standardsdev/publications).

A list of all parts in the IEC 62631 series, published under the general title *Dielectric and resistive properties of solid insulating materials*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under [webstore.iec.ch](http://webstore.iec.ch) in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN IEC 62631-2-2:2022](https://standards.iteh.ai/catalog/standards/sist/521d3f91-85e4-42f7-835e-3cf8cc536ead/sist-en-iec-62631-2-2-2022)

<https://standards.iteh.ai/catalog/standards/sist/521d3f91-85e4-42f7-835e-3cf8cc536ead/sist-en-iec-62631-2-2-2022>

## INTRODUCTION

Permittivity and dissipation factor ( $\tan \delta$ ) are basic parameters for the quality of insulating materials. The dissipation factor depends on several parameters, such as environmental factors, moisture, temperature, applied voltage, and highly depends on frequency, the accuracy of measuring apparatus and other parameters applied to the measured specimen.

The frequency range measurable for permittivity and dissipation factor is highly limited by the design of the electrode system, dimension of the sample and impedance of the wiring lead. Special consideration should be given to the measurement in the high frequency range. This document focuses on the method for measurements of permittivity and dissipation factor in the high frequency range from 1 MHz to 300 MHz.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN IEC 62631-2-2:2022](https://standards.iteh.ai/catalog/standards/sist/521d3f91-85e4-42f7-835e-3cf8cc536ead/sist-en-iec-62631-2-2-2022)

<https://standards.iteh.ai/catalog/standards/sist/521d3f91-85e4-42f7-835e-3cf8cc536ead/sist-en-iec-62631-2-2-2022>