

---

---

**Plastics — Determination of dynamic  
mechanical properties —**

**Part 7:  
Torsional vibration — Non-  
resonance method**

**iTeh STANDARD PREVIEW**  
*(standards.iteh.ai)*  
*Plastiques — Détermination des propriétés mécaniques  
dynamiques —  
Partie 7: Vibration en torsion — Méthode hors résonance*

ISO 6721-7:2019

<https://standards.iteh.ai/catalog/standards/sist/088f597a-93c3-49c2-bf4d-dbc81bd0d84d/iso-6721-7-2019>



## iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 6721-7:2019

<https://standards.iteh.ai/catalog/standards/sist/088f597a-93c3-49c2-bf4d-dbc81bd0d84d/iso-6721-7-2019>



### **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

Foreword .....	iv
<b>1 Scope .....</b>	<b>1</b>
<b>2 Normative references .....</b>	<b>1</b>
<b>3 Terms and definitions .....</b>	<b>1</b>
<b>4 Principle .....</b>	<b>1</b>
<b>5 Test device .....</b>	<b>2</b>
5.1 Loading assembly .....	2
5.1.1 General .....	2
5.1.2 Clamps .....	2
5.1.3 Transducers .....	2
5.2 Electronic data-processing equipment .....	3
5.3 Temperature measurement and control .....	3
5.4 Devices for measuring test specimen dimensions .....	3
<b>6 Test specimens .....</b>	<b>3</b>
6.1 General .....	3
6.2 Shape and dimensions .....	3
6.3 Preparation .....	3
<b>7 Number of specimens .....</b>	<b>3</b>
<b>8 Conditioning .....</b>	<b>3</b>
<b>9 Procedure .....</b>	<b>3</b>
9.1 Test atmosphere .....	3
9.2 Measuring the cross-section of the specimen .....	4
9.3 Clamping the specimen .....	4
9.4 Varying the temperature .....	4
9.5 Performing the test .....	4
<b>10 Expression of results .....</b>	<b>5</b>
10.1 Symbols .....	5
10.2 Calculation of the shear storage modulus $G'$ .....	6
10.2.1 General .....	6
10.2.2 Avoidance of specimen resonance .....	6
10.2.3 Correction for transducer resonance .....	7
10.2.4 Correction for apparatus compliance .....	7
10.2.5 Application of a length correction .....	7
10.3 Calculation of the shear loss factor $\tan \delta_G$ .....	8
10.4 Calculation of the shear loss modulus .....	8
10.5 Presentation of data as a function of temperature .....	8
<b>11 Precision .....</b>	<b>8</b>
<b>12 Test report .....</b>	<b>8</b>
<b>Bibliography .....</b>	<b>10</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 5, *Physical-chemical properties*.

<https://standards.iteh.ai/catalog/standards/sist/088f597a-93c3-49c2-bf4d->

This second edition cancels and replaces the first edition (ISO 6721-7:1996), which has been technically revised. It also incorporates the Amendment ISO 6721-7:1996/Amd.1:2007. The main changes compared to the previous edition are as follows:

- the document has been revised editorially;
- normative references have been changed to undated.

A list of all parts in the ISO 6721 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

# Plastics — Determination of dynamic mechanical properties —

## Part 7: Torsional vibration — Non-resonance method

### 1 Scope

This document describes a torsional, non-resonance method for determining the components of the shear complex modulus  $G^*$  of solid polymers in the form of bars or rods at frequencies typically in the range 0,001 Hz to 100 Hz. Higher-frequency measurements can be made, but significant errors in the dynamic properties measured are likely to result (see 10.2.1 and 10.2.2). The method is suitable for measuring dynamic storage moduli ranging from about 10 MPa, which is typical of values obtained for stiff rubbers, to values of about 10 GPa which are representative of fibre-reinforced plastics. Although materials with moduli less than 10 MPa can be studied, more accurate measurements of their dynamic properties can be made using simple shear (see ISO 6721-6) or torsional deformations of thin layers between parallel plates.

This method is particularly suited to the measurement of loss factors greater than 0,02 and may therefore be conveniently used to study the variation of dynamic properties with temperature and frequency through most of the glass-rubber relaxation region (see ISO 6721-1). The availability of data determined over wide ranges of both frequency and temperature enable master plots to be derived, using frequency-temperature shift procedures, which display dynamic properties over an extended frequency range at different temperatures.

NOTE Although loss factors below 0,1 can be more accurately determined using the torsion pendulum (see ISO 6721-2), the method described in this document enables a much wider and continuous frequency range to be covered.

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 6721-1, *Plastics — Determination of dynamic mechanical properties — Part 1: General principles*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 6721-1 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

### 4 Principle

The specimen is subjected to a sinusoidal torque or angular displacement at a frequency significantly below the fundamental torsion resonance frequency (see 10.2.1). The amplitudes of the torque and displacement cycles applied to the specimen and the phase angle between these cycles are measured.

The storage and loss components of the shear complex modulus and the loss factor are calculated using formulae given in [Clause 10](#).

## 5 Test device

### 5.1 Loading assembly

#### 5.1.1 General

The requirements on the apparatus are that it shall permit measurements of the amplitudes of, and phase angle between, the torque and angular displacement cycles for a specimen subjected to a sinusoidal torque or displacement. Various designs of apparatus are possible, as illustrated schematically in [Figures 1 a\)](#) and [1 b\)](#). In [Figure 1 a\)](#), a sinusoidal angular displacement is generated by the drive unit D and applied to one end of the specimen S through the moving clamp C<sub>1</sub>. The amplitude and frequency of the angular displacement are variable and monitored by the rotary displacement transducer R. The specimen is held at the opposite end by a fixed clamp C<sub>2</sub> and thus undergoes sinusoidal torsional deformations. The sinusoidal torque applied in deforming the specimen is monitored by a torque transducer T connected to C<sub>2</sub>. The members between the clamp C<sub>1</sub> and D and between C<sub>2</sub> and T should be much stiffer than the specimen and should have a low thermal conductance if the specimen is to be enclosed in a temperature-controlled cabinet. Where tests are carried out at elevated temperatures, a facility shall be included in the loading assembly to avoid buckling of the specimen resulting from thermal expansion.

While each member of the loading assembly may have a much higher stiffness than the specimen, the presence of clamped or bolted connections can significantly increase the apparatus compliance. It may then be necessary to apply a compliance correction as described in [10.2.3](#).

Various other loading assemblies may be employed as alternatives to that detailed above. For example, the torque on the specimen may be calculated from the current supplied to the drive unit, thus eliminating the need for a separate torque transducer. With this method [[Figure 1 b\)](#)], it should be recognized that part of the torque generated by the drive current is used to accelerate the drive shaft and also to deform any drive shaft suspension (S<sub>u</sub>) in parallel with the specimen. That part of the generated torque used to deform the specimen shall be determined with the aid of a separate calibration with the specimen absent. Alternatively, the suspension member may be replaced by an air bearing, thereby making the torsional rigidity of the suspension zero.

#### 5.1.2 Clamps

The clamps shall be capable of gripping the test specimen with a force which is sufficient to prevent the specimen from slipping during the torsional deformation and maintaining the force at low temperatures.

The separation between the two clamps should preferably be variable so that specimens of different length can be accommodated and length corrections may be determined (see [10.2.4](#)). A facility to permit small variations in the clamp separation would also allow for thermal expansion of the specimens and is necessary to avoid errors in the apparent moduli due to buckling of the specimens at high temperatures.

Any misalignment of the clamps with respect to the force transducer will produce a lateral component of the torque applied to the transducer during loading of the specimen. The alignment of the loading assembly and test specimen shall be such that any lateral component recorded by the transducer is less than 1 % of the applied torque.

#### 5.1.3 Transducers

The term transducer in this document refers to any device capable of measuring the applied torque or displacement, or the ratio of these quantities, as a function of time. The calibrations of the transducers shall be traceable to national standards for the measurement of torque and length. The calibrations shall be accurate to  $\pm 2$  % of the minimum torque and displacement cycle amplitudes applied to the specimen for the purpose of determining dynamic properties.

## 5.2 Electronic data-processing equipment

Data-processing equipment shall be capable of recording the torque and displacement cycle amplitudes to an accuracy of  $\pm 1$  % the phase angle between the torque and displacement cycles to an accuracy of  $\pm 0,1^\circ$  and the frequency to an accuracy of  $\pm 10$  %.

## 5.3 Temperature measurement and control

According to ISO 6721-1.

## 5.4 Devices for measuring test specimen dimensions

According to ISO 6721-1.

# 6 Test specimens

## 6.1 General

According to ISO 6721-1.

## 6.2 Shape and dimensions

Test specimens in the form of rectangular Bars or cylindrical rods are recommended. The width and thickness of the bars and the diameter of the rods shall not vary along the specimen length by more than 2 % of a mean value.

Dimensions of the specimens are not critical, although length corrections for clamping effects can be minimized by increasing the length of the specimen and, for rectangular specimens, these corrections become negligible for certain values of  $b/h$  (see 10.1 and 10.2.4). For test conditions under which the storage moduli are high ( $\geq 1$  GPa), sufficiently long, thin specimens shall be employed so that angular displacements are generated that may be measured with high accuracy. Alternatively, when the storage moduli are low ( $< 100$  MPa), relatively short, thick specimens may be required to achieve sufficient accuracy in the measurement of torque. A variation in dynamic properties may be observed between specimens of different thickness prepared by injection moulding owing to slight differences which may be present in the structure of the polymer in each specimen.

## 6.3 Preparation

According to ISO 6721-1.

# 7 Number of specimens

According to ISO 6721-1.

# 8 Conditioning

According to ISO 6721-1.

# 9 Procedure

## 9.1 Test atmosphere

According to ISO 6721-1.

## 9.2 Measuring the cross-section of the specimen

According to ISO 6721-1.

## 9.3 Clamping the specimen

Mount the specimen between the clamps using a clamping force that is sufficient to prevent slip under all test conditions. If measurements are observed to depend upon clamp pressure, then a constant pressure should preferably be used for all measurements, especially when applying a length correction (see [10.2.4](#)).

If measurements are observed to depend upon clamp pressure, then the clamped area of the specimen is probably too small. A larger clamp face or a wider specimen should eliminate this problem.

## 9.4 Varying the temperature

According to ISO 6721-1.

## 9.5 Performing the test

A dynamic torque shall be applied by the drive motor which yields torque and displacement amplitudes for the specimen that can be measured to the accuracy specified in [5.1.3](#).

If the maximum shear strain within the specimen exceeds the limit for linear behaviour, then the derived dynamic properties will depend on the magnitude of the applied displacement. The limiting strain varies with the composition of the polymer and the temperature and is typically in the region of 0,2 % for glassy plastics. The dynamic strain range for linear behaviour can be explored by varying the dynamic displacement amplitude at a constant frequency and recording any change in dynamic stiffness with strain amplitude. A low frequency should be used for this purpose to minimize any temperature increase caused by mechanical loss. However, it should be noted that, because of the non-uniform strain in the specimen in this test, the onset of non-linear behaviour will be less apparent than in tests where the strain distribution is uniform. If non-linear behaviour is detected in the strain range of interest, the dynamic strain limit should be recorded in the test report.

The amplitudes of, the phase difference between and the frequency of the torque and displacement signals and the temperature of the test shall be recorded. Where measurements are to be made over ranges of frequency and temperature, it is recommended that the lowest temperature be selected first and measurements be made with increasing frequency, keeping the temperature constant. The frequency range is then repeated at the next higher temperature (see ISO 6721-1).

For test conditions under which the polymer exhibits medium or high loss (for example in the glass-rubber transition region), the energy dissipated by the polymer may raise its temperature sufficiently to give a significant change in dynamic properties. Any temperature rise will increase rapidly with increasing strain amplitude and frequency. If the data processing electronics is capable of analysing the transducer outputs within the first few cycles, then the influence of any temperature rise will be minimized. Subsequent measurements will then change with time as the specimen temperature continues to rise, and such observations will indicate the need to exercise some caution in the presentation and interpretation of results.



## 10 Expression of results

### 10.1 Symbols

$L_a$	length of specimen between the two clamps, in metres
$l$	length correction term for clamping, in metres
$b$	width of rectangular specimen, in metres
$h$	thickness of rectangular specimen, in metres
$r$	radius of cylindrical specimen, in metres
$f$	measurement frequency, in hertz
$\theta_A$	measured amplitude of the dynamic angular displacement, in radians
$T_A$	measured amplitude of the dynamic torque applied to the specimen, in newton metres
$\delta_{G_a}, \delta_G$	measured phase difference and corrected phase difference, respectively, between the torque and angular-displacement cycles, in degrees
$\Gamma_a, \Gamma$	measured absolute value and corrected absolute value, respectively, of the torsional complex stiffness of the specimen, in newton metres per radian (N·m·rad <sup>-1</sup> )
$G'_a, G'$	apparent shear storage modulus and corrected shear storage modulus, respectively, in pascals
$G''$	shear loss modulus, in pascals
$\tan \delta_{G_a}, \tan \delta_G$	apparent shear loss factor and corrected shear loss factor, respectively
$\kappa$	shape factor giving the ratio of torsional complex stiffness to shear complex modulus per unit length of specimen, in metres to the power four per radian (m <sup>4</sup> ·rad <sup>-1</sup> )
$I_p$	polar second moment of area of the cross-section per unit specimen length, in metres to the power four (m <sup>4</sup> )
$\Gamma_T$	torsional stiffness of the torque transducer, in newton metres per radian (N·m·rad <sup>-1</sup> )
$I_T$	moment of inertia of that part of the loading assembly between the torque transducer and the test specimen, in kilogram square metres (kg·m <sup>2</sup> )
$\Gamma_\infty$	measured torsional stiffness, in newton metres per radian (N·m·rad <sup>-1</sup> ), of a steel test specimen whose cross-sectional dimensions and length are such that it is at least 100 times stiffer than the stiffest polymer specimen to be tested

NOTE The magnitude of  $\Gamma_\infty$  will give an estimate of the torsional stiffness of the loading assembly, which is equivalent to a spring connected in series with the specimen and will enable a correction for apparatus compliance to be deduced (see [10.2.3](#)).