
Rare earth — Vocabulary —

Part 1:

Minerals, oxides and other compounds

Terres rares — Vocabulaire —

Partie 1: Minéraux, oxydes et autres composants

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO 22444-1:2020

<https://standards.iteh.ai/catalog/standards/iso/85a17f04-93e8-4be9-b3f6-c9dcbb776448/iso-22444-1-2020>



iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO 22444-1:2020

<https://standards.iteh.ai/catalog/standards/iso/85a17f04-93e8-4be9-b3f6-c9dcbb776448/iso-22444-1-2020>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Terms related to rare earth minerals and ore	4
4.1 Rare earth minerals	4
4.2 Rare earth ores and concentrate	5
5 Terms related to rare earth oxides and other compounds	6
5.1 General terms.....	6
5.2 Rare earth compounds.....	6
6 Terms related to the rare earth production process	9
6.1 Production of rare earth concentrate	9
6.2 Rare earth hydrometallurgy	9
Annex A (informative) Characteristics of rare earth elements and individual rare earth oxides	10
Bibliography	13

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 22444-1:2020](https://standards.iteh.ai/catalog/standards/iso/85a17f04-93e8-4be9-b3f6-c9dcbb776448/iso-22444-1-2020)

<https://standards.iteh.ai/catalog/standards/iso/85a17f04-93e8-4be9-b3f6-c9dcbb776448/iso-22444-1-2020>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 298, *Rare earth*.

A list of all parts in the ISO 22444 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Rare earth elements are widely used. Different business and industry sectors have various descriptions for rare earth elements and their compounds and alloys. Therefore, it is of vital importance to unify the terminology used in the rare earth industry.

About 250 minerals contain significant amounts of rare earth elements although there are only a few that are economically exploited at this time. Various rare earth oxides and other compounds are obtained from these rare earth minerals as they are processed through to intermediate products and on to final products.

This document specifies terms for use by producers, consumers and traders in the field of rare earth minerals, oxides and other compounds. This document will serve as a reference that will help to reduce discrepancies or trade disputes caused by inconsistencies in terms used when dealing with rare earth minerals, oxides and other compounds.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 22444-1:2020](https://standards.iteh.ai/catalog/standards/iso/85a17f04-93e8-4be9-b3f6-c9dcbb776448/iso-22444-1-2020)

<https://standards.iteh.ai/catalog/standards/iso/85a17f04-93e8-4be9-b3f6-c9dcbb776448/iso-22444-1-2020>

Rare earth — Vocabulary —

Part 1: Minerals, oxides and other compounds

1 Scope

The document defines the terms for rare earth minerals, oxides and other compounds, as well as for related production processes.

This document can be used as a reference to unify technical terms in rare earth production, application, inspection, circulation, trading, scientific research and education.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

rare earth element

collective name for scandium (Sc), yttrium (Y) and the lanthanides (La, Ce, Pr, Nd, Pm, Sm, Eu, Gd, Tb, Dy, Ho, Er, Tm, Yb, Lu), which was approved by the International Union for Pure and Applied Chemistry (IUPAC) in its 2005 Nomenclature of Inorganic Chemistry Recommendations^[1]

Note 1 to entry: Certain terms and corresponding abbreviated terms are common such as rare earth element (REE or RE) and *rare earth oxide (REO)* (5.2.1).

Note 2 to entry: Rare earth elements are frequently referred to as being either light rare earth (LREE), medium rare earth (MREE) or heavy rare earth (HREE), with LREE including the elements between lanthanum (La) and neodymium (Nd), MREE including the elements between samarium (Sm) and gadolinium (Gd), and HREE including the elements from terbium (Tb) to lutetium (Lu) as well as scandium (Sc) and yttrium (Y).

Note 3 to entry: Didymium is commonly used to express a mixture of the elements Pr and Nd.

Note 4 to entry: Characteristics of rare earth elements are described in [Annex A](#).

3.2

rare earth mineral

mineral containing one or more *rare earth elements* (3.1)

Note 1 to entry: Rare earths can be present as a simple compound, incorporated in the lattice of another mineral, or sorbed to another mineral, such as *bastnaesite* (4.1.1), *monazite* (4.1.2) or montmorillonite as in ionic clay deposits.

3.3

rare earth ore

rare earth mineralization found in nature in various types of ore deposit

Note 1 to entry: Those deposit types that are now, or have previously been, commercially exploited include *Baiyun Obo ore* (4.2.1), *ion-adsorption rare earth ore* (4.2.2), *carbonatite/alkalic pipe* (4.2.3), *weathered carbonatite* (4.2.4) and *beach sand* (4.2.5).

3.4

rare earth deposit

area or volume of the earth's crust where there is an accumulation of *rare earth minerals* (3.2), with or without other valuable minerals, that is of economic interest

3.5

rare earth grade

mass fraction of *rare earth oxide (REO)* (5.2.1) in the deposit/concentrate or tailings

Note 1 to entry: The grade can be present as a percentage or as either kg/t or g/t. Statements of grade shall clearly state if the data are given on a REE, RE or REO basis.

Note 2 to entry: When a rare earth metal mass is converted to oxide mass, all *rare earth elements (REEs)* (3.1) should be taken as trivalent except for the following oxide forms: ceric oxide, CeO_2 , praseodymium oxide, Pr_6O_{11} , and terbium oxide, Tb_4O_7 .

3.6

rare earth mineral resource and mineral reserve

resources of ore or minerals containing rare earths, which can be mined legally and profitably under existing conditions

Note 1 to entry: Indicated reserve is the estimate of ore computed from boreholes, outcrops and developmental data, and is projected for a reasonable distance on geologic evidence.

3.7

rare earth content

total rare earth content

mass fraction of rare earths in the material

ISO 22444-1:2020

<https://standards.iteh.ai/iso/85a17f04-93e8-4be9-b3f6-c9dcb776448/iso-22444-1-2020>

Note 1 to entry: For *rare earth oxides* (5.2.1) and other compounds, the fraction is generally provided as a percentage of rare earth oxide, i.e. % REO or % TREO. For metals and alloys, the content is generally provided as a percentage of rare earth metal, i.e. % REM or % TREM.

3.8

rare earth distribution

mass fraction of each individual rare earth in a material containing a mixture of rare earths compared to the *rare earth content* (3.7) of the material

Note 1 to entry: The distribution is normally expressed as the percentage of rare earth metal, i.e. % RE or % REM for metals and alloys, and percentage of *rare earth oxide* (5.2.1), i.e. % REO, for compounds and other materials.

3.9

average molar mass of mixed rare earth compounds

\bar{M}

ratio of the total mass of all rare earth compounds to their total number of moles, as shown by the formula:

$$\bar{M} = \frac{m_{\text{total}}}{n_{\text{total}}} = \frac{\sum_{i=1}^N m_i}{\sum_{i=1}^N \frac{m_i}{M_i}} = \frac{m_1 + m_2 + \dots + m_N}{\frac{m_1}{M_1} + \frac{m_2}{M_2} + \dots + \frac{m_N}{M_N}}$$

where

m_{total} is the total mass of mixed rare earths, in g;

n_{total} is the total number of moles of mixed rare earths, in moles;

m_i is the mass of rare earth compound i , $i = 1, 2, \dots, N$, in g;

M_i is the molar mass of rare earth compound i , $i = 1, 2, \dots, N$. The basic unit of calculation is $1/x(\text{RE}_x\text{B}_y)$, in g/mol.

Note 1 to entry: \bar{M} is given in g/mol.

EXAMPLE 1 The average molar mass of a mixed *rare earth oxide* (5.2.1) containing 40 % mass of lanthanum oxide and 60 % of yttrium oxide is calculated as follows:

$m_{\text{La}_2\text{O}_3} = 40$ units, $m_{\text{Y}_2\text{O}_3} = 60$ units, $M_{\text{La}} = 325,81/2 = 162,90$ g/mol, $M_{\text{Y}} = 225,81/2 = 112,90$ g/mol

$$\bar{M} = \frac{40+60}{\frac{40}{162,9} + \frac{60}{112,9}} = 128,7 \text{ g/mol}$$

EXAMPLE 2 The average molar mass of a mixed *rare earth oxide* (5.2.1) containing 25 % of praseodymium oxide and 75 % of neodymium oxide is calculated as follows:

$m_{\text{Pr}_6\text{O}_{11}} = 25$ units, $m_{\text{Nd}_2\text{O}_3} = 75$ units, $M_{\text{Pr}} = 1\,021,44/6 = 170,24$ g/mol, $M_{\text{Nd}} = 336,48/2 = 168,24$ g/mol

$$\bar{M} = \frac{25+75}{\frac{25}{170,2} + \frac{75}{168,2}} = 168,7 \text{ g/mol}$$

EXAMPLE 3 The average molar mass of a mixed *rare earth chloride* (5.2.2) containing 40 % of lanthanum chloride and 60 % of cerium chloride is calculated as follows:

$m_{\text{LaCl}_3} = 40$ units, $m_{\text{CeCl}_3} = 60$ units, $M_{\text{LaCl}_3} = 245,26$ g/mol, $M_{\text{CeCl}_3} = 246,48$ g/mol

$$\bar{M} = \frac{40+60}{\frac{40}{245,26} + \frac{60}{246,48}} = 246,0 \text{ g/mol}$$

3.10

rare earth impurity

undesirable *rare earth element* (3.1), apart from the target rare earth component(s) in a rare earth product

3.11

non-rare earth impurity

undesirable non-rare earth component in a rare earth product

EXAMPLE Fe, Al, Ca, SO_4^{2-} .

3.12

rare earth purity

absolute rare earth purity

mass fraction of a specified *rare earth element* (3.1) or *rare earth oxide* (5.2.1) in a rare earth product

Note 1 to entry: It is expressed as a percentage and with the basis (REM or REO) stated.

Note 2 to entry: The content of target element in the oxide, metal or compound is expressed by purity when the content is higher than 90 %.

3.13

relative rare earth purity

mass fraction of the specified *rare earth element* (3.1) or *rare earth oxide* (5.2.1) out of the *rare earth content* (3.7)

Note 1 to entry: It is expressed as a percentage and with the basis (REM or REO) stated.

4 Terms related to rare earth minerals and ore

4.1 Rare earth minerals

4.1.1

bastnaesite

yellow, reddish brown, light green or brown carbonate-fluoride mineral, usually containing 65 % to 75 % *rare earth oxide* (5.2.1), with the formula of $(\text{Ce}, \text{La}, \text{Nd}, \text{Pr}) \text{CO}_3\text{F}$

Note 1 to entry: The family of carbonate-fluoride minerals includes bastnaesite-(Ce) with a formula of $(\text{Ce}, \text{La}) \text{CO}_3\text{F}$, bastnaesite-(La) with a formula of $(\text{La}, \text{Ce}) \text{CO}_3\text{F}$, and bastnaesite-(Y) with a formula of $(\text{Y}, \text{Ce}) \text{CO}_3\text{F}$. Most of the mineral is bastnaesite-(Ce), and cerium is by far the most common of the rare earths in this class of minerals.

Note 2 to entry: The Mohs hardness of the mineral is 4 to 4,5, and the density is generally 4 700 kg/m³ to 5 100 kg/m³.

Note 3 to entry: The mineral is soluble in HCl, H₂SO₄, HNO₃ and H₃PO₄.

4.1.2

monazite

yellow-brown, brown, red and sometimes green mineral, usually containing 55 % to 70 % of *rare earth oxide* (5.2.1), with the formula of $(\text{Ce}, \text{La}, \text{Nd}, \text{Pr}, \text{Th}) \text{PO}_4$

Note 1 to entry: The mineral is usually found in small free crystals, and the mineral composition is mostly light rare earth. The presence of thorium can create radioactivity issues.

Note 2 to entry: The Mohs hardness of the mineral is 5,05 to 5,5, and the density is generally 4 900 kg/m³ to 5 500 kg/m³.

Note 3 to entry: The mineral is soluble in H₃PO₄, H₂SO₄ and HClO₄ depending on composition and pre-treatment processes.

4.1.3

xenotime

yellow, brown and sometimes yellowish green *rare earth phosphate* (5.2.9) mineral, typically containing 50 % to 65 % *rare earth oxide* (5.2.1), which is generally yttrium phosphate (YPO₄)

Note 1 to entry: Besides yttrium, the mineral often contains other heavy *rare earth elements* (3.1) such as dysprosium, erbium, terbium and ytterbium. The presence of thorium can create radioactivity issues. The mineral is a significant source of yttrium and heavy rare earth metals.

Note 2 to entry: The Mohs hardness of the mineral is 4 to 5 and the density is generally 4 400 kg/m³ to 5 100 kg/m³.

4.1.4

fergusonite

typically yellow, tawny or black complex mineral, typically containing 43 % to 53 % *rare earth oxide* (5.2.1), with the chemical formula of $(\text{Y}, \text{REE}) \text{NbO}_4$

Note 1 to entry: Usually, the main rare earth in the mineral is yttrium, but sometimes cerium, lanthanum and neodymium can be substituted.

Note 2 to entry: The Mohs hardness of the mineral is 5,5 to 6,5 and the density is generally 4 900 kg/m³ to 5 800 kg/m³.