



Designation: ~~C1311-02~~ Designation: C1311 - 10

Standard Specification for Solvent Release Sealants¹

This standard is issued under the fixed designation C1311; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope

1.1 This specification describes the properties of a one-component solvent release sealant for use in building construction. These sealants are generally formulated to withstand a maximum joint movement of 7.5 % in extension and 7.5 % in compression of the nominal joint width.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 The committee with jurisdiction of this specification is not aware of any similar specification within ISO or any other organization.

2. Referenced Documents

2.1 ASTM Standards:²

C661 Test Method for Indentation Hardness of Elastomeric-Type Sealants by Means of a Durometer

C712 Test Method for Bubbling of One-Part, Elastomeric, Solvent-Release Type Sealants

C717 Terminology of Building Seals and Sealants

C1193 Guide for Use of Joint Sealants

C1216 Test Method for Adhesion and Cohesion of One-Part Elastomeric Solvent Release Sealants

C1257 Test Method for Accelerated Weathering of Solvent-Release-Type Sealants

C1442 Practice for Conducting Tests on Sealants Using Artificial Weathering Apparatus

D2202 Test Method for Slump of Sealants

D2203 Test Method for Staining from Sealants

D2377 Test Method for Tack-Free Time of Caulking Compounds and Sealants

D2452 Test Method for Extrudability of Oil- and Resin-Base Caulking Compounds

3. Terminology

3.1 *Definitions*—Definitions of the following terms used in this specification are found in Terminology C717: adhesive failure (adhesion loss), caulk (v), compound, durometer, hardness, joint, primer, seal, sealant, sealing material, and solvent release sealant.

4. Materials and Manufacture

4.1 The sealing compound shall be a solvent release material compounded to conform to the requirements prescribed in this specification.

4.2 All material and workmanship shall be in accordance with good commercial practice. The producer is permitted a wide latitude in choice of raw materials for making these products. Consequently, there is no implication that the compounds are equivalent in all physical properties.

4.3 The manufacturing process shall be such as will ensure a homogeneous mix, free of defects that would affect serviceability, and of a consistency suitable for immediate application.

5. General Requirements

5.1 *Standard Conditions*—~~Perform all of the tests in a laboratory controlled at $23 \pm 2^\circ\text{C}$ ($73 \pm 3.6^\circ\text{F}$) and $50 \pm 10\%$ relative humidity. Condition sealant samples for at least 5 h at these conditions before any tests are performed.~~—Perform all of the tests

¹ This specification is under the jurisdiction of ASTM Committee C24 on Building Seals and Sealants and is under the direct responsibility of Subcommittee C24.10 on Specifications, Guides and Practices.

Current edition approved May 10, 2002. Published June 2002. Originally published as C1311-95. Last previous edition C1311-95. DOI: 10.1520/C1311-02.

Current edition approved March 1, 2010. Published April 2010. Originally approved in 1995. Last previous edition approved in 2002 as C1311-02. DOI: 10.1520/C1311-10.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.