



SLOVENSKI STANDARD
SIST ISO 11845:2021

01-julij-2021

Nadomešča:
SIST ISO 11845:1999

Korozija kovin in zlitin - Splošna načela preskušanja korozije

Corrosion of metals and alloys -- General principles for corrosion testing

iTeh STANDARD PREVIEW
Corrosion des métaux et alliages -- Principes généraux des essais de corrosion
(standards.iteh.ai)

Ta slovenski standard je istoveten z: ISO 11845:2021

<https://standards.iteh.ai/catalog/standards/sist/d64c632e-bf2f-4e2f-be7f-16b0dc63dea1/sist-iso-11845-2021>

ICS:

77.060

Korozija kovin

Corrosion of metals

SIST ISO 11845:2021

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 11845:2021](#)

<https://standards.iteh.ai/catalog/standards/sist/d64c632e-bf2f-4e2f-be7f-16b0dc63dca1/sist-iso-11845-2021>

INTERNATIONAL
STANDARD

ISO
11845

Second edition
2020-03

**Corrosion of metals and alloys —
General principles for corrosion testing**

Corrosion des métaux et alliages — Principes généraux des essais de corrosion

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 11845:2021](https://standards.iteh.ai/catalog/standards/sist/d64c632e-bf2f-4e2f-be7f-16b0dc63dca1/sist-iso-11845-2021)

<https://standards.iteh.ai/catalog/standards/sist/d64c632e-bf2f-4e2f-be7f-16b0dc63dca1/sist-iso-11845-2021>



Reference number
ISO 11845:2020(E)

© ISO 2020

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST ISO 11845:2021](https://standards.iteh.ai/catalog/standards/sist/d64c632e-bf2f-4e2f-be7f-16b0dc63dca1/sist-iso-11845-2021)

<https://standards.iteh.ai/catalog/standards/sist/d64c632e-bf2f-4e2f-be7f-16b0dc63dca1/sist-iso-11845-2021>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents		Page
Foreword		iv
Introduction		v
1 Scope		1
2 Normative references		1
3 Terms and definitions		1
4 General principles		1
5 Materials		2
6 Corrosive medium		3
7 Test procedure		3
8 Test report		5
Annex A (informative) General requirements for corrosion tests under constant immersion for a specific purpose		7
Bibliography		10

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 11845:2021](https://standards.iteh.ai/catalog/standards/sist/d64c632e-bf2f-4e2f-be7f-16b0dc63dca1/sist-iso-11845-2021)

<https://standards.iteh.ai/catalog/standards/sist/d64c632e-bf2f-4e2f-be7f-16b0dc63dca1/sist-iso-11845-2021>

ISO 11845:2020(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 156, *Corrosion of metals and alloys*.

This second edition cancels and replaces the first edition (ISO 11845:1995), which has been technically revised. The main changes compared with the previous edition are as follows:

- the format has been changed;
- [Annex A](#) has been added with general requirements for corrosion tests under constant immersion.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

The existence of a wide range of corrosion tests, partly as a function of the various materials and corrosive media in existence, calls for guidance in the general procedures that should be used. Corrosion tests, if they are to evaluate and give comparable results, are carried out in accordance with established conditions. Conditions deviating from these conditions are precisely quoted, taking into account all the details given in this document. The most relevant results on corrosion behaviour of metals can normally be obtained from long-term tests under conditions close to those obtained in practice.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST ISO 11845:2021](https://standards.iteh.ai/catalog/standards/sist/d64c632e-bf2f-4e2f-be7f-16b0dc63dca1/sist-iso-11845-2021)

<https://standards.iteh.ai/catalog/standards/sist/d64c632e-bf2f-4e2f-be7f-16b0dc63dca1/sist-iso-11845-2021>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 11845:2021](#)

<https://standards.iteh.ai/catalog/standards/sist/d64c632e-bf2f-4e2f-be7f-16b0dc63dca1/sist-iso-11845-2021>

Corrosion of metals and alloys — General principles for corrosion testing

1 Scope

This document specifies general principles for carrying out corrosion tests under conditions of constant immersion. Some of these general principles are applicable to other types of corrosion testing.

This document does not cover important procedures for stress corrosion testing, such as those given in ISO 7539 (all parts).

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 8044, *Corrosion of metals and alloys — Vocabulary*

ISO 8407, *Corrosion of metals and alloys — Removal of corrosion products from corrosion test specimens*

3 Terms and definitions (standards.iteh.ai)

For the purposes of this document, the terms and definitions given in ISO 8044 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 General principles

4.1 Corrosion tests are generally carried out as comparative tests, i.e. a number of materials or corrosive media are compared under the given test conditions. It is, however, also advisable to include reference materials or reference solutions in which the behaviour under practical conditions of attack are known. It is important to have a clear understanding of the objectives of any corrosion testing programme and to make a judicious choice of the most practical methods in order to evaluate corrosion damage.

4.2 During the tests, the degree of attack as a function of time is observed and, as far as possible, quantitatively recorded. The objective of most types of testing should be to determine the state of the specimens on more than three separate occasions apart from the start of the test. The duration of tests should be such that, on completion of the test, a clear result is obtained concerning the behaviour of the material and, where applicable, the reference material under the given test conditions. If necessary, additional tests extending beyond the time originally planned should be required.

4.3 Because results often exhibit considerable scatter, a single value provides little useful information. For this reason, whenever possible, every test result should be verified by taking the mean of at least three tests per measurement point. For this purpose, each specimen should be used only once.

ISO 11845:2020(E)

4.4 The test conditions should, as far as possible, be matched to the practical conditions under which the material and the corrosive media will be used, except for short-duration tests as detailed in [4.5](#). This applies:

- a) to the material, in relation to its shape, surface condition, grain structure, etc., for details see [Clause 5](#);
- b) to the corrosive medium, in relation to concentration, temperatures, etc., for details see [Clause 7](#).

4.5 In the case of short-duration corrosion tests, the object is to achieve usable results in the shortest possible time by intensifying the attack conditions. However, intensification of the attack conditions, e.g. by increasing the temperature or concentration of the corrosive medium, often gives results that do not correspond to behaviour under practical conditions. Care shall therefore be exercised when applying such results in practice.

4.6 Particular care is necessary when applying the results of accelerated corrosion tests to practical conditions since, with this type of corrosion test, corrosion media differing from those occurring in practice are often used.

4.7 For the specific purpose, the material, the corrosive medium, the ratio of solution volume to surface area, the surface area, the temperature, the agitation, the test duration, the evaluation, and the corrosion form should be in accordance with the International Standards given in [Annex A](#).

5 Materials

iTeh STANDARD PREVIEW
(standards.iteh.ai)

5.1 Test specimens shall be clearly identified. The following information should be given, when applicable:

- a) chemical composition of the material and the appropriate designation, according to the relevant international, regional or national standards;
- b) condition of the material and fabrication details (e.g. presence of welds, sand cast, gravity die cast, pressure die cast, hot rolled, cold rolled, forged, heat-treatment, whether naturally or artificially aged);
- c) form of material (sheet, wire, tube, solid bars or similar);
- d) position and orientation of the specimens in the original material (with a sketch if necessary);
- e) dimensions (exact size, shape, area) and mass of specimens;
- f) condition of the surface of the material (with or without rolling skin, thickness of rolling skin, pickled, ground, polished, or other pretreatment);
- g) mechanical properties of the material;
- h) structure of the material, including any chemical or mechanical pretreatment;
- i) protective layers and coatings (type, composition and thickness).

5.2 The method of producing the specimens from the test piece should be documented. Specimens should preferably be taken from the test piece in such a manner as to exclude the effect of any significant additional mechanical cold working and any substantial temperature rise at the cut edges during machining. Any burr at the cut edges produced when the specimen is obtained should be removed. In general, it is necessary to protect the edges where it is likely that unwanted effects on the corrosion behaviour of the material being tested should originate at the edges (e.g. in the case of coated specimens).