

---

---

**Preparation of steel substrates before  
application of paints and related  
products — Specifications for metallic  
blast-cleaning abrasives —**

**Part 5:  
Cut steel wire**

iTeh STANDARD PREVIEW

(standards.iteh.ai)  
*Préparation des subjectiles d'acier avant application de peintures  
et de produits assimilés — Spécifications pour préparation par  
projection d'abrasifs métalliques —*

ISO 11124-5:2019

*Partie 5: Fils d'acier coupés*  
<https://standards.iteh.ai/catalog/standards/sis/3627956c-4ff1-434c-a65d-9ab679a1b155/iso-11124-5-2019>



**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 11124-5:2019

<https://standards.iteh.ai/catalog/standards/sist/3627e56e-4ff1-434c-a65d-9ab679a1b155/iso-11124-5-2019>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
Foreword .....	iv
<b>1 Scope .....</b>	<b>1</b>
<b>2 Normative references .....</b>	<b>1</b>
<b>3 Terms and definitions .....</b>	<b>2</b>
<b>4 Designation of abrasives .....</b>	<b>3</b>
<b>5 Sampling .....</b>	<b>3</b>
<b>6 Requirements for cut steel wire abrasives .....</b>	<b>4</b>
<b>7 Package identification and lot traceability .....</b>	<b>4</b>
<b>8 Information to be provided by the manufacturer or supplier .....</b>	<b>5</b>
<b>Annex A (informative) Approximately equivalent codings for cut steel wire abrasives .....</b>	<b>6</b>
<b>Bibliography .....</b>	<b>7</b>

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 11124-5:2019](https://standards.iteh.ai/catalog/standards/sist/3627e56e-4ff1-434c-a65d-9ab679a1b155/iso-11124-5-2019)

<https://standards.iteh.ai/catalog/standards/sist/3627e56e-4ff1-434c-a65d-9ab679a1b155/iso-11124-5-2019>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 12, *Preparation of steel substrates before application of paints and related products*.

A list of all parts in the ISO 11124 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

# Preparation of steel substrates before application of paints and related products — Specifications for metallic blast-cleaning abrasives —

## Part 5: Cut steel wire

### 1 Scope

This document specifies requirements for 13 grades of cut steel wire abrasives, as supplied for blast-cleaning processes. It specifies ranges of particle sizes, together with corresponding grade designations. Values are specified for hardness, density, defect/structural requirements, metallographic structure and chemical composition.

This document is suitable for cut steel wire supplied for blast-cleaning processes which is made by cutting new cold drawn wire.

The requirements specified in this document apply to abrasives manufactured from virgin wire supplied in the new and unconditioned state only. They do not apply to abrasives either during or after use.

NOTE 1 Information on commonly referenced national standards for cut steel wire abrasives and their approximate relationship with ISO 11124 is given in [Annex A](#).

NOTE 2 Although this document has been developed specifically to meet requirements for preparation of steelwork, the properties specified will generally be appropriate for use when preparing other material surfaces, or components, using blast-cleaning techniques.

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 439, *Steel and iron — Determination of total silicon content — Gravimetric method*

ISO 629, *Steel and cast iron — Determination of manganese content — Spectrophotometric method*

ISO 4935, *Steel and iron — Determination of sulfur content — Infrared absorption method after combustion in an induction furnace*

ISO 9556, *Steel and iron — Determination of total carbon content — Infrared absorption method after combustion in an induction furnace*

ISO 10714, *Steel and iron — Determination of phosphorus content — Phosphovanadomolybdate spectrophotometric method*

ISO 11125-1, *Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives — Part 1: Sampling*

ISO 11125-3, *Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives — Part 3: Determination of hardness*

ISO 11125-4, *Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives — Part 4: Determination of apparent density*

ISO 11125-5, *Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives — Part 5: Determination of percentage defective particles and of microstructure*

ISO 11125-6, *Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives — Part 6: Determination of foreign matter*

ISO 11125-7, *Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives — Part 7: Determination of moisture*

### 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

#### 3.1

##### **cut steel wire**

metallic blast-cleaning abrasive made by cutting cold drawn steel wire

#### 3.2

##### **virgin wire**

wire which is unaltered from its original manufactured state, and which has not previously been used as a component in any other manufactured product or composite material

Note 1 to entry: Wire which has been previously used poses a potential risk of imparting invisible contaminants onto a prepared surface, which could have an adverse effect on the performance of subsequently applied coatings.

#### 3.3

##### **cylindrical**

sharp-edged particles, having a diameter to length ratio of 1:1, cut so that their faces are approximately at right angles to their centreline

#### 3.4

##### **defect**

fault or weakness in an abrasive which, if present at or above a given level, can be detrimental to the performance characteristics of the abrasive

Note 1 to entry: See [Table 2](#).

#### 3.5

##### **over-length particles**

particles of which the axial length to diameter ratio is equal to or greater than 2

#### 3.6

##### **crack**

linear discontinuity that has a length-to-width ratio of 3:1 or greater, that extends over more than 20 % of the diameter or shortest dimension of a particle

#### 3.7

##### **foreign matter**

material or particles mixed with the abrasive which are not attached to the abrasive particles and which are nonmagnetic

## 4 Designation of abrasives

Cut steel wire shall be identified by "Abrasive ISO 11124" and the abbreviation "M/CW", indicating metallic, cut steel wire abrasive. The symbol "C" shall follow to indicate the required cylindrical particle shape of the cut steel wire as purchased. The designation shall be completed by a 3-digit number denoting the grade, or nominal particle size, required. Grade requirements and codes are specified in [Table 1](#). The grade code is based on the 3-digit number indicating the diameter of the wire, for each grade, expressed in millimetres  $\times 100$ . If alternative hardness of abrasive is available, the particular Vickers hardness (HV) range required shall be specified (see Example 2).

### EXAMPLE 1

Abrasive ISO 11124 M/CW/C100.

Denotes an abrasive of the metallic, cut steel wire type, conforming to the requirements of this document, of cylindrical particle shape and grade 100 (i.e. nominal particle size 1,00 mm).

### EXAMPLE 2

Abrasive ISO 11124 M/CW/C080/570-710HV.

Denotes an abrasive of the metallic, cut steel wire type, conforming with the requirements of this document, of cylindrical particle shape and grade 080 (i.e. nominal particle size 0,80 mm), and with a hardness range of 570 HV to 710 HV.

This full product designation shall be quoted on all orders.

NOTE [Annex A](#) provides guidance on approximately equivalent grades and codings in other commonly referenced national standards for cut steel wire abrasives.

**Table 1 — Mass specifications by grade — Cut steel wire**

Grade code	Nominal size mm	Mass of N random particles g	Number of particles (N)
C250	2,5	4,080 to 5,620	N = 50
C200	2,0	2,050 to 2,920	
C160	1,6	1,030 to 1,520	
C140	1,4	0,680 to 1,030	
C120	1,2	0,420 to 0,660	
C100	1,0	0,260 to 0,400	
C090	0,9	0,190 to 0,260	
C080	0,8	0,130 to 0,190	
C070	0,7	0,080 to 0,130	
C060	0,6	0,050 to 0,080	
C050	0,5	0,030 to 0,050	
C040	0,4	0,030 to 0,055	N = 100
C030	0,3	0,010 to 0,030	

By agreement between interested parties non-standard wire diameters can be used but mass tolerances should be established as part of the specification.

## 5 Sampling

Sampling procedures shall be as specified in ISO 11125-1.

## 6 Requirements for cut steel wire abrasives

The requirements for cut steel wire abrasives shall be as specified in [Table 2](#).

**Table 2 — Requirements of cut steel wire abrasives**

Property	Requirement	Test method	
<b>Particle size</b>	See <a href="#">Table 1</a>	Weighing random particles to an accuracy of 0,001 g	
<b>Hardness</b>	90 % of the particles tested shall have a hardness value within one of the ranges specified below: Standard hardnesses: 390 HV to 520 HV 470 HV to 610 HV 570 HV to 710 HV Equal or greater than 700 HV Special hardnesses: Other hardness ranges can be specified by both supply and demand sides, with a minimum of 90 % of the particles within the regulation range.	ISO 11125-3	
<b>Apparent density</b>	Min. $7,8 \times 10^3 \text{ kg/m}^3$ (7,8 g/cm <sup>3</sup> )	ISO 11125-4	
<b>Defects</b>	Defects present in the particles examined shall not exceed the following levels: Over-length particles: Max. 5 % Crack: Max. 5 % Total defects: Max. 10 % For the particles with more defects than above, the number should be calculated only once in total defects.	ISO 11125-5	
<b>Foreign matter</b>	Max. 0,5 % (mass fraction)	ISO 11125-6	
<b>Metallographic structure</b>	Shall be the deformed sorbite.	ISO 11125-5	
<b>Chemical composition</b>	carbon	0,45 % (mass fraction) to 0,85 % (mass fraction)	ISO 9556
	manganese	0,30 % (mass fraction) to 1,30 % (mass fraction)	ISO 629
	silicon	0,15 % (mass fraction) to 0,35 % (mass fraction)	ISO 439
	sulfur	Max. 0,050 % (mass fraction)	ISO 4935
	phosphorus	Max. 0,040 % (mass fraction)	ISO 10714
<b>Moisture</b>	Max. 0,2 % (mass fraction)	ISO 11125-7	
NOTE The cut steel wire abrasives can be stored indoors in dry surroundings to prevent condensation, rusting and deterioration of the abrasive, rendering it unsuitable for use.			

## 7 Package identification and lot traceability

All supplies shall be clearly marked and identified using the designation system specified in [Clause 4](#). The unit of sale, i.e. commercial packaging unit, shall be clearly labelled with the full product coding, including hardness range, if applicable.

Sub-units, i.e. bags, shall be marked with the particle shape and grade codes.



Inclusion of additional marking to allow product traceability to a particular production period or lot is recommended. Traceability references should be included at least at the pallet, drum or box level of package marking.

## **8 Information to be provided by the manufacturer or supplier**

The manufacturer or supplier shall provide, if requested, a test report detailing results for any relevant property as determined by the appropriate method specified in [Table 2](#).

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 11124-5:2019](#)

<https://standards.iteh.ai/catalog/standards/sist/3627e56e-4ff1-434c-a65d-9ab679a1b155/iso-11124-5-2019>