



Designation: E 527 – 83 (Reapproved 1997)^{ε1}

Standard Practice for Numbering Metals and Alloys (UNS)¹

This standard is issued under the fixed designation E 527; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

^{ε1} NOTE—Keywords were added editorially in October 1997.

1. Scope

1.1 This practice (Note 1) covers a unified numbering system (UNS) for metals and alloys that have a “commercial standing” (see Note 2), and covers the procedure by which such numbers are assigned. Section 2 describes the system of alphanumeric designations or “numbers” established for each family of metals and alloys. Section 3 outlines the organization established for administering the system. Section 4 describes the procedure for requesting number assignment to metals and alloys for which UNS numbers have not previously been assigned.

NOTE 1—UNS designations shall not be used for metals and alloys that are not registered under the system described herein, or for any metal or alloy whose composition differs from those registered.

NOTE 2—The terms “commercial standing,” “production usage,” and others are intended to portray a material in active industrial use, although the actual amount of such use will depend, among other things, upon the type of materials. (Obviously gold will not be used in the same “tonnages” as hot-rolled steel.)

Different standardizing groups use different criteria to define the status that a material has to attain before a standard number will be assigned to it. For instance, the American Iron and Steel Institute requires for stainless steels “two or more producers with combined production of 200 tons per year for at least two years”; the Copper Development Association requires that the material be “in commercial use (without tonnage limits)”; the Aluminum Association requires that the alloy be “offered for sale (not necessarily in commercial use)”; the SAE Aerospace Materials Division calls for “repetitive procurement by at least two users.”

While it is apparent that no hard and fast usage definition can be set up for an all-encompassing system, the UNS numbers are intended to identify metals and alloys that are in more or less regular production and use. A UNS number will not ordinarily be issued for a material that has just been conceived or that is still in only experimental trial.

1.2 The UNS provides a means of correlating many nationally used numbering systems currently administered by societies, trade associations, and individual users and producers of metals and alloys, thereby avoiding confusion caused by use of

more than one identification number for the same material; and by the opposite situation of having the same number assigned to two or more entirely different materials. It also provides the uniformity necessary for efficient indexing, record keeping, data storage and retrieval, and cross referencing.

1.3 A UNS number is not in itself a specification, since it establishes no requirements for form, condition, quality, etc. It is a unified identification of metals and alloys for which controlling limits have been established in specifications published elsewhere.

NOTE 3—Organizations that issue specifications should report to appropriate UNS number-assigning offices (3.1.2) any specification changes that affect descriptions shown in published UNS listings.

2. Description of Numbers (or Codes) Established for Metals and Alloys

2.1 The unified numbering system (UNS) establishes 18 series of numbers for metals and alloys, as shown in Table 1. Each UNS number consists of a single letter-prefix followed by five digits. In most cases the letter is suggestive of the family of metals identified; for example, A for aluminum, P for precious metals, and S for stainless steels.

2.2 Whereas some of the digits in certain UNS number groups have special assigned meaning, each series is independent of the others in such significance; this practice permits greater flexibility and avoids complicated and lengthy UNS numbers.

NOTE 4—This arrangement of alphanumeric six-character numbers is a compromise between the thinking that identification numbers should indicate many characteristics of the material, and the belief that numbers should be short and uncomplicated to be widely accepted and used.

2.3 Wherever feasible, identification “numbers” from existing systems are incorporated into the UNS numbers. For example: carbon steel, presently identified by AISI 1020 (American Iron and Steel Institute), is covered by “UNS G 10200”; and free cutting brass, presently identified by CDA (Copper Development Association C 36000), is covered by “UNS C 36000.” Table 2 shows the secondary division of some primary series of numbers.

¹ This practice is under the jurisdiction of ASTM Committee A-1 on Steel, Stainless Steel, and Related Alloys and is the direct responsibility of Subcommittee A01.91 on Editorial.

Current edition approved March 10, 1997. Published October 1997. Originally published as E 527 – 74. Last previous edition E 527 – 83.


 **E 527 – 83 (1997)^{e1}**

TABLE 1 Primary Series of Numbers

<i>Nonferrous Metals and Alloys</i>	
A00001–A99999	aluminum and aluminum alloys
C00001–C99999	copper and copper alloys
E00001–E99999	rare earth and rare earth-like metals and alloys (18 items; see Table 2)
L00001–L99999	low melting metals and alloys (15 items; see Table 2)
M00001–M99999	miscellaneous nonferrous metals and alloys (12 items; see Table 2)
N00001–N99999	nickel and nickel alloys
P00001–P99999	precious metals and alloys (8 items; see Table 2)
R00001–R99999	reactive and refractory metals and alloys (14 items; see Table 2)
Z00001–Z99999	zinc and zinc alloys
<i>Ferrous Metals and Alloys</i>	
D00001–D99999	specified mechanical properties steels
F00001–F99999	cast irons and cast steels
G00001–G99999	AISI and SAE carbon and alloy steels
H00001–H99999	AISI H-steels
J00001–J99999	cast steels (except tool steels)
K00001–K99999	miscellaneous steels and ferrous alloys
S00001–S99999	heat and corrosion resistant (stainless) steels
T00001–T99999	tool steels
<i>Specialized Metals and Alloys</i>	
W00001–W99999	welding filler metals, covered and tubular electrodes, classified by weld deposit composition (see Table 2)

TABLE 2 Secondary Division of Some Series of Numbers

E00001–E99999 Rare Earth and Rare Earth-Like Metals and Alloys

E00000–E00999	actinium
E01000–E20999	cerium
E21000–E45999	mixed rare earths ⁴
E46000–E47999	dysprosium
E48000–E49999	erbium
E50000–E51999	europium
E52000–E55999	gadolinium
E56000–E57999	holmium
E58000–E67999	lanthanum
E68000–E68999	lutetium
E69000–E73999	neodymium
E74000–E77999	praseodymium
E78000–E78999	promethium
E79000–E82999	samarium
E83000–E84999	scandium
E85000–E86999	terbium
E87000–E87999	thulium
E88000–E89999	ytterbium
E90000–E99999	yttrium

F00001–F9999 Cast Irons

K00001–K99999 Miscellaneous Steels and Ferrous Alloys

L00001–L99999 Low-Melting Metals and Alloys

L00001–L00999	bismuth
L01001–L01999	cadmium
L02001–L02999	cesium
L03001–L03999	gallium
L04001–L04999	indium
L05001–L05999	lead
L06001–L06999	lithium
L07001–L07999	mercury
L08001–L08999	potassium
L09001–L09999	rubidium
L10001–L10999	selenium
L11001–L11999	sodium
L12001–L12999	thallium
L13001–L13999	tin

M00001–M99999 Miscellaneous Nonferrous Metals and Alloys

M00001–M00999	antimony
M01001–M01999	arsenic
M02001–M02999	barium
M03001–M03999	calcium

TABLE 2 *Continued*

M04001–M04999	germanium
M05001–M05999	plutonium
M06001–M06999	strontium
M07001–M07999	tellurium
M08001–M08999	uranium
M10001–M19999	magnesium
M20001–M29999	manganese
M30001–M39999	silicon
<i>P00001–P99999 Precious Metals and Alloys</i>	
P00001–P00999	gold
P01001–P01999	iridium
P02001–P02999	osmium
P03001–P03999	palladium
P04001–P04999	platinum
P05001–P05999	rhodium
P06001–P06999	ruthenium
P07001–P07999	silver
<i>R00001–R99999 Reactive and Refractory Metals and Alloys</i>	
R01001–R01999	boron
R02001–R02999	hafnium
R03001–R03999	molybdenum
R04001–R04999	niobium (columbium)
R05001–R05999	tantalum
R06001–R06999	thorium
R07001–R07999	tungsten
R08001–R08999	vanadium
R10001–R19999	beryllium
R20001–R29999	chromium
R30001–R39999	cobalt
R40001–R49999	rhenium
R50001–R59999	titanium
R60001–R69999	zirconium
<i>W00001–W99999 Welding Filler Metals Classified by Weld Deposit Composition</i>	
W00001–W09999	carbon steel with no significant alloying elements
W10000–W19999	manganese-molybdenum low alloy steels
W20000–W29999	nickel low alloy steels
W30000–W39999	austenitic stainless steels
W40000–W49999	ferritic stainless steels
W50000–W59999	chromium low alloy steels
W60000–W69999	copper base alloys
W70000–W79999	surfacing alloys
W80000–W89999	nickel base alloys
<i>Z00001–Z99999 Zinc and Zinc Alloys</i>	

^A Alloys in which the rare earths are used in the ratio of their natural occurrence (that is, unseparated rare earths). In this mixture, cerium is the most abundant of the rare earth elements.

2.4 Welding filler metals fall into two general categories: those whose compositions are determined by the filler metal analysis (e.g. solid bare wire or rods and cast rods) and those whose composition is determined by the weld deposit analysis (e.g. covered electrodes, flux-cored and other composite wire electrodes). The latter are assigned to a new primary series with the letter W as shown in Table 1. The solid bare wire and rods continue to be assigned in the established number series according to their composition.

NOTE 5—Readers are cautioned *not* to make their own assignments of numbers from such listings, as this can result in unintended and unexpected duplication and conflict.

2.5 ASTM and SAE periodically publish up-to-date listings of all UNS numbers assigned to specific metals and alloys, with appropriate reference information on each.² Many trade

associations also publish similar listings related to materials of primary interest to their organizations.

3. Organization for Administering the UNS for Metals and Alloys

3.1 The organization for administering the UNS consists of the following:

3.1.1 *Advisory Board*—The Advisory Board has approximately 20 volunteer members who are affiliated with major producing and using industries, trade associations, government agencies, and standards societies, and who have extensive experience with identification, classification, and specification of materials. The Board is the administrative arm of SAE and ASTM on all matters pertaining to the UNS. It coordinates thinking on the format of each series of numbers and the administration of each by selected experts. It sets up ground rules for determining eligibility of any material for a UNS number, for requesting such numbers, and for appealing unfavorable rulings. It is the final referee on matters of disagreement between requesters and assigners.

² Request ASTM DS 56A and SAE Handbook Supplement HS 1086a, *Unified Numbering System for Metals and Alloys*, (a joint ASTM–SAE publication), PCN 05-056001-01.