



Designation: B422 – 10

Standard Specification for Copper-Aluminum-Silicon-Cobalt Alloy, Copper-Nickel- Silicon-Magnesium Alloy, Copper-Nickel-Silicon Alloy, Copper-Nickel-Aluminum-Magnesium Alloy, and Copper- Nickel-Tin Alloy Sheet and Strip¹

This standard is issued under the fixed designation B422; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This specification establishes the requirements for² Copper Alloy UNS Nos. C19002, C19010, C19015, C19020, C19025, C63800, C64725, C70250, C70260, C70265, and C70310 sheet and strip.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 The following documents of the issue in effect on date of material purchase form a part of this specification to the extent referenced herein:

2.2 *ASTM Standards:*³

B248 Specification for General Requirements for Wrought Copper and Copper-Alloy Plate, Sheet, Strip, and Rolled Bar

¹ This specification is under the jurisdiction of ASTM Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.01 on Plate, Sheet, and Strip.

Current edition approved April 1, 2010. Published May 2010. Originally approved in 1965. Last previous edition approved in 2008 as B422 – 08a. DOI: 10.1520/B0422-10.

² The UNS system for copper and copper alloys (see Practice E527) is a simple expansion of the former standard designation system accomplished by the addition of a prefix “C” and a suffix “00.” The suffix can be used to accommodate composition variations of the base alloy.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard’s Document Summary page on the ASTM website.

B248M Specification for General Requirements for Wrought Copper and Copper-Alloy Plate, Sheet, Strip, and Rolled Bar (Metric)

B846 Terminology for Copper and Copper Alloys

E527 Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

3. General Requirements

3.1 Material furnished to this specification shall be in accordance with the applicable requirements of the current edition of Specification B248.

4. Terminology

4.1 *Definitions*—For definitions of terms related to copper and copper alloys, refer to Terminology B846.

5. Ordering Information

5.1 Orders for material under this specification should include the following information:

5.1.1 Quantity (of each size),

5.1.2 Alloy: Copper Alloy UNS No. (Section 1),

5.1.3 Form of material (sheet or strip),

5.1.4 Temper (see 7.1),

5.1.5 Dimensions (thickness, width, length (if applicable),

5.1.6 How furnished (rolls, specific lengths with or without ends, stock lengths with or without ends),

5.1.7 Type of edge, if required (slit, sheared, sawed, square corners, rounded corners, rounded edges, or full-rounded edges (see 10.6),

5.1.8 Type of width and straightness tolerances, if required (slit-metal tolerances, square sheared-metal tolerances, sawed-metal tolerances, straightened or edge-rolled-metal tolerances) (Section 10), and

5.1.9 ASTM specification number and year of issue.

5.2 In addition, when material is purchased for agencies of the U.S. government, it shall conform to the Supplementary Requirements as defined in Specification B248 when specified in the contract or purchase order.

*A Summary of Changes section appears at the end of this standard

6. Chemical Composition

6.1 The materials shall conform to the compositions prescribed in **Table 1**.

6.2 These specification limits do not preclude the presence of other elements. Limits for unnamed elements may be established by agreement between manufacturer or supplier and purchaser.

6.3 When copper is listed as remainder, copper may be taken as the difference between the sum of all the elements analyzed and 100 %. When all the elements in **Table 1** for Alloys C19002, C19010, C63800, C64725, C70250, C70260, C70265, and C70310 are analyzed, their sum shall be 99.5 % min. When all the elements in **Table 1** for Alloy C19025 are analyzed, their sum shall be 99.7 % min. When all the elements in **Table 1** for Alloys C19015 and C19020 are analyzed, their sum shall be 99.8 % min.

7. Temper

7.1 Tempers available under this specification are as designated in **Tables 2-7**.

8. Mechanical Properties

8.1 Copper Alloy UNS No. C63800 is a dispersion-strengthened alloy which does not require heat treatment. The annealed and rolled tempers shall conform to the tensile property requirements prescribed in **Table 2**.

8.2 Copper Alloy UNS No. C70250 is supplied in a mill-hardened, or cold-worked and precipitation heat-treated, or precipitation heat-treated or spinodal heat-treated, 1/2 Hd and stress-relieved tempers. The 0.2 % offset yield strength shall be the standard tests for these tempers and shall conform to the requirements specified in **Table 3**.

8.2.1 If ductility or formability requirements are desired, they shall be negotiated and agreed upon between manufacturer and purchaser.

8.3 Copper Alloys UNS No. C70260 and C70265 are supplied in a mill-hardened temper. The 0.2 % offset yield strength shall be the standard test for the mill-hardened tempers

TM00, TM02, TM03, and TM04 and shall conform to the requirements specified in **Table 4**. The tensile strength shall be the standard test for the mill-hardened temper TM01 and shall conform to the requirements specified in **Table 4**.

8.3.1 If ductility or formability requirements are desired, they shall be negotiated and agreed upon between manufacturer and purchaser.

8.4 Copper Alloy UNS Nos. C19020 and C19025 are supplied in cold-worked, stress-relieved temper. These tempers shall conform to the tensile strength and elongation requirements in **Table 5**. The 0.2 % offset yield strength shall be the standard test for the mill-hardened tempers and shall conform to the requirements specified in **Table 7** and **Table 5**, respectively.

8.4.1 If ductility or formability requirements are desired, they shall be negotiated and agreed upon between manufacturer and purchaser.

8.5 Copper Alloy UNS No. C19010 is supplied in either precipitation heat-treated (TM03 to TM08) tempers, or mill-hardened (H01 to H10) tempers. The 0.2 % offset yield strength shall be the standard test for the precipitation heat-treated and mill-hardened tempers and shall conform to the requirements specified in **Table 6**.

8.5.1 If ductility or formability requirements are desired, they shall be negotiated and agreed upon between manufacturer and purchaser.

8.6 Copper alloy C64725 is supplied in either mill-hardened temper (TM02–TM08) temper, or cold-worked, stress relieved (HR04) temper. Tempers shall conform to the 0.2 % offset yield requirements specified in **Table 8**.

8.6.1 If ductility or formability requirements are desired, they shall be negotiated and agreed upon between manufacturer and purchaser.

8.7 Copper alloy C19002 is supplied in the mill hardened temper (TM04–TM08) temper. Tempers shall conform to the 0.2 % offset yield requirements specified in **Table 9**.

TABLE 1 Chemical Requirements Composition %

Element	C19002	C19010	C19015	C19020	C19025	C63800	C64725	C70250	C70260	C70265	C70310
Nickel	1.4–1.7 ^A	0.8–1.8	0.50–2.4	0.50–3.0	0.80–1.2	0.20 max.	1.3–2.7 ^A	2.2–4.2 ^B	1.0–3.0 ^B	1.0–3.0 ^B	1.0–4.0 ^A
Silicon	0.20–0.35	0.15–0.35	0.10–.40	1.5–2.1	0.20–0.8	0.25–1.2	0.20–0.7	0.20–0.7	0.08–1.0
Lead, max	0.05	0.05	0.01	0.05	...	0.05	0.05
Iron, max	0.10	0.10	0.20	0.25	0.20	0.10
Zinc, max	0.04–0.35	0.20	0.8	0.50–1.5	1.0	...	0.30	2.0
Aluminum	2.5–3.1
Copper ^A	remainder	remainder	remainder	remainder	remainder	remainder	95.0 min	remainder	remainder	remainder	remainder
Cobalt	0.25–0.55
Manganese, max	0.10	...	0.10
Magnesium	0.01	...	0.02–0.15	0.20 max	0.05–0.30	0.01
Tin	0.02–0.30	0.30–0.9	0.7–1.1	...	0.20–0.8	0.05–0.8	1.0
Phosphorus	.05	0.01–0.05	...	0.01–0.20	0.03–0.07	0.01 max	0.01 max	0.05
Calcium	0.01
Chromium	0.09
Silver	0.02–0.50	0.02–0.50
Zirconium	0.005–0.05	0.005–0.05

^A Including silver.

^B Including cobalt.