
**Calculation of load capacity of spur
and helical gears —**

**Part 22:
Calculation of micropitting load
capacity**

*Calcul de la capacité de charge des engrenages cylindriques à
dentures droite et hélicoïdale —*

Partie 22: Calcul de la capacité de charge aux micropiqûres

Document Preview

[ISO/TS 6336-22:2018](https://standards.iteh.ai/catalog/standards/iso/733c53ec-cfb0-4f34-8fe7-019bcb20f497/iso-ts-6336-22-2018)

<https://standards.iteh.ai/catalog/standards/iso/733c53ec-cfb0-4f34-8fe7-019bcb20f497/iso-ts-6336-22-2018>



iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO/TS 6336-22:2018](https://standards.iteh.ai/catalog/standards/iso/733c53ec-cfb0-4f34-8fe7-019bcb20f497/iso-ts-6336-22-2018)

<https://standards.iteh.ai/catalog/standards/iso/733c53ec-cfb0-4f34-8fe7-019bcb20f497/iso-ts-6336-22-2018>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	v
Introduction	vi
1 Scope	1
2 Normative references	1
3 Terms, definitions, symbols and units	1
3.1 Terms and definitions.....	1
3.2 Symbols and units.....	2
4 Micropitting	4
5 Basic formulae	5
5.1 General.....	5
5.2 Safety factor against micropitting, S_λ	6
5.3 Local specific lubricant film thickness, λ_{GFY}	6
5.4 Permissible specific lubricant film thickness, λ_{GFP}	7
5.5 Recommendation for the minimum safety factor against micropitting, $S_{\lambda,min}$	8
6 Material parameter, G_M	9
6.1 General.....	9
6.2 Reduced modulus of elasticity, E_r	10
6.3 Pressure viscosity coefficient at bulk temperature, $\alpha_{\theta M}$	10
7 Local velocity parameter, U_Y	11
7.1 General.....	11
7.2 Sum of tangential velocities, $v_{\Sigma,Y}$	11
7.3 Dynamic viscosity at bulk temperature, $\eta_{\theta M}$	12
7.3.1 General.....	12
7.3.2 Kinematic viscosity at bulk temperature, $\nu_{\theta M}$	12
7.3.3 Density of the lubricant at bulk temperature, $\rho_{\theta M}$	12
8 Local load parameter, W_Y	13
8.1 General.....	13
8.2 Local Hertzian contact stress, $p_{dyn,Y,A}$, according to Method A.....	13
8.3 Local Hertzian contact stress, $p_{dyn,Y,B}$, according to Method B.....	14
8.3.1 General.....	14
8.3.2 Local nominal Hertzian contact stress, $p_{H,Y,B}$	14
9 Local sliding parameter, S_{GFY}	15
9.1 General.....	15
9.2 Pressure viscosity coefficient at local contact temperature, $\alpha_{\theta B,Y}$	15
9.3 Dynamic viscosity at local contact temperature, $\eta_{\theta B,Y}$	15
9.3.1 General.....	15
9.3.2 Kinematic viscosity at local contact temperature, $\nu_{\theta B,Y}$	16
9.3.3 Density of the lubricant at local contact temperature, $\rho_{\theta B,Y}$	16
10 Definition of contact point Y on the path of contact	16
11 Load sharing factor, X_Y	19
11.1 General.....	19
11.2 Spur gears with unmodified profiles.....	19
11.3 Spur gears with profile modification.....	20
11.4 Local buttressing factor, $X_{but,Y}$	21
11.5 Helical gears with $\epsilon_\beta \leq 0,8$ and unmodified profiles.....	22
11.6 Helical gears with $\epsilon_\beta \leq 0,8$ and profile modification.....	23
11.7 Helical gears with $\epsilon_\beta \geq 1,2$ and unmodified profiles.....	24
11.8 Helical gears with $\epsilon_\beta \geq 1,2$ and profile modification.....	24
11.9 Helical gears with $0,8 < \epsilon_\beta < 1,2$	26

12	Local contact temperature, $\theta_{B,Y}$	26
13	Local flash temperature, $\theta_{fl,Y}$	26
14	Bulk temperature, θ_M	27
14.1	General.....	27
14.2	Mean coefficient of friction, μ_m	28
14.3	Load losses factor, H_V	30
14.4	Tip relief factor, X_{Ca}	30
14.5	Lubricant factor, X_S	32
Annex A (informative) Calculation of the permissible specific lubricant film thickness for oils with a micropitting test result according to FVA-Information Sheet 54/7		33
Annex B (informative) Guideline for reference values of λ_{GFP}		35
Bibliography		38

iTeh Standards
(<https://standards.itih.ai>)
Document Preview

[ISO/TS 6336-22:2018](#)

<https://standards.itih.ai/catalog/standards/iso/733c53ec-cfb0-4f34-8fe7-019bcb20f497/iso-ts-6336-22-2018>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 60, *Gears*, Subcommittee SC 2, *Gear capacity calculation*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

This first edition of ISO/TS 6336-22 cancels and replaces ISO/TR 15144-1:2014.

A list of all parts in the ISO 6336 series can be found on the ISO website. See also the Introduction for an overview.

Introduction

The ISO 6336 series consists of International Standards, Technical Specifications (TS) and Technical Reports (TR) under the general title *Calculation of load capacity of spur and helical gears* (see [Table 1](#)).

- International Standards contain calculation methods that are based on widely accepted practices and have been validated.
- TS contain calculation methods that are still subject to further development.
- TR contain data that is informative, such as example calculations.

The procedures specified in ISO 6336-1 to ISO 6336-19 cover fatigue analyses for gear rating. The procedures described in ISO 6336-20 to ISO 6336-29 are predominantly related to the tribological behaviour of the lubricated flank surface contact. ISO 6336-30 to ISO 6336-39 include example calculations. The ISO 6336 series allows the addition of new parts under appropriate numbers to reflect knowledge gained in the future.

Requesting standardized calculations according to ISO 6336 without referring to specific parts requires the use of only those parts that are currently designated as International Standards (see [Table 1](#) for listing). When requesting further calculations, the relevant part or parts of ISO 6336 need to be specified. Use of a Technical Specification as acceptance criteria for a specific design needs to be agreed in advance between manufacturer and purchaser.

Table 1 — Overview of ISO 6336

Calculation of load capacity of spur and helical gears	International Standard	Technical Specification	Technical Report
<i>Part 1: Basic principles, introduction and general influence factors</i>	X		
<i>Part 2: Calculation of surface durability (pitting)</i>	X		
<i>Part 3: Calculation of tooth bending strength</i>	X		
<i>Part 4: Calculation of tooth flank fracture load capacity</i>		X	
<i>Part 5: Strength and quality of materials</i>	X		
<i>Part 6: Calculation of service life under variable load</i>	X		
<i>Part 20: Calculation of scuffing load capacity (also applicable to bevel and hypoid gears) — Flash temperature method</i> (Replaces: ISO/TR 13989-1)		X	
<i>Part 21: Calculation of scuffing load capacity (also applicable to bevel and hypoid gears) — Integral temperature method</i> (Replaces: ISO/TR 13989-2)		X	
<i>Part 22: Calculation of micropitting load capacity</i> (Replaces: ISO/TR 15144-1)		X	
<i>Part 30: Calculation examples for the application of ISO 6336 parts 1, 2, 3, 5</i>			X
<i>Part 31: Calculation examples of micropitting load capacity</i> (Replaces: ISO/TR 15144-2)			X

At the time of publication of this document, some of the parts listed here were under development. Consult the ISO website.

This document provides principles for the calculation of the micropitting load capacity of cylindrical involute spur and helical gears with external teeth.

The basis for the calculation of the micropitting load capacity of a gear set is the model of the minimum operating specific lubricant film thickness in the contact zone. Many parameters can influence the occurrence of micropitting. These include surface topography, contact stress level, and lubricant chemistry. Whilst these parameters are known to affect the performance of micropitting for a gear set,

the subject area remains a topic of research and, as such, the science has not yet developed such that all aspects of these specific parameters are fully included in the calculation methods. Furthermore, the correct application of tip and root relief (involute modification) has been found to greatly influence micropitting; the suitable values should therefore be applied. Surface finish is another crucial parameter. At present, R_a is used but other aspects such as R_z or skewness have been observed to have significant effects which can be reflected in the finishing process applied.

Although the calculation of specific lubricant film thickness (which is also referred to in literature as "film thickness ratio" or "lambda ratio") does not provide a direct method for assessing micropitting load capacity, it can serve as an evaluation criterion when applied as part of a suitable comparative procedure based on known gear performance.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO/TS 6336-22:2018](#)

<https://standards.iteh.ai/catalog/standards/iso/733c53ec-cfb0-4f34-8fe7-019bcb20f497/iso-ts-6336-22-2018>

Calculation of load capacity of spur and helical gears —

Part 22:

Calculation of micropitting load capacity

1 Scope

This document describes a procedure for the calculation of the micropitting load capacity of cylindrical gears with external teeth. It has been developed on the basis of testing and observation of oil-lubricated gear transmissions with modules between 3 mm and 11 mm and pitch line velocities of 8 m/s to 60 m/s. However, the procedure is applicable to any gear pair where suitable reference data are available, providing the criteria specified below are satisfied.

The formulae specified are applicable for driving as well as for driven cylindrical gears with tooth profiles in line with the basic rack specified in ISO 53. They are also applicable for teeth conjugate to other basic racks where the virtual contact ratio ($\epsilon_{\alpha m}$) is less than 2,5. The results are in good agreement with other methods for normal working pressure angles up to 25°, reference helix angles up to 25° and in cases where pitch line velocity is higher than 2 m/s.

This document is not applicable for the assessment of types of gear tooth surface damage other than micropitting.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 53, *Cylindrical gears for general and heavy engineering — Standard basic rack tooth profile*

ISO 1122-1, *Vocabulary of gear terms — Part 1: Definitions related to geometry*

ISO 1328-1, *Cylindrical gears — ISO system of flank tolerance classification — Part 1: Definitions and allowable values of deviations relevant to flanks of gear teeth*

ISO 6336-1, *Calculation of load capacity of spur and helical gears — Part 1: Basic principles, introduction and general influence factors*

ISO 6336-2, *Calculation of load capacity of spur and helical gears — Part 2: Calculation of surface durability (pitting)*

3 Terms, definitions, symbols and units

3.1 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 1122-1, ISO 6336-1 and ISO 6336-2 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.2 Symbols and units

The symbols used in this document are given in [Table 2](#). The units of length metre, millimetre and micrometre are chosen in accordance with common practice. The conversions of the units are already included in the given formulae.

Table 2 — Symbols and units

Symbol	Description	Unit
a	centre distance	mm
A	ISO tolerance class according to ISO 1328-1	—
B_{M1}	thermal contact coefficient of pinion	$N/(m \cdot s^{0,5} \cdot K)$
B_{M2}	thermal contact coefficient of wheel	$N/(m \cdot s^{0,5} \cdot K)$
b	face width	mm
C	auxiliary constant	mm
C_{a1}	tip relief of pinion	μm
C_{a2}	tip relief of wheel	μm
C_{eff}	effective tip relief	μm
c_{M1}	specific heat capacity of pinion	$J/(kg \cdot K)$
c_{M2}	specific heat capacity of wheel	$J/(kg \cdot K)$
c'	maximum tooth stiffness per unit face width (single stiffness) of a tooth pair	$N/(mm \cdot \mu m)$
$c_{\gamma\alpha}$	mean value of mesh stiffness per unit face width	$N/(mm \cdot \mu m)$
d_{a1}	tip diameter of pinion	mm
d_{a2}	tip diameter of wheel	mm
d_{b1}	base diameter of pinion	mm
d_{b2}	base diameter of wheel	mm
d_{w1}	pitch diameter of pinion	mm
d_{w2}	pitch diameter of wheel	mm
d_{Y1}	Y-circle diameter of pinion	mm
d_{Y2}	Y-circle diameter of wheel	mm
E_r	reduced modulus of elasticity	N/mm^2
E_1	modulus of elasticity of pinion	N/mm^2
E_2	modulus of elasticity of wheel	N/mm^2
EAP	end of active profile (for driving pinion: contact point E, for driving wheel: contact point A)	—
F_{bt}	nominal transverse load in plane of action (base tangent plane)	N
F_t	(nominal) transverse tangential load at reference cylinder per mesh	N
G_M	material parameter	—
g_Y	parameter on the path of contact (distance of point Y from point A)	mm
g_α	length of path of contact	mm
H_v	load losses factor	—
h_Y	local lubricant film thickness	μm
K_A	application factor	—
$K_{B\gamma}$	helical load factor	—
$K_{H\alpha}$	transverse load factor	—
$K_{H\beta}$	face load factor	—
K_v	dynamic factor	—
K_γ	mesh load factor	—

Table 2 (continued)

Symbol	Description	Unit
n_1	rotation speed of pinion	min^{-1}
P	transmitted power	kW
p_{et}	transverse base pitch on the path of contact	mm
$p_{dyn,Y}$	local Hertzian contact stress including the load factors K	N/mm^2
$p_{H,Y}$	local nominal Hertzian contact stress	N/mm^2
R_a	effective arithmetic mean roughness value	μm
R_{a1}	arithmetic mean roughness value of pinion	μm
R_{a2}	arithmetic mean roughness value of wheel	μm
$S_{GF,Y}$	local sliding parameter	—
S_λ	safety factor against micropitting	—
$S_{\lambda,min}$	minimum required safety factor against micropitting	—
SAP	start of active profile (for driving pinion: contact point A, for driving wheel: contact point E)	—
T_1	nominal torque at the pinion	Nm
U_Y	local velocity parameter	—
u	gear ratio	—
$v_{g,Y}$	local sliding velocity	m/s
VI	viscosity index	—
$v_{r1,Y}$	local tangential velocity on pinion	m/s
$v_{r2,Y}$	local tangential velocity on wheel	m/s
$v_{\Sigma,C}$	sum of tangential velocities at pitch point	m/s
$v_{\Sigma,Y}$	sum of tangential velocities at point Y	m/s
W_W	material factor	—
W_Y	local load parameter	—
$X_{but,Y}$	local buttressing factor	—
X_{Ca}	tip relief factor	—
X_L	lubricant factor	—
X_R	roughness factor	—
X_S	lubrication factor	—
X_Y	local load sharing factor	—
Z_E	elasticity factor	$(\text{N}/\text{mm}^2)^{0.5}$
z_1	number of teeth of pinion	—
z_2	number of teeth of wheel	—
α_t	transverse pressure angle	$^\circ$
α_{wt}	pressure angle at the pitch cylinder	$^\circ$
$\alpha_{\theta B,Y}$	pressure-viscosity coefficient at local contact temperature	m^2/N
$\alpha_{\theta M}$	pressure-viscosity coefficient at bulk temperature	m^2/N
α_{38}	pressure-viscosity coefficient at 38 °C	m^2/N
β_b	base helix angle	$^\circ$
ϵ_{max}	maximum addendum contact ratio	—
ϵ_α	transverse contact ratio	—
$\epsilon_{\alpha n}$	virtual contact ratio, transverse contact ratio of a virtual spur gear	—
ϵ_β	overlap ratio	—
ϵ_γ	total contact ratio	—

Table 2 (continued)

Symbol	Description	Unit
ε_1	addendum contact ratio of the pinion	—
ε_2	addendum contact ratio of the wheel	—
$\eta_{\theta B,Y}$	dynamic viscosity at local contact temperature	N·s/m ²
$\eta_{\theta M}$	dynamic viscosity at bulk temperature	N·s/m ²
$\eta_{\theta oil}$	dynamic viscosity at oil inlet/sump temperature	N·s/m ²
η_{38}	dynamic viscosity at 38 °C	N·s/m ²
$\theta_{B,Y}$	local contact temperature	°C
$\theta_{fl,Y}$	local flash temperature	°C
θ_M	bulk temperature	°C
θ_{oil}	oil inlet/sump temperature	°C
$\lambda_{GF,min}$	minimum specific lubricant film thickness in the contact area	—
$\lambda_{GF,Y}$	local specific lubricant film thickness	—
λ_{GFP}	permissible specific lubricant film thickness	—
λ_{GFT}	limiting specific lubricant film thickness of the test gears	—
λ_{M1}	specific heat conductivity of pinion	W/(m·K)
λ_{M2}	specific heat conductivity of wheel	W/(m·K)
μ_m	mean coefficient of friction	—
$\nu_{\theta B,Y}$	kinematic viscosity at local contact temperature	mm ² /s
$\nu_{\theta M}$	kinematic viscosity at bulk temperature	mm ² /s
ν_1	Poisson's ratio of pinion	—
ν_2	Poisson's ratio of wheel	—
ν_{100}	kinematic viscosity at 100 °C	mm ² /s
ν_{40}	kinematic viscosity at 40 °C	mm ² /s
ρ_{M1}	density of pinion	kg/m ³
ρ_{M2}	density of wheel	kg/m ³
$\rho_{n,C}$	normal radius of relative curvature at pitch diameter	mm
$\rho_{n,Y}$	normal radius of relative curvature at point Y	mm
$\rho_{t,Y}$	transverse radius of relative curvature at point Y	mm
$\rho_{t1,Y}$	transverse radius of curvature of pinion at point Y	mm
$\rho_{t2,Y}$	transverse radius of curvature of wheel at point Y	mm
$\rho_{\theta B,Y}$	density of lubricant at local contact temperature	kg/m ³
$\rho_{\theta M}$	density of lubricant at bulk temperature	kg/m ³
ρ_{15}	density of lubricant at 15 °C	kg/m ³
Subscripts to symbols		
Y	parameter for any contact point Y in the contact area for Method A and on the path of contact for Method B; (all parameters subscript Y have to be calculated with local values)	

4 Micropitting

Micropitting is a phenomenon that occurs in Hertzian type of rolling and sliding contact that operates in mixed elastohydrodynamic or boundary lubrication regimes. Micropitting is influenced by operating conditions such as load, speed, sliding, temperature, surface topography, specific lubricant film thickness and chemical composition of the lubricant. Micropitting is more commonly observed on materials with a high surface hardness.