



SLOVENSKI STANDARD SIST EN ISO 7231:2023

01-november-2023

Polimerni materiali - Penjeni polimeri - Mehke pene - Določanje vrednosti zračnega pretoka pri konstantni razliki tlakov (ISO 7231:2023)

Polymeric materials, cellular, flexible - Determination of air flow value at constant pressure-drop (ISO 7231:2023)

Weich-elastische Polymerschaumstoffe - Bestimmung der Luftdurchlässigkeit bei konstantem Differenzdruck (ISO 7231:2023)

Matériaux polymères alvéolaires souples - Détermination de l'indice d'écoulement d'air à chute de pression constante (ISO 7231:2023)

<https://standards.iteh.ai/catalog/standards/sist/6a1af4fe-8083-4c43-8bd9-8220a2b6fdbf/sist-en-iso-7231-2023>

Ta slovenski standard je istoveten z: EN ISO 7231:2023

ICS:

83.100 Penjeni polimeri Cellular materials

SIST EN ISO 7231:2023 en,fr,de

EUROPEAN STANDARD

EN ISO 7231

NORME EUROPÉENNE

EUROPÄISCHE NORM

August 2023

ICS 83.100

Supersedes EN ISO 7231:2010

English Version

Polymeric materials, cellular, flexible - Determination of air flow value at constant pressure-drop (ISO 7231:2023)

Matériaux polymères alvéolaires souples -
Détermination de l'indice d'écoulement d'air à chute de
pression constante (ISO 7231:2023)

Weich-elastische Polymerschäume - Bestimmung
der Luftdurchlässigkeit bei konstantem Differenzdruck
(ISO 7231:2023)

This European Standard was approved by CEN on 6 August 2023.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.

<https://standards.iteh.ai/catalog/standards/sist/0a1af4fe-8083-4c43-8bd9-8220a2b6fdbf/sist-en-iso-7231-2023>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword.....	3

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 7231:2023](https://standards.iteh.ai/catalog/standards/sist/0a1af4fe-8083-4c43-8bd9-8220a2b6fdbf/sist-en-iso-7231-2023)

<https://standards.iteh.ai/catalog/standards/sist/0a1af4fe-8083-4c43-8bd9-8220a2b6fdbf/sist-en-iso-7231-2023>

European foreword

This document (EN ISO 7231:2023) has been prepared by Technical Committee ISO/TC 45 "Rubber and rubber products" in collaboration with Technical Committee CEN/TC 249 "Plastics" the secretariat of which is held by SIS.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2024, and conflicting national standards shall be withdrawn at the latest by February 2024.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 7231:2010.

Any feedback and questions on this document should be directed to the users' national standards body/national committee. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

(standards.iteh.ai)

Endorsement notice

SIST EN ISO 7231:2023

The text of ISO 7231:2023 has been approved by CEN as EN ISO 7231:2023 without any modification.

<https://standards.iteh.ai/catalog/standards/sist/0a1af3fe-8083-4c43-8bd9-8220a2b6f1bf/sist-en-iso-7231-2023>

INTERNATIONAL
STANDARD

ISO
7231

Third edition
2023-08

**Polymeric materials, cellular,
flexible — Determination of air flow
value at constant pressure-drop**

*Matériaux polymères alvéolaires souples — Détermination de l'indice
d'écoulement d'air à chute de pression constante*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 7231:2023](https://standards.iteh.ai/catalog/standards/sist/0a1af4fe-8083-4c43-8bd9-8220a2b6fdbf/sist-en-iso-7231-2023)

<https://standards.iteh.ai/catalog/standards/sist/0a1af4fe-8083-4c43-8bd9-8220a2b6fdbf/sist-en-iso-7231-2023>



Reference number
ISO 7231:2023(E)

© ISO 2023

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 7231:2023

<https://standards.iteh.ai/catalog/standards/sist/0a1af4fe-8083-4c43-8bd9-8220a2b6fdbf/sist-en-iso-7231-2023>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Principle.....	1
5 Method A.....	2
5.1 Apparatus.....	2
5.2 Test pieces.....	4
5.3 Test conditions.....	4
5.4 Procedure.....	5
5.5 Test report.....	5
6 Method B.....	6
6.1 Method B1 with manual measurement.....	6
6.1.1 Apparatus.....	6
6.1.2 Test pieces.....	8
6.1.3 Test conditions.....	8
6.1.4 Procedure.....	8
6.1.5 Precision.....	8
6.1.6 Test report.....	8
6.2 Method B2 with automatic measurement.....	9
6.2.1 Apparatus.....	9
6.2.2 Test pieces.....	10
6.2.3 Test conditions.....	10
6.2.4 Procedure.....	11
6.2.5 Test report.....	11
Annex A (informative) Precision of methods B1 and B2.....	12
Bibliography.....	14

ISO 7231:2023(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC45, *Rubber and rubber products*, Subcommittee SC 4, *Products (other than hoses)*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 249, *Plastics*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 7231:2010), which has been technically revised.

The main changes are as follows:

- the previous [Annex A](#) has been moved to [Clause 6](#) as method B2;
- the previous 6.5 (the precision of method B1) has been moved to a new [Annex A](#).
- the previous precision of method B2 has been added to a new [Annex A](#).

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Polymeric materials, cellular, flexible — Determination of air flow value at constant pressure-drop

WARNING — Persons using this document should be familiar with normal laboratory practice. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to determine the applicability of any national regulatory conditions.

1 Scope

This document specifies two methods for determining the air flow value of flexible cellular polymeric materials:

- method A, for conventional types of flexible cellular polymeric material;
- method B, for all types of flexible cellular polymeric material, but especially for materials with a low permeability to air.

For method B, two methods are specified in this document:

- method B1: with manual measurement;
- method B2: with automatic measurement.

NOTE 1 Air flow values can be used to give an indication of the effects of formulation and production variables on the cellular structure.

NOTE 2 In this document, the expression “conventional type of flexible cellular polymeric material” means types which are unsuitable for sealing purposes.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1

air flow value

volume flow rate required to maintain a constant pressure differential across a flexible foam test piece

4 Principle

A specified constant air pressure differential is created across a standard flexible foam specimen. The rate of flow of air required to maintain this pressure differential is measured as the air flow value.