

Designation: D6471 – 10

Standard Specification for Recycled Prediluted Aqueous Glycol Base Engine Coolant (50 Volume % Minimum) for Automobile and Light-Duty Service¹

This standard is issued under the fixed designation D6471; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers the requirements for a recycled prediluted aqueous ethylene glycol (50 volume % minimum) base engine coolant and recycled prediluted aqueous propylene glycol (50 volume % minimum) base engine coolant for use in automobiles and light-duty vehicles. Committee D15 has developed this specification using experience, knowledge and research from recycling used aqueous base engine coolant and blends of used aqueous base engine coolant and virgin glycol. This standard does not apply to coolant produced from other glycol sources such as medical waste, distillation bottoms, airplane/airport deicers and polyester production waste. This specification provides a procedure for evaluating engine coolant recycling technologies through the recycling of a reference synthetic used engine coolant. It also specifies the chemical, physical, and performance requirements for the recycled prediluted aqueous glycol base engine coolant that is produced from that procedure. When used without further dilution, this product functions effectively during both winter and summer-This material is intended to provide protection against freezing, boiling, and corrosion in automobile or other light-duty service cooling systems.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are approximate equivalents and provided for information only.

1.3 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

- 2.1 ASTM Standards:²
- D512 Test Methods for Chloride Ion In Water
- D516 Test Method for Sulfate Ion in Water
- D1119 Test Method for Percent Ash Content of Engine Coolants
- D1120 Test Method for Boiling Point of Engine Coolants
- D1121 Test Method for Reserve Alkalinity of Engine Coolants and Antirusts
- D1122 Test Method for Density or Relative Density of Engine Coolant Concentrates and Engine Coolants By The Hydrometer
- D1126 Test Method for Hardness in Water
- D1176 Practice for Sampling and Preparing Aqueous Solutions of Engine Coolants or Antirusts for Testing Purposes
- D1177 Test Method for Freezing Point of Aqueous Engine Coolants
- D1193 Specification for Reagent Water
- D1287 Test Method for pH of Engine Coolants and Antirusts
- D1293 Test Methods for pH of Water
- D1384 Test Method for Corrosion Test for Engine Coolants in Glassware
- D1881 Test Method for Foaming Tendencies of Engine Coolants in Glassware
- D1882 Test Method for Effect of Cooling System Chemical Solutions on Organic Finishes for Automotive Vehicles
- D2570 Test Method for Simulated Service Corrosion Testing of Engine Coolants
- D2809 Test Method for Cavitation Corrosion and Erosion-Corrosion Characteristics of Aluminum Pumps With Engine Coolants
- D2847 Practice for Testing Engine Coolants in Car and Light Truck Service

*A Summary of Changes section appears at the end of this standard

¹ This specification is under the jurisdiction of ASTM Committee D15 on Engine Coolants and Related Fluids and is the direct responsibility of Subcommittee D15.15 on Recycled Engine Coolant.

Current edition approved April 1, 2010. Published May 2010. Originally approved in 1999. Last previous edition approved in 2006 as D6471–06. DOI: 10.1520/D6471-10.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- D3306 Specification for Glycol Base Engine Coolant for Automobile and Light-Duty Service
- D3634 Test Method for Trace Chloride Ion in Engine Coolants
- D4327 Test Method for Anions in Water by Suppressed Ion Chromatography
- D4340 Test Method for Corrosion of Cast Aluminum Alloys in Engine Coolants Under Heat-Rejecting Conditions
- D5827 Test Method for Analysis of Engine Coolant for Chloride and Other Anions by Ion Chromatography
- D5931 Test Method for Density and Relative Density of Engine Coolant Concentrates and Aqueous Engine Coolants by Digital Density Meter
- D6129 Test Method for Silicon in Engine Coolant Concentrates by Atomic Absorption Spectroscopy
- D6130 Test Method for Determination of Silicon and Other Elements in Engine Coolant by Inductively Coupled Plasma-Atomic Emission Spectroscopy
- D6208 Test Method for Repassivation Potential of Aluminum and Its Alloys by Galvanostatic Measurement
- D6472 Specification for Recycled Glycol Base Engine Coolant Concentrate for Automobile and Light-Duty Service
- D6660 Test Method for Freezing Point of Aqueous Ethylene Glycol Base Engine Coolants by Automatic Phase Transition Method

2.2 Other Documents:

- Federal Method 2540B Total Dissolved Solids Dried at 103–105°C³
- GM 6043M—Automotive Engine Coolant Concentrate— Ethylene Glycol Type⁴
- GM 1825M—Automotive Engine Coolant Concentrate— Ethylene Glycol; §3.11 Storage Stability and Compatibility⁵

3. Reagents and Materials

3.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society where such specifications are available.⁶ Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

3.2 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean reagent water as defined by Type IV of Specification D1193.

4. Procedure

4.1 In order to properly evaluate a coolant recycling technology, a reference synthetic used coolant (Annex A1) is to

⁴ Applicable rewrite available in Annex A2.

be used as the feed stock. The reference synthetic used coolant shall be prepared in accordance with Annex A1. An appropriately sized batch of reference synthetic used coolant is to be prepared and used to purge the recycling process components and yield enough consistent product to complete the testing specified within this specification.

4.2 Prepare the coolant recycling equipment or technology according to the manufacturer's directions and recommendations.

4.3 Vigorously stir or mix the reference synthetic used coolant using appropriate vessels and mixing equipment immediately prior to and during the processing through the coolant recycling process.

4.4 Recycle the reference synthetic used coolant according to the manufacturer's directions and recommendations.

4.5 Evaluate the recycled coolant per the requirements listed in this specification.

5. General Requirements

5.1 The recycled prediluted aqueous glycol base engine coolant shall consist essentially of water and ethylene glycol or propylene glycol obtained from the processing of light, medium or heavy duty engine coolant products. The recycled prediluted aqueous glycol base engine coolant can in part contain virgin glycol. It also shall contain suitable corrosion inhibitors and a foam suppressor.

5.1.1 Recycled prediluted aqueous ethylene glycol base engine coolant may contain glycols other than ethylene glycol up to 7.5 % provided the chemical and physical properties of Table 1 are met.

5.1.2 Recycled prediluted aqueous propylene glycol base engine coolant may contain glycols other than propylene glycol up to 0.5 % provided the chemical and physical properties of Table 1 are met.

5.2 The recycled prediluted aqueous glycol base engine coolant shall conform to the chemical and physical properties in Table 1. If the recycled prediluted aqueous glycol base engine coolant contains chloride or sulfate, or both, at levels greater than the requirements specified in Table 1, fleet testing requirements described in Section 6 shall be met. If the chloride and sulfate requirements in Table 1 are met, fleet testing is not required.

Note 1—The intention of conducting fleet testing is to verify that the effects of residual contaminants left in the recycled glycol base engine coolant are neutralized through real world application in a fleet test. Due to the fact that there are not enough industry field test data available to support setting hard specification limits, the fleet test requirements in Section 6 specify a protocol and limits based on comparing the recycled glycol base engine coolant to an industry standard reference engine coolant that is known to adequately protect modern day cooling systems from corrosion.

5.3 The recycled prediluted aqueous glycol base engine coolant shall conform to the general requirements in Table 2.

5.4 The recycled prediluted aqueous glycol base engine coolant shall be in accordance with the performance requirements in Table 3.

³ Standard Method for the Examinaiton of Water and Wastewater. American Public Health Association, et al, 1015 15th Street, N.W. Washington, DC 20005.

⁵ Applicable rewrite available in Annex A3.

⁶ Reagent Chemicals, American Chemical Society Specifications, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see Analar Standards for Laboratory Chemicals, BDH Ltd., Poole, Dorset, U.K., and the United States Pharmacopeia and National Formulary, U.S. Pharmacopeial Convention, Inc., (USPC), Rockville, MD.

🕼 D6471 – 10

TABLE 1 Physical and Chemical Requirements of the Recycled Prediluted Product

Property	Ethylene Glycol Base Specific Values	Propylene Glycol Base Specific Values	ASTM Test Method
Relative density, 15.5°C (60/60°F) Freezing point, °C (°F)	1.0650 min –36.4 (–33.5) max or lower	1.0250 min –31 (–23.8) max or lower	D1122, D5931 D1177, D6660
Boiling point, °C (°F)	107.8 (226) min	`104 (219) min	D1120
Effect on automotive finish (use clear coat thermoset urethane or acrylic ure- thane finish)	no effect	no effect	D1882 ^A
Ash content, mass %	2.5 max	2.5 max	D1119
pH, 50 volume % in distilled water	7.5 to 11.0	7.5 to 11.0	D1287
Chloride, ppm	33 max	33 max	D3634 ^{<i>B</i>} , D5827
Sulfate, ppm	140 max	140 max	D5827
Reserve alkalinity, mL	report ^C	report ^C	D1121

^ACurrently, many vehicle manufacturers prepare test panels using the specific paint finishes employed on their actual product. Coolant suppliers and vehicle manufacturers should agree on the exact test procedures and acceptance criteria on an individual basis.

^BIn case of dispute, D3634 shall be the preferred test method.

^CAgreed value between the supplier and the customer.

TABLE 2 General Requirements of the Recycled P	rediluted	
Product		

Property	Specified Values	ASTM Test Method
Color	distinctive ^A	—
Effect on nonmetals	no adverse affect	_

^ACommonly used color: green to blue-green.

5.5 This product, when installed in accordance with the recommendations of the manufacturer of the vehicle, or the coolant recycling process, and those on the product label, shall be suitable for use in a properly maintained cooling system (see Appendix X1) in normal light-duty or passenger car service for a minimum of one year without adversely affecting fluid flow and heat transfer.

6. Fleet Testing Requirements

6.1 *Engine Coolants*—Reference engine coolant concentrate (Annex A2) and recycled prediluted engine coolant shall be 47 used to conduct the fleet testing.og/standards/sist/5c7e0425-1

6.2 *Vehicles*—A minimum of fourteen vehicles is recommended to start the test: seven containing reference engine coolant concentrate (control vehicles) and seven containing recycled prediluted engine coolant (test vehicles). A minimum of five control vehicles and five test vehicles shall finish the test. Starting with fourteen vehicles allows for vehicles to drop out of the test for various reasons, that is, mechanical failure, coolant contamination, etc.

6.2.1 *Vehicle Selection*—All vehicle cooling systems should be inspected prior to selection. Vehicles with corroded cooling systems should not be used for testing purposes. Vehicle selection shall be made as follows:

6.2.1.1 Control vehicles and test vehicles shall be matched pairs and be new or have similar low mileage accumulation.

6.2.1.2 Same year, make, and model.

6.2.1.3 Similar mileage and cooling system condition.

6.2.1.4 Same cooling system and power train configuration.

6.2.1.5 Aluminum head(s), aluminum radiator, aluminum heater core and aluminum water pump (housing).

6.2.1.6 Cast iron block (optional).

Note 2—Vehicles equipped with cast iron heads may be tested in addition to those specified above. A minimum of five control vehicles and five test vehicles, equipped with aluminum heads, shall complete the test

TABLE 3 Performance Requirements of the Recycled Prediluted
Product

Property	Specific Values	ASTM Test Method
Corrosion in glassware; Weight loss, mg/specimen		D1384 ^A
Copper	10 max	
Solder	30 max	
Brass	10 max	
Steel	10 max	
Cast iron	10 max	
Cast aluminum	30 max	
Simulated service test; Weight loss, mg/specimen		D2570 ^B
Copper	20 max	
Solder	60 max	
Brass	20 max	
Steel	20 max	
Cast iron	20 max	
Cast aluminum	60 max	
Corrosion of cast aluminum alloys at heat-rejecting		D4340 ^C
Surfaces; Weight loss, mg/cm ² /week	1.0 max	
Foaming		D1881
Volume, mL	150 max	
Break time, s	5 max	
Cavitation-erosion rating for pitting, cavitation, or		D2809 ^D
Erosion of the water pump Aluminum galvanostatic pitting potential, V v SHE	8 min -0.40 min	0 _{D6208} <i>€</i>
Fleet test		l appropriate ections

^AThe recycled product shall be mixed with the proper quantity of ASTM Type IV reagent water (Specification D1193) to result in a 33-1/3 volume % coolant test solution. To each liter of test solution add 99 mg of sodium sulfate, 110 mg of sodium chloride and 92 mg sodium bicarbonate.

^BThe recycled product shall be mixed with the proper quantity of ASTM Type IV reagent water (Specification D1193) to result in a 44 volume % coolant test solution. To each liter of test solution add 83 mg of sodium sulfate, 92 mg of sodium chloride and 77 mg of sodium bicarbonate.

^CThe adjusted recycled product shall be mixed with an equal volume of ASTM Type IV reagent water (Specification D1193). To each liter of test solution add 165 mg of sodium chloride.

^DOne volume of the recycled product shall be mixed with two volumes of ASTM Type IV reagent water (Specification D1193). To each liter of test solution add 123 mg of sodium sulfate, 137 mg of sodium chloride and 115 mg of sodium bicarbonate.

^EThe test solution is to be prepared as follows: 50 volume % of the prediluted coolant to be tested, 25 volume % of the corrosive water specified in Test Method D6208, and the remainder deionized or distilled water.

and be included in the conclusive analysis report.

6.2.2 *Vehicle Setup*—All vehicles shall be set up in accordance with Practice D2847 unless otherwise specified within this specification.

6.2.2.1 All vehicles shall be set up with a new aluminum head(s), aluminum radiator, aluminum water pump, thermostat, hoses, belts and radiator/cooling system cap. Installation of new heater cores is recommended. New aluminum heads and radiators are required as they will be sectioned for evaluation at the end of the test.

6.2.2.2 Each vehicle shall be set up with six coupon bundles in the bypass heater circuit coupon bundle capsule(s). Once the test has been started, no additional or replacement corrosion coupon bundles can be added to any of the vehicle cooling systems. The coupon bundle capsule(s) should be arranged in the cooling system to minimize the amount of coolant spillage when coupon bundles are removed throughout the testing period. More than one coupon bundle capsule may be used in the bypass heater circuit in series if the vehicle design does not accommodate the incorporation of a single capsule.

Note 3—Additional coupon bundles may be added to the cooling system prior to starting the test for informational purposes.

6.3 *Reference Coolant Solution*—Prepare the reference coolant solution with reference engine coolant concentrate and corrosive water described in Test Method D1384. The glycol concentration should give a freeze point of $-36.4 \pm 1^{\circ}C$ ($-33.5 \pm 2^{\circ}F$) for a 50 volume % ethylene glycol base reference coolant solution or a freeze point of $-31 \pm 1^{\circ}C$ ($-23.8 \pm 2^{\circ}F$) for a 50 volume % propylene glycol base reference coolant solution. Enough reference coolant solution should be prepared to allow for additions to the vehicle cooling systems throughout the test duration and for individual vehicle test restarts.

6.4 *Test Coolant Solution*—Prepare the test coolant solution with recycled prediluted engine coolant and corrosive water contaminants described in Test Method D1384 (see Note 4). The glycol concentration should give a freeze point of $-36.4 \pm 1^{\circ}C$ ($-33.5 \pm 2^{\circ}F$) for a 50 volume % ethylene glycol base test coolant solution or a freeze point of $-31 \pm 1^{\circ}C$ ($-23.8 \pm 2^{\circ}F$) for a 50 volume % propylene glycol base test coolant solution. Enough test coolant solution should be prepared to allow for additions to the vehicle cooling systems throughout the test duration and for individual vehicle test restarts.

Note 4—If necessary, the recycled prediluted engine coolant shall be adjusted with the proper quantity of ASTM Type IV reagent water (Specification D1193) to result in a 50 volume % test coolant solution. To each litre of balanced recycled prediluted engine coolant add 74 mg of sodium sulfate, 83 mg of sodium chloride, and 69 mg of sodium bicarbonate.

6.5 Vehicle Test Parameters:

6.5.1 *Preparation and Testing*—All vehicles shall be tested in accordance with Practice D2847, unless otherwise specified within this specification.

6.5.2 *Duration*—One year, 48,280 km (30,000 miles) minimum, and 4,828 km (3,000 miles) per month maximum.

6.5.3 *Driving Conditions*—All vehicles shall undergo similar driving conditions. A minimum of 40 % of the test duration shall be city driving (stop and go).

6.5.4 *Duty Cycle*—All vehicles shall be turned off and allowed to cool for a minimum of eight hours per day.

6.5.5 *Coolant Solution Additions*—Coolant solution additions are not to exceed 10 volume % of the vehicle cooling system capacity within the fleet test duration for top-off or to replace lost coolant solution. Coolant solution used to top-off the cooling system shall be from the same batch that was initially prepared and put into that vehicle.

6.5.6 *Number of Vehicles to Finish*—A minimum of five control vehicles containing the reference coolant solution and a minimum of five test vehicles containing the test coolant solution shall finish the fleet test and have valid results.

6.6 *Vehicle Exclusion Criteria*—Criteria for vehicle exclusion from the fleet test evaluation are:

6.6.1 If the fleet testing requirements are not followed.

6.6.2 If cooling system leakage exceeds 10 volume % or cooling system failure occurs.

6.6.3 If the vehicle becomes disabled, that is, accident, engine failure, vehicle becomes inoperable, etc.

6.6.4 If the cooling system becomes contaminated with oil.

6.6.5 If the cooling system is topped off or the coolant solution was replaced with a coolant solution volume greater than 10 volume % of the vehicle cooling system capacity.

6.6.6 Coolant solutions or chemicals other than those prepared for that vehicle are added to the cooling system.

6.6.7 If the coolant solution has to be drained or removed for major vehicle repairs, for example milling or warped heads, engine overhaul, etc.

6.6.8 If the vehicle coolant solution properties significantly change, that is, cooling system contamination, coolant solution dilution, addition of cooling system additives, etc.

Note 5—If a vehicle falls out of the fleet testing requirements, that same vehicle can be rebuilt and restarted providing the fleet is not more than 8,047 km (5,000 miles) into the test. Replacement or additional matched vehicles conforming to the requirements specified previously may be added to the fleet test provided the original fleet is not more than 8,047 km (5,000 miles) into the test. Vehicles run together in a fleet test should be started at the same time so that all the vehicles in the test experience similar environmental and driving conditions.

6.7 Fleet Test Evaluation: 227e/astm-d6471-10

6.7.1 *Beginning of Test*—Sample coolant solutions from each vehicle (60 mL [2 oz]) and conduct coolant analysis. The coolant analysis for each vehicle shall include pH, reserve alkalinity, glycol weight %, glycol corrosion inhibitor content, contaminants (chloride, sulfate, etc.), and corrosion metal levels. Analysis for glycol degradation products is optional. The reference and test coolant solutions in the vehicles shall have a glycol concentration near 50 volume %. Report the results.

6.7.2 *Middle of Test (24,140 km [15,000 miles])*—Conduct mid-test coolant and coupon bundle analysis as follows:

6.7.2.1 Remove two coupon bundles from each vehicle cooling system, clean the coupons, and measure weight losses or gains and report the average weight losses or gains for each coupon type.

6.7.2.2 Sample the coolant solutions from each vehicle (60 mL [2 oz]) and conduct coolant analysis. The coolant analysis for each vehicle shall include pH, reserve alkalinity, glycol weight %, corrosion inhibitor content, contaminants (chloride, sulfate, etc.), and corrosion metal levels. Analysis for glycol degradation products is optional. The reference and test coolant solutions in the vehicles shall have a glycol concentration near 50 volume %. Report the results.

6.7.2.3 Coolant samples and extra coupon bundles placed in the cooling system for information purposes may be removed at intervals more frequently than that specified within this specification but shall not be more frequent than 8,047 km (5,000 miles) intervals. If excessive amounts of coolant solution are removed from control or test vehicle cooling systems for analysis purposes or otherwise, the maximum allowable amount of coolant to top-off the cooling systems may be exceeded.

Note 6—The intended application of conducting mid-test analysis is to determine the status of the fleet test. If the reference or test coolant solutions are performing outside the expected performance levels, vehicles can be withdrawn from the test, saving considerable amounts of time and expenses.

6.7.3 *End of Test (48,280 km [30,000 miles])*—Conduct end of test coolant, coupon, and vehicle component analysis on all vehicles that finish the fleet test as follows:

6.7.3.1 Remove the remaining four coupon bundles from each finishing vehicle cooling system, clean the coupons, measure the weight losses or gains and report the results as described in Practice D2847. Results shall be reported on all finishing vehicles with a minimum of five vehicles being from the control vehicle group and five from the test vehicle group. Report the average weight loss or gain for each coupon type for each vehicle. Report the control vehicle group average coupon weight losses or gains from the individual control vehicle average coupon weight losses or gains. Also report the test vehicle group average coupon weight losses or gains from the individual test vehicle average coupon weight losses or gains. Conduct statistical analysis on the coupon weight losses or gains for the fleet test and report the results at the 95th percentile confidence level. The T-test and F-test may be used to conduct statistical analysis on the fleet test results.

6.7.3.2 Sample the coolant solutions from each test vehicle (60 mL [2 oz] min) and conduct coolant sample analysis. The coolant analysis for each vehicle shall include pH, reserve alkalinity, glycol weight %, corrosion inhibitor content, contaminants (chloride, sulfate, etc.), and corrosion metal levels. Analysis for glycol degradation products is optional. The reference and test coolant solutions in the vehicles shall have a glycol concentration near 50 volume %. Report the results.

6.7.3.3 Evaluate each of the control and test vehicle cooling system components in accordance with Practice D2847. Additional to Practice D2847, the cooling system components of each finishing vehicle, unless otherwise specified, shall be photographed and evaluated as described in the following subsections.

(a) Radiator—Section each radiator, visually evaluate and report on the tube and tube-end deposits, erosion/corrosion, tube pitting and header crevice corrosion.

(b) Water Pump—Disassemble each water pump and rate the pump impeller and housings in accordance with Practice D2809 water pump rating system. Average the ratings for the test vehicles and report the result. Average the ratings for the control vehicles and report the result.

(c) Cylinder Head(s)—Section each head from a minimum of three control vehicles and three test vehicles near an exhaust port and a valve bridge. The sectioning of each head shall be in

the same location for comparison evaluation purposes. Evaluate each head for deposits, pitting, corrosion and discoloration on the coolant side of the exhaust valve ports and valve bridge areas. Also, evaluate each head for general corrosion. In this context, corrosion means pitting, etching, copper plating, metal surface phenomena, erosion, cavitation, or crevice corrosion.

6.8 Fleet Test Performance Specifications:

6.8.1 *Metal Coupons*—For each metal test coupon type, the test vehicle group average coupon weight loss shall be less than or equal to the maximum weight losses specified in the following subsections or shall be less than or equal to the average coupon weight losses obtained from the control vehicle group, whichever is greater for each coupon type (see Note 7).

6.8.1.1 Copper Weight Loss: 20 mg/coupon max.

6.8.1.2 Solder Weight Loss: 40 mg/coupon max.

6.8.1.3 Brass Weight Loss: 20 mg/coupon max.

6.8.1.4 Steel Weight Loss: 20 mg/coupon max.

6.8.1.5 Cast Iron Weight Loss: 20 mg/coupon max.

6.8.1.6 Cast Aluminum Weight Loss: 40 mg/coupon max.

Note 7—If the average weight loss for one or more coupon types in the control vehicle group is higher than the maximums specified in 6.8.1.1 - 6.8.1.6, then the average weight loss obtained for the control vehicle group for that metal coupon or coupons takes precedence and becomes the maximum allowed weight loss for that metal coupon type. Otherwise, the maximums specified in 6.8.1.1 - 6.8.1.6 apply.

6.8.2 *Radiator*—The radiators from the test vehicle group shall exhibit similar or less deposit formation in the radiator tubes and at the tube ends, erosion/corrosion, and header crevice corrosion than radiators from the control vehicle group.

6.8.3 *Water Pump Cavitation/Erosion Rating*—The average rating for test vehicle water pumps shall be a minimum of eight or shall be equal to or greater than the obtained average control vehicle water pump rating.

6.8.4 *Cylinder Heads*—The cylinder heads from the test vehicle group shall exhibit similar or lesser amounts of deposits, pitting, and corrosion on the coolant side of the exhaust ports and valve bridges than the heads from the control vehicle group. They also shall exhibit similar or less general corrosion in the head cooling system passageways than that generated in the heads from the control vehicle group. Report any head surface discoloration on the coolant side of the exhaust ports and valve bridges.

6.9 *Fleet Testing Coordinator*—Either the fleet test managing company or coordinator name, or both, as well as the contact information, shall be reported and included with fleet testing results and documentation.

Note 8—Inclusion of either the fleet test managing company or coordinator information, or both, provides a means for the customer to verify and validate test results provided by the supplier. It is generally the supplier's responsibility to locate qualified parties to coordinate the fleet test and conduct evaluations; however, this may be negotiated and agreed upon between the customer and supplier.

6.10 *Fleet Test Cooling System Component Evaluation*— The cooling system components that require evaluation (radiators, water pumps, and heads) within Section 6 shall be evaluated and reported on by an independent laboratory with automotive and ASTM coolant testing and evaluation experience.

6.11 Fleet Test Cooling System Component Storage—The cooling system components that are evaluated in this fleet test protocol shall be kept for a minimum of one year for reference purposes. The components shall be kept in a suitable location or environment that prevents or minimizes component deterioration or degradation beyond that obtained from testing.

7. Other Requirements

7.1 The recycled prediluted glycol base engine coolant shall visually provide a similar or smaller amount of precipitate than the reference coolant concentrate (see Annex A2) in the test

method for storage stability and compatibility (see Annex A3). The comparison evaluation of the reference coolant concentrate versus the recycled prediluted coolant specified within this section takes precedence over limits or specifications detailed in Annex A3.

Note 9—When conducting testing for purposes of approval by a customer, generally it is recommended to have the testing conducted or supervised by an independent laboratory where reference materials are produced by a qualified laboratory or manufacturer.

8. Keywords

8.1 glycol base; light-duty engine coolant; recycled prediluted aqueous engine coolant; reference engine coolant concentrate; reference synthetic used coolant

ANNEXES

(Mandatory Information)

A1. REFERENCE SYNTHETIC USED COOLANT

A1.1 The reference synthetic used coolant described in the following is predilute and represents a synthetic used coolant feedstock. An equivalent used coolant may be used in the evaluation of a coolant recycling process; however, it shall meet the requirements specified in Section A1.3.

A1.2 Preparation of the Reference Synthetic Used Coolant—The Reference Synthetic Used Coolant is to be prepared by blending the components listed in Table A1.1 in an appropriately sized stainless steel or plastic vessel with aggressive mixing or agitation capabilities. Blending vessels, tanks, mixing equipment, transfer pumps, hoses and lines shall be clean, free of contaminants and rinsed with deionized or distilled water prior to blending and use.

A1.2.1 Blend an appropriately sized batch with all the components listed in Table A1.1 in the order that the components are listed, with the exception of the SAE 5W30 engine oil.

A1.2.2 Once all of the components listed in Table A1.1 have been blended together, with the exception of the SAE 5W30 engine oil, adjust the pH of the solution to 8.0 ± 0.2 with sodium hydroxide (50 weight % aqueous sodium hydroxide may be used).

A1.2.3 Add the SAE 5W30 engine oil to the blend and vigorously mix. Complete emulsification of the engine oil is not necessary and it is expected that oil will rise to the surface of the final blend.

A1.3 Blended batches of Reference Synthetic Used Coolant shall be tested for ingredient presence and quality by conforming to the parameters listed below after being filtered through a 0.7 micron filter.

TABLE A1.1 Reference Synthetic Used Coolant Components ^A			
dards Material	Ethylene Glycol Base Weight, %	Propylene Glycol Base Weight, %	
Glycol ^B	52.5250 47.0972	50.7236 48.8986	
Sodium tetraborate (Na ₂ B ₄ O ₇ 5H ₂ O)		40.0900	
Sodium sulfate (Na ₂ SO ₄)		0.0419	
Glycolic acid $(C_2H_4O_3)$ Formic acid (CH_2O_2)	0.1100 0.0300		
Acetic acid, glacial ($C_2H_4O_2$)	0.0100		
Sodium chloride (NaCl)	0.0324		
Sodium Nitrate (NaNO ₃)	0.0110		
Copper chloride (CuCl ₂ 2H ₂ O)	e/astm-d640.0009 () 0.0050		
Aluminum nitrate ($AI(NO_3)_3$ 9H ₂ O)	0.0028		
Lead nitrate (Pb(NO ₃) ₂)	0.0008		
Silicate stabilizer (Dow Corning Q1-6083) ^D	0.0100		
Sodium metasilicate (Na ₂ SiO ₃ 5H ₂ O) Surfactant (BASF Pluronic L61) ^D	0.0140 0.0100		
SAE 5W30 Engine Oil ^E		850	

^AMaterials listed are to be ACS Reagent Grade or equivalent unless otherwise specified. Materials may be substituted for alternative species materials provided the ionic concentrations of importance are maintained. Section A1.3 lists the ionic species minimums and maximums allowed.

^BA high quality technical grade ethylene or propylene glycol shall be used.

^CWater quality shall conform to Specification D1193 Type IV water requirements. ^DChemical equivalents may be used.

^EA commercially available SAE 5W30 engine oil may be used. The engine oil concentration represents oil contamination in used coolants and was arrived at by surveying coolant recyclers in the industry.

A1.4 Reference Synthetic Used Coolant conforming to the above specification is suitable for use to evaluate a coolant recycling process. To evaluate a coolant recycling process or technology, the reference synthetic used coolant shall be recycled within 30 days from when it was made and shall be thoroughly agitated immediately prior to recycling.