

---

**Polimerni materiali - Določanje aerobne biorazgradljivosti polimernih materialov, izpostavljenih morski vodi - 1. del: Metoda z analizo sproščenega ogljikovega dioksida (ISO 23977-1:2020)**

Plastics - Determination of the aerobic biodegradation of plastic materials exposed to seawater - Part 1: Method by analysis of evolved carbon dioxide (ISO 23977-1:2020)

Kunststoffe - Bestimmung des aeroben Bioabbaus von Meerwasser ausgesetzten Kunststoff-Materialien - Teil 1: Verfahren mittels Analyse des freigesetzten Kohlenstoffdioxids (ISO 23977-1:2020)

Plastiques - Détermination de la biodegradation aérobie des matières plastiques exposées à l'eau de mer - Partie 1: Méthode par analyse du dioxyde de carbone dégagé (ISO 23977-1:2020)

**Ta slovenski standard je istoveten z: EN ISO 23977-1:2021**

**ICS:**

|           |  |   |
|-----------|--|---|
| 13.020.40 | Onesnaževanje, nadzor nad onesnaževanjem in ohranjanje | Pollution, pollution control and conservation |
| 83.080.01 | Polimerni materiali na splošno                         | Plastics in general                           |

**SIST EN ISO 23977-1:2022****en,fr,de**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN ISO 23977-1:2022](https://standards.iteh.ai/catalog/standards/sist/c3368155-6cbe-480b-9a5a-ef2babb5f3ea/sist-en-iso-23977-1-2022)

<https://standards.iteh.ai/catalog/standards/sist/c3368155-6cbe-480b-9a5a-ef2babb5f3ea/sist-en-iso-23977-1-2022>

EUROPEAN STANDARD

EN ISO 23977-1

NORME EUROPÉENNE

EUROPÄISCHE NORM

November 2021

ICS 83.080.01

English Version

## Plastics - Determination of the aerobic biodegradation of plastic materials exposed to seawater - Part 1: Method by analysis of evolved carbon dioxide (ISO 23977-1:2020)

Plastiques - Détermination de la biodégradation aérobie des matières plastiques exposées à l'eau de mer - Partie 1: Méthode par analyse du dioxyde de carbone dégagé (ISO 23977-1:2020)

Kunststoffe - Bestimmung des aeroben Bioabbaus von Meerwasser ausgesetzten Kunststoff-Materialien - Teil 1: Verfahren mittels Analyse des freigesetzten Kohlenstoffdioxids (ISO 23977 1:2020)

This European Standard was approved by CEN on 8 November 2021.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

| Contents               | Page |
|------------------------|------|
| European foreword..... | 3    |

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN ISO 23977-1:2022](https://standards.iteh.ai/catalog/standards/sist/c3368155-6cbe-480b-9a5a-ef2babb5f3ea/sist-en-iso-23977-1-2022)  
<https://standards.iteh.ai/catalog/standards/sist/c3368155-6cbe-480b-9a5a-ef2babb5f3ea/sist-en-iso-23977-1-2022>

## European foreword

The text of ISO 23977-1:2020 has been prepared by Technical Committee ISO/TC 61 "Plastics" of the International Organization for Standardization (ISO) and has been taken over as EN ISO 23977-1:2021 by Technical Committee CEN/TC 249 "Plastics" the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2022, and conflicting national standards shall be withdrawn at the latest by May 2022.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

Any feedback and questions on this document should be directed to the users' national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

iTeh STANDARD PREVIEW

(standards.iteh.ai)

Endorsement notice

The text of ISO 23977-1:2020 has been approved by CEN as EN ISO 23977-1:2021 without any modification.

SIST EN ISO 23977-1:2022  
<https://standards.iteh.ai/catalog/standards/sist/c5568155-6cbe-480b-9a5a-ef2babb5f3ea/sist-en-iso-23977-1-2022>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN ISO 23977-1:2022

<https://standards.iteh.ai/catalog/standards/sist/c3368155-6cbe-480b-9a5a-ef2babb5f3ea/sist-en-iso-23977-1-2022>

INTERNATIONAL  
STANDARD

ISO  
23977-1

First edition  
2020-11

---

---

**Plastics — Determination of the  
aerobic biodegradation of plastic  
materials exposed to seawater —**

**Part 1:  
Method by analysis of evolved carbon  
dioxide**

iTeh STANDARD PREVIEW

*(standards.iteh.ai)*  
*Plastiques — Détermination de la biodégradation aérobie des  
matières plastiques exposées à l'eau de mer —*

*Partie 1: Méthode par analyse du dioxyde de carbone dégagé*

<https://standards.iteh.ai/catalog/standards/sist/c3368155-6cbe-480b-9a5a-ef2babb5f3ea/sist-en-iso-23977-1-2022>



Reference number  
ISO 23977-1:2020(E)

© ISO 2020

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 23977-1:2022](https://standards.iteh.ai/catalog/standards/sist/c3368155-6cbe-480b-9a5a-ef2babb5f3ea/sist-en-iso-23977-1-2022)

<https://standards.iteh.ai/catalog/standards/sist/c3368155-6cbe-480b-9a5a-ef2babb5f3ea/sist-en-iso-23977-1-2022>



### **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland



| <b>Contents</b>  | <b>Page</b> |
|--|-------------|
| <b>Foreword</b> .....  | <b>iv</b>   |
| <b>Introduction</b> .....  | <b>v</b>    |
| <b>1 Scope</b> .....   | <b>1</b>    |
| <b>2 Normative references</b> .....                                  | <b>1</b>    |
| <b>3 Terms and definitions</b> .....                                 | <b>1</b>    |
| <b>4 Principle</b> .....   | <b>3</b>    |
| <b>5 Test environment</b> .....                                      | <b>3</b>    |
| <b>6 Reagents</b> .....  | <b>3</b>    |
| <b>7 Apparatus</b> .....   | <b>4</b>    |
| <b>8 Procedure</b> .....   | <b>5</b>    |
| 8.1 Test material.....   | 5           |
| 8.2 Reference materials.....   | 5           |
| 8.3 Test set up.....   | 6           |
| 8.4 Pre-conditioning phase.....                                      | 6           |
| 8.5 Start of the test.....   | 6           |
| 8.6 Carbon dioxide measurement.....                                  | 7           |
| 8.7 End of the test.....   | 7           |
| <b>9 Calculation and expression of results</b> .....                 | <b>8</b>    |
| 9.1 Calculation.....   | 8           |
| 9.1.1 Amount of CO <sub>2</sub> produced.....                        | 8           |
| 9.1.2 Percentage of biodegradation.....                              | 10          |
| 9.2 Visual inspection.....   | 11          |
| 9.3 Expression and interpretation of results.....                    | 11          |
| <b>10 Validity of results</b> .....                                  | <b>11</b>   |
| <b>11 Test report</b> .....  | <b>12</b>   |
| <b>Annex A (informative) Example of a respirometric system</b> ..... | <b>13</b>   |
| <b>Bibliography</b> .....  | <b>15</b>   |

## ISO 23977-1:2020(E)

### Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 14, *Environmental aspects*.

A list of all parts in the ISO 23997 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

## Introduction

According to the United Nations Environment Program (UNEP), one of the most notable properties of synthetic polymers and plastics is their durability which, combined with their accidental loss, deliberate release and poor waste management has resulted in the ubiquitous presence of plastic in oceans (UNEP, 2015<sup>[16]</sup>).

It is well known and documented that marine litter can pose risks and a negative impact on living marine organisms and on human beings. Degradability of plastic materials exposed to the marine environment is one of the factors affecting impact and strength of effects. The uncontrolled dispersion of biodegradable plastics in natural environments is not desirable. The biodegradability of products cannot be considered as an excuse to spread wastes that should be recovered and recycled. However, test methods to measure rate and level of biodegradation in natural environments are of interest in order to better characterize the behaviour of plastics in these very particular environments. Thus, the degree and rate of biodegradation is of major interest in order to obtain an indication of the potential biodegradability of plastic materials when exposed to different marine habitats.

ISO/TC 61/SC 14 has established several test methods for biodegradation testing of plastic materials under laboratory conditions covering different environmental compartments and test conditions, as shown in [Table 1](#).

**Table 1 — Test methods for biodegradation testing of plastics**

| Environmental compartment                  | Conditions                 | Test methods             |
|--|----------------------------|--------------------------|
|  | Presence/absence of oxygen |                          |
| Controlled composting conditions           | Aerobic conditions         | ISO 14855-1              |
|  |                            | ISO 14855-2              |
| High-solids anaerobic-digestion conditions | Anaerobic conditions       | ISO 15985                |
| Controlled anaerobic slurry system         | Anaerobic conditions       | ISO 13975                |
| Soil                                       | Aerobic conditions         | ISO 17556                |
| Aqueous medium                             | Aerobic conditions         | ISO 14851                |
|  | Anaerobic conditions       | ISO 14852                |
| Seawater/sandy sediment interface          | Aerobic conditions         | ISO 18830 <sup>a</sup>   |
|  |                            | ISO 19679 <sup>a</sup>   |
| Marine sediment                            | Aerobic conditions         | ISO 22404 <sup>a</sup>   |
| Seawater                                   | Aerobic conditions         | ISO 23977-1 <sup>a</sup> |
|  |                            | ISO 23977-2 <sup>a</sup> |

<sup>a</sup> Test method for measuring biodegradation of plastic materials when exposed to marine microbes.

All marine biodegradation test methods are based on exposure of plastic materials to marine samples (seawater and/or sediment) taken from shoreline areas. By a quantitative viewpoint, these methods are not equivalent, because, for example, the microbial density in seawater is generally lower compared to the density determined in sediment. In addition, the microbial composition and diversity can be different. Moreover, as a rule, the nutrient concentration found in sediment is normally higher compared to the concentration in seawater.

This document provides a test method for determining the biodegradation level of plastic materials exposed to the microbial population present in seawater from a pelagic zone under laboratory conditions. The biodegradation is followed by measuring the evolved CO<sub>2</sub>.

The test is performed with either seawater only (“pelagic seawater test”) or with seawater to which little sediment was added (“suspended sediment seawater test”).