
**Iron ores — Determination of
nickel — Flame atomic absorption
spectrometric method**

*Minerais de fer — Dosage du nickel — Méthode par spectrométrie
d'absorption atomique dans la flamme*

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 15633:2017](https://standards.iteh.ai/catalog/standards/iso/69d205f1-62ec-4d3d-bec9-b6ea01eb3109/iso-15633-2017)

<https://standards.iteh.ai/catalog/standards/iso/69d205f1-62ec-4d3d-bec9-b6ea01eb3109/iso-15633-2017>



iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO 15633:2017

<https://standards.iteh.ai/catalog/standards/iso/69d205f1-62ec-4d3d-bec9-b6ea01eb3109/iso-15633-2017>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Reagents	2
6 Apparatus	2
7 Sampling and samples	3
7.1 Laboratory sample.....	3
7.2 Preparation of predried test samples.....	3
8 Procedure	4
8.1 Number of determinations.....	4
8.2 Test portion.....	4
8.3 Blank test and check test.....	4
8.4 Determination	4
8.4.1 Decomposition of the test portion.....	4
8.4.2 Removal of iron.....	5
8.4.3 Treatment of the residue.....	5
8.4.4 Preparation of the calibration solutions.....	5
8.4.5 Adjustment of the atomic absorption spectrometer.....	6
8.4.6 Atomic absorption measurements.....	6
9 Expression of results	6
9.1 Calculation of nickel content.....	6
9.2 General treatment of results.....	7
9.2.1 Repeatability and permissible tolerance.....	7
9.2.2 Determination of analytical result.....	7
9.2.3 Between-laboratories precision.....	7
9.2.4 Check for trueness.....	8
9.2.5 Calculation of final result.....	9
9.3 Oxide factor.....	9
10 Test report	9
Annex A (normative) Flowsheet of the procedure for the acceptance of analytical values for test samples	11
Annex B (informative) Derivation of repeatability and permissible tolerance formulae	12
Annex C (informative) Precision data obtained by international analytical trial	13
Bibliography	14

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 102, *Iron ore and direct reduced iron*, Subcommittee SC 02, *Chemical analysis*.

This third edition cancels and replaces the second edition (ISO 15633:2015), of which it constitutes a minor revision with the following changes:

- in [Clause 1](#) “0,1 %” has been replaced by “0,10 %”;
- in [7.1](#) “<160 μm ” has been replaced by “–160 μm ”;
- in [8.2](#) a new sentence has been included to make reference to ISO 2596;
- in the titles of [9.1](#), [Table B.1](#) and [Figure C.1](#) “sulfur” has been replaced by “nickel”;
- in [9.2.4 Formula \(8\)](#) and the relevant descriptions have been modified to harmonize this subclause across all documents for which ISO/TC 102/SC 2 is responsible.

Introduction

The objective of a proposed revision of ISO 9685:1991 was to extend the lower limit for a flame atomic absorption spectrometric method determination of both chromium and nickel in iron ores down to 0,001 %. However, due to bias, the method for nickel could not be approved for referee purposes.

The 22nd meeting of ISO/TC 102/SC 2 decided to progress this document as a non-referee method.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 15633:2017](https://standards.iteh.ai/catalog/standards/iso/69d205f1-62ec-4d3d-bec9-b6ea01eb3109/iso-15633-2017)

<https://standards.iteh.ai/catalog/standards/iso/69d205f1-62ec-4d3d-bec9-b6ea01eb3109/iso-15633-2017>

Iron ores — Determination of nickel — Flame atomic absorption spectrometric method

WARNING — This document might involve hazardous materials, operations and equipment. This document does not purport to address all of the safety problems associated with its use. It is the responsibility of the user of this document to establish appropriate health and safety practices prior to use.

1 Scope

This document specifies a flame atomic absorption spectrometric method for the determination of the nickel mass fraction of iron ores.

This method is applicable to mass fractions of nickel between 0,001 % and 0,10 % in natural iron ores, iron ore concentrates and agglomerates including sinter products.

This method is not appropriate for referee purposes.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 648, *Laboratory glassware — Single-volume pipettes*

ISO 1042, *Laboratory glassware — One-mark volumetric flasks*

ISO 2596, *Iron ores — Determination of hygroscopic moisture in analytical samples — Gravimetric, Karl Fischer and mass-loss methods*

ISO 3082, *Iron ores — Sampling and sample preparation procedures*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 7764, *Iron ores — Preparation of predried test samples for chemical analysis*

ISO 80000-1:2009, *Quantities and units — Part 1: General*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 Principle

The test portion of iron ore is decomposed by treatment with hydrochloric and nitric acids.

The major portion of iron in the filtrate is removed by extraction with 4-methylpentan-2-one.

The insoluble residue is ignited and silicon dioxide is removed by evaporation with hydrofluoric and sulfuric acids. The residue is fused with a mixture of sodium carbonate and sodium tetraborate, and then dissolved with hydrochloric acid and combined with the main solution.

5 Reagents

During the analysis, use only reagents of recognized analytical grade and only water that conforms to Grade 2 of ISO 3696.

5.1 Sodium carbonate (Na_2CO_3), anhydrous powder.

5.2 Sodium tetraborate ($\text{Na}_2\text{B}_4\text{O}_7$), anhydrous powder.

5.3 Lithium tetraborate ($\text{Li}_2\text{B}_4\text{O}_7$), anhydrous powder.

5.4 Hydrochloric acid, $\rho = 1,16$ g/ml to 1,19 g/ml.

5.5 Hydrochloric acid, $\rho = 1,16$ g/ml to 1,19 g/ml, diluted 2 + 1.

5.6 Hydrochloric acid, $\rho = 1,16$ g/ml to 1,19 g/ml, diluted 1 + 1.

5.7 Hydrochloric acid, $\rho = 1,16$ g/ml to 1,19 g/ml, diluted 2 + 100.

5.8 Nitric acid, $\rho = 1,4$ g/ml.

5.9 Nitric acid, $\rho = 1,4$ g/ml, diluted 1 + 1.

5.10 Hydrofluoric acid, $\rho = 1,13$ g/ml, 40 % (mass fraction) or $\rho = 1,19$ g/ml, 48 % (mass fraction).

5.11 Sulfuric acid, $\rho = 1,84$ g/ml.

5.12 Sulfuric acid, $\rho = 1,84$ g/ml, diluted 1 + 1.

5.13 4-methylpentan-2-one, (methyl isobutyl ketone, MIBK).

5.14 Nickel standard solution A, 100 μg Ni/ml.

Dissolve 0,100 0 g of nickel metal [purity > 99,9 % (mass fraction)] (see Note of [5.15](#)) in 30 ml of nitric acid ([5.9](#)). After cooling, transfer quantitatively to a 1 000 ml one-mark volumetric flask, dilute to volume with water and mix.

5.15 Nickel standard solution B, 10 μg Ni/ml.

Transfer 100,0 ml of nickel standard solution A ([5.14](#)) to a 1 000 ml one-mark volumetric flask. Dilute to volume with water and mix.

NOTE The purity of the metals stated on the certificates does not generally take into account the presence of absorbed gases such as oxygen, carbon monoxide, etc.

6 Apparatus

Ordinary laboratory apparatus including one-mark pipettes and one-mark volumetric flasks complying with the specifications of ISO 648, ISO 1042 and the following.

6.1 Platinum crucible, of minimum capacity 25 ml.

6.2 Muffle furnace.

6.3 Atomic absorption spectrometer, equipped with an air-acetylene burner.

WARNING — Follow the manufacturer's instructions for igniting and extinguishing the air-acetylene flame to avoid possible explosion hazards. Wear tinted safety glasses whenever the burner is in operation.

The atomic absorption spectrometer used in this method shall meet the following criteria.

- a) Minimum sensitivity: the absorbance of the most concentrated calibration solution (see 8.4.4) is at least 0,3.
- b) Graph linearity: the slope of the calibration graph covering the top 20 % of the concentration range (expressed as a change in absorbance) is not less than 0,7 of the value of the slope for the bottom 20 % of the concentration range determined in the same way.
- c) Minimum stability: the standard deviation of the absorbance of the most concentrated calibration solution and that of the zero calibration solution each being calculated from a sufficient number of repetitive measurements are less than 1,5 % and 0,5 %, respectively of the mean value of the absorbance of the most concentrated solution.

The use of a strip-chart recorder and/or digital readout device is recommended to evaluate criteria a), b) and c) and for all subsequent measurements.

NOTE Instrument parameters vary with each instrument. The following parameters were successfully used in several laboratories and they can be used as guidelines. An air-acetylene flame was used.

Hollow-cathode lamp, mA	10
Wavelength, nm	232,0
Air flow rate, l/min	10
Acetylene flow rate, l/min	2,5

In systems where the values shown above for gas flow rates do not apply, the ratio of the gas flow rates can still be a useful guideline.

7 Sampling and samples

7.1 Laboratory sample

For analysis, use a laboratory sample of $-100\ \mu\text{m}$ particle size which has been taken and prepared in accordance with ISO 3082. In the case of ores having significant contents of combined water or oxidizable compounds, use a particle size of $-160\ \mu\text{m}$.

NOTE A guideline on significant contents of combined water and oxidizable compounds is incorporated in ISO 7764.

Ensure that the sample has not been pulverized in a nickel/chromium pot.

7.2 Preparation of predried test samples

Thoroughly mix the laboratory sample and, taking multiple increments, extract a test sample in such a manner that it is representative of the entire contents of the container. Dry the test sample at $105\ ^\circ\text{C} \pm 2\ ^\circ\text{C}$ as specified in ISO 7764. This is the predried test sample.

8 Procedure

8.1 Number of determinations

Carry out the analysis at least in duplicate, in accordance with [Annex A](#) and independently on one predried test sample.

NOTE The expression “independently” means that the second and any subsequent result is not affected by the previous result(s). For this particular analytical method, this condition implies that the repetition of the procedure is carried out either by the same operator at a different time or by a different operator including, in either case, appropriate recalibration.

8.2 Test portion

Taking several increments, weigh, to the nearest 0,000 2 g, approximately 1 g of the predried test sample in accordance with [7.2](#). For ores having significant content of combined water or oxidizable compounds, an air-equilibrate test sample shall be prepared in accordance with ISO 2596.

The test portion should be taken and weighed quickly, in order to avoid reabsorption of moisture.

8.3 Blank test and check test

In each run, one blank test and one analysis of a certified reference material of the same type of ore shall be carried out in parallel with the analysis of the ore sample(s) under the same conditions. A predried test sample of the certified reference material shall be prepared as specified in [7.2](#).

The certified reference material should be of the same type as the sample to be analysed and the properties of the two materials should be sufficiently similar to ensure that in either case, no significant changes in the analytical procedure become necessary. Where a certified reference material is not available, a reference material can be used (see [9.2.4](#)).

Where the analysis is carried out on several samples at the same time, the blank value may be represented by one test provided that the procedure is the same and the reagents used are from the same reagent bottles.

Where the analysis is carried out on several samples of the same type of ore at the same time, the analytical value of one certified reference material can be used.

8.4 Determination

8.4.1 Decomposition of the test portion

Transfer the test portion ([8.2](#)) to a 250 ml tall-form beaker. Moisten with a few millilitres of water. Add 25 ml of hydrochloric acid ([5.4](#)), cover with a watch-glass and heat for about 1 h on a hotplate adjusted to give a temperature of 100 °C in a test beaker containing a similar volume and depth of sulfuric acid ([5.11](#)).

If the amount of insoluble residue is high, continue heating on a higher temperature zone of the hotplate without boiling the solution.

After heating the volume of the solution should have decreased to about 10 ml.

Add 5 ml of nitric acid ([5.8](#)) and 0,2 ml of sulfuric acid ([5.12](#)), digest for about 15 min and evaporate the solution almost to dryness.

If the test sample contains significant barium content, the addition of sulfuric acid ([5.12](#)) should be omitted.

Be sure to cover with a watch-glass in order to prevent sublimation of chlorides. During evaporation, shift the glass slightly.