



Designation: D3344 – 90 (Reapproved 2010)

## Standard Test Method for Total Wax Content of Corrugated Paperboard<sup>1</sup>

This standard is issued under the fixed designation D3344; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This test method covers the determination of the weight of wax that is present in a specimen of wax-treated corrugated paperboard. The test method is applicable to specimens that have been waxed by either impregnation (saturation) operations or coating operations, or combinations of such operations.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* For precautionary statement, see 5.4 and 7.2.

### 2. Terminology

#### 2.1 Definitions:

2.1.1 *weight of applied wax coating*—the weight of wax that has been applied to the corrugated board as a coating, expressed as weight per unit area, usually grams of coating per square metre or pounds of coating per thousand square feet of board covered.

NOTE 1—When it is known that a wax-coated specimen has no impregnating wax present, this extraction procedure is normally calculated to express the data as “weight of applied wax coating.”

2.1.2 *weight percent wax content*—the weight percent of wax present in and on corrugated board relative to the weight of unwaxed board substrate measured at 23°C (73°F) and 50 % relative humidity.

### 3. Summary of Test Method

3.1 The total quantity of wax associated with the corrugated board specimen is determined by extracting the wax from the board and evaporating the extract to dryness.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D02 on Petroleum Products and Lubricants and is the direct responsibility of Subcommittee D02.10.0A on Physical/Chemical Properties.

Current edition approved May 1, 2010. Published May 2010. Originally approved in 1974. Last previous edition approved in 2005 as D3344 – 90 (2005). DOI: 10.1520/D3344-90R10.

### 4. Significance and Use

4.1 Many of the functional properties of wax-treated corrugated paperboard and cartons are dependent on the amount of wax present.

4.2 In the case of wax-saturated, or wax-impregnated, paperboard the principal concern is with the weight of wax used relative to the weight of paperboard present, that is, the weight percent content or pickup. In some applications the saturating wax may be deposited in the three elements of the corrugated board in such a way as to individually control the amount in each element, that is, the medium and the two facings.

4.3 In the case of wax-coated corrugated paperboard the principal concern is the weight of wax on the board surface per unit area. The functional values of the wax coating as a barrier or a decorative coating are dependent, in part, on the amount of wax in the continuous surface layer, relative to the area covered. The weight of coating relative to the weight of substrate is not usually a concern with regard to product quality.

### 5. Apparatus

5.1 *Sample Trimming Equipment*—A suitable trimming board or template arrangement equipped with a razor edge knife for even cutting of specimens so that they have parallel sides and are of the right size. (A guillotine-type paper cutter is not recommended.)

5.2 *Measuring Rule*, steel-edged, rule for measuring the size of specimen to within 0.5 mm.

5.3 *Beakers*, 1000-cm<sup>3</sup>, Griffin-type.

5.4 *Solvent*<sup>2</sup>—Chlorinated hydrocarbon solvent, 1,1,1-trichloroethane. (**Warning**—May cause irritation. Avoid contact with the eyes, skin, and clothing. Use only with adequate ventilation. Avoid prolonged breathing of vapor or spray mist. Avoid prolonged or repeated contact with skin. Do not take internally.) The solvent used should be residue-free, and should be checked for a residue upon evaporation before using.

<sup>2</sup> The sole source of supply of the apparatus known to the committee at this time is Inhibisol (Brand), Amerace-Esna Corp., Chemical Specialties Division, Tenafly, NJ 07670. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee<sup>1</sup>, which you may attend.