



SLOVENSKI STANDARD

oSIST prEN 1396:2022

01-april-2022

Aluminij in aluminijeve zlitine - Pre vlečena ali premazana pločevina in trakovi za splošno uporabo - Specifikacije

Aluminium and aluminium alloys - Coil coated sheet and strip for general applications - Specifications

Aluminium und Aluminiumlegierungen - Bandbeschichtete Bleche und Bänder für allgemeine Anwendungen - Spezifikationen

Aluminium et alliages d'aluminium - Tôles et bandes revêtues en continu pour applications générales - Specifications

Ta slovenski standard je istoveten z: prEN 1396

<https://standards.iteh.ai/catalog/standards/sist/f07e3911-34a9-49cb-b281-42e812663733/osist-pren-1396-2022>

ICS:

77.150.10 Alumijski izdelki Aluminium products

oSIST prEN 1396:2022

en,fr,de

**iTeh STANDARD
PREVIEW
(standards.iteh.ai)**

[oSIST prEN 1396:2022](https://standards.iteh.ai/catalog/standards/sist/f07e3911-34a9-49cb-b281-42e812663733/osist-pren-1396-2022)

<https://standards.iteh.ai/catalog/standards/sist/f07e3911-34a9-49cb-b281-42e812663733/osist-pren-1396-2022>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

DRAFT
prEN 1396

February 2022

ICS 77.150.10

Will supersede EN 1396:2015

English Version

Aluminium and aluminium alloys - Coil coated sheet and strip for general applications - Specifications

Aluminium et alliages d'aluminium - Tôles et bandes revêtues en continu pour applications générales - Spécifications

Aluminium und Aluminiumlegierungen - Bandbeschichtete Bleche und Bänder für allgemeine Anwendungen - Spezifikationen

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 132.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

[oSIST prEN 1396:2022](http://osist.prEN.1396:2022)

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents

European foreword.....	4
Introduction	5
1 Scope.....	6
2 Normative references.....	6
3 Terms and definitions	7
4 Technical conditions for inspection and delivery	9
4.1 Ordering information	9
4.2 Requirements	11
4.2.1 Production and manufacturing processes	11
4.2.2 Quality control	11
4.2.3 Freedom from defects.....	11
4.2.4 Chemical composition	11
4.2.5 Mechanical properties.....	11
4.2.6 Tolerances on shape and dimensions.....	11
4.2.7 Coating properties	12
4.3 Test procedures.....	12
4.3.1 Chemical composition	12
4.3.2 Tensile test	12
4.3.3 Coating tests.....	12
4.3.4 Retests.....	13
5 Mechanical properties.....	13
6 Organic coating properties.....	16
6.1 Tolerances on thickness	16
6.2 Tolerances on gloss	16
6.3 Tolerances on colour	17
7 Inspection documents	17
8 Marking.....	17
9 Packing.....	18
10 Arbitration tests	18
Annex A (normative) Rules for rounding	19
Annex B (informative) Examples of coating systems	20
Annex C (informative) Guidelines for organic coatings	22
C.1 General.....	22
C.2 Colour	22
C.3 Flexibility	22
C.4 Adhesion.....	23
C.5 Pencil hardness.....	24

C.6	Durability of the organic coating	24
C.6.1	General	24
C.6.2	Corrosion resistance (outdoor exposure)	26
C.6.3	UV resistance	26
C.6.3.1	General	26
C.6.3.2	Natural outdoor UV radiation resistance tests	27
C.6.3.3	UV radiation resistance (accelerated test)	28
C.6.4	Humidity resistance (accelerated test)	28
C.6.5	Acetic acid salt spray fog resistance (accelerated corrosion test)	28
C.6.6	Filiform corrosion test, FFC (accelerated corrosion test)	29
	Annex D (informative) Guidelines for storage and subsequent processing	30
D.1	Storage	30
D.2	General instructions for processing	30
D.3	Forming	30
D.4	Cutting	30
D.5	Joining	31
D.6	Cleaning	31
D.7	Temporary protective films	31
	Bibliography	32

[oSIST prEN 1396:2022](https://standards.iteh.ai/catalog/standards/sist/f07e3911-34a9-49cb-b281-42e812663733/osist-pren-1396-2022)
<https://standards.iteh.ai/catalog/standards/sist/f07e3911-34a9-49cb-b281-42e812663733/osist-pren-1396-2022>

prEN 1396:2022 (E)

European foreword

This document (prEN 1396:2022) has been prepared by Technical Committee CEN/TC 132 “Aluminium and aluminium alloys”, the secretariat of which is held by AFNOR.

This document is currently submitted to the CEN Enquiry.

This document will supersede EN 1396:2015.

**iTeh STANDARD
PREVIEW
(standards.iteh.ai)**

[oSIST prEN 1396:2022](https://standards.iteh.ai/catalog/standards/sist/f07e3911-34a9-49cb-b281-42e812663733/osist-pren-1396-2022)
<https://standards.iteh.ai/catalog/standards/sist/f07e3911-34a9-49cb-b281-42e812663733/osist-pren-1396-2022>

Introduction

Organic coated aluminium and aluminium alloy strip and sheet products can be used to advantage in cases where corrosion resistance and decorative appearance are of primary importance. They have applications throughout the flat products processing industry e.g. in the building, automotive, caravans, appliances, fabricating and packaging industries.

Organic coated aluminium and aluminium alloy flat products can be delivered in numerous types and grades, depending on the base material used (various grades of aluminium), on the coating material and types of coating and on the requirements for the surface appearance and the formability.

The properties of the products can vary within greater or smaller limits depending on the choice and combination of properties required. It is therefore not practicable to specify in detail minimum requirements for all properties for all types of products.

As a general rule, material specifications shall be agreed between manufacturer and user/purchaser using, when appropriate, the guidelines from Annex C.

Guidelines for proper storage and subsequent processing of organic coated aluminium flat products are given in Annex D.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN 1396:2022
https://standards.iteh.ai/catalog/standards/sist/f07e3911-
34a9-49cb-b281-42e812663733/osist-pren-1396-2022](https://standards.iteh.ai/catalog/standards/sist/f07e3911-34a9-49cb-b281-42e812663733/osist-pren-1396-2022)

prEN 1396:2022 (E)**1 Scope**

This document specifies the particular requirements for wrought aluminium and wrought aluminium alloys in the form of coil coated sheet and strip for general applications. This product is generally supplied in thicknesses up to 3,0 mm.

It applies to cold-rolled aluminium and aluminium alloy strip coated by the coil coating process both with liquid as well as with powder paints, either in the final width or slit afterwards, and to sheet obtained from such strip.

It does not apply to coil coated sheet and strip used for special applications such as cans, closures and lids which are dealt with in separate EN 541.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 485-1, *Aluminium and aluminium alloys - Sheet, strip and plate - Part 1: Technical conditions for inspection and delivery*

EN 485-4, *Aluminium and aluminium alloys - Sheet, strip and plate - Part 4: Tolerances on shape and dimensions for cold-rolled products*

EN 515:2017, *Aluminium and aluminium alloys - Wrought products - Temper designations*

EN 573-3:2019, *Aluminium and aluminium alloys - Chemical composition and form of wrought products - Part 3: Chemical composition and form of products*

EN 12258-1:2012, *Aluminium and aluminium alloys - Terms and definitions - Part 1: General terms*

EN 13523-1, *Coil coated metals - Test methods - Part 1: Film thickness*

EN 13523-2, *Coil coated metals - Test methods - Part 2: Gloss*

EN 13523-3, *Coil coated metals - Test methods - Part 3: Colour difference and metamerism - Instrumental comparison*

EN 13523-4, *Coil coated metals - Test methods - Part 4: Pencil hardness*

EN 13523-6, *Coil coated metals - Test methods - Part 6: Adhesion after indentation (cupping test)*

EN 13523-8, *Coil coated metals - Test methods - Part 8: Resistance to salt spray (fog)*

EN 13523-10, *Coil coated metals - Test methods - Part 10: Resistance to fluorescent UV radiation and water condensation*

EN 13523-19, *Coil coated metals - Test methods - Part 19: Panel design and method of atmospheric exposure testing*

EN 13523-21, *Coil coated metals - Test methods - Part 21: Evaluation of outdoor exposed panels*

EN 13523-22, *Coil coated metals - Test methods - Part 22: Colour difference - Visual comparison*

EN ISO 1520, *Paints and varnishes - Cupping test (ISO 1520)*

EN ISO 4623-2, *Paints and varnishes - Determination of resistance to filiform corrosion - Part 2: Aluminium substrates (ISO 4623-2)*

EN ISO 6892-1:2019, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature (ISO 6892-1:2019)*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 12258-1:2012 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at <https://www.iso.org/obp>

— IEC Electropedia: available at <http://www.electropedia.org/>

3.1

aluminium

unalloyed aluminium or aluminium alloy

Note 1 to entry: In the USA the term “Aluminum” is used.

[SOURCE: EN 12258-1:2012]

3.2

aluminium alloy

aluminium which contains alloying elements, where aluminium predominates by mass over each of the other elements and where the aluminium content is not greater than 99,00%

[SOURCE: EN 12258-1:2012]

3.3

metal substrate

base material from cold rolled aluminium or aluminium alloy strip

3.4

coating material

material comprising organic polymers e.g. synthetic resins or plastics, to which pigments, additives and sol-vents (if required) have generally been added, suitable for coil coating

Note 1 to entry: These can be paints (liquid or powder) or plastic films.

3.5

coil coating

method in which a coating material is applied in a continuous process on a cold rolled metal strip

Note 1 to entry: This process includes cleaning and chemical pre-treatment of the surface and either:

— one-side or two-side, single or multiple application of liquid or powder coating materials which are subsequently cured, or

— laminating with plastic films.

prEN 1396:2022 (E)**3.6****organic coating**

paint or lacquer film on a coated product produced from wet paint or from powder coating, or the laminated organic film

[SOURCE: EN 12258-1:2012]

3.7**top side**

side of the strip with the highest decorative demand and which, in normal production, is uppermost

Note 1 to entry: For strip supplied in coil form, the top side is normally the outside of the coil. For sheet supplied in stacks or bundles the top side is normally uppermost.

3.8**reverse side**

underside of the strip, generally coated with a backing coat (see 3.12), but possibly pre-treated only or coated with one of the other systems described in 3.10, 3.11 and 3.13, to fulfil special requirements such as foam or glue adhesion, specially defined friction, etc

3.9**coating system**

combination of coatings either on the top side or on the reverse side of the metal substrate

Note 1 to entry: The name of the coating system derives from the topcoat coating material (see examples in Annex B).

3.10**single layer coating**

single coating either with requirements on appearance, formability, corrosion protection, subsequent painting etc., or as a primer with special properties regarding adhesion and corrosion protection for post-painting applications

3.11**multilayer coating**

system comprising a primer or a base coat, possibly intermediate coat(s), and a top coat with particular requirements on appearance, formability, corrosion protection etc

3.12**backing coat**

single coating of any type with no particular requirements for appearance, formability, corrosion protection etc., usually on the reverse side of the coated product

3.13**film coating**

organic film applied to a substrate to which an adhesive and, if appropriate, a primer has been applied before-hand

[SOURCE: EN 12258-1:2012]

3.14**master coil / mother coil**

coil-coated in coil form from which products (coil or sheet) are obtained

3.15**order document**

document or set of documents agreed between supplier and purchaser at the time of ordering

Note 1 to entry: An order document can be an order of the purchaser confirmed by the supplier or a quotation of the supplier confirmed by the purchaser.

4 Technical conditions for inspection and delivery**4.1 Ordering information**

The order document shall define the product required and shall contain the following information:

- a) the form and type of product:
 - 1) the form of the product (organic coated coil, sheet or strip);
 - 2) the designation of the aluminium or aluminium alloy, in accordance with EN 573-3:2019;
- b) the temper of the material for delivery (degree of hardness or heat treatment condition) in accordance with EN 515:2017 and EN ISO 6892-1:2019;
- c) the dimensions and shape of the product:
 - 1) thickness (of the metal substrate);
 - 2) width;
 - 3) length of sheet (in the rolling direction);
 - 4) internal and external diameters of the coil;
 - 5) core size and type.

NOTE Unless otherwise agreed, the length is the largest dimension.
- d) the quantity:
 - 1) mass or number of pieces;
- e) the coating system (see examples in Annex B):
 - 1) for the top side:
 - i. colour designation (international and/or company code);
 - ii. nominal gloss value;
 - iii. protective strippable film when required ¹⁾

1) If the surface is likely to be damaged during transportation, storage, processing or erection, the coil coated material may, on agreement, be supplied with the additional protection of a temporary strippable film. Type, thickness, adhesion properties, formability, tear strength and light fastness are to be taken into consideration

prEN 1396:2022 (E)

- 2) for the reverse side:
 - i. whether it is a backing coat or not;
 - ii. colour designation (international and/or company code);
 - iii. nominal gloss value;
- f) the type and the design of embossing, when required;
- g) any requirements for inspection documents;
- h) any special requirements for packing:
 - 1) mass per coil and per packing unit;
 - 2) number of sheets per stack;
 - 3) position of coil axis (vertical or horizontal);
 - 4) design of pallet;
 - 5) direction of winding;

Optional information to be mentioned in the order:

- i) the form and type of product:
 - 1) the purchaser application;
- j) the number of this European Standard, i.e. EN 1396, or a specific identification number, or, where none exists, the properties agreed between manufacturer and purchaser;
 - 1) the quantity;
- k) quantity tolerances if required;
- l) the coating system
 - 1) for the top side
 - i. special requirements when required such as coat system (single, multiple); type of organic coating (see Table B.1); coating thickness in micrometers, if different from normal (see Table B.1); stripe code etc.;
 - 2) for the reverse side
 - i. special requirements when required such as coat system (single, multiple); type of organic coating (see Table B.1); coating thickness in micrometers, if different from normal (see

when choosing protective films. Only certain protective films can be exposed to outdoor weathering, and these only for a limited period.