



Designation: D7040 – 04(Reapproved 2010)

Standard Test Method for Determination of Low Levels of Phosphorus in ILSAC GF 4 and Similar Grade Engine Oils by Inductively Coupled Plasma Atomic Emission Spectrometry¹

This standard is issued under the fixed designation D7040; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the quantitative determination of phosphorus in unused lubricating oils, such as International Lubricant Standardization and Approval Committee (ILSAC) GF 4 and similar grade engine oils, by inductively coupled plasma atomic emission spectrometry.

1.2 The precision statements are valid for dilutions in which the mass % sample in solvent is held constant in the range of 1 to 5 mass % oil.

1.3 The precision tables define the concentration ranges covered in the interlaboratory study (500 to 800 mg/kg). However, both lower and higher concentrations can be determined by this test method. The low concentration limits are dependent on the sensitivity of the ICP instrument and the dilution factor. The high concentration limits are determined by the product of the maximum concentration defined by the linear calibration curve and the sample dilution factor.

1.4 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D4057 Practice for Manual Sampling of Petroleum and Petroleum Products

¹ This test method is under the jurisdiction of ASTM Committee D02 on Petroleum Products and Lubricants and is the direct responsibility of Subcommittee D02.03 on Elemental Analysis.

Current edition approved May 1, 2010. Published May 2010. Originally approved in 2004. Last previous edition approved in 2004 as D7040-04. DOI: 10.1520/D7040-04R10.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

D4307 Practice for Preparation of Liquid Blends for Use as Analytical Standards

D4927 Test Methods for Elemental Analysis of Lubricant and Additive Components—Barium, Calcium, Phosphorus, Sulfur, and Zinc by Wavelength-Dispersive X-Ray Fluorescence Spectroscopy

D4951 Test Method for Determination of Additive Elements in Lubricating Oils by Inductively Coupled Plasma Atomic Emission Spectrometry

D5185 Test Method for Multielement Determination of Used and Unused Lubricating Oils and Base Oils by Inductively Coupled Plasma Atomic Emission Spectrometry (ICP-AES)

D6299 Practice for Applying Statistical Quality Assurance and Control Charting Techniques to Evaluate Analytical Measurement System Performance

D6792 Practice for Quality System in Petroleum Products and Lubricants Testing Laboratories

3. Summary of Test Method

3.1 A sample portion is weighed and diluted by mass with mixed xylenes or other solvent. An internal standard, which is required, is either weighed separately into the test solution or is previously combined with the dilution solvent. Calibration standards are prepared similarly. The solutions are introduced to the ICP instrument by a peristaltic pump (required). By comparing emission intensity of phosphorus in the test specimen with emission intensities measured with the calibration standards and by applying the appropriate internal standard and background corrections, the concentrations of phosphorus in the sample is calculated.

4. Significance and Use

4.1 This test method usually requires several minutes per sample. Other test methods which can be used for the determination of phosphorus in lubricating oils include WDXRF Test Method **D4927** and ICPAES Test Methods **D4951** and **D5185**. However, this test method provides more precise results than Test Methods **D4951** or **D5185**.

4.2 Lubricating oils are typically blends of additive packages, and their specifications are also determined, in part,

by elemental composition. This test method can be used to determine if unused lubricating oils meet specifications with respect to elemental composition.

4.3 It is expected that GF 4 grade engine oils marketed in the years 2004-2005 will have a maximum phosphorus concentration level of 500 to 800 mg/kg. These limits are required to minimize poisoning of automotive emission control catalysts by volatile phosphorus species. It is anticipated that the later grades of oils may have even lower phosphorus levels.

5. Interferences

5.1 *Spectral*—There are no known spectral interferences between phosphorus and other elements covered by this test method when using the spectral lines 177.51, 178.29, 185.94, 213.62, 214.91, or 253.40 nm for phosphorus. These wavelengths are only suggested and do not represent all possible choices. Wavelengths below 190 nm require a vacuum or inert gas purged optical path be used. However, if spectral interferences exist because of other interfering elements or selection of other spectral lines, correct for the interference using the technique described in Test Method **D5185**.

5.2 *Viscosity Index Improver Effect*—Viscosity index improvers, which can be present in multi-grade lubricating oils, can bias the measurements.³ However, the biases can be reduced to negligible proportion by using the specified solvent-to-sample dilution and an internal standard.

6. Apparatus

6.1 *Inductively-Coupled Plasma Atomic Emission Spectrometer*—Either a sequential or simultaneous spectrometer is suitable, if equipped with a quartz ICP torch and r-f generator to form and sustain the plasma.

6.2 *Analytical Balance*, capable of weighing to 0.001 g or 0.0001 g, capacity of 150 g.

6.3 *Peristaltic Pump (Required)*—A peristaltic pump is required to provide a constant flow of solution. The pumping speed shall be in the range 0.5 to 3 mL/min. The pump tubing shall be able to withstand at least a 6-h exposure to the dilution solvent. Fluoroelastomer copolymer⁴ tubing is recommended.

6.4 *Solvent Dispenser (Optional)*—A solvent dispenser calibrated to deliver the required weight of diluent can be advantageous. Ensure that solvent drip does not affect accuracy.

6.5 *Specimen Solution Containers*, of appropriate size, glass or polyolefin vials, or bottles with screw caps.

6.6 *Vortexer (Optional)*—Vortex the sample plus diluent mixture until the sample is completely dissolved.

6.7 *Ultrasonic Homogenizer (Optional)*—A bath-type or probe-type ultrasonic homogenizer can be used to homogenize the test specimen.

³ Bansal, J. G., and McElroy, F. C., *SAE Paper 932694*, October 1993. Available from Society of Automotive Engineers (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001.

⁴ Fluoroelastomer copolymer is manufactured as Viton, a trademark owned by E. I. duPont de Nemours.

7. Reagents and Materials

7.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society where such specifications are available.⁵

7.2 *Base Oil*, U.S.P. white oil, or a lubricating base oil that is free of analytes, having a viscosity at room temperature as close as possible to that of the samples to be analyzed.

7.3 *Internal Standard (Required)*—An oil-soluble internal standard element is required. The following internal standards were successfully used in the interlaboratory study on precision: Co (most common), Sc, and Y. Other appropriate internal standards may also be used.

7.4 *Organometallic Standards*—Multi-element standards, containing known concentrations (approximately 0.1 mass %) of each element, can be prepared from the individual metal concentrates. Refer to Practice **D4307** for a procedure for preparation of multi-component liquid blends. When preparing multi-element standards, be certain that proper mixing is achieved. Commercially available multi-element blends (with known concentrations of each element at approximately 0.1 mass %) are also satisfactory.

7.4.1 It can be advantageous to select concentrations that are typical of unused oils. However, it is imperative that concentrations are selected such that the emission intensities measured with the working standards can be measured precisely (that is, the emission intensities are significantly greater than background) and that these standards represent the linear region of the calibration curve. Frequently, the instrument manufacturer publishes guidelines for determining linear range.

7.4.2 Some commercially available organometallic standards are prepared from metal sulfonates and, therefore, contain sulfur.

7.4.3 Petroleum additives can also be used as organometallic standards if their use does not adversely affect precision nor introduce significant bias.

7.5 *Dilution Solvent*—Mixed xylenes, o-xylene, and kerosine were successfully used in the interlaboratory study on precision.

8. Internal Standardization (Required)

8.1 The internal standard procedure requires that every test solution (sample and standard) have the same concentration (or a known concentration) of an internal standard element that is not present in the original sample. The internal standard is usually combined with the dilution solvent. Internal standard compensation is typically handled in one of two different ways, summarized as follows:

8.1.1 Calibration curves are based on the measured intensity of each analyte divided (that is, scaled) by the measured

⁵ *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For Suggestions on the testing of reagents not listed by the American Chemical Society, see *Annual Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.

intensity of the internal standard per unit internal standard element concentration. Concentrations for each analyte in the test specimen solution are read directly from these calibration curves.

8.1.2 For each analyte and the internal standard element, calibration curves are based on measured (unscaled) intensities. Uncorrected concentrations for each analyte in the test specimen solution are read from these calibration curves. Corrected analyte concentrations are calculated by multiplying the uncorrected concentrations by a factor equal to the actual internal standard concentration divided by the uncorrected internal standard concentration determined by analysis.

8.2 Dissolve the organometallic compound representing the internal standard in dilution solvent and transfer to a dispensing vessel. The stability of this solution shall be monitored and prepared fresh (typically weekly) when the concentration of the internal standard element changes significantly. The concentration of internal standard element shall be at least 100 times its detection limit. A concentration in the range of 10 to 20 mg/kg is typical.

NOTE 1—This test method specifies that the internal standard is combined with the dilution solvent because this technique is common and efficient when preparing many samples. However, the internal standard can be added separately from the dilution solvent as long as the internal standard concentration is constant or accurately known.

9. Sampling

9.1 The objective of sampling is to obtain a test specimen that is representative of the entire quantity. Thus, take laboratory samples in accordance with the instructions in Practice D4057. The specific sampling technique can affect the accuracy of this test method.

10. Preparation of Apparatus

10.1 *Instrument*—Design differences between instruments, ICP excitation sources, and different selected analytical wavelengths for individual spectrometers make it impractical to detail the operating conditions. Consult the manufacturer's instructions for operating the instrument with organic solvents. Set up the instrument for use with the particular dilution solvent chosen.

10.2 *Peristaltic Pump*—Inspect the pump tubing and replace it, if necessary, before starting each day. Verify the solution uptake rate and adjust it to the desired rate.

10.3 *ICP Excitation Source*—Initiate the plasma source at least 30 min before performing an analysis. During this warm-up period, nebulize the dilution solvent. Inspect the torch for carbon buildup during the warm-up period. If carbon buildup occurs, replace the torch immediately and consult the manufacturer's operating guide to take proper steps to remedy the situation.

NOTE 2—Carbon that accumulates on the tip of the torch injector tube can be removed by using nebulizer gas that consists of approximately 1 % oxygen in argon.

10.3.1 Generally, carbon buildup can be minimized by increasing the intermediate argon flow rate or lowering the torch, or both, relative to the load coil.

NOTE 3—Some manufacturers recommend even longer warm-up peri-

ods to minimize changes in the slopes of the calibration curves.

10.4 *Wavelength Profiling*—Perform any wavelength profiling that is specified in the normal operation of the instrument.

10.5 *Operating Parameters*—Assign the appropriate operating parameters to the instrument task file so that the desired elements can be determined. Parameters to be included are element, wavelength, background correction points (required), interelement correction factors (refer to 5.1), integration time, and internal standard compensation (required). Multiple integrations (typically three) are required for each measurement. A typical integration time is 10 s.

11. Preparation of Test Specimens

11.1 *Diluent*—Diluent refers to the dilution solvent containing the internal standard (refer to 8.2).

11.2 Test specimen solutions are prepared in the same way that calibration standards are prepared (refer to 12.2). The mass % oil in diluent shall be the same for calibration standards and test specimen solutions.

11.2.1 *Lubricating Oil Specimens*—Weigh appropriate amount of the test specimen to the nearest 0.001 g. The weight of the test specimen taken will vary depending upon the metal concentration of the specimen. Dilute by mass with the diluent. Mix well.

11.3 Record all weights and calculate dilution factors by dividing the sum of the weights of the diluent, sample, and base oil (if any) by the weight of the sample.

11.4 The user of this test method has the option of selecting the dilution factor, that is, the relative amounts of sample and diluent. However, the mass % sample in diluent (for calibration standards and test specimens) shall be constant throughout this test method, and the mass % sample in diluent shall be in the range of 1 to 5 mass %.

11.4.1 All references to dilute and diluting in this test method refer to the user-selected dilution.

11.5 *Blank*—Prepare a blank by diluting the base oil or white oil with the diluent.

11.6 *Working Standards*—Weigh to the nearest 0.001 g, approximately 1 to 3 g of each multi-element standard (refer to 7.4) into separate bottles. Dilute by mass with the diluent.

11.7 *Check Standard*—Prepare instrument check standards in the same manner as the working standards such that the concentrations of elements in the check standards are similar to the concentrations of elements in the test specimen solutions. It is advisable to prepare the check standard from alternative sources of certified organometallic standards.

12. Calibration

12.1 The linear range of all calibration curves shall be determined for the instrument being used. This is accomplished by running intermediate standards between the blank and the working standards and by running standards containing higher concentrations than the working standards. Analyses of test specimen solutions shall be performed within the linear range of the calibration curve.