



Designation: E1405 – 98(Reapproved 2010)

## Standard Specification for Laboratory Glass Distillation Flasks<sup>1</sup>

This standard is issued under the fixed designation E1405; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This specification covers standard dimensional requirements for glass distillation flasks. It includes general purpose flasks and flasks designed for specific tests especially in the petroleum testing area.

NOTE 1—For packaging standards, choose among Specifications E920, E1157, and E1133.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>2</sup>

- D20 Test Method for Distillation of Road Tars
- D86 Test Method for Distillation of Petroleum Products at Atmospheric Pressure
- D216 Method of Test for Distillation of Natural Gasoline (Withdrawn 1988)<sup>3</sup>
- D233 Test Methods of Sampling and Testing Turpentine
- D246 Test Method for Distillation of Creosote and Creosote-Coal Tar Solutions (Withdrawn 2006)<sup>3</sup>
- D285 Test Method for DISTILLATION OF CRUDE PETROLEUM (Withdrawn 1985)<sup>3</sup>
- D402 Test Method for Distillation of Cutback Asphalt
- D447 Test Method for Distillation Of Plant Spray Oils (Withdrawn 1998)<sup>3</sup>
- D801 Test Methods for Sampling and Testing Dipentene
- D802 Test Methods for Sampling and Testing Pine Oils
- D850 Test Method for Distillation of Industrial Aromatic Hydrocarbons and Related Materials
- D1078 Test Method for Distillation Range of Volatile Organic Liquids

D2569 Test Method for Distillation of Pitch (Withdrawn 2006)<sup>3</sup>

- E3 Guide for Preparation of Metallographic Specimens
- E4 Practices for Force Verification of Testing Machines
- E438 Specification for Glasses in Laboratory Apparatus
- E671 Specification for Maximum Permissible Thermal Residual Stress in Annealed Glass Laboratory Apparatus
- E920 Specification for Commercially Packaged Laboratory Apparatus
- E921 Specification for Export Packaged Laboratory Apparatus
- E1133 Practice for Performance Testing of Packaged Laboratory Apparatus for United States Government Procurements
- E1157 Specification for Sampling and Testing of Reusable Laboratory Glassware

#### 2.2 Other Documents:

- U.S. Bureau of Mines Technical Paper 323B Method 100.13<sup>4</sup>

### 3. Classification

3.1 Distillation flasks shall be of the following types and sizes:

3.1.1 *Type I*—General purpose distilling flasks shall be of the following nominal capacities: 10 mL; 25 mL; 50 mL; 125 mL; 200 mL; 250 mL; 500 mL; 1000 mL; 2000 mL.

3.1.2 *Type II*—Special purpose distilling flasks shall be of the following classes:

3.1.2.1 *Class 1*—Barrett, 200 mL.

3.1.2.2 *Class 2*—Church, in the following sizes: 300 mL; 500 mL.

3.1.2.3 *Class 3*—Engler, 100 mL.

3.1.2.4 *Class 4*—Hempel, 500 mL.

3.1.2.5 *Class 5*—Saybolt, 250 mL.

NOTE 2—The term millilitre (mL) is commonly used as a special name for the cubic centimetre (cm<sup>3</sup>) and similarly the litre (L) for 1000 cm<sup>3</sup>, in accordance with the International System of Units (SI).

### 4. Materials and Manufacture

4.1 Flasks shall be made of borosilicate glass conforming to the requirement of Type I, Class A of Specification E438.

<sup>4</sup> Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, http://dodssp.daps.dla.mil.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee E41 on Laboratory Apparatus and is the direct responsibility of E41.01 on Apparatus.

Current edition approved May 15, 2010. Published May 2010. Originally approved in 1991. Last previous edition approved in 2003 as E1405 - 98 (2003). DOI: 10.1520/E1405-98R10.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> The last approved version of this historical standard is referenced on www.astm.org.