



Designation: F436M – 10

## Standard Specification for Hardened Steel Washers (Metric)<sup>1</sup>

This standard is issued under the fixed designation F436M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope\*

1.1 This specification covers the chemical, mechanical, and dimensional requirements for metric hardened steel washers for use with fasteners having nominal thread diameters M12 through M100. These washers are intended for general-purpose mechanical and structural use with bolts, nuts, studs, and other internally and externally threaded fasteners. These washers are suitable for use with fasteners covered in Specifications [A325M](#), [A490M](#), [A563M](#) and with fasteners of Specification [F568M](#) property classes 8.8 and higher.

1.2 The types of washers covered in this specification are:

1.2.1 *Type 1*—Washers made of carbon steel.

1.2.2 *Type 3*—Washers made of steel having atmospheric corrosion resistance and weathering characteristics comparable to that of steels covered in Specifications [A242/A242M](#), [A588/A588M](#), and [A709/A709M](#). The atmospheric corrosion resistance of these steels is substantially better than that of carbon steel with or without copper addition. See [5.1](#). When properly exposed to the atmosphere, these steels can be used bare (uncoated) for many applications.

1.2.3 This specification provides for furnishing Type 3 to chemical composition or a Corrosion Resistance Index (CRI) of 6 or higher at the suppliers option.

1.3 The styles of washers covered in this specification are:

1.3.1 *Circular Washers*—Circular washers in nominal sizes 12 mm through 100 mm, are suitable for applications where sufficient space exists and angularity permits.

1.3.2 *Beveled Washers*—Beveled washers are square and rectangular, in nominal sizes 12 mm through 36 mm, with a beveled 1:6 surface for use with American Standard beams and channels.

1.3.3 *Clipped Washers*—Clipped washers are circular or beveled for use where space limitations necessitate that one side be clipped.

1.4 Terms used in this specification are defined in Terminology [F1789](#) unless otherwise defined herein.

1.5 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

NOTE 1—This specification is the metric counterpart of Specification [F436](#).

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

2.1 *ASTM Standards*:<sup>2</sup>

[A153/A153M](#) Specification for Zinc Coating (Hot-Dip) on Iron and Steel Hardware

[A242/A242M](#) Specification for High-Strength Low-Alloy Structural Steel

[A325M](#) Specification for Structural Bolts, Steel, Heat Treated 830 MPa Minimum Tensile Strength (Metric)

[A490M](#) Specification for High-Strength Steel Bolts, Classes 10.9 and 10.9.3, for Structural Steel Joints (Metric)

[A563M](#) Specification for Carbon and Alloy Steel Nuts (Metric)

[A588/A588M](#) Specification for High-Strength Low-Alloy Structural Steel, up to 50 ksi [345 MPa] Minimum Yield Point, with Atmospheric Corrosion Resistance

[A709/A709M](#) Specification for Structural Steel for Bridges

[A751](#) Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products

[B695](#) Specification for Coatings of Zinc Mechanically Deposited on Iron and Steel

[D3951](#) Practice for Commercial Packaging

[F436](#) Specification for Hardened Steel Washers

[F568M](#) Specification for Carbon and Alloy Steel Externally Threaded Metric Fasteners (Metric)

[F606M](#) Test Methods for Determining the Mechanical Properties of Externally and Internally Threaded Fasteners, Washers, and Rivets (Metric)

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee [F16](#) on Fasteners and is the direct responsibility of Subcommittee [F16.02](#) on Steel Bolts, Nuts, Rivets and Washers.

Current edition approved May 1, 2010. Published June 2010. Originally approved in 1983. Last previous edition approved in 2009 as [A436M – 09](#). DOI: 10.1520/F0436M-10.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

\*A Summary of Changes section appears at the end of this standard.

- F1470 Practice for Fastener Sampling for Specified Mechanical Properties and Performance Inspection
- F1136M Specification for Zinc/Aluminum Corrosion Protective Coatings for Fasteners (Metric)
- F1789 Terminology for F16 Mechanical Fasteners
- G101 Guide for Estimating the Atmospheric Corrosion Resistance of Low-Alloy Steels

2.2 ANSI Standard:<sup>3</sup>

B 18.23.2M Metric Beveled Washers

### 3. Ordering Information

3.1 Orders for washers under this specification shall include the following:

3.1.1 Quantity,

3.1.2 Name of product, (that is, circular washer, beveled washer, clipped circular washer, or clipped beveled washer),

3.1.3 Coating, if required (that is, hot-dip galvanized, mechanically galvanized, Zinc/Aluminum Corrosion Protective Coating, etc.),

3.1.3.1 When galvanized washers are specified, the type of galvanizing, such as hot-dip or mechanical (see 6.1 and 6.3),

3.1.3.1.1 When the type of galvanizing is not specified, the manufacturer, at his option, may furnish hot-dip or mechanically galvanized washers,

3.1.4 Dimensions, nominal size, and other dimensions, if modified from those covered in this specification,

3.1.5 Material type of washer (that is, Type 1 or Type 3),

3.1.5.1 When the type is not specified, either Type 1 or Type 3 washers may be supplied when permitted by the purchaser.

3.1.5.2 When atmospheric corrosion resistance is required, Type 3 washers shall be specified by the purchaser.

3.1.6 Surface roughness control (see S1),

3.1.7 ASTM designation and year of issue, and

3.1.8 Any special requirements.

NOTE 2—Two examples of ordering descriptions follow: (1) 1000 pieces, circular washers, hot-dip galvanized, 24 mm, Type 1 ASTM A436M, dated \_\_\_\_\_. (2) 5000 pieces, beveled washers, 22 mm, Type 3, ASTM, A436M, dated \_\_\_\_\_.

### 4. Materials and Manufacture

4.1 Steel used in the manufacture of washers shall be produced by the open-hearth, basic-oxygen, or electric-furnace process.

4.2 All washers in nominal sizes 12 through 36 mm, shall be through-quenched-and-tempered. Washers in nominal sizes larger than 36 mm may be either through-quenched-and-tempered or carburized, quenched-and-tempered at the manufacturer's option.

4.3 Hot-dip galvanized washers shall be hot-dip galvanized in accordance with the requirements for Class C of Specification A153/A153M. Mechanically galvanized washers shall be mechanically zinc-coated, and the coating and coated washers shall conform to the requirements for Class 50 of Specification B695. Zinc/Aluminum Corrosion Protective Coating shall be coated and the coating and coated washers shall conform to the requirements of Grade 3 of Specification F1136M.

4.4 If washers are heat treated by a subcontractor, they shall be returned to the manufacturer for testing prior to shipment to the purchaser.

### 5. Chemical Composition

5.1 Type 1 washers shall conform to the chemical composition requirements specified in Table 1.

5.2 Type 3 washers shall conform to the Heat Analysis specified in Table 1. Alternatively, at the suppliers option, Type 3 washers having a Copper minimum Heat Analysis of 0.25%, Phosphorous and Sulfur conforming to Table 1 and a Corrosion Index of 6 or higher calculated from the Heat Analysis as described in Guide G101 Predictive method based on the data of Larabee and Coburn shall be accepted .

5.3 For Type 1 and 3 furnished to the Chemical Compositions in Table 1, Product Analyses may be made by the purchaser on finished washers representing each lot. The Chemical Composition shall conform to the requirements in Table 1, Product Analysis.

5.4 Product Analysis are not applicable to Type 3 washers furnished to a CRI of 6 or higher. Acceptance shall be based on the CRI of 6 or higher calculated from the Heat Analysis.

5.5 Individual heats of steel are not identified in the finished product.

5.6 Chemical analyses shall be performed in accordance with Test Methods, Practices, and Terminology A751.

### 6. Mechanical Properties

6.1 Through-quenched-and-tempered washers shall have a Rockwell hardness of 38 to 45 HRC, except when hot-dip galvanized, in which case they shall have a Rockwell hardness of 26 to 45 HRC.

6.2 Carburized, quenched-and-tempered washers shall be carburized to a minimum depth of 0.40 mm and shall have a Rockwell hardness of 69 to 73 HRA.

6.3 When mechanically galvanized, washers shall have the same hardness range as noncoated washers.

TABLE 1 Chemical Requirements

Element	Composition, %	
	Type 1	Type 3 <sup>A</sup>
Phosphorus, max		
Heat analysis	0.040	0.040
Product analysis	0.050	0.045
Sulfur, max		
Heat analysis	0.050	0.050
Product analysis	0.060	0.055
Silicon		
Heat analysis	...	0.15–0.35
Product analysis	...	0.13–0.37
Chromium		
Heat analysis	...	0.45–0.65
Product analysis	...	0.42–0.68
Nickel		
Heat analysis	...	0.25–0.45
Product analysis	...	0.22–0.48
Copper		
Heat analysis	...	0.25–0.45
Product analysis	...	0.22–0.48

<sup>A</sup> Type 3 steel washers may also be manufactured from any of the steels listed in Table 2 of Specification F568M.

<sup>3</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, http://www.ansi.org.