
**Textiles and textile products —
Determination of organotin
compounds —**

**Part 2:
Direct method using liquid
chromatography**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

*Textiles et produits textiles — Détermination des composés
organostanniques —*

Partie 2: Méthode directe utilisant la chromatographie en phase liquide

[https://standards.iteh.ai/catalog/standards/sist/9a31ac18-2ab3-4267-8fa0-
aaed0da44cd/iso-22744-2-2020](https://standards.iteh.ai/catalog/standards/sist/9a31ac18-2ab3-4267-8fa0-aaed0da44cd/iso-22744-2-2020)



iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 22744-2:2020](https://standards.iteh.ai/catalog/standards/sist/9a31ac18-2ab3-4267-8fa0-aaaed0da44cd/iso-22744-2-2020)

<https://standards.iteh.ai/catalog/standards/sist/9a31ac18-2ab3-4267-8fa0-aaaed0da44cd/iso-22744-2-2020>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Principle.....	1
5 Reagents.....	2
6 Apparatus and materials.....	2
7 Preparation of the test sample.....	3
8 Procedure.....	3
8.1 General.....	3
8.2 Preparation of the extraction solvent (250 mg/l of tropolone in methanol/ethanol mixture).....	3
8.3 Preparation of standard solution.....	3
8.3.1 General.....	3
8.3.2 Internal standards — Stock solution (1 000 mg/l of organotin cation).....	4
8.3.3 Internal standards — Working solution (2 mg/l of organotin cation).....	4
8.3.4 Standards — Stock solution (1 000 mg/l of organotin cation).....	4
8.3.5 Standards — Working solution (10 mg/l of organotin cation).....	4
8.4 Sample extraction.....	5
8.5 Sample analysis.....	5
9 Expression of results.....	6
9.1 Calibration curve.....	6
9.2 Calculation.....	6
9.3 Reliability of the method.....	7
10 Test report.....	7
Annex A (informative) Example of chromatographic condition.....	8
Annex B (informative) Example of calibration preparation.....	10
Annex C (informative) Reliability of the method.....	11
Bibliography.....	12

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 38, *Textiles*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 248, *Textiles and textile products*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

A list of all parts in the ISO 22744 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Textiles and textile products — Determination of organotin compounds —

Part 2: Direct method using liquid chromatography

WARNING — The use of this document involves hazardous materials. It does not purport to address all of the safety or environmental problems associated with its use. It is the responsibility of users of this document to take appropriate measures to ensure the safety and health of personnel and the environment prior to application of the document.

1 Scope

This document specifies a test method for the qualification and quantification of organotin compounds. This test method is applicable to all types of materials of textile products.

NOTE CEN/TR 16741 defines which materials are applicable to this determination.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4787, *Laboratory glassware — Volumetric instruments — Methods for testing of capacity and for use*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Principle

The organotin compounds are extracted from the material of a textile product with a methanol-ethanol mixture using tropolone as a complexing agent. The mono- and di-organotin-tropolone complexes and tri-organotin cations formed in the extraction procedure are directly analysed by a liquid chromatograph with a tandem mass spectrometer (LC-MS/MS). This method does not require additional derivatization step.

[Table 1](#) indicates the list of organotin compounds which can be analysed with this document.

This document is also applicable for further organotin compounds provided that the method is validated with the additional compounds.

Table 1 — List of organotin compounds that can be analysed and internal standards

Type of compound	Compound	CAS ^a number
Monosubstituted	Internal standard: n-Heptyltin trichloride	59344-47-7
	n-Butyltin trichloride	1118-46-3
	n-Octyltin trichloride	3091-25-6
	Phenyltin trichloride	1124-19-2
Disubstituted	Internal standard: Di-n-heptyltin dichloride	74340-12-8
	Di-n-butyltin dichloride	683-18-1
	Di-n-octyltin dichloride	3542-36-7
	Diphenyltin dichloride	1135-99-5
Trisubstituted	Internal standard: Tri-n-propyltin chloride	2279-76-7
	Tri-n-butyltin chloride ^b	1461-22-9
	Tri-n-octyltin chloride	2587-76-0
	Triphenyltin chloride (or fentin chloride)	639-58-7
	Tricyclohexyltin chloride	3091-32-5
^a Chemical Abstract Service.		
^b If bis(tri-n-butyltin)oxide (TBTO), CAS number 56-35-9, is present, it is detected as tri-n-butyltin.		

iTeh STANDARD PREVIEW (standards.iteh.ai)

5 Reagents

Unless otherwise specified, analytical grade chemicals, especially relevant for liquid chromatography (5.1 to 5.5) shall be used.

[ISO 22744-2:2020](https://standards.iteh.ai/catalog/standards/sist/9a31ac18-2ab3-4267-8fa0-aaed0da44cd/iso-22744-2-2020)

<https://standards.iteh.ai/catalog/standards/sist/9a31ac18-2ab3-4267-8fa0-aaed0da44cd/iso-22744-2-2020>

5.1 Water.

5.2 Methanol.

5.3 Ethanol.

5.4 Ammonium formate.

5.5 Formic acid.

5.6 Tropolone (2-hydroxy-2,4,6-cycloheptatrien-1-one), CAS number: 533-75-5.

5.7 Organotin compounds, listed in [Table 1](#).

6 Apparatus and materials

The usual equipment and laboratory glassware, according to ISO 4787, shall be used, in addition to the following.

6.1 Analytical balance, with resolution of 0,1 mg.

6.2 Glass vessel, with screw cap, e.g. 40 ml.

6.3 Ultrasonic water bath, with adjustable temperature suitable for operation at about 60 °C.

6.4 Disposable syringe and syringe filter, with 0,45 µm pore size or less.

6.5 Glass vial, with septum cap for LC, e.g. 2 ml.

6.6 Micropipettes, 10 µl to 500 µl range, with disposable tips.

6.7 Pipettes, 1 ml to 10 ml capacity.

6.8 Liquid chromatograph with tandem mass spectrometer (LC-MS/MS).

NOTE C18 reverse phase column for liquid chromatography has been found suitable for the analysis.

7 Preparation of the test sample

The test sample consists of a single material taken from the textile product, such as textile, coated material, polymer or other. The preparation of the sample should involve the removal of the individual materials from the textile product and the preparation of a test piece, which results in particles with a maximum edge length of 4 mm.

Up to three test specimens (of equal mass) of the same material type can be tested together, taking into consideration the limits of detection and quantification.

8 Procedure **iTeh STANDARD PREVIEW** (standards.iteh.ai)

8.1 General

SAFETY PRECAUTIONS — Organotin compounds are both toxic and known endocrine system disrupters; therefore, they should be treated with utmost care.

All the chemicals that are stored below room temperature should be allowed to reach room temperature before an aliquot is taken.

8.2 Preparation of the extraction solvent (250 mg/l of tropolone in methanol/ethanol mixture)

For example, use the analytical balance (6.1) to measure 0,125 g of tropolone (5.6) into a glass beaker and dissolve in approximately 20 ml of methanol (5.2)/ethanol (5.3) mixture (80/20 in volume). Dilute to 500 ml with the same methanol (5.2)/ethanol (5.3) mixture in a volumetric flask to obtain a 250 mg/l solution of tropolone.

This solution can be used for up to one month from preparation and stored in a refrigerator at about 6 °C.

8.3 Preparation of standard solution

8.3.1 General

Commercial solutions are available on the market for use in preparing the internal standards working solution and standards working solution. Be mindful of the concentration and the species (chloride or cation forms) of the commercial solution. The mass concentration for the calibration curve and the result are expressed as organotin cations.

EXAMPLE With the Di-n-butyltin dichloride (Bu_2SnCl_2) is the chloride form and $\text{Bu}_2\text{Sn}^{2+}$ is the cation form.

8.3.2 Internal standards — Stock solution (1 000 mg/l of organotin cation)

Internal standards are available commercially as certified solutions. Alternatively, a solution of internal standards can be made. Three internal standards shall be used as solutions in methanol (5.2).

To prepare an internal standard solution, use the analytical balance (6.1) to weigh the appropriate amount of Tri-n-propyltin chloride, Di-n-heptyltin dichloride and n-Heptyltin trichloride. Dissolve them together in methanol (5.2) in a single volumetric flask to obtain the mass concentration of 1 000 mg/l for each organotin cation.

Store the standard solution for a maximum of one year in a refrigerator at about 6 °C, when not in use, to minimize evaporation of the solvent.

8.3.3 Internal standards — Working solution (2 mg/l of organotin cation)

Use a micropipette (6.6) to transfer an appropriate volume of the internal standard stock solution (see 8.3.2) into a volumetric flask and make the solution up to volume with methanol (5.2) to create a 2 mg/l solution of each organotin cation.

8.3.4 Standards — Stock solution (1 000 mg/l of organotin cation)

Standards are available commercially as certified solutions. Alternatively, a solution of standards may be made.

Use the analytical balance (6.1) to weigh the appropriate amount of each organotin compounds (see Table 2). Dissolve each of them (separately) in methanol (5.2) in an appropriate volumetric flask to obtain the mass concentration of 1 000 mg/l for each organotin cation.

Store the standard solution for a maximum of one year in a refrigerator at about 6 °C, when not in use, to minimize evaporation of the solvent.

ISO 22744-2:2020

<https://standards.iteh.ai/catalog/standards/sist/9a31ac18-2ab3-4267-8fa0-110147702222>

8.3.5 Standards — Working solution (10 mg/l of organotin cation)

Use a micropipette (6.6) to transfer an appropriate volume of each standard stock solution (see 8.3.4) into an appropriate volumetric flask and make the solution up to volume with methanol (5.2) to create a 10 mg/l solution of organotin cation.

Table 2 — Amount of organotin chloride and weighting factor for recalculation of organotin cations

OTC	OC	Acronym ^a	Weighting factor ^b	Mass ^c mg
Standards				
n-Butyltin trichloride	n-Butyltin cation	MBT	0,623	160,5
n-Octyltin trichloride	n-Octyltin cation	MOT	0,686	145,8
Phenyltin trichloride	Phenyltin cation	MPhT	0,648	154,3
Di-n-butyltin dichloride	Di-n-butyltin cation	DBT	0,767	130,4
Di-n-octyltin dichloride	Di-n-octyltin cation	DOT	0,830	120,5
Diphenyltin dichloride	Diphenyltin cation	DPhT	0,793	126,1
Tri-n-butyltin chloride	Tri-n-butyltin cation	TBT	0,891	112,2
Tri-n-octyltin chloride	Tri-n-octyltin cation	TOT	0,927	107,9

^a Acronyms correspond organotin chlorides (OTC) and organotin cations (OC).

^b Weighting factor = molar mass (OC)/molar mass (OTC).

^c If the mass of the compounds weighed is different from that given in this table, use the weighting factor to calculate the actual concentration of the OC.

Table 2 (continued)

OTC	OC	Acronym ^a	Weighting factor ^b	Mass ^c mg
Triphenyltin chloride	Triphenyltin cation	TPhT	0,908	110,1
Tricyclohexyltin chloride	Tricyclohexyltin cation	TCyT	0,912	109,6
Internal Standards				
n-Heptyltin trichloride	n-Heptyltin cation	MHT	0,672	148,8
Di-n-heptyltin dichloride	Di-n-heptyltin cation	DHT	0,817	122,4
Tri-n-propyltin chloride	Tri-n-propyltin cation	TPT	0,875	114,3
^a Acronyms correspond organotin chlorides (OTC) and organotin cations (OC). ^b Weighting factor = molar mass (OC)/molar mass (OTC). ^c If the mass of the compounds weighed is different from that given in this table, use the weighting factor to calculate the actual concentration of the OC.				

The mass concentration of organotin cation is usually calculated using [Formula \(1\)](#):

$$\rho_{\text{Sn}} = \rho_{\text{Cl}} \times W_{\text{F}} \quad (1)$$

where

ρ_{Sn} is the mass concentration of organotin cation in mg/l;

ρ_{Cl} is the mass concentration of organotin chloride, in mg/l;

W_{F} is the weighting factor.

EXAMPLE 1 If you weigh 160,5 mg of n-Butyltin trichloride (BuSnCl_3), into 100 ml solvent, you have a solution of 1 605 mg/l of n-Butyltin trichloride, which corresponds to a concentration of: $1\ 605 \times 0,623 = 1\ 000$ mg/l of n-Butyltin cation (BuSn^{3+}).

EXAMPLE 2 If you weigh 110,4 mg of Di-n-octyltin dichloride [$(\text{C}_8\text{H}_{17})_2\text{SnCl}_2$], into 100 ml solvent, you have a solution of 1 104 mg/l of Di-n-octyltin dichloride, which correspond to a concentration of: $1\ 104 \times 0,830 = 916$ mg/l of Di-n-octyltin cation [$(\text{C}_8\text{H}_{17})_2\text{Sn}^{2+}$].

8.4 Sample extraction

8.4.1 Use the analytical balance ([6.1](#)) to weigh 1 g of sample (see [Clause 7](#)) into a glass vessel ([6.2](#)) and record the mass, m_1 .

8.4.2 Add 9,5 ml of extraction solvent ([8.2](#)) and 0,5 ml of the internal standard working solution (see [8.3.3](#)).

8.4.3 Extract in an ultrasonic water bath ([6.3](#)) at (60 ± 5) °C for 1 h \pm 5 min.

8.4.4 Cool the extract down to room temperature and filter approximately 1 ml to 2 ml of extract into a glass vial ([6.5](#)) using a disposable syringe and a syringe filter ([6.4](#)).

8.4.5 Close the glass vial (see [8.4.4](#)) with cap immediately for analysis.

8.5 Sample analysis

Qualitative and quantitative analysis of organotin compounds is performed using LC-MS/MS.

Example of suitable chromatographic conditions is given in [Annex A](#).