



Designation: ~~F1859-04 (Reapproved 2009)~~^{ε1} Designation: F1859 – 10

Standard Specification for Rubber Sheet Floor Covering Without Backing¹

This standard is issued under the fixed designation F1859; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

~~^{ε1}Note—Removed the year/date from ANSI/ASQC Z1.4 editorially in May 2009.~~

1. Scope

1.1 This specification covers the requirements for the compound and physical characteristics of rubber sheet floor covering without backing.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 The following precautionary statement pertains only to the test method portion, Section 10, of this specification: *This standard does not purport to address all the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 The following documents of the issue in effect on the date of the material purchase form a part of this specification to the extent referenced herein:

2.2 ASTM Standards:²

D412 Test Methods for Vulcanized Rubber and Thermoplastic Elastomers Tension

D883 Terminology Relating to Plastics

D1566 Terminology Relating to Rubber

D2240 Test Method for Rubber Property Durometer Hardness

F141 Terminology Relating to Resilient Floor Coverings

F386 Test Method for Thickness of Resilient Flooring Materials Having Flat Surfaces

F410 Test Method for Wear Layer Thickness of Resilient Floor Coverings by Optical Measurement

F710 Practice for Preparing Concrete Floors to Receive Resilient Flooring

F925 Test Method for Resistance to Chemicals of Resilient Flooring

F970 Test Method for Static Load Limit

F1482 Practice for Installation and Preparation of Panel Type Underlayments to Receive Resilient Flooring

F1514 Test Method for Measuring Heat Stability of Resilient Flooring by Color Change

F1515 Test Method for Measuring Light Stability of Resilient Flooring by Color Change

2.3 ANSI Standard:

ANSI/ASQC Z1.4 Sampling Procedures and Tables for Inspection by Attributes³

3. Terminology

3.1 *Definitions*—For definitions of other terms used in this standard, see Terminology F141.

4. Classification

4.1 Rubber sheet floor covering covered by this specification shall conform to the following types:

4.1.1 *Type I*—Homogeneous rubber sheet floor covering, and

4.1.2 *Type II*—Layered rubber sheet floor covering.

¹ This specification is under the jurisdiction of ASTM Committee F06 on Resilient Floor Coverings and is the direct responsibility of Subcommittee F06.80 on Specifications.

Current edition approved May 1, 2009; 2010. Published July 2009; June 2010. Originally approved in 1998. Last previous edition approved in 2004/2009 as F1859 – 04(2009)^{ε1}. DOI: 10.1520/F1859-04R09E01.10.1520/F1859-10.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

- 4.2 The above may have either smooth, embossed, or molded pattern surfaces.
- 4.3 These products shall not contain asbestos.

5. Ordering Information

5.1 Purchasers shall state whether this specification is to be used, select the preferred options permitted herein and include the following information in the invitation to bid or purchase order:

- 5.1.1 Title, number, and date of this specification,
- 5.1.2 Type, color, and surface (see Section 4 and Section 6),
- 5.1.3 Quantity, in square feet, square yards, or square metres,
- 5.1.4 Thickness required. (see Section 8),
- 5.1.5 Overall thickness, if molded pattern sheet flooring is specified (see 8.1),
- 5.1.6 Width required (see 8.4),
- 5.1.7 Length required (see 8.5),
- 5.1.8 Resistance to chemicals, (see 7.4),
- 5.1.9 Lot information, if other than as specified in ANSI/ASQC Z1.4 (see 10.1 and 11.1),
- 5.1.10 Sampling, if other than as specified in ANSI/ASQC Z1.4 (see 10.1 and 11.1),
- 5.1.11 Statement requesting certification, if certification of compliance is required (see 12.1),
- 5.1.12 Packing requirements, if other than as specified (see 14.1),
- 5.1.13 Palletization, if required,
- 5.1.14 Marking required, if other than specified (see 13.1), and
- 5.1.15 Other requirements.

6. Materials and Manufacture

6.1 *Material*—The polymeric binder of the rubber sheet floor covering shall satisfy the definition of rubber in Terminology D1566, and have been vulcanized, as defined in Terminology D1566 (under vulcanization), such that it becomes thermoset as defined in Terminology D883. The rubber sheet flooring made from this compound shall be resistant to neutral pH cleaners.

6.2 *Color, Pattern, and Wear Layer Surface*—The color, pattern, and wear layer surface, as applicable, shall be as specified in the contract or order (see 5.1).

NOTE 1—The colors and patterns that are available are indicated in individual manufacturer's current catalogs. As manufactured, colors may vary somewhat in hue or shade from the catalog.

NOTE 2—Where color match is a concern, samples from the manufacturer shall be obtained to verify color acceptability.

6.3 *Homogeneous Rubber Sheet Floor Covering*—The surface coloring or mottling shall be uniform throughout the entire thickness of the rubber sheet floor covering.

6.4 *Layered Rubber Sheet Floor Covering*—The surface coloring or mottling need not extend through the entire thickness of the rubber sheet floor covering, but must extend throughout the entire thickness of the wear layer.

6.4.1 The wear layer must have a minimum thickness of 0.040 in. (1.0 mm) when measured in accordance with Test Method F410.

6.4.2 The appearance of the rubber sheet floor covering, after removing 0.020 in. (0.51 mm) of the wear layer thickness, shall compare favorably in appearance with the rubber sheet flooring's original appearance. The removal of the wear layer may be accomplished by any suitable method.

7. Performance Requirements

7.1 *Hardness*—The rubber sheet floor covering shall have a durometer hardness of not less than 85 (Shore, Type A) when tested in accordance with Test Method D2240.

7.2 *Modulus at 10 % Elongation*—When tested in accordance with Test Method D412 at a rate of 6 in. (152.4 mm)/min, using a 1 in. (25.4 mm) by 5 in. (127 mm) gage length rectangular specimen, the modulus shall not be less than 300 psi (2.07 MPa). For molded pattern rubber sheet floor covering, the raised pattern shall be removed by any suitable method.

7.3 *Static Load Limit*—When tested in accordance with Test Method F970, with an applied load of 250 lb (113.4 kg), the residual indentation shall not be greater than 0.005 in. (0.127 mm).

7.4 *Resistance to Chemicals*—When tested in accordance with Test Method F925, the rubber sheet floor covering shall have no more than a slight change in surface dulling, surface attack, or staining when exposed to the following chemicals:

- 7.4.1 White vinegar (5 % acetic acid),
- 7.4.2 Rubbing alcohol (70 % isopropyl alcohol),
- 7.4.3 Sodium hydroxide solution (5 % NaOH),
- 7.4.4 Hydrochloric acid solution (5 % HCl),
- 7.4.5 Sulfuric acid solution (5 % H₂SO₄),
- 7.4.6 Household ammonia solution (5 % NH₄OH),
- 7.4.7 Household bleach (5.25 % NaOCl),