SLOVENSKI STANDARD
kSIST-TS FprCEN ISO/TS 80004-13:2024

01-junij-2024

Nanotehnologije - Slovar - 13. del: Grafen in drugi dvodimenzionalni (2D) materiali (ISO/DTS 80004-13:2024)

Nanotechnologies - Vocabulary - Part 13: Graphene and other two-dimensional (2D) materials (ISO/DTS 80004-13:2024)

Nanotechnologien - Fachwörterverzeichnis - Teil 13: Graphen und andere zweidimensionale (2D) Werkstoffe (ISO/DTS 80004-13:2024)

Nanotechnologies - Vocabulaire - Partie 13: Graphène et autres matériaux bidimensionnels (2D) (ISO/DTS 80004-13:2024)

Ta slovenski standard je istoveten z: **FprCEN ISO/TS 80004-13**

ICS:

01.040.07	Naravoslovne in uporabne vede (Slovarji)	Natural and applied sciences (Vocabularies)
07.120	Nanotehnologije	Nanotechnologies

kSIST-TS FprCEN ISO/TS 80004-13:2024 en,fr,de

FINAL DRAFT
Technical Specification

ISO/DTS 80004-13

Nanotechnologies — Vocabulary —

Part 13: Graphene and other two-dimensional (2D) materials

Nanotechnologies — Vocabulaire —

Partie 13: Graphène et autres matériaux bidimensionnels (2D)

ISO/TC **229**

Secretariat: **BSI**

Voting begins on:
2024-04-29

Voting terminates on:
2024-07-22

This draft is submitted to a parallel vote in ISO and in IEC.

ISO/CEN PARALLEL PROCESSING

Reference number
ISO/DTS 80004-13:2024(en)

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword

ISO (the International Organization for Standardization) and IEC (the International Electrotechnical Commission) form the specialized system for worldwide standardization. National bodies that are members of ISO or IEC participate in the development of International Standards through technical committees established by the respective organization to deal with particular fields of technical activity. ISO and IEC technical committees collaborate in fields of mutual interest. Other international organizations, governmental and non-governmental, in liaison with ISO and IEC, also take part in the work.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives or www.iec.ch/members_experts/refdocs).

ISO and IEC draw attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO and IEC take no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO and IEC had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents and https://patents.iec.ch. ISO and IEC shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html. In the IEC, see www.iec.ch/understanding-standards.

This document was prepared jointly by Technical Committee ISO/TC 229, *Nanotechnologies*, and Technical Committee IEC/TC 113, *Nanotechnology for electrotechnical products and systems,* and in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC CEN/TC 352, *Nanotechnologies,* in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement). The draft was circulated for voting to the national bodies of both ISO and IEC.

This second edition cancels and replaces the first edition (ISO/TS 80004-13:2017) which has been technically revised.

The main changes are as follows:

— addition of the term "graphene-related 2D material, GR2M";

— expansion of defined terms to include "enhanced", "modified", "enabled" and "based", and derivatives thereof;

— indication that use of some terms are deprecated.

A list of all parts in the ISO 80004 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Over the last decade, huge interest has arisen in graphene both scientifically and commercially, due to the many exceptional properties associated with this material, such as the electrical and thermal conductivity. More recently, other materials with a structure similar to that of graphene have also shown promising properties, including:

a) monolayer and few-layer versions of hexagonal boron nitride (hBN);

b) transition metal dichalcogenides such as molybdenum disulphide (MoS_2) and tungsten diselenide (WSe_2);

c) silicene and germanene;

d) layered assemblies of mixtures of these materials.

These materials have their thickness constrained within the nanoscale or smaller and consist of between one and several layers. These materials are thus termed two-dimensional (2D) materials as they have one dimension at the nanoscale or smaller, with the other two dimensions generally at scales larger than the nanoscale. A layered material consists of 2D layers weakly stacked or bound to form three-dimensional structures. Examples of 2D materials and the different stacking configurations in graphene are shown in Figure 1. 2D materials are not necessarily topographically flat in reality and can have a buckled structure. They can also form aggregates and agglomerates which can have different morphologies. 2D materials are an important subset of nanomaterials.



a) Examples of different 2D materials consisting of different elements and structures, as shown by the different coloured orbs and top-down and side views



b) Bernal stacked bilayer graphene (3.1.2.7)



c) turbostratic bilayer or twisted bilayer graphene with relative stacking angle (θ)(3.1.2.8)



ABA trilayer



ABC trilayer

d) Bernal stacked (AB) (3.4.1.12) tri-layer graphene (3.1.2.10) and Rhombohedral (ABC) (3.4.1.13) stacked tri-layer graphene (3.1.2.10)

Figure 1 — Examples of 2D materials and the different stacking configurations in graphene layers

It is important to standardize the terminology for graphene, graphene-related and other 2D materials at the international level, as the number of publications, patents and organizations is increasing rapidly. Thus, these materials need an associated vocabulary as they become commercialized and sold throughout the world.

The document contains general terms related to 2D materials, those related to graphene, and those related to other 2D materials. It provides terms related to commonly used methods for producing and characterising 2D materials along, with terms related to 2D materials characteristics. It also includes performance related terms, such as “-enhanced” and “-enabled”, and those related to composition, such as “-based” and “-modified”, as shown in Figure 2.



Figure 2 — General terms to describe 2D materials split into performance and composition related terms

This document belongs to a multi-part vocabulary, covering the different aspects of nanotechnologies. It builds upon ISO 80004-1, ISO/TS 80004-3 and ISO/TS 80004-6, and uses existing definitions where possible.

Nanotechnologies — Vocabulary —

Part 13: Graphene and other two-dimensional (2D) materials

1 Scope

This document defines terms for graphene, graphene-related and other two-dimensional (2D) materials. It includes terms related to production methods, properties and their characterization.

It is intended to facilitate communication between organizations and individuals in research, industry and other interested parties and those who interact with them.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at http://www.iso.org/obp

— IEC Electropedia: available at http://www.electropedia.org/

3.1 Terms related to materials

3.1.1 General terms related to graphene and other 2D materials

3.1.1.1
two-dimensional material
2D material
material, consisting of one or several *layers* (3.1.1.8) with the atoms in each layer strongly bonded to neighbouring atoms in the same layer, which has one dimension, its thickness, in the nanoscale or smaller and the other two dimensions generally at larger scales

Note 1 to entry: The number of layers when a two-dimensional material becomes a bulk material varies depending on both the material being measured and its properties. In the case of *graphene layers* (3.1.2.1), it is a two-dimensional material of up to 10 layers thick for electrical measurements,[10] beyond which the electrical properties of the material are not distinct from those for the bulk [also known as *graphite* (3.1.2.2)].

Note 2 to entry: Interlayer bonding is distinct from and weaker than intralayer bonding.

Note 3 to entry: Each layer can contain more than one element.

Note 4 to entry: A two-dimensional material can be a *nanoplate* (3.1.1.5).

3.1.1.2
graphene-related 2D material
GR2M
DEPRECATED: graphene-based material, graphene-material
carbon-based *two-dimensional material* (3.1.1.1) consisting of one to 10 *layers* (3.1.1.8), including *graphene* (3.1.2.1), *graphene oxide* (3.1.2.15), *reduced graphene oxide* (3.1.2.16), and functionalized variations thereof

Note 1 to entry: This includes *bilayer graphene* (3.1.2.7), *trilayer graphene* (3.1.2.10) and *few-layer graphene* (3.1.2.11).

Note 2 to entry: The terms graphene-based material and graphene-material are deprecated here. They have been used to describe materials other than graphene, such as graphene oxide.

Note 3 to entry: "Graphene-related 2D material" is defined in contrast with *graphene-based* (3.1.1.20) and *GR2M-based* (3.1.1.21).

3.1.1.3
flake
<2D material> distinct particle of planar morphology, consisting of 1 or more *layers* (3.1.1.8) of material, with a nanoscale thickness that is significantly smaller than its lateral dimensions

3.1.1.4
sheet
<2D material> *2D material* (3.1.1.1) typically situated upon a substrate, with extended lateral dimensions at the micro to macroscale

3.1.1.5
nanoplate
nano-object with one external dimension in the nanoscale and the other two external dimensions significantly larger

Note 1 to entry: The larger external dimensions are not necessarily in the nanoscale.

[SOURCE: ISO 80004-1:2023, 3.3.6]

3.1.1.6
nanofoil
nanosheet
nanoplate (3.1.1.5) with extended lateral dimensions

Note 1 to entry: Nanofoil and nanosheet are used synonymously in specific industrial areas.

Note 2 to entry: Nanofoil and nanosheet extend further with respect to their length and width compared to nanoplate or nanoflake.

[SOURCE: ISO 80004-1:2023, 3.3.6.2]

3.1.1.7
nanoribbon
nanotape
nanoplate (3.1.1.5) with the two larger dimensions significantly different from each other

[SOURCE: ISO 80004-1:2023, 3.3.10]

3.1.1.8
layer
discrete material restricted in one dimension, within or at the surface of a condensed phase

[SOURCE: ISO 80004-1:2023, 3.6.2]

3.1.1.9
quantum dot
nanoparticle or region which exhibits quantum confinement in all three spatial directions

[SOURCE: ISO/TS 80004-12:2016, 4.1]

3.1.1.10
enhanced
<2D material> exhibiting function or performance intensified or improved through the use of a *2D material* (3.1.1.1)

EXAMPLE Graphene oxide-enhanced film.

Note 1 to entry: In enhanced products, the 2D material is typically used in low concentration in the product.

Note 2 to entry: Typical usage is: "X-enhanced Y", where X is the 2D material and Y is the product.

Note 3 to entry: Compare to *based* (3.1.1.19).

3.1.1.11
graphene-enhanced
exhibiting function or performance intensified or improved through the use of *graphene* (3.1.2.1)

EXAMPLE Graphene-enhanced solar cells.

Note 1 to entry: In graphene-enhanced products, the graphene is typically used in low concentration in the product.

Note 2 to entry: In common usage, this term is often incorrectly used to apply to *GR2M* (3.1.1.2) and not just to *single-layer graphene* (3.1.2.1). The correct term is *GR2M-enhanced* (3.1.1.12) or, for example, when referring to graphene nanoplatelets: GNP-enhanced.

Note 3 to entry: Compare to *graphene-based* (3.1.1.20).

3.1.1.12
GR2M-enhanced
DEPRECATED: graphene-enhanced
exhibiting function or performance intensified or improved through the use of *GR2M* (3.1.1.2)

EXAMPLE GR2M-enhanced solar cells.

Note 1 to entry: In GR2M-enhanced products, the is typically used in low concentration in the product.

Note 2 to entry: Compare to *GR2M-based* (3.1.1.21).

Note 3 to entry: Graphene-enhanced is deprecated since the use of this term only applies to the use of *(single-layer) graphene* (3.1.2.1) as defined by 3.1.1.11.

3.1.1.13
modified
<2D material> intentional addition of the indicated *2D material* (3.1.1.1)

Note 1 to entry: Typical usage is: "X-modified", where X is either a specific 2D material or a class of 2D materials.

Note 2 to entry: The use of this term does not imply property or performance enhancement through the use of the 2D material.

3.1.1.14
graphene-modified
intentional addition of *graphene* (3.1.2.1) to a material

Note 1 to entry: In common usage, this term is often incorrectly used to apply to *GR2M* (3.1.1.2) and not just to *single-layer graphene* (3.1.2.1). The correct term is *GR2M-modified* (3.1.1.15) or, for example, when referring to graphene nanoplatelets: GNP-modified.