

ISO/TC 17/SC 3

Secretariat: AFNOR

Voting begins on:
2020-12-29

Voting terminates on:
2021-02-23

Structural steels —

Part 3: Technical delivery conditions for fine- grain structural steels

Aciers de construction —

*Partie 3: Conditions techniques de livraison pour aciers de
construction à grains fins*
(standards.iteh.ai)

[ISO/FDIS 630-3](https://standards.iteh.ai/catalog/standards/sist/9953f633-db4c-4c1a-bbbf-fd19385c8f2/iso-fdis-630-3)

<https://standards.iteh.ai/catalog/standards/sist/9953f633-db4c-4c1a-bbbf-fd19385c8f2/iso-fdis-630-3>

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.



Reference number
ISO/FDIS 630-3:2020(E)

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO/FDIS 630-3

<https://standards.iteh.ai/catalog/standards/sist/9953f633-db4c-4c1a-bbbf-fd1d9385c8f2/iso-fdis-630-3>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Classification and designation	2
4.1 Classification.....	2
4.2 Designation (grades and qualities).....	2
4.3 Normative annexes.....	2
5 Information to be supplied by the purchaser	2
5.1 Mandatory information.....	2
5.2 Options.....	2
6 Requirements	3
6.1 Steelmaking process.....	3
6.2 Delivery condition.....	3
6.3 Chemical composition.....	3
6.3.1 Heat analysis.....	3
6.3.2 Product analysis.....	3
6.3.3 Carbon equivalent value.....	3
6.4 Mechanical properties.....	3
6.4.1 Tensile properties.....	3
6.4.2 Charpy V-notch impact properties.....	3
6.5 Surface condition.....	3
6.6 Internal soundness.....	4
6.7 Dimensions, tolerances on dimensions and shape, mass.....	4
7 Inspection	4
8 Sampling - Frequency of testing	4
8.1 Verification.....	4
8.2 Test units.....	4
8.2.1 Annex A	4
8.2.2 Annex B	4
9 Test methods	4
10 Marking	4
Annex A (normative) Steel grades S275, S355, S390, S420, S460 and S500: Chemical composition and mechanical properties	5
Annex B (normative) Steel grades SG245, SG290, SG325, SG345, SG365, SG415 and SG460: Chemical composition and mechanical properties	15
Bibliography	17

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html. (standards.iteh.ai)

This document was prepared by Technical Committee ISO/TC 17, Steel, Subcommittee SC 3, Steel for structural purposes.

<https://standards.iteh.ai/catalog/standards/sist/9953f633-db4c-4c1a-bbbf-6f19385d1076>

This second edition cancels and replaces the first edition (ISO 630-3:2012), which has been technically revised. The main changes compared to the previous edition are as follows:

- grades S390N, S390M, S500M and pertaining requirements have been added;
- applicable thickness ranges have been added in the scope;
- additional terms and definitions concerning heat treatments have been deleted because ISO 4885 is in normative references of ISO 630-1;
- quality E has been renamed L (impact testing at -50 °C) to keep quality E for impact testing at -40 °C in all parts;
- quality E (impact testing at -40 °C) has been added
- quality F (impact testing at -60 °C) has been added to S355N and S355M;
- list of options has been integrated in ISO 630-1;
- the formula for CEV has been deleted because given in ISO 630-1;
- test units have been updated;
- in Tables, the designation concerning thickness have been changed into “nominal thickness”;
- order of listing chemical elements has been updated for grades of [Annex A](#) in accordance with ISO 6306;
- bibliography has been updated;
- the content of the document has been updated to harmonize with all parts of ISO 630.

A list of all parts in the ISO 630 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO/FDIS 630-3

<https://standards.iteh.ai/catalog/standards/sist/9953f633-db4c-4c1a-bbbf-fd19385c8f2/iso-fdis-630-3>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO/FDIS 630-3

<https://standards.iteh.ai/catalog/standards/sist/9953f633-db4c-4c1a-bbbf-f1fd9385c8f2/iso-fdis-630-3>

Structural steels —

Part 3:

Technical delivery conditions for fine-grain structural steels

1 Scope

This document specifies requirements for flat and long products of hot-rolled weldable fine-grain structural steels in the as-rolled (for SG grades only), normalized/normalized rolled and thermomechanical processed delivery conditions. It applies to steel plates rolled on a reversing mill, wide flats, hot-rolled sections and bars, which are intended for use in heavily loaded parts of welded or bolted structures.

This document covers 13 grades and 6 qualities. Grades S275, S355, S390, S420, S460 and S500 are covered in [Annex A](#). Grades SG245, SG290, SG325, SG345, SG365, SG415 and SG460 are covered in [Annex B](#). Not all grades are available in all qualities, and some qualities have Charpy V-notch requirements.

The steels specified in this document are applicable to hot-rolled plates, wide flats, sections and bars with a minimum nominal thickness of 3 mm and a maximum nominal thickness of 250 mm for grades S275N, S355N, S390N, S420N and S460N, a maximum nominal thickness of 150 mm for grades S275M, S355M, S390M, S420M, S460M, and S500M, a maximum nominal thickness of 200 mm for grades SG245, SG325 and SG415, a maximum nominal thickness of 100 mm for grades SG345, SG365 and SG460, and a maximum nominal thickness of 40 mm for grades SG290.

This document does not include the following structural steels, some of which are covered by other International Standards:

- Sheet and strip — refer to ISO TC 17/SC 12, *Continuous mill flat rolled products*;
- Tubular products — refer to ISO TC 5/SC 1, *Steel tubes*.

NOTE 1 Lists of standards covered by ISO/TC 17/SC 12 and ISO/TC 5/SC 1 are available on the ISO Web site.

NOTE 2 In all parts of ISO 630, the term of "thickness" is considered as "nominal thickness", unless otherwise stated.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 630-1, *Structural steels — Part 1: General technical delivery conditions for hot-rolled products*

ISO 643, *Steels — Micrographic determination of the apparent grain size*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 630-1 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>

— IEC Electropedia: available at <http://www.electropedia.org/>

3.1 fine-grain steel
steel with fine-grain structure with an equivalent index of grain size ≥ 6 determined in accordance with ISO 643

Note 1 to entry: See [6.1](#).

4 Classification and designation

4.1 Classification

The steel grades specified in this document shall be classified as unalloyed or alloy steels.

4.2 Designation (grades and qualities)

This document specifies 13 steel grades. Grades S275, S355, S390, S420, S460 and S500 are covered in [Annex A](#). Grades SG245, SG290, SG325, SG345, SG365, SG415 and SG460 are covered in [Annex B](#).

Each grade is available in up to 6 qualities. These grades and qualities differ in their specified mechanical properties and impact energy requirements. All S grades require impact testing. SG grades require impact testing upon agreement at the time of ordering:

- Quality A: no impact testing;
- Quality C: impact testing at 0 °C;
- Quality D: impact testing at -20 °C;
- Quality E: impact testing at -40 °C;
- Quality L: impact testing at -50 °C;
- Quality F: impact testing at -60 °C.

4.3 Normative annexes

The requirements of [Annex A](#) or [Annex B](#) are to be regarded separately. Each annex is independent of the other without combining in any way.

5 Information to be supplied by the purchaser

5.1 Mandatory information

The information that shall be supplied by the purchaser at the time of the order is specified in ISO 630- 1.

5.2 Options

The options of ISO 630-1 may apply. If the purchaser does not indicate a wish to implement any of these options at the time of the order, the products shall be supplied in accordance with the basic specification (see [5.1](#)).

6 Requirements

6.1 Steelmaking process

See ISO 630-1.

If a special steelmaking process has been specified, this shall be reported in the inspection document.

The steels shall contain sufficient amount of nitrogen-binding elements and have a fine-grain structure.

The steels specified in this specification shall be fully killed.

6.2 Delivery condition

The products covered by this document are delivered in the as-rolled (for SG grades only), normalized rolled, normalized (including normalized + tempered) or thermomechanical processed (including thermomechanical processed + tempered) condition. The delivery condition shall be indicated in the inspection document.

6.3 Chemical composition

6.3.1 Heat analysis

The chemical composition determined by heat analysis shall conform with the values given in [Table A.1](#) or [Table A.2](#) or [Table B.1](#).

6.3.2 Product analysis

The product analysis of grades S275, S355, S390, S420, S460 and S500 shall comply with the values given in [Table A.3](#) or [Table A.4](#).

The permitted deviations on analysis of grades SG245, SG290, SG325, SG345, SG365, SG415 and SG460, relative to the values for heat analysis, are given in [Table B.2](#).

6.3.3 Carbon equivalent value

The maximum carbon equivalent value (CEV) requirements for [Annex A](#) grades are given in [Tables A.5](#) or [Table A.6](#), and for [Annex B](#) grades in [Table B.3](#).

6.4 Mechanical properties

6.4.1 Tensile properties

The tensile properties at room temperature shall conform with the values specified in [Table A.7](#) or [Table A.8](#) or [Table B.4](#).

6.4.2 Charpy V-notch impact properties

The impact properties of Charpy V-notch test pieces shall conform with the values specified in [Table A.9](#) or [Table A.10](#) or [Table A.11](#) or [Table A.12](#) or [Table B.5](#). The orientation of the specimens shall be longitudinal unless a transverse orientation is agreed between the purchaser and manufacturer (see [5.2](#), ISO 630-1 and the values in [Table A.10](#)).

6.5 Surface condition

See ISO 630-1.

6.6 Internal soundness

See ISO 630-1.

6.7 Dimensions, tolerances on dimensions and shape, mass

See ISO 630-1.

7 Inspection

Specific inspection is required for all grades. Refer to ISO 630-1.

8 Sampling - Frequency of testing

8.1 Verification

The verification of mechanical properties shall be by heat.

8.2 Test units

8.2.1 Annex A

The test unit shall contain products of the same form, grade, quality, delivery condition and thickness range as specified in [Table A.7](#) for the yield strength and shall be by heat and :

- 60 tons or part thereof;
- 80 tons or part thereof for heavy sections with a mass > 200 kg/m;
- 80 tons or part thereof for all sections if the mass of the cast exceeds 200 tons.

By agreement at the time of ordering, two tests by heat may be used.

8.2.2 Annex B

The test unit shall contain products of the same form, grade, quality, delivery condition, and thickness range as specified in [Table B.4](#) for the yield strength and shall be by heat and 50 tons or part thereof. By agreement at the time of ordering, two tests by heat may be used.

9 Test methods

See ISO 630-1.

10 Marking

See ISO 630-1.

Annex A
(normative)

**Steel grades S275, S355, S390, S420, S460 and S500: Chemical
composition and mechanical properties**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO/FDIS 630-3](https://standards.iteh.ai/catalog/standards/sist/9953f633-db4c-4c1a-bbbf-f1f19385c8f2/iso-fdis-630-3)

<https://standards.iteh.ai/catalog/standards/sist/9953f633-db4c-4c1a-bbbf-f1f19385c8f2/iso-fdis-630-3>