



Designation: D2827 – 10

Standard Specification for Styrene Monomer¹

This standard is issued under the fixed designation D2827; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers styrene monomer.

1.2 The following applies to all specified limits in this standard: for purposes of determining conformance with this standard, an observed value or a calculated value shall be rounded off “to the nearest unit” in the last right-hand digit used in expressing the specification limit, in accordance with the rounding-off method of Practice E29.

1.3 The values stated in SI units are to be regarded as standard.

1.4 Consult current OSHA regulations, supplier’s Material Safety Data Sheets, and local regulations for all materials used in this specification.

2. Referenced Documents

2.1 *ASTM Standards*:²

D1016 Test Method for Purity of Hydrocarbons from Freezing Points

D1209 Test Method for Color of Clear Liquids (Platinum-Cobalt Scale)

D2119 Test Method for Aldehydes in Styrene Monomer

D2121 Test Methods for Polymer Content of Styrene Monomer and AMS (α -Methylstyrene)

D2340 Test Method for Peroxides in Styrene Monomer

D3437 Practice for Sampling and Handling Liquid Cyclic Products

D4017 Test Method for Water in Paints and Paint Materials by Karl Fischer Method

D4590 Test Method for Colorimetric Determination of *p*-tert-Butylcatechol In Styrene Monomer or AMS (α -Methylstyrene) by Spectrophotometry

D5135 Test Method for Analysis of Styrene by Capillary

Gas Chromatography

D5386 Test Method for Color of Liquids Using Tristimulus Colorimetry

D6229 Test Method for Trace Benzene in Hydrocarbon Solvents by Capillary Gas Chromatography

D6304 Test Method for Determination of Water in Petroleum Products, Lubricating Oils, and Additives by Coulometric Karl Fischer Titration

D7375 Test Method for Trace Quantities of Water in Aromatic Hydrocarbons and Their Mixtures by Coulometric Karl Fischer Titration

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E1064 Test Method for Water in Organic Liquids by Coulometric Karl Fischer Titration

2.2 *Other Document*:

OSHA Regulations, 29CFR paragraphs 1910.1000 and 1910.1200³

3. Properties

3.1 Styrene monomer shall conform to the following requirements:

Property	Specification	ASTM Test Method ⁴
Purity, min, weight %	99.8 ^B	D5135
Aldehydes, max, weight % as benzaldehyde	0.0100	D2119
Peroxides, max, mg/kg as H ₂ O ₂	50	D2340
Polymer, max, mg/kg	10	D2121, Test Method A
Inhibitor, mg/kg	10 to 15 (or as required)	D4590
Ethylbenzene, max, mg/kg	500	D5135
Benzene, max, mg/kg	1	D6229
Water	If needed	D4017, D6304, D7375, or E1064
Appearance	c	...
Color, max, Pt/Co scale	10	D1209
or		
Color, max, Pt/Co scale	15	D5386

^A If more than one method is listed, the producer and user should agree on the referee method.

^B The most common impurities can be determined by Test Method D5135.

^C Clear liquid free of sediment and haze at 18.3 to 25.6°C (65 to 78°F).

³ Available from U.S. Government Printing Office Superintendent of Documents, 732 N. Capitol St., NW, Mail Stop: SDE, Washington, DC 20401, http://www.access.gpo.gov.

*A Summary of Changes section appears at the end of this standard.