



Designation: ~~B655/B655M-04~~ Designation: B655/B655M - 10

Standard Specification for Niobium-Hafnium Alloy Bar, Rod, and Wire Niobium-Hafnium Alloy Bar and Wire¹

This standard is issued under the fixed designation B655/B655M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope

1.1 This specification covers hafnium alloyed niobium ~~bar, rod, bar~~ and wire.

1.2 The material covered by this specification is R04295, niobium-base alloy containing approximately 10 % hafnium and 1 % titanium.

1.3 The values stated in either ~~inch-pound~~ SI units or ~~SI~~ inch-pound units are to be regarded separately as standard. ~~Within the text, the SI units are shown in brackets. The values stated in each system are~~ may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the ~~specification standard.~~

1.4 The following safety hazards caveat pertains only to the test methods portion, Section 14, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

B652/B652M [Specification for Niobium-Hafnium Alloy Ingots](#)

E8 [Test Methods for Tension Testing of Metallic Materials](#)

E21 [Test Methods for Elevated Temperature Tension Tests of Metallic Materials](#)

E29 [Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications](#) ~~Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications~~

E2626 [Guide for Spectrometric Analysis of Reactive and Refractory Metals](#)

3. Terminology

3.1 *Definitions:*

3.1.1 *bar*lot, n —material less than 6 in. [150 mm] in width and 0.187 in. [4.8 mm] or greater in thickness, with a rectangular or square cross section, supplied in straight lengths. —a lot is defined as that material produced from one ingot and heat treated at the same conditions. Unless otherwise agreed between manufacturer and purchaser, a lot shall be limited to the product of an 8 h period for final continuous anneal or to a single furnace load for a final batch anneal.

3.1.2 *lot*bar, n —a lot is defined as that material produced from one ingot and heat treated at the same conditions. —a hot rolled, forged, or cold worked semifinished solid section product whose cross sectional area is equal to or less than 16 sq in. [10.323 sq mm]; rectangular bar must be less than or equal to 10 in. [254 mm] in width and greater than 0.187 in. [4.8 mm] in thickness.

3.1.3 *rod*, n —material 0.125 to 2½ in. [3.2 to 64 mm] in diameter in round, hexagonal, or octagonal cross section supplied in straight lengths.

3.1.4 *wire*, n —material 0.020 to 0.1240.1875 in. [0.50 to 3-24.8 mm] in diameter furnished in coils, spools, or on reels. Material less than 0.020 in. [0.50 mm] in diameter is not covered in this specification.

4. Ordering Information

4.1 Orders for material under this specification should include the following information as applicable:

4.1.1 General alloy description (see 1.2) and ASTM designation and year of issue,

¹ This specification is under the jurisdiction of ASTM Committee B10 on Reactive and Refractory Metals and Alloys and is the direct responsibility of Subcommittee B10.03 on Niobium and Tantalum.

Current edition approved May 1, 2004-2010. Published May 2004-June 2010. Originally approved in 1979. Last previous edition approved in 1996-2004 as B655/B655M-96(1999)-B655/B655M-04. DOI: 10.1520/B0655_B0655M-104.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- 4.1.2 Quantity in weight or pieces,
- 4.1.3 Size, diameter, and length,
- 4.1.4 Chemical Composition (Section 6),
- 4.1.5 Temper (Section 7),
- 4.1.6 Mechanical test temperature and limits (Sections 8 and 14),
- 4.1.7 Permissible dimensional tolerances and weight or quantity variations (see 9.2 and 9.4),
- 4.1.8 Quality and finish (see 10.2),
- 4.1.9 Sampling (see 13.2),
- 4.1.10 Inspection witnessing (see 15.2),
- 4.1.11 Certification requirements (Section 18), and
- 4.1.12 Packaging (Section 20),

5. Materials and Manufacture

- 5.1 Materials covered by this specification shall be made from ingots in accordance with Specification B652/B652M.
- 5.2 The various niobium-hafnium alloy products covered by this specification are formed with the conventional extrusion, forging, swaging, rolling, and drawing equipment normally available in metal working plants.

6. Chemical Composition

- 6.1 The chemical composition of niobium-hafnium alloy ingots and billets for conversion to finished products covered by this specification shall conform to the requirements prescribed in Table 1. Analysis for elements, not listed in Table 1 and not normally expected in niobium-hafnium alloy, shall not be required unless specified at time of purchase.
- 6.2 The manufacturer's ingot analysis shall be considered the chemical analysis for products supplied under this specification.
- 6.3 When specified in the purchase order, the manufacturer shall test the product for elements specified in Table 2. The results of the tests shall meet the limits shown in Table 2.

7. Temper Designations

- 7.1 Unless otherwise stated, the materials supplied under this specification shall be in the annealed condition, defined as at least 90 % recrystallized.
- 7.2 Other temper designations, such as cold-worked temper or a stress-relieved temper can be specified as agreed upon between purchaser and the manufacturer at the time of purchase.

8. Mechanical Requirements Mechanical Requirements

- 7.2 Other temper designations, such as cold-worked temper or a stress-relieved temper may be specified in the purchase order.

8. Mechanical Requirements

- 8.1 Materials in the annealed condition supplied under this specification shall conform to the requirements for mechanical properties as prescribed in Table 3. Unless otherwise specified in the purchase, the materials shall conform to the requirements for room temperature mechanical properties. In lieu of or in addition to the room temperature properties, the purchaser may specify elevated temperature mechanical properties in the purchase order.

9. Permissible Variations

- 9.1 *Tolerances on Rounds*—Tolerances on niobium-hafnium alloy round products covered by this specification shall be as prescribed in Table 4.
- 9.2 *Tolerances for Square, Rectangular, or Other Shapes*—Tolerances for forged or rolled square, rectangular, or other shapes shall be as agreed upon between the purchaser and manufacturer at the time of purchase.

TABLE 1 Chemical Requirements (Ingot)

Niobium-Hafnium Alloy Grade R04295	
Element	Content, Maximum Weight %, (Except Where Otherwise Specified)
Carbon	0.015
Oxygen	0.025
Nitrogen	0.010
Hydrogen	0.0015
Hafnium	9–11
Titanium	0.7–1.3
Zirconium	0.700
Tungsten	0.500
Tantalum	0.500
Niobium by difference	