



SLOVENSKI STANDARD
SIST EN 1677-6:2001

01-december-2001

GYghUj b]`XY]`cVYg!`JUfbcgh!*`"XY.` `Yb]!`?U_cj cglb]`fUhfYX`(`

Components for slings - Safety - Part 6: Links - Grade 4

Einzelteile für Anschlagmittel - Sicherheit - Teil 6: Einzelglieder - Güteklasse 4

Accessoires pour élingues - Sécurité - Partie 6: Mailles - Classe 4

Ta slovenski standard je istoveten z: EN 1677-6:2001

SIST EN 1677-6:2001
<https://standards.iteh.ai/catalog/standards/sist/57901261-0a37-4c6a-a144-9e1d2ab549e5/sist-en-1677-6-2001>

ICS:

53.020.30 Pribor za dvigalno opremo Accessories for lifting equipment

SIST EN 1677-6:2001

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 1677-6:2001

<https://standards.iteh.ai/catalog/standards/sist/579012b1-0a37-4c6a-a144-9e1d2ab549e5/sist-en-1677-6-2001>

English version

Components for slings - Safety - Part 6: Links - Grade 4

Accessoires pour élingues - Sécurité - Partie 6: Mailles -
Classe 4

Einzelteile für Anschlagmittel - Sicherheit - Teil 6:
Einzelglieder - Güteklasse 4

This European Standard was approved by CEN on 18 February 2001.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

STANDARD PREVIEW
(standards.iteh.ai)
SIST EN 1677-6:2001
<https://standards.iteh.ai/catalog/standards/sist/579012b1-0a37-4c6a-a144-9e1d2ab549e5/sist-en-1677-6-2001>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

	Page
Foreword	3
Introduction	4
1 Scope	4
2 Normative references	4
3 Terms and definitions	5
4 Hazards	6
5 Safety requirements	7
6 Verification of safety requirements	10
7 Marking	14
8 Manufacturer's certificate	14
9 Instructions for use	14
Annex ZA (informative) Relationship of this document with EC Directives	15
Bibliography	16

iTeh STANDARD PREVIEW
(standards.iteh.ai)
<https://standards.iteh.ai/catalog/standards/sist/579012b1-0a37-4c6a-a144-9e1d2ab549e5/sist-en-1677-6-2001>

Foreword

This European Standard has been prepared by Technical Committee CEN/TC 168 "Chains, ropes, webbing, slings and accessories - Safety", the Secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2001, and conflicting national standards shall be withdrawn at the latest by October 2001.

This European Standard has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EC Directive(s).

For relationship with EC Directive(s), see informative Annex ZA, which is an integral part of this standard.

The other Parts of EN 1677 for components for slings are:

- Part 1: Forged steel components - Grade 8
- Part 2: Forged steel lifting hooks with latch - Grade 8
- Part 3: Forged steel self-locking hooks - Grade 8
- Part 4: Links - Grade 8
- Part 5: Forged steel lifting hooks with latch - Grade 4

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

ITih STANDARD PREVIEW

(standards.iteh.ai)

SIST EN 1677-6:2001

<https://standards.iteh.ai/catalog/standards/sist/579012b1-0a37-4c6a-a144-9e1d2ab549e5/sist-en-1677-6-2001>

Introduction

This European Standard has been prepared to be a harmonized standard providing one means of complying with the essential safety requirements of the Machinery Directive and associated EFTA regulations.

The links covered by this Part of EN 1677 are normally supplied to be part of a sling, but they may also be used for other applications. In such instances it is important that the link design is checked to ensure its fitness for the intended use.

The extent to which hazards are covered is indicated in the scope. In addition, lifting equipment shall conform as appropriate to EN 292 for hazards that are not covered by this standard.

1 Scope

This part of EN 1677 specifies requirements for welded steel master links, intermediate master links, master link assemblies and lower terminal links of grade 4 up to 67 t WLL, mainly for use in:

- chain slings according to EN 818-5
- steel wire rope slings according to prEN 13414-1:1998
- textile slings according to EN 1492-1, EN 1492-2.

intended for lifting objects, materials or goods.

The hazards covered by this Part of EN 1677 are identified in clause 4.

2 Normative references (standards.iteh.ai)

This European Standard incorporates, by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to, or revisions of, any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 292-1	Safety of machinery - Basic concepts - General principles for design Part 1: Basic terminology, methodology
EN 292-2:1991 /A1:1995	Safety of machinery - Basic concepts - General principles for design Part 2: Technical principles and specifications (Amendment 1: 1995)
EN 818-5:1999	Short link chain for lifting purposes – Safety - Part 5: Chain slings - Grade 4
EN 818-6	Short link chain for lifting purposes - Safety Part 6: Chain slings - Specification for information for use and maintenance to be provided by the manufacturer
EN 1050:1996	Safety of machinery - Principles for risk assessment
EN 1492-1	Textile slings – Safety - Part 1: Flat woven webbing slings made of man-made fibres.
EN 1492-2	Textile slings – Safety - Part 2: Round slings made of man-made fibres
EN 10002-2:1991	Metallic materials - Tensile test - Part 2: Verification of the force measuring system of the tensile testing machine
EN 10025:1990 +A1:1993	Hot rolled products of non-alloy structural steels — Technical delivery conditions

prEN 13414-1:1998	Steel wire ropes for slings – Safety - Part 1: Wire rope slings
EN 45012	General requirements for bodies operating assessment and certification/registration of quality systems (ISO/IEC Guide 62:1996)
EN ISO 9002:1994	Quality systems - Model for quality assurance in production, installation and servicing
ISO 643:1983	Steels - Micrographic determination of the ferritic or austenitic grain size

3 Terms and definitions

For the purposes of this Part of EN 1677, the following terms and definitions apply.

3.1

working load limit (WLL)

maximum mass that a link is authorized to sustain in general lifting service

NOTE This term has the same meaning as the term maximum working load used in the amendment to EN 292-2:1991/A1: 1995.

3.2

manufacturing proof force (MPF)

force applied to the link during the manufacturing proof test

3.3

breaking force (BF)

maximum force reached during the static tensile test of the link at which the link fails to retain the load

3.4

sling

assembly consisting of chain, wire rope or textile joined to upper and lower terminals suitable for attaching loads to the hook of a crane or other lifting machine

3.5

master link

link forming the upper terminal of a sling by means of which the sling is attached to the hook of a crane or other lifting machine

3.6

intermediate master link

link used to connect one or two legs of a sling to a master link

3.7

master link assembly

assembly consisting of a master link together with two intermediate master links

3.8

lower terminal

link, hook or other device fitted at the end of a leg of a sling, remote from the master link or upper terminal

3.9

traceability code

series of letters and/or numbers marked on a link that enable its manufacturing history, including the identity of the cast of steel used, to be traced

3.10

lot

specified number of links from which samples are selected for testing purposes, and that have been manufactured from the same cast of steel and subjected to the same heat treatment process

3.11

total ultimate elongation

total extension at the point of fracture of the link expressed as a percentage of the internal length of the test sample

3.12

competent person

designated person, suitably trained, qualified by knowledge and practical experience, and with the necessary instruction to enable the required test and examination to be carried out

NOTE 4.18 of EN ISO 9002:1994 gives guidance on training

4 Hazards

Accidental release of a load, or release of a load due to failure of a link puts at risk, either directly or indirectly, the safety or health of those persons within the danger zone.

In order to provide the necessary strength and durability of links, this Part of EN 1677 gives requirements for the design, manufacture and testing to ensure that specified levels of performance are met.

Fatigue failure has not been identified as a hazard when grade 4 links having the specified levels of performance given in this standard are used for general lifting purposes.

Since failure can be caused by the incorrect choice of grade and specification of link, this standard also gives requirements for marking and the manufacturer's certificate.

Errors in fitting can also lead to failure and this Part of EN 1677 contains dimensional requirements to allow correct fit.

Risk of injury due to sharp edges, sharp angles or rough surfaces when handling is also covered by this standard.

Those aspects of safe use associated with good practice are given in EN 818-6.

Table 1 contains those hazards, that require action to reduce risk identified by risk assessment as being specific and significant for links of grade 4.

Table 1 - Hazards and associated requirements

Hazards identified in annex A of EN 1050: 1996		Relevant clause of annex A of EN 292-2: 1991/A1: 1995	Relevant clause/subclause of this Part of EN1677
1e	Mechanical hazard due to inadequacy of strength	1.3.2	5
		4.1.2.3	5
		4.1.2.5	5
		4.2.4	5
		1.7.3	7
		1.7.4	9
1.3	Cutting hazard	1.3.4	5.4
1.8	Friction or abrasion hazard	1.3.4	5.4
15	Errors of fitting hazard	1.5.4	5.2
			9

5 Safety requirements

5.1 Design

Links shall be parallel-sided links produced by welding.

5.2 Dimensions

The internal dimensions of links covered by this Part of EN 1677 shall be such as to ensure effective articulation so that the load is transmitted axially.

The cross-section of links shall be so as to conform to 5.5.

NOTE This requirement permits a varying shape and area of cross-section.

The internal length of master links shall be $58\sqrt{WLL}$ minimum (in millimetres) and the internal width $31,5\sqrt{WLL}$ minimum (in millimetres) where the WLL is given in tonnes.

5.3 Materials and heat treatment

5.3.1 Quality of material

5.3.1.1 General

Within the limitations given in 5.3.1.2 to 5.3.1.4, the manufacturer shall select the type of steel to be used so that the finished links, when suitably heat-treated conforms to the mechanical properties specified in this Part of EN 1677.

5.3.1.2 Type of steel

The steel shall be produced by an electric process or by an oxygen blown process.

5.3.1.3 Deoxidation

The steel shall be fully killed as defined in EN 10025:1990+A1:1993 stabilized against strain age embrittlement, and have an austenitic grain size of 5 or finer when tested in accordance with ISO 643 : 1983