
**Acoustics — Determination and
application of measurement
uncertainties in building acoustics —**

**Part 1:
Sound insulation**

*Acoustique — Détermination et application des incertitudes de
mesure dans l'acoustique des bâtiments —*

Partie 1: Isolation acoustique

Document Preview

[ISO 12999-1:2020](https://standards.iteh.ai/catalog/standards/iso/cc714481-1d5a-4f84-9c68-ee35c0c1eb6/iso-12999-1-2020)

<https://standards.iteh.ai/catalog/standards/iso/cc714481-1d5a-4f84-9c68-ee35c0c1eb6/iso-12999-1-2020>



iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 12999-1:2020](https://standards.iteh.ai/catalog/standards/iso/cc714481-1d5a-4f84-9c68-eecc35c0c1eb6/iso-12999-1-2020)

<https://standards.iteh.ai/catalog/standards/iso/cc714481-1d5a-4f84-9c68-eecc35c0c1eb6/iso-12999-1-2020>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Detailed uncertainty budget.....	3
5 Uncertainty determination by inter-laboratory measurements.....	3
5.1 General.....	3
5.2 Measurement situations.....	3
5.3 Measurement conditions.....	3
5.4 Number of participating laboratories.....	4
5.5 Stating the test results of inter-laboratory measurements.....	4
5.6 Choice of test specimen.....	4
5.6.1 General.....	4
5.6.2 Use of single test specimen — Same material circulated among participants.....	4
5.6.3 Use of several test specimens taken from a production lot — Nominally identical material exchangeable among participants.....	5
5.6.4 Use of several test specimens constructed <i>in-situ</i> — Nominally identical material not exchangeable among participants.....	5
5.7 Laboratories with outlying measurement results.....	5
5.8 Verification of laboratory results by results of inter-laboratory tests.....	5
6 Uncertainties associated with single-number values.....	6
7 Standard uncertainties for typical measurands.....	7
7.1 General.....	7
7.2 Airborne sound insulation.....	7
7.3 Impact sound insulation.....	8
7.4 Reduction of transmitted impact noise by floor coverings.....	9
8 Application of the uncertainties.....	10
Annex A (informative) Example of handling uncertainties in building acoustics.....	12
Annex B (informative) Example for the calculation of the uncertainty of single number values.....	14
Annex C (informative) Detailed uncertainty budget.....	17
Annex D (informative) Upper limit for the standard deviation of reproducibility for airborne sound insulation.....	19
Bibliography.....	21

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 43, *Acoustics*, Subcommittee SC 2, *Building acoustics* in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 126, *Acoustic properties of building elements and of buildings*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 12999-1:2014), which has been technically revised.

The main changes compared to the previous edition are as follows:

- the quantity σ_{R95} was removed from [Table 2](#);
- the text in [Clause 7](#) referring to this quantity was removed and the wording adapted;
- a new [Annex D](#) was drafted with a new table containing σ_{R95} and text explaining what it is;
- new references were added.

A list of all parts in the ISO 12999 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

An assessment of uncertainties that is comprehensible and close to reality is indispensable for many questions in building acoustics. Whether a requirement is met, a laboratory delivers correct results or the acoustic properties of a product are better than the same properties of some other product can be decided only by adequately assessing the uncertainties associated with the quantities under consideration.

Uncertainties should preferably be determined following the principles of ISO/IEC Guide 98-3. This Guide specifies a detailed procedure for the uncertainty evaluation that is based upon a complete mathematical model of the measurement procedure. At the current knowledge, it seems to be impossible to formulate these models for the different quantities in building acoustics. Therefore, only the principles of such an uncertainty assessment are explained.

To come to uncertainties all the same, the concept of reproducibility and repeatability is incorporated which is the traditional approach for uncertainty determination in building acoustics. This concept offers the possibility to state the uncertainty of a method and of measurements carried out according to the method, based on the results of inter-laboratory measurements.

NOTE Whenever applicable, the terms and definitions used in this document are equivalent to those given in ISO 5725-1^[2], in ISO/IEC Guide 98-3^[2] and in ISO/IEC Guide 99^[8].

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 12999-1:2020](https://standards.iteh.ai/catalog/standards/iso/cc714481-1d5a-4f84-9c68-eec35c0c1eb6/iso-12999-1-2020)

<https://standards.iteh.ai/catalog/standards/iso/cc714481-1d5a-4f84-9c68-eec35c0c1eb6/iso-12999-1-2020>

Acoustics — Determination and application of measurement uncertainties in building acoustics —

Part 1: Sound insulation

1 Scope

This document specifies procedures for assessing the measurement uncertainty of sound insulation in building acoustics. It provides for

- a detailed uncertainty assessment;
- a determination of uncertainties by inter-laboratory tests;
- an application of uncertainties.

Furthermore, typical uncertainties are given for quantities determined according to ISO 10140 (all parts), ISO 16283 (all parts) and ISO 717 (all parts).

2 Normative references

There are no normative references in this document.

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

measurand

particular quantity subject to measurement

EXAMPLE 1 The airborne sound insulation of a particular window pane determined in accordance with ISO 10140 (all parts).

EXAMPLE 2 The standardized level difference of a particular facade according to ISO 16283-3.

3.2

measurement result

value attributed to a *measurand* (3.1), obtained by following the complete set of instructions given in a measurement procedure

Note 1 to entry: The measurement result may be a frequency band level or a single number value determined according to the rating procedures of ISO 717 (all parts).

**3.3
uncertainty**

parameter, associated with the *measurement result* (3.2), that characterizes the dispersion of the values that can reasonably be attributed to the *measurand* (3.1)

**3.4
standard uncertainty**

u
uncertainty (3.3) of the *measurement result* (3.2) expressed as a standard deviation

**3.5
combined standard uncertainty**

u_c
standard uncertainty (3.4) of the result of a measurement when that result is obtained from the values of a number of other quantities, equal to the positive square root of a sum of terms, the terms being the variances or covariances of these other quantities weighted according to how the *measurement result* (3.2) varies with changes in these quantities

**3.6
expanded uncertainty**

U
quantity defining an interval about the *measurement result* (3.2) that can be expected to encompass a large fraction of the distribution of values that can reasonably be attributed to the *measurand* (3.1)

**3.7
coverage factor**

k
numerical factor used as a multiplier of the *combined standard uncertainty* (3.5) in order to obtain an *expanded uncertainty* (3.6)

**3.8
repeatability condition**

condition of measurement that includes the same measurement procedure, same operators, same measuring system, same location (laboratory or usual building), and replicate measurements on the same object over a short period of time

**3.9
repeatability standard deviation**

σ_r
standard deviation of *measurement results* (3.2) obtained under *repeatability conditions* (3.8)

**3.10
reproducibility condition**

condition of measurement that includes the same measurement procedure, different locations (laboratories or usual buildings), operators, measuring systems, and replicate measurements on the same or similar objects

**3.11
reproducibility standard deviation**

σ_R
standard deviation of *measurement results* (3.2) obtained under *reproducibility conditions* (3.10)

**3.12
in-situ condition**

condition of measurement that includes the same location (laboratory or usual building), and replicate measurements on the same object by different operators using different measuring systems

3.13

***in-situ* standard deviation**

σ_{situ}

standard deviation of *measurement results* (3.2) obtained under *in-situ conditions* (3.12)

4 Detailed uncertainty budget

The derivation of a detailed uncertainty budget is desirable to find out which uncertainty contributions are the most important ones and how these contributions can be reduced. Furthermore, such a budget reflects the individual sound fields during the measurement. Consequently, the uncertainty is valid for an individual measurement result and not for a whole family of results. Annex C gives provisions on the derivation of such uncertainty budgets.

5 Uncertainty determination by inter-laboratory measurements

5.1 General

Standard deviations determined by inter-laboratory measurements may serve as an estimate for the standard uncertainty. The general concept and the procedure for determining these standard deviations are given in ISO 5725-1 and ISO 5725-2, respectively. As many operators and laboratories as possible should participate in such inter-laboratory measurements in order to obtain reliable results.

5.2 Measurement situations

In building acoustics, three different measurement situations are to be distinguished.

- a) Situation A is that a building element is characterized by laboratory measurements. In this case, the measurand is defined by the relevant part of ISO 10140, including all additional requirements, e.g. for the measurement equipment and especially for the test facilities. Therefore, all measurement results that are obtained in another test facility or building also comply with this definition. The standard uncertainty, thus, is the standard deviation of reproducibility as determined by inter-laboratory measurements.
- b) Situation B is described by the case that different measurement teams come to the same location to carry out measurements. The location may be a usual building or a test facility. The measurand, thus, is a property of one particular element in one particular test facility or the property of a building. The main difference from situation A is that many aspects of the airborne and structure-borne sound fields involved remain constant since the physical construction is unchanged. The standard uncertainty obtained for this situation is called *in-situ* standard deviation.
- c) Situation C applies to the case when the measurement is simply repeated in the same location by the same operator using the same equipment. The location may be a usual building or a test facility. The standard uncertainty is the standard deviation of repeatability as determined by inter-laboratory measurements.

5.3 Measurement conditions

The acoustical measurement conditions for determining the different standard deviations shall correspond to the conditions given in the standardized measurement procedures. The test specimen shall not be remounted between repeated measurements.

Each laboratory shall use its normal measurement procedure when participating in an inter-laboratory measurement. No deviations from the test procedure laid down shall occur but repeating the measurements several times, the parameters left open in the measurement procedure shall be represented as well as possible. In particular, the set of microphone positions and source positions over which averaging is carried out for one measurement shall be selected anew, more or less randomly,

for each repeated measurement. This is necessary to obtain a mean value and a standard deviation of repeatability that represent the situation correctly.

Before the inter-laboratory measurement is started, each participating laboratory shall report the exact details of its test procedure.

Additional requirements for carrying out inter-laboratory measurements for the test specimen chosen shall be laid down in detail. This refers in particular to the following items:

- quantities being measured and reported, rules for rounding numbers;
- number of repeated measurements required;
- calibration of the measurement equipment;
- mounting and sealing conditions of the test specimen, and curing time where appropriate.

5.4 Number of participating laboratories

The number of laboratories, p , shall, from a statistical point of view, be at least eight, but is preferable to exceed this number in order to reduce the number of replicate measurements required. The number of measurements in each laboratory, n , should be so chosen that $p(n - 1) \geq 35$. In addition, at least five test results are needed for each laboratory. If the number n of measurements is different among the participating laboratories, a mean number of measurements shall be calculated and used (see ISO 5725-2). The measurement results obtained shall not be pre-selected in any way by the participating laboratories before they are reported.

5.5 Stating the test results of inter-laboratory measurements

In order to simplify the evaluation of measurement results reported, it is strongly desirable to supply forms for filling in by the participants. For the statistical analysis, it is important to report special observations and/or any irregularities observed during the test.

5.6 Choice of test specimen

5.6.1 General

The kind of test specimen used for an inter-laboratory measurement depends not only on the quantity being tested (i.e. airborne sound reduction index, normalized impact sound pressure level) but specifically on the mounting and measurement conditions for which the standard deviation of repeatability and reproducibility are being obtained (e.g. walls, floors, windows). Effects influencing the measurement result, like ageing or a strong dependence on humidity or temperature, shall also be considered.

The choice of test specimen also depends on practical considerations. In general, three different approaches (see 5.6.2 to 5.6.4) depending on the type of measurement method and/or on the type of specimen can be appropriate.

5.6.2 Use of single test specimen — Same material circulated among participants

For checking the measurement procedure and the facilities in different laboratories, ideally, the same test specimen should be used by all participants in the inter-laboratory measurement and checked again by the first laboratory at the end of the inter-laboratory measurement.

In building acoustics, this procedure is often not feasible due to the long period of time required, the risk of damage or change of the test specimen and different sizes of test openings. However, the variability resulting from the use of more than one test specimen is avoided and the standard deviation of reproducibility thus obtained is characteristic for the test facility and measurement procedure alone.