

---

**Korozija kovin in zlitin - Pospešeni (stopnjevani) ciklični korozijski preskusi z izpostavljanjem sintetični morski vodi s postopkom nanašanja soli - "Suhi" in "mokri" pogoji pri konstantni absolutni vlažnosti (ISO 16539:2013)**

Corrosion of metals and alloys - Accelerated cyclic corrosion tests with exposure to synthetic ocean water salt-deposition process - "Dry" and "wet" conditions at constant absolute humidity (ISO 16539:2013)

Korrosion von Metallen und Legierungen - Beschleunigte zyklische Korrosionsprüfungen unter Aussetzung von synthetischem Meerwassersalz im Absetzungsprozess - "Trockene" und "feuchte" Bedingungen, bei einer konstanten absoluten Feuchtigkeit (ISO 16539:2013)

Corrosion des métaux et alliages - Essais de corrosion cyclique accélérée avec exposition à l'eau de mer synthétique par procédé de dépôt de sel - Conditions "sèches" et conditions "humides" à taux d'humidité absolue constant (ISO 16539:2013)

**Ta slovenski standard je istoveten z: prEN ISO 16539**

---

**ICS:**

77.060

Korozija kovin

Corrosion of metals

**oSIST prEN ISO 16539:2022****en,fr,de**

**iTeh STANDARD  
PREVIEW  
(standards.iteh.ai)**

[oSIST prEN ISO 16539:2022](https://standards.iteh.ai/catalog/standards/sist/991b3a56-562e-4015-b759-633076484257/osist-pren-iso-16539-2022)

<https://standards.iteh.ai/catalog/standards/sist/991b3a56-562e-4015-b759-633076484257/osist-pren-iso-16539-2022>

INTERNATIONAL  
STANDARD

ISO  
16539

First edition  
2013-03-01

---

---

**Corrosion of metals and alloys —  
Accelerated cyclic corrosion tests  
with exposure to synthetic ocean  
water salt-deposition process — “Dry”  
and “wet” conditions at constant  
absolute humidity**

*Corrosion des métaux et alliages — Essais de corrosion cyclique  
accélérée avec exposition à l'eau de mer synthétique par procédé de  
dépôt de sel — Conditions “sèches” et conditions “humides” à taux  
d'humidité absolue constant*

[oSIST prEN ISO 16539:2022](https://standards.iteh.ai/catalog/standards/sist/991b3a56-562e-4015-b759-633076484257/osist-pren-iso-16539-2022)

[https://standards.iteh.ai/catalog/standards/sist/991b3a56-  
562e-4015-b759-633076484257/osist-pren-iso-16539-  
2022](https://standards.iteh.ai/catalog/standards/sist/991b3a56-562e-4015-b759-633076484257/osist-pren-iso-16539-2022)



Reference number  
ISO 16539:2013(E)

© ISO 2013

**iTeh STANDARD  
PREVIEW  
(standards.iteh.ai)**

[oSIST prEN ISO 16539:2022](https://standards.iteh.ai/catalog/standards/sist/991b3a56-562e-4015-b759-633076484257/osist-pren-iso-16539-2022)

<https://standards.iteh.ai/catalog/standards/sist/991b3a56-562e-4015-b759-633076484257/osist-pren-iso-16539-2022>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2013

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
Foreword.....	iv
Introduction.....	v
<b>1 Scope.....</b>	<b>1</b>
<b>2 Normative references.....</b>	<b>1</b>
<b>3 Test solution.....</b>	<b>2</b>
3.1 Preparation of the mixed salt solution.....	2
3.2 pH adjustment.....	2
3.3 Preparation of the test solution.....	2
<b>4 Apparatus.....</b>	<b>3</b>
4.1 Component protection.....	3
4.2 Exposure cabinet.....	3
4.3 Salt deposition device.....	3
4.4 Temperature and humidity control device.....	3
4.5 Rinse treatment of specimens.....	3
4.6 Types of apparatus.....	3
<b>5 Test specimens.....</b>	<b>4</b>
<b>6 Salt deposition measurement method.....</b>	<b>4</b>
<b>7 Arrangement of the test specimens.....</b>	<b>4</b>
<b>8 Operating conditions and procedure.....</b>	<b>4</b>
<b>9 Treatment of specimens after test.....</b>	<b>9</b>
<b>10 Continuity of tests.....</b>	<b>9</b>
<b>11 Duration of tests.....</b>	<b>9</b>
<b>12 Evaluation of results.....</b>	<b>9</b>
<b>13 Test report.....</b>	<b>9</b>
<b>Annex A (informative) Combined cyclic test instrument with salt deposition unit (two cabinets).....</b>	<b>11</b>
<b>Annex B (informative) Combined cyclic test instrument with salt deposition unit (one cabinet).....</b>	<b>12</b>
<b>Annex C (informative) Salt deposition method by manual spraying.....</b>	<b>13</b>
<b>Annex D (informative) Recommended periods of testing.....</b>	<b>15</b>
<b>Annex E (informative) Methods for evaluation of corrosivity of test.....</b>	<b>17</b>
<b>Bibliography.....</b>	<b>19</b>

**ISO 16539:2013(E)****Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 16539 was prepared by Technical Committee ISO/TC 156, *Corrosion of metals and alloys*.

**iTeh STANDARD  
PREVIEW  
(standards.iteh.ai)**

[oSIST prEN ISO 16539:2022](https://standards.iteh.ai/catalog/standards/sist/991b3a56-562e-4015-b759-633076484257/osist-pren-iso-16539-2022)

<https://standards.iteh.ai/catalog/standards/sist/991b3a56-562e-4015-b759-633076484257/osist-pren-iso-16539-2022>

## Introduction

Corrosion of metallic materials, with or without corrosion protection, is influenced by many environmental factors, the importance of which can vary with the type of metallic materials and with the type of environment. It is impossible, therefore, to design accelerated laboratory corrosion tests in such a way that all environmental factors influencing resistance to corrosion are taken into account. Laboratory tests are, therefore, designed to simulate the effects of most important factors, which enhance the corrosion of metallic materials.

The accelerated corrosion tests described in this International Standard are designed to simulate and enhance the environmental influence on a metallic material of exposure to outdoor climates, where exposure to salt-contaminated conditions occurs and can promote corrosion. It has been prepared by reference to technical papers and reports (see the Bibliography).

The particular advantages of two tests described in this International Standard over conventional accelerated tests, such as the neutral salt spray test (NSS) as specified in ISO 9227 and the wet (salt fog)/dry/humidity test as specified in ISO 14993, lies in their better ability to reproduce the corrosion that occurs in atmospheric environments which contain much sea salt.

Accelerated corrosion tests to simulate atmospheric corrosion in such environments are intended/expected to include the following requirements.

- a) Constant absolute humidity: It is generally observed that temperature and relative humidity change under a constant absolute humidity in outdoor environments. The water absorption of deposited salts is an important factor affecting atmospheric corrosion behaviour. The same relationship, constant absolute humidity, as an actual environment is intended/expected to exist for temperature and relative humidity during dry/wet cycles.
- b) Control of the amount of salt deposition: The amount of the salt deposition on test specimens is intended/expected to be changed according to the corrosivity of the atmosphere in which the tested metallic material can be used. A salt-containing test solution is intended/expected to be diluted or the spraying time is intended/expected to be adjusted to provide the same yearly average amount of the salt deposition as an actual environment.

Therefore, the tests described in this International Standard involve the salt deposition and cyclic dry/wet conditions under a constant absolute humidity.

The results obtained do not permit far-reaching conclusions on the corrosion resistance of the tested metallic material under the whole range of environmental conditions in which it can be used. Nevertheless, the tests provide valuable information on the relative performance of materials exposed to salt-contaminated environments similar to those used in the tests.

The International Organization for Standardization (ISO) draws attention to the fact that it is claimed that compliance with this International Standard can involve the use of a patent concerning the tests given in [Clause 8](#), [Table 3](#), and [Figure 2](#).

ISO takes no position concerning the evidence, validity, and scope of this patent right.

The holder of this patent right has ensured the ISO that he/she is willing to negotiate licences under reasonable and non-discriminatory terms and conditions with applicants throughout the world. In this respect, the statement of the holder of this patent right is registered with ISO. Information can be obtained from:

JFE Steel Corporation

2-2-3, Uchisaiwaicho, Chiyoda-ku, Tokyo 100-0011, JAPAN

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights other than those identified above. ISO shall not be held responsible for identifying any or all such patent rights.

**iTeh STANDARD  
PREVIEW  
(standards.iteh.ai)**

[oSIST prEN ISO 16539:2022](https://standards.iteh.ai/catalog/standards/sist/991b3a56-562e-4015-b759-633076484257/osist-pren-iso-16539-2022)

<https://standards.iteh.ai/catalog/standards/sist/991b3a56-562e-4015-b759-633076484257/osist-pren-iso-16539-2022>



# Corrosion of metals and alloys — Accelerated cyclic corrosion tests with exposure to synthetic ocean water salt-deposition process — “Dry” and “wet” conditions at constant absolute humidity

## 1 Scope

This International Standard specifies two accelerated corrosion test procedures, Methods A and B, for the evaluation of corrosion behaviour of surface-treated metals and their alloys with and without paint on them in atmospheric environments. It also specifies the apparatus used. The two tests involve salt deposition and dry/wet conditions at a constant absolute humidity.

Method A applies to:

metals and their alloys (including corrosion-resistance alloys)

Method B applies to:

metals and their alloys

metals and their alloys with coatings [including metallic coatings (anodic or cathodic), organic coatings, and conversion coatings]

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4628-1, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 1: General introduction and designation system*

ISO 4628-2, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 2: Assessment of degree of blistering*

ISO 4628-3, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 3: Assessment of degree of rusting*

ISO 4628-4, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 4: Assessment of degree of cracking*

ISO 4628-5, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 5: Assessment of degree of flaking*

ISO 8407, *Corrosion of metals and alloys — Removal of corrosion products from corrosion test specimens*

ISO 8993, *Anodizing of aluminium and its alloys — Rating system for the evaluation of pitting corrosion — Chart method*

ISO 9227, *Corrosion tests in artificial atmospheres — Salt spray tests*

ISO 10289, *Methods for corrosion testing of metallic and other inorganic coatings on metallic substrates — Rating of test specimens and manufactured articles subjected to corrosion tests*

## ISO 16539:2013(E)

ISO 11130, *Corrosion of metals and alloys — Alternate immersion test in salt solution*

ISO 14993, *Corrosion of metals and alloys — Accelerated testing involving cyclic exposure to salt mist, “dry” and “wet” conditions*

ISO 17872, *Paints and varnishes — Guidelines for the introduction of scribe marks through coatings on metallic panels for corrosion testing*

### 3 Test solution

#### 3.1 Preparation of the mixed salt solution

The mass of reagents shown in [Table 1](#) shall be dissolved in distilled water or deionized water, with a conductivity of not higher than 20  $\mu\text{S}/\text{cm}$  at  $25\text{ }^\circ\text{C} \pm 2\text{ }^\circ\text{C}$ , to produce a mixed salt solution with a concentration of  $36,0\text{ g/l} \pm 3,6\text{ g/l}$ .

The composition of the mixed salt solution is the same as typical synthetic ocean water shown in ISO 11130:2010, A.3 (test solution for simulating the corrosive effects of ocean water).

**Table 1 — Reagents and their concentrations of a mixed salt solution**

Reagents	Concentration (g/l)
NaCl	24,53
MgCl <sub>2</sub>	5,20
Na <sub>2</sub> SO <sub>4</sub>	4,09
CaCl <sub>2</sub>	1,16
KCl	0,695
NaHCO <sub>3</sub>	0,201
KBr	0,101
H <sub>3</sub> BO <sub>3</sub>	0,027
SrCl <sub>2</sub>	0,025
NaF	0,003

WARNING – Handling of SrCl<sub>2</sub> and NaF can be hazardous and shall be restricted to use by skilled chemists or conducted under their control.

#### 3.2 pH adjustment

To adjust the pH of the solution,  $5,0\text{ g} \pm 0,5\text{ g}$  of NaOH shall be dissolved in water and diluted to total volume of 1 L to make 0,125 mol/l NaOH solution. It shall be added to the mixed salt solution to adjust the pH to  $8,2 \pm 0,1$  at  $25\text{ }^\circ\text{C} \pm 2\text{ }^\circ\text{C}$ .

#### 3.3 Preparation of the test solution

The test solution shall be used as the mixed salt solution or shall be diluted by 1:10 and 1:100 to the mixed salt solution with a concentration of  $36,0\text{ g/l} \pm 3,6\text{ g/l}$ ,  $3,60\text{ g/l} \pm 0,36\text{ g/l}$ , and  $0,360\text{ g/l} \pm 0,036\text{ g/l}$ . When not specified, the concentration shall be agreed by the interested parties.

## 4 Apparatus

### 4.1 Component protection

All components in contact with the test solution shall be made of, or lined with, materials resistant to corrosion by the test solution and which do not influence the corrosivity of the atomized test solution. The apparatus shall include the components described in the following.

### 4.2 Exposure cabinet

It is essential that temperature and humidity in exposure cabinet are controlled constantly.

### 4.3 Salt deposition device

The atomizer shall be made of corrosion resistant materials, e.g. glass, plastic, or titanium. The atomized test solution shall be deposited homogeneously on specimens. The amount of deposited test solution shall be controlled. The diameter of the atomized test solution should be equal to or less than 100  $\mu\text{m}$ .

The amount of deposited test solution can be controlled in the following manners:

- a) by controlling the test period with a continuous atomization;
- b) by controlling the amount of test solution, the atomized pressure, and the moving speed of the atomizer.

The compressed air supplied to the atomizer shall be passed through a filter to remove all trace of oil or solid matter.

### 4.4 Temperature and humidity control device

The device shall be capable of detecting and controlling the temperature and humidity around specimens. In the transition period of temperature and humidity, the device shall be capable of controlling the dry bulb temperature linear to target value and test period. The device shall be capable of controlling the humidity by keeping the absolute humidity constant to dry bulb temperature at least in every minute.

### 4.5 Rinse treatment of specimens

After the temperature and humidity cycle, the rinse treatment is conducted before re-depositing the test solution. Firstly, the test specimens are washed with drinking water, and then with deionized water. Water drops are then removed carefully with clean air in order not to take off corrosion products from the surface of the test specimens.

### 4.6 Types of apparatus

The following are three types of apparatus that satisfy the requirements specified in 4.1 to 4.5.

- a) Two-cabinet type (automatic procedures)

Specimens move between salt deposition cabinet and exposure cabinet. The atomizer moves front to back and side to side, making it possible to change the amount of salt deposition on each specimen. Then, the specimens are moved to the exposure cabinet and wet/dry cycles and rinse treatment are conducted automatically (see [Annex A](#)).

- b) One-cabinet type (automatic procedures)

Specimens are settled in one cabinet. The atomizer is set, and wet/dry cycles and rinse treatment are conducted automatically (see [Annex B](#)).

- c) One-cabinet type (manual procedures)