



Designation: D7405 – 10a

Standard Test Method for Multiple Stress Creep and Recovery (MSCR) of Asphalt Binder Using a Dynamic Shear Rheometer^{1,2}

This standard is issued under the fixed designation D7405; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope

1.1 This test method covers the determination of percent recovery and non-recoverable creep compliance of asphalt binders by means of Multiple Stress Creep and Recovery (MSCR) testing. The MSCR test is conducted using the Dynamic Shear Rheometer (DSR) at a specified temperature.

1.2 This standard is appropriate for unaged material, material aged in accordance with Test Method D2872 (RTFO), material aged in accordance with Practice D6521 (PAV), and material aged in accordance with both Test Method D2872 and Practice D6521.

NOTE 1—The majority of development work on this test method was performed on material aged in accordance with Test Method D2872 (RTFO).

1.3 The percent recovery is intended to provide a means to determine the presence of elastic response and stress dependence of polymer modified and unmodified asphalt binders.

1.4 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:³

C670 Practice for Preparing Precision and Bias Statements for Test Methods for Construction Materials

D8 Terminology Relating to Materials for Roads and Pavements

D2872 Test Method for Effect of Heat and Air on a Moving Film of Asphalt (Rolling Thin-Film Oven Test)

D5801 Test Method for Toughness and Tenacity of Bituminous Materials

D6084 Test Method for Elastic Recovery of Asphalt Materials by Ductilometer

D6373 Specification for Performance Graded Asphalt Binder

D6521 Practice for Accelerated Aging of Asphalt Binder Using a Pressurized Aging Vessel (PAV)

D7175 Test Method for Determining the Rheological Properties of Asphalt Binder Using a Dynamic Shear Rheometer

2.2 AASHTO Standards:⁴

M 320 Specification for Performance-Graded Asphalt Binder

TP 70 Test Method for Multiple Stress Creep and Recovery (MSCR) of Asphalt Binder Using a Dynamic Shear Rheometer

3. Terminology

3.1 *Definitions*—For definitions of general terms used in this standard, refer to Terminology D8.

3.1.1 *creep and recovery, n*—a standard rheological test protocol whereby a specimen is subjected to a constant load for a fixed time period then allowed to recover at zero load for a fixed time period.

3.1.2 *non-recoverable creep compliance (J_{nr}), n*—the residual strain in a specimen after a creep and recovery cycle divided by the stress applied in kPa.

4. Summary of Test Method

4.1 This test method is used to determine the presence of elastic response in an asphalt binder under shear creep and recovery at two stress levels at a specified temperature. For performance grade (PG) binders, the specified temperature will

¹ This test method is under the jurisdiction of ASTM Committee D04 on Road and Paving Materials and is the direct responsibility of Subcommittee D04.44 on Rheological Tests.

Current edition approved June 1, 2010. Published June 2010. Originally approved in 2008. Last previous edition approved in 2010 as D7405 – 10. DOI: 10.1520/D7405-10A.

² This test method is based on a work product of the Federal Highway Administration. A similar standard is published as AASHTO TP 70.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

⁴ Available from American Association of State Highway and Transportation Officials (AASHTO), 444 N. Capitol St., NW, Suite 249, Washington, DC 20001, <http://www.transportation.org>.

typically be the PG grade upper temperature as determined in Specification **D6373** or AASHTO M 320. Sample preparation and apparatus are in accordance with Test Method **D7175** using the 25 mm parallel plate geometry with a 1-mm gap setting. The sample is loaded at constant stress for 1 s then allowed to recover for 9 s. Ten creep and recovery cycles are run at 0.100 kPa creep stress followed by ten at 3.200 kPa creep stress.

5. Significance and Use

5.1 This test method is used to identify the presence of elastic response in a binder and the change in elastic response at two different stress levels. Non-recoverable creep compliance has been shown to be an indicator of the resistance of an asphalt binder to permanent deformation under repeated load.

5.2 This test method is also useful as a surrogate for other test methods used to measure elasticity in asphalt binders such as Test Method **D5801** (Toughness and Tenacity), Test Method **D6084** (Elastic Recovery), and Test Method **D7175** (DSR phase angle).

6. Apparatus

6.1 *Dynamic Shear Rheometer (DSR)*—A dynamic shear rheometer as described in the Apparatus section of Test Method **D7175** and associated materials as described in the Materials section of Test Method **D7175**. The rheometer shall run in stress control mode.

7. Preparation of Test Specimen

7.1 Prepare the test specimen in accordance with the Preparing Test Specimens section of Test Method **D7175**.

NOTE 2—This test may be run on a specimen previously tested in dynamic shear in accordance with the Test Procedure section of Test Method **D7175**.

8. Procedure

8.1 Allow the specimen to reach thermal equilibrium at the desired test temperature in accordance with the Test Procedure section of Test Method **D7175**. If the specimen has previously been tested in dynamic shear, allow the specimen to remain unloaded for at least one minute before starting the creep and recovery test.

8.2 Load the specimen at a constant creep stress of 0.100 kPa for 1.00 second duration creep and follow with a zero stress recovery of 9.00 second duration. The commanded full torque for each creep cycle shall be achieved within 0.003 seconds from the start of the creep cycle as certified by the equipment manufacturer. Record the stress and strain at least every 0.10 seconds for the creep cycle and at least every 0.45 seconds for the recovery cycle on a running accumulated time such that, in addition to other data points, data points at 1.00 s and 10.00 s for each cycle's local time are explicitly recorded.

8.2.1 If the DSR does not record the strain at exactly 1.00 and 10.00 seconds then the DSR software shall extrapolate prior data to determine the strain value at the required time. Extrapolation data shall include a measured data point no more than 0.05 s prior to the required time for a creep cycle, no more than 0.30 s prior to the required time for a recovery cycle.

NOTE 3—If the creep and recovery curves will be used for modeling,

more frequent data points may be required.

8.3 Allowing no rest period between cycles, repeat the creep and recovery cycle in **8.2** nine times for a total of ten cycles.

8.4 Allowing no rest period following **8.3**, repeat the ten creep and recovery cycles of **8.2** and **8.3** utilizing a load of 3.200 kPa.

NOTE 4—The total time required to complete the two-step creep and recovery test is 200 seconds.

8.5 For each of the twenty creep and recovery cycles record the following:

8.5.1 Initial strain value at the beginning of the creep portion of each cycle. This strain shall be denoted as ϵ_0 .

8.5.2 The strain value at the end of the creep portion (that is, after 1.0 s) of each cycle. This strain shall be denoted as ϵ_c .

8.5.3 The adjusted strain value at the end of creep portion (that is, after 1.0 s) of each cycle:

$$\epsilon_1 = \epsilon_c - \epsilon_0 \quad (1)$$

8.5.4 The strain value at the end of the recovery portion (that is, after 10.0 s) of each cycle. This strain shall be denoted as ϵ_r .

8.5.5 The adjusted strain value at the end of recovery portion (that is, after 10.0 s) of each cycle:

$$\epsilon_{10} = \epsilon_r - \epsilon_0 \quad (2)$$

9. Calculation

9.1 Using the results obtained in **8.5** determine the average percent recovery and non-recoverable creep compliance for the asphalt binder at creep stress levels of 0.100 kPa and 3.200 kPa as follows:

9.1.1 For each of the ten cycles at a creep stress of 0.100 kPa calculate the percent recovery, $\epsilon_r(100, N)$, for $N = 1$ to 10:

$$\epsilon_r(100, N) = \frac{(\epsilon_1 - \epsilon_{10}) \cdot 100}{\epsilon_1} \quad (3)$$

9.1.2 For each of the ten cycles at a creep stress of 3.200 kPa calculate the percent recovery, $\epsilon_r(3200, N)$, for $N = 1$ to 10:

$$\epsilon_r(3200, N) = \frac{(\epsilon_1 - \epsilon_{10}) \cdot 100}{\epsilon_1} \quad (4)$$

9.1.3 Calculate average percent recovery at 0.100 kPa:

$$R_{100} = \text{SUM}(\epsilon_r(100, N))/10 \quad \text{for } N = 1 \text{ to } 10 \quad (5)$$

9.1.4 Calculate average percent recovery at 3.200 kPa:

$$R_{3200} = \text{SUM}(\epsilon_r(3200, N))/10 \quad \text{for } N = 1 \text{ to } 10 \quad (6)$$

9.1.5 Calculate percent difference in recovery between 0.100 kPa and 3.200 kPa:

$$R_{diff} = ((R_{100} - R_{3200}) \cdot 100)/(R_{100}) \quad (7)$$

9.1.6 For each of the ten cycles at a creep stress of 0.100 kPa calculate the non-recoverable creep compliance, $J_{nr}(100, N)$, for $N = 1$ to 10:

$$J_{nr}(100, N) = \frac{\epsilon_{10}}{100} \quad (8)$$

9.1.7 For each of the ten cycles at a creep stress of 3.200 kPa calculate the non-recoverable creep compliance, $J_{nr}(3200, N)$, for $N = 1$ to 10: