



Designation: B565 – 04(Reapproved 2010)

Standard Test Method for Shear Testing of Aluminum and Aluminum-Alloy Rivets and Cold-Heading Wire and Rods¹

This standard is issued under the fixed designation B565; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This test method covers the double shear testing of aluminum and aluminum alloy rivets with round, solid shanks and cold-heading wire and rod.²

NOTE 1—Exceptions to this test method may be necessary in individual specifications or methods for tests for a particular material.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 The latest issues of the following documents form a part of this standard to the extent referenced herein:

2.2 *ASTM Standards:*³

B316/B316M Specification for Aluminum and Aluminum-Alloy Rivet and Cold-Heading Wire and Rods

B769 Test Method for Shear Testing of Aluminum Alloys

B831 Test Method for Shear Testing of Thin Aluminum Alloy Products

E4 Practices for Force Verification of Testing Machines

E6 Terminology Relating to Methods of Mechanical Testing

¹ This test method is under the jurisdiction of ASTM Committee B07 on Light Metals and Alloys and is under the jurisdiction of Subcommittee B07.05 on Testing. Current edition approved May 1, 2010. Published June 2010. Originally approved in 1972. Last previous edition approved in 2004 as B565 – 04. DOI: 10.1520/B0565-04R10.

² This product is covered by Specification B316/B316M.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3. Terminology

3.1 *General*—The definitions of terms relating to shear testing in Terminology E6 are applicable to the terms used in this test method.

4. Summary of Test Method

4.1 The test consists of subjecting a length of wire or rod or a rivet in full cross section, or a machined length of rod or rivet, to double-shear loading, with a suitable test device in a tension testing machine, and determining the shear stress required to fracture the specimen (that is, the shear strength).

5. Significance and Use

5.1 This test method is intended solely for the shear testing of rivets and cold-heading wire and rod, and is not generally recommended for the determination of the shear strength of other products. For rivets, this method is limited to rivets having a shank length equal to or greater than $2d$.

NOTE 2—The results of shear tests of specimens machined from products other than wire, rod, and rivets may be greatly dependent upon the orientation of the specimen within the original test material, and the direction in which the force is applied relative to the grain flow in the specimen.⁴ It is recommended that shear strengths of other products be determined by Test Method B769 for products greater than 0.250 in. (6.4 mm) and Test Method B831 for products less than 0.250 in. (6.4 mm). Shear strengths developed by this test method have been shown to vary from those developed by other methods.⁴ If Test Method B565 is used for shear testing of other products, variables such as those described in Test Method B769 should be identified and controlled.

5.2 The results of shear tests are dependent upon the relative and absolute lengths of specimen which are sheared out, and those which are supported.⁴ The results of tests made in accordance with this method should not be directly compared with those determined in other types of tests in which the methods of loading and supporting the specimen are different.

5.3 The presence of a lubricant on the surfaces of the specimen and device may result in shear strengths up to 3 % lower than those determined in the absence of lubrication.

⁴ Kaufman, J. G., and Davies, R. E. "Effects of Test Method and Specimen Orientation on Shear Strengths of Aluminum Alloys," *ASTM Proceedings*, ASTEA, Am. Soc. Testing Mats., Vol 64, 1964.