



Designation: ~~D2103-08~~ Designation: D2103 - 10

## Standard Specification for Polyethylene Film and Sheeting<sup>1</sup>

This standard is issued under the fixed designation D2103; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope\*

1.1 This specification covers the classification of polyethylene film and sheeting up to 0.3 mm (0.012 in.) in thickness, inclusive. The film or sheeting may contain additives for the improvement of the surface properties, pigments, or stabilizers, or combinations thereof.

1.2 The values stated in SI units are to be regarded as standard. The values given in brackets are for information only.

1.3 The following precautionary caveat pertains only to the test method portion, Section 8, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.4 This specification allows for the use of recycled polyethylene film or resin as feedstock, in whole or in part, as long as all the requirements as governed by the producer and end user are also met (see Note 1).

NOTE 1—Guide D7209 describes terminology and definitions related to recycled plastics.

NOTE 2—There is no known ISO equivalent to this specification.

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>2</sup>

D374 Test Methods for Thickness of Solid Electrical Insulation

D618 Practice for Conditioning Plastics for Testing

D792 Test Methods for Density and Specific Gravity (Relative Density) of Plastics by Displacement

D882 Test Method for Tensile Properties of Thin Plastic Sheeting

D883 Terminology Relating to Plastics

D1003 Test Method for Haze and Luminous Transmittance of Transparent Plastics

D1434 Test Method for Determining Gas Permeability Characteristics of Plastic Film and Sheeting

D1505 Test Method for Density of Plastics by the Density-Gradient Technique

D1709 Test Methods for Impact Resistance of Plastic Film by the Free-Falling Dart Method [17ac33/astm-d2103-10](#)

D1746 Test Method for Transparency of Plastic Sheeting ~~D1893 Test Method for Blocking of Plastic Film~~

D1894 Test Method for Static and Kinetic Coefficients of Friction of Plastic Film and Sheeting

D1922 Test Method for Propagation Tear Resistance of Plastic Film and Thin Sheeting by Pendulum Method

D1938 Test Method for Tear-Propagation Resistance (Trouser Tear) of Plastic Film and Thin Sheeting by a Single-Tear Method

D2457 Test Method for Specular Gloss of Plastic Films and Solid Plastics

D2578 Test Method for Wetting Tension of Polyethylene and Polypropylene Films

D2839 Practice for Use of a Melt Index Strand for Determining Density of Polyethylene

D3892 Practice for Packaging/Packing of Plastics

D4321 Test Method for Package Yield of Plastic Film

D4703 Practice for Compression Molding Thermoplastic Materials into Test Specimens, Plaques, or Sheets

D4976 Specification for Polyethylene Plastics Molding and Extrusion Materials

D7209 Guide for Waste Reduction, Resource Recovery, and Use of Recycled Polymeric Materials and Products

E96/E96M Test Methods for Water Vapor Transmission of Materials

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.19 on Film and Sheeting. Current edition approved Nov. 1, 2008. Published November 2008. Originally approved in 1962. Last previous edition approved in 2005 as D2103-05. DOI: [10.1520/D2103-08](#) on Molded and Extruded Products.

Current edition approved April 1, 2010. Published May 2010. Originally approved in 1962. Last previous edition approved in 2008 as D2103-08. DOI: [10.1520/D2103-10](#).

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](#), or contact ASTM Customer Service at [service@astm.org](#). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

\*A Summary of Changes section appears at the end of this standard.

**3. Terminology**

3.1 *Definitions:*

3.1.1 Unless otherwise specified, the definitions of plastics used in this specification are in accordance with Terminology D883.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *treated*—surface characteristics of the sheet or film have been modified by flame, corona discharge, or other means to promote the adhesion of inks, etc.


3.2.2 *yield*—the area provided by a given weight of film or sheeting of specified thickness.

**4. Classification**


4.1 The film and sheeting covered in this specification shall be designated by a type number, composed by listing the desired cell limit for each of the five properties, in the order shown in Table 1.

NOTE 3—Examples of this classification system are as follows:


(1) A high-clarity packaging film might be described as follows:



(2) A thin garment bag film might be described as follows:



(3) A tough, thick, pigmented industrial film might be described as follows:



With this type of classification it is possible to assemble on paper a combination of properties that is impossible to obtain with the present state of technology. A purchaser using this specification for the first time will probably find it necessary to contact material suppliers to learn what materials are commercially available.

4.2 In cases where surface treatment is specified by the purchaser, the test method must be agreed upon between the purchaser and the seller. The recommended test to measure the degree of surface treatment is Test Method D2578.

**5. General Requirements**

5.1 *Appearance*—The material shall have appearance qualities conforming with those produced by good commercial practice. It shall be as free as commercially possible of gels, streaks, pinholes, particles of foreign matter, and undispersed raw material.

**TABLE 1 Type Numbers**

Property Order Number	Property	0	1	2	3	4	5	Units
1	Density <sup>A</sup>	unspecified	0.910–<0.926	0.926–<0.941	0.941–0.965	<0.910	...	g/cm <sup>3</sup>
2	Impact strength <sup>B</sup>	unspecified	<40	40–70	71–150	151–300	>300	g
3	Coefficient of friction	unspecified	<0.20	0.20–0.40	0.41–0.70	>0.70	...	...
4	Haze	unspecified	<5.0	5.0–9.0	>9.0	...	...	...
5	Nominal thickness	unspecified	<sup>C</sup>	<sup>D</sup>	<sup>E</sup>	<sup>F</sup>	<sup>G</sup>	mm (in.)

<sup>A</sup> Annealed density of molded plaques or Melt Index extrudates.

<sup>B</sup> F50 (Results of a recent round robin have shown the equivalency of these two procedures.)

<sup>C</sup> <0.0254 (<0.0010).

<sup>D</sup> 0.0254–<0.0508 (0.0010–<0.0020)

<sup>E</sup> 0.0508–<0.1016 (0.0020–<0.0040)

<sup>F</sup> 0.1016–<0.1778 (0.0040–<0.0070)

<sup>G</sup> 0.1778–≤0.3048 (0.0070–≤0.0120)