
**Textiles — Quantitative chemical
analysis —**

Part 21:

**Mixtures of chlorofibres, certain
modacrylics, certain elastanes,
acetates, triacetates with certain other
fibres (method using cyclohexanone)**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Textiles — Analyse chimique quantitative —

*Partie 21: Mélanges de chlorofibres, certains modacryliques, certains
élasthanes, acétates, triacétates avec certaines autres fibres
(méthode à la cyclohexanone)*



iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 1833-21:2019

<https://standards.iteh.ai/catalog/standards/sist/b28f93e4-8c77-4742-a931-96d7c3f069f/iso-1833-21-2019>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents		Page
Foreword		iv
1 Scope		1
2 Normative references		1
3 Terms and definitions		1
4 Principle		1
5 Reagents		2
6 Apparatus		2
7 Procedure		2
8 Calculation and expression of results		3
9 Precision		3
Annex A (informative) Hot extraction apparatus		4
Bibliography		5

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 1833-21:2019](https://standards.iteh.ai/catalog/standards/sist/b28f93e4-8c77-4742-a931-96d7c3f069f/iso-1833-21-2019)

<https://standards.iteh.ai/catalog/standards/sist/b28f93e4-8c77-4742-a931-96d7c3f069f/iso-1833-21-2019>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html. (standards.iteh.ai)

This document was prepared by Technical Committee ISO/TC 38, *Textiles*.

This second edition cancels and replaces the first edition (ISO 1833-21:2006), which has been technically revised. The main changes compared to the previous edition are as follows:

- the title has been changed from “Mixtures of chlorofibres, certain modacrylics, certain elastanes, acetates, triacetates **and** certain other fibres...” to “Mixtures of chlorofibres, certain modacrylics, certain elastanes, acetates, triacetates **with** certain other fibres...”;
- in [Clause 1](#) some remaining fibres have been added;
- the mandatory [Clause 3](#) "Terms and definitions" has been added and the subsequent clauses have been renumbered;
- in [Clause 7](#) (former Clause 6) tolerances have been added to the washing temperature;
- in [Clause 8](#) (former Clause 7), a specific *d* factor for melamine and polyacrylate has been added;
- in [Clause 9](#) (former Clause 8), “percentage point” has been added to avoid confusion.

A list of all parts in the ISO 1833 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Textiles — Quantitative chemical analysis —

Part 21:

Mixtures of chlorofibres, certain modacrylics, certain elastanes, acetates, triacetates with certain other fibres (method using cyclohexanone)

1 Scope

This document specifies a method, using cyclohexanone, to determine the mass percentage of chlorofibre, modacrylic, elastane, acetate and triacetate, after removal of non-fibrous matter, in textiles made of mixtures of

— acetate, triacetate, chlorofibre, certain modacrylics, certain elastanes

with

— wool, animal hair, silk, cotton, cupro, modal, viscose, lyocell, polyamide, acrylic, melamine, polyacrylate and glass fibres.

It is also possible to analyse mixtures containing chlorofibres by using the test methods described in ISO 1833-13 or ISO 1833-17.

2 Normative references

[ISO 1833-21:2019](#)

[https://www.iso.org/standards/catalog/standards/sist/b28f93e4-8c77-4742-a931-96d7c3f069f/iso-1833-21-2019](#)

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1833-1, *Textiles — Quantitative chemical analysis — Part 1: General principles of testing*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Principle

The acetate and triacetate fibres, chlorofibres, certain modacrylics, and certain elastanes are dissolved out from a known dry mass with cyclohexanone at a temperature close to boiling point. The residue is collected, washed, dried and weighed. Its mass, corrected if necessary, is expressed as a percentage of the dry mass of the mixture. The percentage of chlorofibre, modacrylic, elastane, acetate and triacetate are found by the difference.

5 Reagents

Use the reagents described in ISO 1833-1 together with those given in [5.1](#) and [5.2](#).

5.1 Cyclohexanone.

NOTE The boiling point of cyclohexanone is at 156 °C.

5.2 Ethanol, 50 % by volume with water.

SAFETY PRECAUTIONS — Cyclohexanone is flammable and toxic. Suitable precautions shall be taken in its use.

6 Apparatus

Use the apparatus described in ISO 1833-1 together with those given in [6.1](#) to [6.5](#).

6.1 Hot extraction apparatus (see [Annex A](#)).

NOTE This is a variant of the apparatus described in Reference [\[5\]](#).

6.2 Filter crucible, to contain the specimen.

6.3 Porous baffle (porosity grade 1), flat circular stopper of glass with a glass filter in the middle. The stopper is placed over the glass filter crucible.

6.4 Reflux condenser, that can be adapted to the distillation flask.

[https://standards.iteh.ai/catalog/standards/sist/b28f93e4-8c77-4742-a931-](https://standards.iteh.ai/catalog/standards/sist/b28f93e4-8c77-4742-a931-96d7c3f0697e/iso-1833-21-2019)

6.5 Heating device, suitable for the hot extraction apparatus ([6.1](#)) and for boiling point of cyclohexanone ([5.1](#)).

7 Procedure

Follow the general procedure given in ISO 1833-1, and then proceed as follows.

Where modacrylics or elastanes are present, a preliminary test should be carried out to determine whether the fibre is completely soluble in the reagent.

Pour into the distillation flask 100 ml of cyclohexanone ([5.1](#)) per gram of material.

Insert the extraction container in which the filter crucible ([6.2](#)), containing the specimen and the porous baffle ([6.3](#)), slightly inclined, have previously been placed. Insert the reflux condenser ([6.4](#)). Bring to the boil and continue extraction for 60 min at a minimum rate of 12 cycles per hour.

After extraction and cooling remove the extraction container, take out the filter crucible and remove the porous baffle.

Wash the contents of the filter crucible three or four times with 50 % ethanol heated to (60 ± 2) °C and subsequently with 1 l of water at (60 ± 2) °C.

Do not apply suction during or between the washing operations. Allow the liquid to drain under gravity and then apply suction.

Finally, dry the crucible ([6.2](#)) with the residue, then cool and weigh them.

8 Calculation and expression of results

Calculate the results as described in the general instructions of ISO 1833-1.

The value of d is 1,00 with the following exceptions:

- silk and melamine, $d = 1,01$;
- polyacrylate, $d = 1,02$;
- acrylic, $d = 0,98$.

9 Precision

On homogeneous mixtures of textile fibres, the confidence limits of results obtained by this method are not greater than ± 1 percentage point for a confidence level of 95 %.


iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 1833-21:2019](https://standards.iteh.ai/catalog/standards/sist/b28f93e4-8c77-4742-a931-96d7c3f069f/iso-1833-21-2019)

<https://standards.iteh.ai/catalog/standards/sist/b28f93e4-8c77-4742-a931-96d7c3f069f/iso-1833-21-2019>

Annex A (informative)

Hot extraction apparatus



Key

- 1 porous baffle
- 2 filter crucible

Figure A.1 — Hot extraction apparatus

Bibliography

- [1] ISO 1833-13, *Textiles — Quantitative chemical analysis — Part 13: Mixtures of certain chlorofibres and certain other fibres (method using carbon disulfide/acetone)*
- [2] ISO 1833-17, *Textiles — Quantitative chemical analysis — Part 17: Mixtures of chlorofibres (homopolymers of vinyl chloride) and certain other fibres (method using sulfuric acid)*
- [3] ISO 2076, *Textiles — Man-made fibres — Generic names*
- [4] ISO 6938, *Textiles — Natural fibres — Generic names and definitions*
- [5] *Melliand Textilberichte*, **56**, 1975, pp. 643-645

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 1833-21:2019](https://standards.iteh.ai/catalog/standards/sist/b28f93e4-8c77-4742-a931-96d7c3f069f/iso-1833-21-2019)

<https://standards.iteh.ai/catalog/standards/sist/b28f93e4-8c77-4742-a931-96d7c3f069f/iso-1833-21-2019>