



SLOVENSKI STANDARD
oSIST prEN ISO 8044:2023
01-november-2023

Korozija kovin in zlitin - Slovar (ISO/DIS 8044:2023)

Corrosion of metals and alloys - Vocabulary (ISO/DIS 8044:2023)

Korrosion von Metallen und Legierungen - Grundbegriffe (ISO/DIS 8044:2023)

Corrosion des métaux et alliages - Vocabulaire (ISO/DIS 8044:2023)

Ta slovenski standard je istoveten z: prEN ISO 8044

<https://standards.iteh.ai/catalog/standards/sist/201f94fe-91e0-42e9-9062-144a39b95c28/osist-pren-iso-8044-2023>

ICS:

01.040.77	Metalurgija (Slovarji)	Metallurgy (Vocabularies)
77.060	Korozija kovin	Corrosion of metals

oSIST prEN ISO 8044:2023

en,fr,de

DRAFT INTERNATIONAL STANDARD

ISO/DIS 8044

ISO/TC 156

Secretariat: SAC

Voting begins on:
2023-08-28Voting terminates on:
2023-11-20

Corrosion of metals and alloys — Vocabulary

Corrosion des métaux et alliages — Vocabulaire

ICS: 01.040.77; 77.060

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN ISO 8044:2023](https://standards.iteh.ai/catalog/standards/sist/201f94fe-91e0-42c9-9062-144a39b95c28/osist-pren-iso-8044-2023)<https://standards.iteh.ai/catalog/standards/sist/201f94fe-91e0-42c9-9062-144a39b95c28/osist-pren-iso-8044-2023>

This document is circulated as received from the committee secretariat.

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 8044:2023(E)

© ISO 2023

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 8044:2023](https://standards.iteh.ai/catalog/standards/sist/201f94fe-91e0-42c9-9062-144a39b95c28/osist-pren-iso-8044-2023)

<https://standards.iteh.ai/catalog/standards/sist/201f94fe-91e0-42c9-9062-144a39b95c28/osist-pren-iso-8044-2023>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms related to corrosion in general.....	1
4 Terms related to types of corrosion.....	4
5 Terms related to corrosion protection.....	9
6 Terms related to corrosion testing.....	11
7 Terms related to electrochemical matters.....	12
7.1 The electrochemical cell.....	12
7.2 Reaction rates.....	16
7.3 Passivation.....	18
7.4 Electrochemical protection.....	19
7.5 Electrochemical corrosion tests.....	20
Annex A (informative) Graphical representations of certain terms.....	22
Bibliography.....	24
Index.....	25

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN ISO 8044:2023](https://standards.iteh.ai/catalog/standards/sist/201f94fe-91e0-42c9-9062-144a39b95c28/osist-pren-iso-8044-2023)

<https://standards.iteh.ai/catalog/standards/sist/201f94fe-91e0-42c9-9062-144a39b95c28/osist-pren-iso-8044-2023>

ISO/DIS 8044:2023(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 156, *Corrosion of metals and alloys*.

This fifth edition cancels and replaces the fifth edition (ISO 8044:2020). Only three definitions have been changed in this edition, but because one of them is the definition of corrosion, TC 156 determined that a new revision was justified.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

The definitions in this document have been drawn up with the objective of achieving a proper balance between precision and simplicity. The main objective of this document is to provide definitions that can be understood to have the same meaning by all concerned. Some corrosion terms in present use have developed through common usage and are not always logical. It has not, therefore, been possible to define certain terms in the form they are used in some countries. Because of the occasional conflicts between tradition and logic, some definitions inevitably represent a compromise.

An example of this kind of conflict is the term “corrosion”. This has been used to mean the process, results of the process and damage caused by the process. In this document, corrosion is understood to mean the process. Any detectable result of corrosion in any part of a corrosion system is termed “corrosion effect”. The term “corrosion damage” covers any impairment of the function of the technical system of which the metal and the environment form a part. Consequently, the term “corrosion protection” implies that the important thing is to avoid corrosion damage rather than to prevent corrosion, which in many cases is impossible and sometimes not necessary.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN ISO 8044:2023](https://standards.iteh.ai/catalog/standards/sist/201f94fe-91e0-42c9-9062-144a39b95c28/osist-pren-iso-8044-2023)

<https://standards.iteh.ai/catalog/standards/sist/201f94fe-91e0-42c9-9062-144a39b95c28/osist-pren-iso-8044-2023>

Corrosion of metals and alloys — Vocabulary

1 Scope

This document defines terms relating to corrosion that are widely used in modern science and technology. In addition, some definitions are supplemented with short explanations.

NOTE 1 Throughout the document, IUPAC rules for electrode potential signs are applied. The term “metal” is also used to include alloys and other metallic materials.

NOTE 2 Terms and definitions related to the inorganic surface treatment of metals are given in ISO 2080.

2 Normative references

There are no normative references in this document.

3 Terms related to corrosion in general

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at <https://www.iso.org/obp>

— IEC Electropedia: available at <https://www.electropedia.org/>

3.1

corrosion

Chemical or electrochemical interaction between a material, usually a metal, and its environment

Note 1 to entry: This may lead to deterioration of material properties, the environment, or the function of the system containing that material.

3.2

corrosive agent

substance that will initiate or promote *corrosion* (3.1) when in contact with a given metal

3.3

corrosive environment

environment that contains one or more *corrosive agents* (3.2)

3.4

corrosion system

system consisting of one or more metals and those parts of the environment that influence *corrosion* (3.1)

Note 1 to entry: Parts of the environment may be, for example, coatings, surface layers or additional *electrodes* (7.1.2).

3.5

corrosion effect

change in any part of the *corrosion system* (3.4) caused by *corrosion* (3.1)

3.6

corrosion damage

corrosion effect (3.5) that causes impairment of the function of the metal, the environment or the technical system, of which these form a part

ISO/DIS 8044:2023(E)

- 3.7**
corrosion failure
corrosion damage (3.6) characterized by the total loss of function of the technical system
- 3.8**
corrosion product
substance formed as a result of *corrosion* (3.1)
- 3.9**
scale
solid layer of *corrosion products* (3.8) formed on a metal at high temperature
- Note 1 to entry: The term “scale” is also used in some countries for deposits from supersaturated water.
- 3.10**
rust
visible *corrosion products* (3.8) consisting mainly of hydrated iron oxides
- 3.11**
corrosion depth
distance between a point on the surface of a metal affected by *corrosion* (3.1) and the original surface of the metal
- 3.12**
corrosion rate
corrosion effect (3.5) on a metal per unit time
- Note 1 to entry: The unit used to express the corrosion rate depends on the technical system and on the type of corrosion effect. Thus, corrosion rate is typically expressed as an increase in *corrosion depth* (3.11) per unit time, or the mass of metal turned into *corrosion products* (3.8) per area of surface and per unit time, etc. The corrosion effect may vary with time and may not be the same at all points of the corroding surface. Therefore, reports of corrosion rates are typically accompanied by information on the type, time dependency and location of the corrosion effect.
- 3.13**
corrosion resistance
ability of a metal to maintain *serviceability* (3.16) in a given *corrosion system* (3.4)
- 3.14**
corrosivity
ability of an environment to cause *corrosion* (3.1) of a metal in a given *corrosion system* (3.4)
- 3.15**
corrosion likelihood
qualitative and/or quantitative expression of the expected *corrosion effects* (3.5) in a defined *corrosion system* (3.4)
- 3.16**
serviceability
<corrosion> ability of a *corrosion system* (3.4) to perform its specified functions without impairment due to *corrosion* (3.1)
- 3.17**
durability
<corrosion> ability of a *corrosion system* (3.4) to maintain *serviceability* (3.16) over a specified time when the specified requirements for use and maintenance have been fulfilled
- 3.18**
service life
<corrosion> time during which a *corrosion system* (3.4) meets the requirements for *serviceability* (3.16)

3.19**critical humidity**

value of the relative humidity of an atmosphere above which there is a sharp increase in the *corrosion rate* (3.12) of a given metal

3.20**corrosion attack**

corrosion effect (3.5) that is detrimental but has not progressed to the point of impairment of the function of the metal, the environment or the technical system, of which these form a part

3.21**pickling**

removal of oxides or other compounds from a metal surface by chemical or electrochemical action

3.22**pitting resistance equivalent number****PREN**

indication of the resistance of stainless steels and nickel-based alloys to pitting in the presence of chloride-containing water

Note 1 to entry: An example formula for PREN is given by

$$\text{PREN} = \% \text{Cr} + 3,3 \left[(\% \text{Mo}) + 0,5 (\% \text{W}) \right] + 16 (\% \text{N})$$

Note 2 to entry: In general, the higher the PREN, the higher is the resistance to pitting corrosion.

3.23**trap**

micro structural site at which the residence time for a hydrogen atom is long compared to the residence time in an interstitial lattice site

3.24**time of wetness**

period when a metallic surface is covered by adsorptive and/or liquid films of electrolyte to be capable of causing *atmospheric corrosion* (4.4)

3.25**threshold stress**

<stress corrosion cracking> tensile stress above which stress corrosion cracks initiate and grow for specified test conditions

3.26**threshold stress intensity factor for stress corrosion cracking** K_{ISCC}

stress intensity factor above which stress corrosion crack propagation is sustained

Note 1 to entry: The threshold stress intensity factor is a concept of linear elastic fracture mechanics (LEFM) and is applicable when the plastic zone size is large compared with the microstructure, the crack is sufficiently long, and a high constraint to plastic deformation prevails, i.e. under plane strain predominant conditions. For growing stress corrosion cracks, LEFM is not necessarily applicable in all detail but is adopted as a pragmatic tool that is commonly used.

Note 2 to entry: Stress corrosion cracks may initiate at a surface or a surface defect and grow in the “small crack” regime at stress intensity factor levels below the apparent threshold stress intensity factor. Therefore, LEFM is not applicable in the “small crack” regime.

ISO/DIS 8044:2023(E)

4 Terms related to types of corrosion

- 4.1 electrochemical corrosion**
corrosion (3.1) involving at least one *anodic reaction* (7.1.9) and one *cathodic reaction* (7.1.6)
- 4.2 chemical corrosion**
corrosion (3.1) not involving an electrochemical reaction
- 4.3 gaseous corrosion**
corrosion (3.1) with dry gas as the *corrosive environment* (3.3) and without any liquid phase on the surface of the metal
- 4.4 atmospheric corrosion**
corrosion (3.1) with the earth's atmosphere at ambient temperature as the *corrosive environment* (3.3)
- 4.5 marine corrosion**
corrosion (3.1) with sea water as the main agent of the *corrosive environment* (3.3)

Note 1 to entry: This definition includes both immersed and splash zone conditions.

- 4.6 underground corrosion**
corrosion (3.1) of buried metals, soil being the *corrosive environment* (3.3)

Note 1 to entry: The term soil includes not only the naturally occurring material but also any other material, such as ballast and backfill, used to cover a structure.

- 4.7 bacterial corrosion**
 microbiologically influenced corrosion (3.37) due to the action of bacteria

- 4.8 general corrosion**
corrosion (3.1) proceeding over the whole surface of the metal exposed to the *corrosive environment* (3.3)

- 4.9 uniform corrosion**
general corrosion (4.8) proceeding at almost the same rate over the whole surface

- 4.10 localized corrosion**
corrosion (3.1) preferentially concentrated on discrete sites of the metal surface exposed to the *corrosive environment* (3.3)

Note 1 to entry: Localized corrosion can result in, for example, pits, cracks or grooves.

- 4.11 galvanic corrosion**
corrosion (3.1) due to the action of a *corrosion cell* (7.1.13)

Note 1 to entry: The term has often been restricted to the action of bimetallic corrosion cells, i.e. to *bimetallic corrosion* (4.12).