



~~Designation: D3018/D3018M-09~~ Designation: D3018/D3018M – 10

## Standard Specification for Class A Asphalt Shingles Surfaced with Mineral Granules<sup>1</sup>

This standard is issued under the fixed designation D3018/D3018M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope

1.1 This specification covers granule-surfaced asphalt roofing shingles that meet the ~~conditions~~ requirements for Class A fire test, behavior on heating, and wind testing.

1.2 Shingles meeting this specification are intended to be applied with a headlap of not less than 51 mm [2 in.].

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

D228 [Test Methods for Sampling, Testing, and Analysis of Asphalt Roll Roofing, Cap Sheets, and Shingles Used in Roofing and Waterproofing](#)

D1079 [Terminology Relating to Roofing and Waterproofing](#)

D3161 [Test Method for Wind-Resistance of Asphalt Shingles \(Fan-Induced Method\)](#)

E108 [Test Methods for Fire Tests of Roof Coverings](#)

### 3. Terminology

3.1 *Definition:*

3.1.1 *glass mat*—for testing purposes in accordance with Test Methods D228, glass mat shall be considered as felt.

3.2 For definitions of terms used in this specification, see Terminology D1079.

### 4. Classification

4.1 Asphalt shingles covered by this specification are of two types: 8M-10

4.1.1 *Type I*—Self-sealing.

4.1.2 *Type II*—Non-self-sealing.

### 5. Materials and Manufacture

5.1 The shingles covered by this specification shall consist of organic felt or glass mat(s) saturated or impregnated and coated on both sides with a hot asphaltic material and completely surfaced on the weather side with mineral granules embedded in the coating.

5.2 The hot asphaltic material used to saturate or impregnate and coat the organic felt or glass mat(s) may be compounded with a mineral stabilizer.

5.3 The reverse side of the shingles shall be covered with a suitable material to prevent the shingles from sticking together in the package.

5.4 Type I shingles shall have a factory-applied adhesive that will seal the shingles together after application.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D08 on Roofing and Waterproofing and is the direct responsibility of Subcommittee D08.02 on Prepared Roofings, Shingles and Siding Materials.

Current edition approved Aug. 1, 2009. Published August 2009. Originally approved in 1972. Last previous edition approved in 2009 as D3018-03(2009). DOI: 10.1520/D3018-D3018M-09 on Steep Roofing Products and Assemblies.

Current edition approved June 15, 2010. Published July 2010. Originally approved in 1972. Last previous edition approved in 2009 as D3018-09. DOI: 10.1520/D3018-D3018M-10.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.