



Designation: F1869 – 10

Standard Test Method for Measuring Moisture Vapor Emission Rate of Concrete Subfloor Using Anhydrous Calcium Chloride¹

This standard is issued under the fixed designation F1869; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the quantitative determination of the rate of moisture vapor emitted from below-grade, on-grade, and above-grade (suspended) bare concrete floors.

1.2 This test shall not be used to evaluate the rate of moisture vapor emitted by lightweight concrete floors containing lightweight aggregate.

1.3 This test shall not be used to evaluate moisture vapor emissions over coatings on concrete or over patching or leveling compounds.

1.4 This quantity of moisture shall be expressed as the rate of moisture vapor emission, measured in pounds of moisture over a 1000 ft² area during a 24-h period.

1.5 This test shall not be used to evaluate moisture emissions over gypsum concrete.

1.6 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.7 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices, and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards*:²

C670 [Practice for Preparing Precision and Bias Statements for Test Methods for Construction Materials](#)

F141 [Terminology Relating to Resilient Floor Coverings](#)

2.2 *Resilient Floor Covering Institute Standard*:

Recommended Work Practices³

2.3 *Military Standard*:

Mil Spec B-131H Type 1, Class III⁴

2.4 *ICRI Guide*:

Guideline No. 03732: [Selecting and Specifying Concrete Preparation for Sealers, Coatings, and Polymer Overlays](#)⁵

3. Terminology

3.1 *Definitions*: See Terminology F141 for definitions of the terms, above-grade (suspended), below-grade, concrete, on-grade, and resilient flooring.

3.2 *Definitions of Terms Specific to This Standard*:

3.2.1 *moisture vapor emission rate (MVER)*—amount of water vapor in pounds emitted from a 1000 ft² area of concrete flooring during a 24-h period (multiply by 56.51 to convert to $\mu\text{g/s m}^2$).

4. Significance and Use

4.1 Use this test method to obtain a quantitative value indicating the rate of moisture vapor emission from a concrete floor and whether or not that floor is acceptable to receive resilient floor covering. The moisture vapor emission rate only reflects the condition of the concrete floor at the time of the test. All concrete subfloors emit some amount of moisture in vapor form. Concrete moisture emission is a natural process driven by environmental conditions. All floor coverings are susceptible to failure from excessive moisture vapor emissions. The moisture vapor emitted from a concrete slab is measured in pounds. This measurement is the equivalent weight of water evaporating from 1000 ft² of concrete surface in a 24-h period. The calcium chloride moisture test has been the industry standard for making this determination and is a practical, well-established and accepted test of dynamic moisture. It will

¹ This test method is under the jurisdiction of ASTM Committee F06 on Resilient Floor Coverings and is the direct responsibility of Subcommittee F06.40 on Practices.

Current edition approved July 1, 2010. Published July 2010. Originally approved in 1998. Last previous edition approved in 2009 as F1869–09. DOI: 10.1520/F1869-10.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from Resilient Floor Covering Institute, 966 Hungerford Drive, Suite 12-B, Rockville, MD 20850.

⁴ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

⁵ Available from International Concrete Repair Institute, International Concrete Repair Institute 3 166 S. River Road, Suite 132, Des Plaines, IL 60018; www.icri.org